



Standard Specification for Polyethylene (PE) Plastic Tubing¹

This standard is issued under the fixed designation D2737; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers polyethylene (PE) plastic tubing in outside diameters and SDR's that are pressure rated for water. Included are requirements for PE compounds, and requirements and test methods for PE plastic tubing workmanship, dimensions, elevated temperature sustained pressure, burst pressure and marking.

1.2 The text of this specification references notes, footnotes, and appendixes which provide explanatory material. These notes and footnotes shall not be considered as requirements of the specification. Notes and footnotes in tables and figures, and Supplementary Requirements are requirements of the specification.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

NOTE 1—Joining PE plastic tubing with fittings that require flaring the tubing is not recommended because Practice D3140, the technique used to make the flare has been withdrawn (discontinued).

NOTE 2—References and PE compound descriptions for PE2305, PE2406, PE3306, PE3406, and PE3408 have been removed due to changes in Specification D3350 and PPI TR-3. For removed designations, refer to previous editions of Specification D2737, Specification D3350, PPI TR-3 and PPI TR-4. The removal of these PE compounds does not affect pipelines that are in service. PE compounds and material designations resulting from changes in Specification D3350 and PPI TR-3 are addressed in Section 5.

1.4 The following safety hazards caveat pertains only to the test methods portion, Section 7, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

¹ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.26 on Olefin Based Pipe.

Current edition approved Jan. 15, 2012. Published January 2012. Originally approved in 1968. Last previous edition approved in 2003 as D2737 – 03. DOI: 10.1520/D2737-12.

2. Referenced Documents

2.1 ASTM Standards:²

- D618 Practice for Conditioning Plastics for Testing
- D638 Test Method for Tensile Properties of Plastics
- D1238 Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer
- D1598 Test Method for Time-to-Failure of Plastic Pipe Under Constant Internal Pressure
- D1599 Test Method for Resistance to Short-Time Hydraulic Pressure of Plastic Pipe, Tubing, and Fittings
- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D1603 Test Method for Carbon Black Content in Olefin Plastics
- D2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings
- D2565 Practice for Xenon-Arc Exposure of Plastics Intended for Outdoor Applications
- D2837 Test Method for Obtaining Hydrostatic Design Basis for Thermoplastic Pipe Materials or Pressure Design Basis for Thermoplastic Pipe Products
- D3350 Specification for Polyethylene Plastics Pipe and Fittings Materials
- D3140 Practice For Flaring Polyolefin Pipe And Tubing³
- D4218 Test Method for Determination of Carbon Black Content in Polyethylene Compounds By the Muffle-Furnace Technique
- F412 Terminology Relating to Plastic Piping Systems
- G154 Practice for Operating Fluorescent Light Apparatus for UV Exposure of Nonmetallic Materials
- G155 Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials

2.2 APWA Standard:⁴

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

⁴ APWA, 2345 Grand Boulevard, suite 500, Kansas, City, MO 64108-2641.

*A Summary of Changes section appears at the end of this standard.

APWA Uniform Color Code

2.3 NSF Standards:⁵

NSF/ANSI Standard No. 14 for Plastic Piping Components and Related Materials

NSF/ANSI Standard No. 61 for Drinking Water Systems Components—Health Effects

2.4 PPI Standards:⁶

PPI TR-3 Policies and Procedures for Developing Hydrostatic Design Basis (HDB), Pressure Design Basis (PDB), Strength Design Basis (SDB), and Minimum Required Strength (MRS) Ratings for Thermoplastic Piping Materials or Pipe

PPI TR-4 HDB/SDB/PDB/MRS Listed Materials, PPI Listing of Hydrostatic Design Basis (HDB), Strength Design Basis (SDB), Pressure Design Basis (PDB), and Minimum Required Strength (MRS) Ratings for Thermoplastic Piping Materials or Pipe

3. Terminology

3.1 Definitions—Unless otherwise specified, definitions are in accordance with Terminology F412 and abbreviations are in accordance with Terminology D1600.

4. Tubing Classification

4.1 General—This specification covers PE plastic tubing made from PE compounds in three standard dimension ratios and pressure rated for water. Pressure ratings for water are

dependent on the PE compound in accordance with the following relationship:

$$PR = \frac{2 \times HDS}{(SDR + 1)} \quad (1)$$

Where:

PR = pressure rating for water, 73°F (23°C), psi (kPa)

HDS = hydrostatic design stress for water at 73°F (23°C), psi (kPa)

SDR = standard dimension ratio

NOTE 3—PR and HDS must have the same units. See Appendix X1 for maximum pressure ratings for water.

4.2 This specification covers PE tubing in standard dimension ratios SDR 7.3, SDR 9, and SDR 11.

5. Materials

5.1 Polyethylene Compound—Polyethylene compounds suitable for use in the manufacture of tubing under this specification shall meet thermoplastic materials designation codes PE2708 or PE3608 or PE4608 or PE4710, and shall meet Table 1 requirements for PE2708 or PE3608 or PE4608 or PE4710, and shall meet thermal stability, brittleness temperature and elongation at break requirements in accordance with Specification D3350.

5.1.1 Color and Ultraviolet (UV) Stabilization—Polyethylene compounds shall meet Specification D3350 code C, D or E. In addition, Code C polyethylene compounds shall have 2 to 3 percent carbon black, and Code D or E polyethylene compounds shall have sufficient UV stabilizer to protect tubing from deleterious UV exposure effects during unprotected outdoor shipping and storage for at least eighteen (18) months.

TABLE 1 Polyethylene Compound Requirements

Requirement	Material Designation			
	PE2708	PE3608	PE4608	PE4710
HDB at 140°F (60°C), psi (MPa), per Test Method D2837 and PPI TR-3 ^A	B	B	B	B
HDS for water at 73°F (23°C) psi (MPa), per Test Method D2837 and PPI TR-3 ^C	800 (5.5)	800 (5.5)	800 (5.5)	1000 (6.9)
Melt flow rate per Test Method D1238	≤0.40 g/10 min Cond. 190/2.16 or ≤20 g/10 min Cond. 190/21.6	≤0.15 g/10 min Cond. 190/2.16 or ≤20 g/10 min Cond. 190/21.6	≤0.15 g/10 min Cond. 190/2.16 or ≤20 g/10 min Cond. 190/21.6	≤0.15 g/10 min Cond. 190/2.16 or ≤20 g/10 min Cond. 190/21.6
Specification D3350 Cell Classification Property Requirement	Required Value			
Density (natural base resin)	2	3	4	4
SCG Resistance	7	6	6	7
Color and UV Stabilizer Code ^D	C, D or E	C, D or E	C, D or E	C, D or E

^A HDB at 140°F (60°C) not required. Contact manufacturer about pipe use at temperatures other than 73°F (23°C).

^B HDB at 140°F (60°C) required. Contact manufacturer or see PPI TR-4 for listed value.

^C Contact manufacturer or see PPI TR-4 for listed value.

^D See 5.1.1.

NOTE 4—Pipe users should consult with the pipe manufacturer about the outdoor exposure life of the product under consideration. Evaluation of UV stabilizer in Code D or E PE compound using Practice **D2565** or Practice **G154** or Practice **G155** may be useful for this purpose.

5.1.2 *Colors for solid color, an external color layer or color stripes*—In accordance with the **APWA** Uniform Color Code, blue shall identify potable water service; green shall identify sewer service; and purple (lavender) shall identify reclaimed water service. Yellow identifies gas service and shall not be used.

5.2 Products intended for contact with potable water shall be evaluated, tested and certified for conformance with **NSF/ANSI Standard No. 61** or the health effects portion of **NSF/ANSI Standard No. 14** by a certifying organization acceptable to the authority having jurisdiction.

5.3 *Rework Material*—Clean polyethylene compound from the manufacturer’s own tubing production that met 5.1 through 5.2 as new PE compound is suitable for re-extrusion into tubing when blended with new PE compound having the same material designation. Tubing containing rework material shall meet all the requirements of this specification.

6. Requirements

6.1 *Workmanship*—The tubing shall be homogeneous throughout and free from visible cracks, holes, foreign inclusions, or other defects. The tubing shall be as uniform as commercially practicable in color, opacity, density, and other physical properties. See 5.1.2.

6.2 Dimensions and Tolerances:

6.2.1 *Outside Diameters*—The outside diameters and tolerances shall be as shown in **Table 2** when measured in accordance with 7.4.

6.2.1.1 *Out-of-roundness*—Out of roundness shall be in accordance with **Table 2** as extruded, but before coiling for packaging when measured in accordance with 7.4.

NOTE 5—Coiling may increase out-of-roundness, depending on the coiling method and coil dimensions.

6.2.2 *Wall Thicknesses*—The wall thicknesses and tolerance shall be as shown in **Table 3** when measured in accordance with 7.4. Wall thickness shall be inclusive of all extruded concentric layers.

6.2.3 *Wall Thickness Variation*—The wall thickness variation shall not exceed 12 % when measured in accordance with 7.4.

6.2.4 *Thickness of Outer Layer*—For tubing produced by simultaneous multiple extrusion, the outer concentric layer shall be at least 0.020 in (0.5 mm) thick.

6.3 *Bond*—For tubing produced by simultaneous multiple extrusion, the bond between the layers shall be strong and uniform. It shall not be possible to cleanly separate any two layers with a probe or point of a knife blade at any point.

6.4 *Carbon Black*—Polyethylene tubing produced using Code C polyethylene compound per 5.1.1 shall contain 2 to 3% carbon black when tested in accordance with 7.5.

6.5 *Burst Pressure*—The minimum burst pressure for tubing shall be as given in **Table 4**, when determined in accordance with 7.6 using a minimum hoop stress of 2520 psi (17.4 MPa) for **Table 1** density cell 2 polyethylene compound or 2900 psi (20.0 MPa) for **Table 1** density cell 3 or 4 polyethylene compound. In addition, the failure shall be ductile.

6.6 *Elevated Temperature Sustained Pressure*—Elevated temperature sustained pressure tests for each polyethylene compound designation per **Table 1** used in production at the facility shall be conducted twice annually per 7.7.

6.7 *Inside Surface Ductility for Tubing*—Tubing shall be tested for inside surface ductility in accordance with 7.8 or 7.9.

NOTE 6—Tensile elongation testing per 7.9 provides a quantifiable result and is used for referee testing and in cases of disagreement.

7. Test Methods

7.1 *Conditioning*—Condition as specified in the test method. Where conditioning is not specified in the test method, condition the test specimens at 73 ± 3.6°F (23 ± 2°C) without regard to relative humidity for not less than 4 h prior to the test in accordance with Procedure A of Practice **D618**, or at 73 ± 3.6°F (23 ± 2°C) for not less than 1 h in accordance with Procedure D of Practice **D618**.

7.2 *Test Conditions*—Conduct tests in accordance with the conditions specified in the test method, or if not specified in the test method, at 73.4 ± 3.6°F (23 ± 2°C) without regard to relative humidity.

7.3 *Sampling*—The number and selection of samples shall be as specified in the test method, or if not specified in the test method, sample selection shall be as agreed upon by the purchaser and seller. In case of no prior agreement, any sample selected by the testing laboratory shall be deemed adequate.

7.3.1 *Test Specimens*—Not less than 50 % of the test specimens required for any pressure test shall have at least a part of the marking in their central sections. The central section is that portion of the tubing sample that is at least one pipe diameter away from an end closure. The entire marking shall be documented in testing records.

TABLE 2 Outside Diameters and Tolerances for PE Plastic Tubing

Tubing Size	Outside Diameter, in. (mm)	Outside Diameter Tolerance, in. (mm)	Out-of-Roundness, in. (mm)
1/2	0.625 (15.87)	±0.004 (±0.10)	0.030 (0.76)
5/8	0.750 (19.05)	±0.004 (±0.10)	0.030 (0.76)
3/4	0.875 (22.23)	±0.004 (±0.10)	0.030 (0.76)
1	1.125 (28.58)	±0.005 (±0.13)	0.030 (0.76)
1 1/4	1.375 (34.93)	±0.005 (±0.13)	0.030 (0.76)
1 1/2	1.625 (41.23)	±0.006 (±0.15)	0.030 (0.76)
2	2.125 (53.98)	±0.006 (±0.15)	0.030 (0.76)