



Designation: D1863/D1863M – 05 (Reapproved 2011)<sup>ε1</sup>

## Standard Specification for Mineral Aggregate Used on Built-Up Roofs<sup>1</sup>

This standard is issued under the fixed designation D1863/D1863M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

<sup>ε1</sup> NOTE—Units information was editorially corrected in January 2012.

### 1. Scope

1.1 This specification covers the quality and grading of crushed stone, crushed slag, and water-worn gravel suitable for use as coarse mineral aggregate on built-up roofs.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

**C29/C29M** Test Method for Bulk Density (“Unit Weight”) and Voids in Aggregate

**C33** Specification for Concrete Aggregates

**C117** Test Method for Materials Finer than 75- $\mu\text{m}$  (No. 200) Sieve in Mineral Aggregates by Washing

**C136** Test Method for Sieve Analysis of Fine and Coarse Aggregates

**D75** Practice for Sampling Aggregates

**D448** Classification for Sizes of Aggregate for Road and Bridge Construction

**D1864** Test Method for Moisture in Mineral Aggregate Used on Built-Up Roofs

**D1865** Test Method for Hardness of Mineral Aggregate Used on Built-Up Roofs

**E11** Specification for Woven Wire Test Sieve Cloth and Test Sieves

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.03 on Surfacing and Bituminous Materials for Membrane Waterproofing and Built-up Roofing.

Current edition approved Nov. 1, 2011. Published January 2012. Originally approved in 1961. Last previous edition approved in 2005 as D1863 – 05. DOI: 10.1520/D1863\_D1863M-05R11E01.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

### 3. Materials and Manufacture

3.1 *Crushed Stone and Gravel*—The crushed stone and gravel at the time of application shall be hard, durable, opaque, and free of clay, loam, sand, or other foreign substances.

3.2 *Crushed Slag*—Crushed slag shall be hard, air-cooled, blast-furnace slag, or electric furnace phosphate slag that is free of sand, clay, or other foreign substances at the time of application.

### 4. Requirements

4.1 The aggregate shall conform to the gradation requirements specified in **Table 1**.

4.2 The aggregate shall conform to the physical properties specified in **Table 2**.

4.3 *Suggested Field Checks*:

4.3.1 Aggregate shall be free of ice and snow.

4.3.2 A handful of aggregate shall not drip water.

4.3.3 The aggregate shall be dry and clean enough to adhere to the hot bitumen flood coat when installed.

### 5. Sampling

5.1 Sample aggregates received in bulk in accordance with Practice **D75**.

5.2 For aggregates received in bags or small containers, select a number of bags or small containers at random equivalent to the cube root of the total number in the shipment.

### 6. Test Methods

6.1 *Gradation*—Test Method **C136**.

6.2 *Moisture*—Test Method **D1864**.

6.3 *Unit Mass (Loose)*—Test Method **C29/C29M**, utilizing the shoveling procedure.

6.4 *Dust*—Test Method **C117**.

6.5 *Hardness*—Test Method **D1865**.

### 7. Inspection

7.1 Inspection of the material shall be as agreed upon between the purchaser and the supplier.