



Standard Specification for Thermoplastic Chlorinated Polyethylene (CM) Jacket for Wire and Cable¹

This standard is issued under the fixed designation D4363; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers thermoplastic chlorinated polyethylene (CM) compounds suitable for use as an outer covering or jacket on electrical cables.

1.2 These jacket materials are suitable for use on cables which will be installed at temperatures above -35°C .

~~1.3 Whenever two sets of values are presented, in different units, the values in the first set are the standard, while those in parentheses are for information only.~~

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 *ASTM Standards:*²

D2633 [Test Methods for Thermoplastic Insulations and Jackets for Wire and Cable](#)

D1499 [Practice for Filtered Open-Flame Carbon-Arc Exposures of Plastics](#)

D1711 [Terminology Relating to Electrical Insulation](#)

G153 [Practice for Operating Enclosed Carbon Arc Light Apparatus for Exposure of Nonmetallic Materials](#)

3. Terminology

3.1 *Definitions:* For definitions of terms used in this specification refer to Terminology D1711.

3.2 *Definition of Term Specific to This Standard:*

3.2.1 *aging, (act of), n*—exposure of materials to air at a temperature of 121°C for 168 h and oil at 100°C for 18 h.

4. Physical Properties

4.1 Thermoplastic jackets shall conform to the requirements for physical properties specified in Table 1.

4.2 When used on single-conductor non-shielded cable rated 2001 to 5000 V phase to phase, the jacket shall also conform to the requirements for surface resistivity and U-bend discharge prescribed in Table 2.

5. Sunlight and Weather Resistance Requirements

5.1 If sunlight and weather resistance are required of the jackets, the jackets shall conform to the requirements specified in Table 3.

6. Sampling

6.1 Sample the jacket in accordance with Methods D2633.

7. Test Methods

7.1 Test the jacket in accordance with Methods D2633. If the sunlight and weather resistance test is required, perform it in accordance with Practice D1499 and Practice G153.

8. Keywords

8.1 chlorinated polyethylene; heat distortion; oil immersion; sunlight resistance; tensile strength; tensile stress; thermoplastic;

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.18 on Solid Insulations, Non-Metallic Shieldings and Coverings for Electrical and Telecommunication Wires and Cables.

Current edition approved Oct. 1, 2010; 2012. Published October 2010; February 2012. Originally approved in 1987. Last previous edition approved in 2003; 2010 as D4363–98(2010). DOI: ~~10.1520/D4363-98R10~~ 10.1520/D4363-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.