

INTERNATIONAL STANDARD

ISO 2897-1

First edition
1990-10-15

Plastics — Impact-resistant polystyrene (SB) moulding and extrusion materials —

Part 1: Designation

iTeh STANDARD PREVIEW
(standards.iteh.ai)

*Plastiques — Polystyrène (SB) résistant au choc pour moulage et
extrusion —*

ISO 2897-1:1990

<https://standards.iteh.ai/standards/ISO/ISO-2897-1:1990>
Partie 1: Désignation

<https://standards.iteh.ai/standards/ISO/ISO-2897-1:1990>



Reference number
ISO 2897-1:1990(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 2897-1 was prepared by Technical Committee ISO/TC 61, *Plastics*.

Together with ISO 2897-2, this International Standard cancels and replaces ISO 2897:1976.

ISO 2897 consists of the following parts, under the general title *Plastics — Impact-resistant polystyrene (SB) moulding and extrusion materials*:

- Part 1: *Designation*
- Part 2: *Determination of properties*

© ISO 1990

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Plastics — Impact-resistant polystyrene (SB) moulding and extrusion materials —

Part 1: Designation

1 Scope

1.1 This part of ISO 2897 establishes a system of designation for impact-resistant polystyrene (SB) thermoplastic materials, which may be used as the basis for specifications.

1.2 The types of impact-resistant polystyrene plastic are differentiated from each other by a classification system based on appropriate levels of the designatory properties

- a) Vicat softening temperature,
- b) melt flow rate,
- c) impact strength and
- d) flexural modulus,

and on information about intended application, method of processing, important properties, additives and colour.

1.3 This designation system is applicable to all impact-resistant polystyrene plastics with a two-phase polymer system comprised of a continuous phase, consisting of polystyrene and/or a copolymer of styrene with an alkyl-substituted styrene, and a dispersed elastomeric phase based on butadiene.

It applies to materials ready for normal use, unmodified and modified by colorants, additives, etc.

This part of ISO 2897 does not apply to expandable materials.

1.4 It is not intended to imply that materials having the same designation give necessarily the same performance. This part of ISO 2897 does not provide engineering data, performance data or data on processing conditions which may be required to specify a material for a particular application or method of processing.

If such additional properties are required, they shall be determined in accordance with the test methods specified in ISO 2897-2, if suitable.

1.5 In order to specify a thermoplastic material for a particular application, additional requirements may be specified in Data Block 5 (see clause 3).

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 2897. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 2897 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 178:1975, *Plastics — Determination of flexural properties of rigid plastics.*

ISO 180:1982, *Plastics — Determination of Izod impact strength of rigid materials.*

ISO 293:1986, *Plastics — Compression moulding test specimens of thermoplastic materials.*

ISO 306:1987, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature.*

ISO 1043-1:1987, *Plastics — Symbols — Part 1: Basic polymers and their special characteristics.*

ISO 1133:1981, *Plastics — Determination of the melt flow rate of thermoplastics.*

ISO 2557-1:1989, *Plastics — Amorphous thermoplastics — Preparation of test specimens with a specified maximum reversion — Part 1: Bars.*

ISO 2897-2:1981, *Plastics — Impact-resistant polystyrenes — Part 2: Determination of properties.*

ISO 8328:1989, *Plastics — Amorphous thermoplastic moulding materials — Determination of maximum reversion.*

3 Designation system

The designation system for thermoplastics is based on the standardized pattern given in figure 1.

The designation consists of an optional Description Block, reading Thermoplastics, and an Identity Block comprising the International Standard number and an Individual Item Block. For unambiguous designation, the Individual Item Block is subdivided into 4 data blocks comprising the following information:

Data Block 1: Identification of the plastic by its symbol (SB) (see 3.1)

Data Block 2: Position 1: Intended application or method of processing (see 3.2).

Positions 2 to 4: Important properties, additives and supplementary information (see 3.2).

Data Block 3: Designatory properties (see 3.3).

Data Block 4: Fillers or reinforcing materials and the nominal content thereof (not included in this part of ISO 2897).

For the purpose of specifications, a fifth data block may be added containing additional information. The kind of information and the code-letters used are not the subject of this part of ISO 2897.

The first character of the Individual Item Block shall be a hyphen.

The four data blocks shall be separated from each other by a comma.

If a data block is not used, this shall be indicated by doubling the separation sign, i.e. by two commas (,,).

3.1 Data Block 1

In this data block, after the hyphen, impact-resistant polystyrene is identified by its symbol (SB) in accordance with ISO 1043-1.

Designation						
Description Block (optional)	Identity Block					
	International Standard Block	Individual Item Block				
		Data Block 1	Data Block 2	Data Block 3	Data Block 4	Data Block 5

Figure 1 — Data block designation system

3.2 Data Block 2

In this data block, information about the intended application or method of processing is given in position 1 and information about important properties, additives and colour in positions 2 to 4. The code-letters used are specified in table 1.

Table 1 — Code-letters used in Data Block 2

Code-letter	Position 1	Positions 2 to 4
A		Processing stabilized
B		Antiblocking
C		Coloured
E	Extrusion of pipes, profiles and sheet	
F	Extrusion of film and thin sheeting	Special burning characteristics
G	General use	Pellets; granules
L		Light and/or weather stabilized
M	Injection moulding	
N		Natural (not coloured)
R		Moulding release agent
S		Lubricated
T		Improved transparency
X	No indication	
Z		Antistatic

If information is presented in positions 2 to 4 and no specific information is given in position 1, the letter X shall be inserted in position 1.

3.3 Data Block 3

In this data block, the Vicat softening temperature is represented by a three-figure code-number (see 3.3.1), the melt flow rate by a two-figure code-number (see 3.3.2), the impact strength by a two-figure code-number (see 3.3.3) and the flexural modulus by a two-figure code-number (see 3.3.4). The four codes are separated from each other by hyphens.

If a property value falls on or near a range limit, the manufacturer shall state which range will designate the material. If subsequent individual test values lie on, or either side of, the range limit because of manufacturing tolerances, the designation is not affected.

NOTE 1 Not all combinations of the values of the designatory properties are provided by currently available materials.

3.3.1 Vicat softening temperature

The Vicat softening temperature (VST) shall be determined in accordance with ISO 306, method B, using a test load of $50 \text{ N} \pm 1 \text{ N}$ and a heating rate of $50 \text{ }^\circ\text{C/h} \pm 5 \text{ }^\circ\text{C/h}$. The possible values of the VST are divided into six ranges, each represented by a three-figure code-number, as specified in table 2.

Table 2 — Codes used for Vicat softening temperature in Data Block 3

Code	VST range °C
078	≤ 80
083	$> 80 \text{ to } \leq 85$
088	$> 85 \text{ to } \leq 90$
093	$> 90 \text{ to } \leq 95$
098	$> 95 \text{ to } \leq 100$
103	> 100

3.3.2 Melt flow rate

The melt flow rate (MFR) shall be determined in accordance with ISO 1133, using set of test conditions No. 8 (temperature $200 \text{ }^\circ\text{C}$, load 5 kg).

The possible values of the MFR are divided into four ranges, each represented by a two-figure code-number, as specified in table 3.

Table 3 — Codes used for melt flow rate in Data Block 3

Code	MFR range g/10 min
03	≤ 4
06	$> 4 \text{ to } \leq 8$
12	$> 8 \text{ to } \leq 16$
20	> 16

3.3.3 Izod impact strength

The Izod impact strength shall be determined with test specimens in the basic state (see ISO 2557-1), having a maximum reversion S_m , measured in accordance with ISO 8328, of $< 5 \%$. The test specimens shall be prepared either by compression moulding, in accordance with ISO 293, or, alternatively, by thermal relaxation of injection-moulded test specimens, as specified in ISO 2557-1.

The impact strength shall be determined by method 4A of ISO 180.

The possible values of the impact strength are divided into five ranges, each represented by a two-figure code-number, as specified in table 4.

Table 4 — Codes used for Izod impact strength in Data Block 3

Izod impact strength	
Code	Range kJ/m ²
02	> 1,5 to ≤ 3
04	> 3 to ≤ 6
07	> 6 to ≤ 9
10	> 9 to ≤ 12
15	> 12

3.3.4 Flexural modulus

The flexural modulus shall be determined in accordance with ISO 178 with 80 mm × 10 mm × 4 mm test specimens in the basic state, prepared as specified in 3.3.3. The possible values of the flexural modulus are divided into four ranges, each repres-


ented by a two-figure code-number, as specified in table 5.

Table 5 — Codes used for flexural modulus in Data Block 3

Code	Flexural modulus range MPa
12	≤ 1 500
18	> 1 500 to ≤ 2 000
23	> 2 000 to ≤ 2 500
30	> 2 500

4 Example of designation

An SB intended for injection moulding (M), light and/or weather stabilized (L), natural (not coloured) (N), with a Vicat softening temperature of 84 °C (083), a melt flow rate of 14 g/10 min (12), an Izod impact strength of 8 kJ/m² (07) and a flexural modulus of 2 200 MPa (23), would be designated:



Designation: ISO 2897-SB,MLN,083-12-07-23

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2897-1:1990

<https://standards.iteh.ai/catalog/standards/sist/7539aab1-c2e8-44dc-b72c-2f7d5854eb87/iso-2897-1-1990>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2897-1:1990

<https://standards.iteh.ai/catalog/standards/sist/7539aab1-c2e8-44dc-b72c-2f7d5854eb87/iso-2897-1-1990>

UDC 678.746.222.001.33:678.01:539.411.5

Descriptors: plastics, polystyrene, moulding materials, extrusions, designation.

Price based on 4 pages
