

---

---

---

**6Al-4V titanium alloys —  
Determination of aluminium and  
vanadium contents — Inductively  
coupled plasma atomic emission  
spectrometric method**

iT  
6Al-4V alliages de titane — Détermination de la teneur en aluminium  
et en vanadium — Méthode par spectrométrie d'émission atomique  
avec plasma à couplage inductif  
(<https://standards.iteh.ai>)  
Document Preview

[ISO 21339:2023](https://standards.iteh.ai/catalog/standards/iso/e2af1d53-3b03-48d0-9a62-704a68e9a8d7/iso-21339-2023)  
<https://standards.iteh.ai/catalog/standards/iso/e2af1d53-3b03-48d0-9a62-704a68e9a8d7/iso-21339-2023>



Reference number  
ISO 21339:2023(E)

# iTeh Standards

## (<https://standards.iteh.ai>)

### Document Preview

[ISO 21339:2023](#)

<https://standards.iteh.ai/catalog/standards/iso/e2af1d53-3b03-48d0-9a62-704a68e9a8d7/iso-21339-2023>



#### COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Page

<b>Foreword</b>	iv
<b>1 Scope</b>	1
<b>2 Normative references</b>	1
<b>3 Terms and definitions</b>	1
<b>4 Principle</b>	1
<b>5 Reagents</b>	1
5.1 General	1
5.2 Hydrochloric acid solution, 1+1	1
5.3 Nitric acid solution, 1+1	2
5.4 Hydrofluoric acid solution, 1+1	2
5.5 Titanium	2
5.6 Indium solution, 1 g/l	2
5.7 Cobalt solution, 1 g/l	2
5.8 Strontium solution, 1 g/l	2
5.9 Aluminium standard solution, 1 g/l	2
5.10 Vanadium standard solution, 1 g/l	2
<b>6 Apparatus</b>	2
6.1 General	2
6.2 Volumetric glassware	3
6.3 Plastic beaker, volumetric plastic flask and plastic watch glass	3
6.4 Atomic emission spectrometer, equipped with an inductively coupled plasma (ICP-AES)	3
<b>7 Sampling</b>	3
<b>8 Procedure</b>	3
8.1 Test portion	3
8.2 Number of determinations	3
8.3 Preparation of the calibration solutions	3
8.4 Preparation of the test solutions	4
8.5 Determination	4
8.5.1 General	4
8.5.2 Spectrometric measurements of the calibration solutions	4
8.5.3 Spectrometric measurements of the test solutions	5
<b>9 Expression of result</b>	5
<b>10 Precision</b>	6
<b>11 Test report</b>	7
<b>Annex A (informative) Additional information on the international inter-laboratory test</b>	8
<b>Annex B (informative) Graphical representation of the precision data</b>	9
<b>Bibliography</b>	11

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at [www.iso.org/patents](http://www.iso.org/patents). ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 11, *Titanium*.

ISO 21339:2023

<https://standards.iteh.ai/catalog/standards/iso/c2af1d53-3b03-48d0-9a62-704a68e9a8d7/iso-21339-2023>  
Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# 6Al-4V titanium alloys — Determination of aluminium and vanadium contents — Inductively coupled plasma atomic emission spectrometric method

## 1 Scope

This document specifies an inductively coupled plasma atomic emission spectrometric method for the determination of the contents (mass fraction) of aluminium and vanadium in 6Al-4V titanium alloys.

This method is applicable to all kinds of 6Al-4V titanium alloys specified in ISO 23515 (designation of titanium alloys) for aluminium in the range from 4,70 % to 7,00 % and vanadium in the range from 3,00 % to 5,00 %.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

## 3 Terms and definitions

[ISO 21339:2023](https://standards.iteh.ai/iso-21339-2023)

<https://standards.iteh.ai/iso-21339-2023>

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

## 4 Principle

A test portion is dissolved with nitric and hydrofluoric acids. After suitable dilution and, if necessary, addition of an internal standard element, the solution is nebulized into an inductively coupled plasma atomic emission spectrometer and the intensity of the emitted light from each element is measured (including, where relevant, the intensity of the internal standard element).

## 5 Reagents

### 5.1 General

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only grade 2 water as specified in ISO 3696.

### 5.2 Hydrochloric acid solution, 1+1

Add slowly 500 ml of hydrochloric acid ( $\rho_{20}$  1,16 g/ml to 1,19 g/ml) to 500 ml of water and mix.

### 5.3 Nitric acid solution, 1+1

Add slowly 500 ml of nitric acid ( $\rho_{20}$  1,42 g/ml) to 500 ml of water and mix.

### 5.4 Hydrofluoric acid solution, 1+1

Add, carefully and slowly, 100 ml of hydrofluoric acid ( $\rho_{20}$  1,14 g/ml) to 100 ml of water and mix.

### 5.5 Titanium

High purity titanium [min 99,9 % (mass fraction)], containing less than or equal to 0,005 % (mass fraction) of aluminium and vanadium.

### 5.6 Indium solution, 1 g/l

Weigh 1,000 g of high purity indium [min 99,9 % (mass fraction)]. Transfer it into a 300 ml beaker and add 100 ml of hydrochloric acid (5.2) and 20 ml of nitric acid (5.3). Heat gently to complete dissolution. Cool, transfer the solution quantitatively into a 1 000 ml one-mark volumetric flask, dilute to the mark with water and mix.

### 5.7 Cobalt solution, 1 g/l

Weigh 1,000 g of high purity cobalt [min 99,9 % (mass fraction)]. Transfer it into a 300 ml beaker and add 100 ml of nitric acid (5.3). Heat gently to complete dissolution. Cool, transfer the solution quantitatively into a 1 000 ml one-mark volumetric flask, dilute to the mark with water and mix.

### 5.8 Strontium solution, 1 g/l

Weigh 3,043 g of strontium chloride [ $\text{SrCl}_2 \cdot 6\text{H}_2\text{O}$ ]. Transfer it into a 300 ml beaker. Dissolve with water, transfer the solution quantitatively into a 1 000 ml one-mark volumetric flask, dilute to the mark with water and mix.

ISO 21339:2023

### 5.9 Aluminium standard solution, 1 g/l

Weigh 1,000 g of high purity aluminium [min 99,9 % (mass fraction)]. Transfer it into a 300 ml beaker and add 100 ml of hydrochloric acid (5.2) and 20 ml of nitric acid (5.3). Heat gently to complete dissolution. Cool, transfer the solution quantitatively into a 1 000 ml one-mark volumetric flask, dilute to the mark with water and mix.

1 ml of this solution contains 1 mg of aluminium.

### 5.10 Vanadium standard solution, 1 g/l

Weigh 1,000 g of high purity vanadium [min 99,9 % (mass fraction)]. Transfer it into a 300 ml beaker and add 100 ml of hydrochloric acid (5.2) and 20 ml of nitric acid (5.3). Heat gently to complete dissolution. Cool, transfer the solution quantitatively into a 1 000 ml one-mark volumetric flask, dilute to the mark with water and mix.

1 ml of this solution contains 1 mg of vanadium.

## 6 Apparatus

### 6.1 General

The usual laboratory apparatus and, in particular, the following shall be used.