
**Petroleum, petrochemical and natural
gas industries — External corrosion
protection of risers by coatings and
linings —**

Part 2:

**Maintenance and field repair coatings
for riser pipes**
(standards.iteh.ai)

*Industries du pétrole, de la pétrochimie et du gaz naturel —
Protection de la corrosion externe des tubes de production par
revêtements et doublures —*
Partie 2: Entretien et réparation in situ des tubes de production

<https://standards.iteh.ai/catalog/standards/sist/41c413c7-c13d-4df4-9f46-c076ac48a76/iso-18797-2-2021>



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 18797-2:2021

<https://standards.iteh.ai/catalog/standards/sist/41d4a5c7-c13d-4df4-9f46-c076aa4f8a76/iso-18797-2-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	vi
Introduction	vii
1 Scope	1
2 Normative references	1
3 Terms and definitions	4
4 Symbols and abbreviated terms	7
4.1 Symbols.....	7
4.2 Abbreviated terms.....	7
5 Coating types	7
6 General requirements	8
6.1 Client's requirements.....	8
6.1.1 Approval of repair coating and repair method.....	8
6.1.2 Specification of purchase order mandatory information.....	8
6.1.3 Specification of purchase order additional information.....	9
6.2 Contractor's requirements.....	9
6.2.1 Documented information.....	9
6.2.2 Marking of coating materials.....	10
6.3 Rounding.....	10
6.4 Conformity to requirements.....	10
6.5 Criteria for the condition assessment of an existing coating.....	10
6.5.1 General – Evaluation of coating condition.....	10
6.5.2 Applicable inspection techniques.....	11
7 Qualification processes and application procedures	11
7.1 General.....	11
7.2 APS and ITP.....	12
7.2.1 General.....	12
7.2.2 APS.....	12
7.2.3 ITP.....	13
7.3 Technical assessment of coating conformity.....	13
7.4 Procedure qualification trial.....	13
7.5 Pre-production trial.....	14
7.6 Production, testing and inspection.....	15
7.6.1 General.....	15
7.6.2 Inspection documents and traceability.....	15
8 Selection criteria for repair coatings	15
8.1 General.....	15
8.2 Application constraints.....	16
8.2.1 Wet substrates.....	16
8.2.2 Contamination by soluble salts.....	17
8.2.3 Dust contamination.....	17
8.2.4 Contamination by oil, grease and other petroleum-like products.....	17
8.2.5 Compatibility with existing coating.....	17
8.2.6 Feasibility of surface cleaning.....	18
8.2.7 Space and riser access constraints.....	18
8.2.8 Time constraints.....	18
8.2.9 Temperatures and relative humidity.....	18
8.2.10 Coating continuity.....	18
8.3 Operational conditions.....	19
8.3.1 Resistance to ageing, weathering and water.....	19
8.3.2 Resistance to mechanical loads.....	19
8.3.3 Interaction with cathodic protection.....	19

9	Test programs	19
9.1	Substrate conditions used for tests	19
9.2	Inspections, tests and frequencies	19
9.3	Thickness testing	20
9.4	Retest	20
10	Non-crystalline low-viscosity polyolefin-based coatings	21
10.1	Coating identification	21
10.2	Description of the coatings	21
10.3	Surface preparation	22
10.4	Application of coatings	22
	10.4.1 General	22
	10.4.2 Overlap	22
10.5	Testing of coatings	22
	10.5.1 General	22
	10.5.2 Thickness	22
	10.5.3 Glass transition temperature and crystallization temperature	23
	10.5.4 Holiday detection	23
	10.5.5 Drip resistance	23
	10.5.6 Adhesion to pipe surface and existing coating	23
	10.5.7 Lap shear resistance	24
	10.5.8 Specific electrical insulation resistance	24
	10.5.9 Impact resistance	24
	10.5.10 Indentation resistance	24
	10.5.11 Cathodic disbondment resistance	25
	10.5.12 Resistance to ageing and weathering	25
	10.5.13 Peel strength between layers of outer wrap	25
	10.5.14 Thermal ageing resistance	26
	10.5.15 Hot-water immersion test	26
11	Petrolatum and wax-based tape wrap systems	31
11.1	Coating identification	31
11.2	Description of the tape wrap systems	32
	11.2.1 Petrolatum tape wrap systems (type 11A)	32
	11.2.2 Wax-based tape wrap systems (type 11B)	32
11.3	Surface preparation	32
11.4	Application of coating systems	32
	11.4.1 General	32
	11.4.2 Overlap	32
11.5	Testing of the coating systems	33
	11.5.1 General	33
	11.5.2 Density	33
	11.5.3 Dielectric strength	33
	11.5.4 Thickness	33
	11.5.5 Holiday detection	34
	11.5.6 Impact resistance	34
	11.5.7 Specific electrical insulation resistance	34
	11.5.8 Cathodic disbondment resistance	34
	11.5.9 Adhesion to pipe surface and existing coating	34
	11.5.10 Drip resistance	35
	11.5.11 Hot water immersion test	35
	11.5.12 Resistance to ageing and weathering	35
12	Polychloroprene-based elastomeric coatings	41
12.1	Coating identification	41
12.2	Description of the coatings	41
12.3	Surface preparation	41
12.4	Application of the coating	41
	12.4.1 General	41
	12.4.2 Overlap	42

12.5	Testing of the coatings	42
12.5.1	General	42
12.5.2	Visual appearance	42
12.5.3	Thickness	42
12.5.4	Holiday detection	42
12.5.5	Hardness	42
12.5.6	Adhesion to pipe surface and existing coating	42
12.5.7	Cathodic disbondment resistance	43
12.5.8	Density	43
12.5.9	Rheometer curve	43
12.5.10	Tensile strength	43
12.5.11	Elongation at break	43
12.5.12	Tear strength	43
12.5.13	Electrical volume resistivity	43
12.5.14	Ozone resistance	43
12.5.15	Resistance to seawater	44
12.5.16	Hot-water immersion test	44
12.5.17	Thermal ageing resistance	44
12.5.18	Resistance to ageing and weathering	44
13	Liquid-applied epoxy coatings	46
13.1	Coating identification	46
13.2	Description of the liquid-applied epoxy coating	47
13.3	Surface preparation	47
13.4	Application of the coatings	47
13.4.1	General	47
13.4.2	Overlap	47
13.5	Testing of the coatings	47
13.5.1	General	47
13.5.2	Dry-film thickness	48
13.5.3	Holiday detection	48
13.5.4	Hardness	48
13.5.5	Impact resistance	48
13.5.6	Indentation resistance	48
13.5.7	Specific electrical insulation resistance	48
13.5.8	Cathodic disbondment resistance	49
13.5.9	Adhesion to pipe surface and existing coating	49
13.5.10	Thermal ageing resistance	49
13.5.11	Hot-water immersion test	49
13.5.12	Resistance to ageing and weathering	49
	Annex A (informative) Likelihood of exposure in splash zone area	54
	Annex B (informative) Tests for coatings applied on wet substrates	56
	Bibliography	65

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 12, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

A list of all parts in the ISO 18797 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document has been developed in response to worldwide demand for minimum specifications for field applied maintenance and repair coatings for riser pipes. ISO 18797-1 specifies the shop applied coatings for risers. Coated offshore risers are intermittently exposed to varying conditions. These include – but are not limited to – sunlight, rain, snow, hail, water spray, salt spray, high humidity, fluctuating ambient temperatures (varying from sub-zero to high temperature), water currents, and impacts from waves, drifting debris and marine growth. Exposure to such conditions can cause severe coating deterioration in time, resulting in ineffective corrosion prevention of the steel riser pipe.

Users of this document are advised that further or differing requirements can be utilized for individual applications. This document can also be used for the maintenance and repair of coatings on other types of structures in the offshore splash zone, such as jetty piles and platform legs. This document does not limit the contractor or the manufacturer from proposing, or from accepting, alternative engineering solutions for the individual application. This can be particularly applicable where there is innovative or developing technology. Where an alternative is proposed, the specification issuer is expected to identify any deviations from this document and provide details.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 18797-2:2021

<https://standards.iteh.ai/catalog/standards/sist/41d4a5c7-c13d-4df4-9f46-c076aa4f8a76/iso-18797-2-2021>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18797-2:2021

<https://standards.iteh.ai/catalog/standards/sist/41d4a5c7-c13d-4df4-9f46-c076aa4f8a76/iso-18797-2-2021>

Petroleum, petrochemical and natural gas industries — External corrosion protection of risers by coatings and linings —

Part 2: Maintenance and field repair coatings for riser pipes

1 Scope

This document specifies the selection criteria and minimum requirements for protective coating systems for maintenance and field repair of risers exposed to conditions in the splash zone. It is applicable for maintenance requirements and field repairs of riser coatings.

This document does not apply to the selection of techniques and materials used to restore integrity of the risers to be coated, nor does it apply to the selection of additional mechanical protective materials that are not part of the coating systems described in this document.

New construction shop applied riser coatings are covered in ISO 18797-1. Compatible maintenance and repair coating systems specified in ISO 18797-1 are covered in this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 34-1, *Rubber, vulcanized or thermoplastic — Determination of tear strength — Part 1: Trouser, angle and crescent test pieces*

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 48-2, *Rubber, vulcanized or thermoplastic — Determination of hardness — Part 2: Hardness between 10 IRHD and 100 IRHD*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 527-3, *Plastics — Determination of tensile properties — Part 3: Test conditions for films and sheets*

ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1431-1, *Rubber, vulcanized or thermoplastic — Resistance to ozone cracking — Part 1: Static and dynamic strain testing*

ISO 1523, *Determination of flash point — Closed cup equilibrium method*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 18797-2:2021(E)

ISO 2781, *Rubber, vulcanized or thermoplastic — Determination of density*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 2811-1, *Paints and varnishes — Determination of density — Part 1: Pycnometer method*

ISO 3233-1, *Paints and varnishes — Determination of percentage volume of non-volatile matter — Part 1: Method using a coated test panel to determine non-volatile matter and to determine dry-film density by the Archimedes' principle*

ISO 3251, *Paints, varnishes and plastics — Determination of non-volatile-matter content*

ISO 3801, *Textiles — Woven fabrics — Determination of mass per unit length and mass per unit area*

ISO 4591, *Plastics — Film and sheeting — Determination of average thickness of a sample, and average thickness and yield of a roll, by gravimetric techniques (gravimetric thickness)*

ISO 4593, *Plastics — Film and sheeting — Determination of thickness by mechanical scanning*

ISO 4624, *Paints and varnishes — Pull-off test for adhesion*

ISO 4628-2, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 2: Assessment of degree of blistering*

ISO 4628-3, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 3: Assessment of degree of rusting*

ISO 4628-4, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 4: Assessment of degree of cracking*

ISO 4628-5, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 5: Assessment of degree of flaking*

ISO 4628-6, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 6: Assessment of degree of chalking by tape method*

ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps*

ISO 6502-2, *Rubber — Measurement of vulcanization characteristics using curemeters — Part 2: Oscillating disc curemeter*

ISO 6964, *Polyolefin pipes and fittings — Determination of carbon black content by calcination and pyrolysis — Test method*

ISO 8501-1, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings*

ISO 8501-4, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 4: Initial surface conditions, preparation grades and flash rust grades in connection with high-pressure water jetting*

ISO 8502-3, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 3: Assessment of dust on steel surfaces prepared for painting (pressure-sensitive tape method)*

ISO 8502-4, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 4: Guidance on the estimation of the probability of condensation prior to paint application*

ISO 8502-6, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 6: Extraction of water soluble contaminants for analysis (Bresle method)*

ISO 8502-9, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 9: Field method for the conductometric determination of water-soluble salts*

ISO 8503-2, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 2: Method for the grading of surface profile of abrasive blast-cleaned steel — Comparator procedure*

ISO 8503-5, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 5: Replica tape method for the determination of the surface profile*

ISO 10474, *Steel and steel products — Inspection documents*

ISO 11357-1, *Plastics — Differential scanning calorimetry (DSC) — Part 1: General principles*

ISO 11357-2, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature and step height*

ISO 11357-3, *Plastics — Differential scanning calorimetry (DSC) — Part 3: Determination of temperature and enthalpy of melting and crystallization*

ISO 12944-9:2018, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 9: Protective paint systems and laboratory performance test methods for offshore and related structures*

ISO 16474-3, *Paints and varnishes — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps*

ISO 18797-1, *Petroleum, petrochemical and natural gas industries — External corrosion protection of risers by coatings and linings — Part 1: Elastomeric coating systems-polychloroprene or EPDM*

ISO 19840, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Measurement of, and acceptance criteria for, the thickness of dry films on rough surfaces*

ISO 21809-3:2016, *Petroleum and natural gas industries — External coatings for buried or submerged pipelines used in pipeline transportation systems — Part 3: Field joint coatings*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

ISO 80000-1:2009, *Quantities and units — Part 1: General*

ASTM D149, *Standard Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies*

ASTM D991, *Standard Test Method for Rubber Property — Volume Resistivity Of Electrically Conductive and Antistatic Products*

ASTM D1141, *Standard Practice for the Preparation of Substitute Ocean Water*

ASTM D5894, *Standard Practice for Cyclic Salt Fog/UV Exposure of Painted Metal, (Alternating Exposures in a Fog/Dry Cabinet and a UV/Condensation Cabinet)*

ASTM F22, *Standard Test Method for Hydrophobic Surface Films by the Water-Break Test*

NACE SP0274, *High-Voltage Electrical Inspection of Pipeline Coatings*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 application procedure specification APS

document describing procedures, methods, equipment and tools used for coating application

3.2 applicator

contractor (3.6) or subcontractor having the technical capability, knowledge, equipment and qualified personnel that is approved by the *client* (3.4) for the coating process

3.3 atmospheric zone

external *surface* (3.26) of a *riser* (3.19) that extends upward from the *splash zone* (3.22) up to the top decks of the platform which are exposed to sun, wind, sprays and rains

3.4 client

organization for which professional services are rendered or person that receives a product

3.5 complete coating

installed coating ready for commissioning comprising all individual parts of the coating material

3.6 contractor

organization that agrees to furnish materials and/or perform specific services to the *client* (3.4)

3.7 dry film thickness DFT

thickness of a coating remaining over the peaks of a rough *surface* (3.26) when the coating has hardened

[SOURCE: ISO 19840:2012, 3.1]

3.8 failure mechanism

process that leads to failure

Note 1 to entry: ISO 14224:2016, B.2.2 and Table B.2, define failure causes for all equipment classes.

3.9 failure mode

manner in which failure occurs

Note 1 to entry: ISO 14224:2016, B.2.6, contains tables with relevant failure modes defining failure modes to be used for each equipment class.

3.10 holiday

coating discontinuity that exhibits electrical conductivity when exposed to a specific voltage

3.11 inspection and testing plan ITP

document providing an overview of the sequence of inspections and tests, including standard references, recommended apparatuses (tools) and testing procedures

3.12 maintenance and repair of a coating

activities dedicated to retaining or restoring the integrity of the existing coating in order to reach a level of protection against corrosion that enables a metallic structure to continue in service operation safely and economically for a determinate period

Note 1 to entry: Maintenance of a coating can refer to the activities to restore either the damages that are localized on small areas and do not require the complete removal of existing coating, or damage over larger areas that require the complete removal of existing coating and installation of field repair coating.

Note 2 to entry: For the purposes of this document, all types of coating used for maintenance and repair of riser coatings are designated as "repair coating".

Note 3 to entry: In ISO 14224:2016, 3.49, "maintenance" is defined as a combination of all technical and management actions intended to retain an item in, or restore it to, a state in which it can perform as required.

Note 4 to entry: In ISO 14224:2016, 3.8, "corrective maintenance" is defined as maintenance carried out after fault detection to effect restoration.

Note 5 to entry: "Repair" is a type of maintenance activity as defined in ISO 14224:2016, Table B.5.

3.13 manufacturer

organization responsible for the manufacture of coating material(s)

3.14 nominal dry film thickness NDFT

dry film thickness (3.7) specified for each coat or for the whole paint system to achieve the required durability

[SOURCE: ISO 19840:2012, 3.6]

3.15 nominal strain at break elongation at break

nominal strain at the last recorded data point before the stress is reduced to less than or equal to 10 % of the strength if the break occurs after yielding

Note 1 to entry: Nominal strain is the representation of strain calculated from grip displacement and the gripping distance.

[SOURCE: ISO 527-1:2019, 3.8 and 3.8.1]

3.16 nominal thickness

dimension as specified by the *manufacturer* (3.13)

Note 1 to entry: The nominal thickness of the complete coating is the calculated sum of the nominal thicknesses of all the layers of the coating before application.

3.17
pre-production trial
PPT

application of coating and subsequent inspection and testing of its properties, to confirm that the *application procedure specification* (3.1) contains all necessary instructions to install the coatings in conformity with specific minimum requirements, carried out at the job site immediately prior to production

3.18
procedure qualification trial
PQT

application of coating and subsequent inspection and testing of its properties, to confirm that the *application procedure specification* (3.1) contains all necessary instructions to install the coatings in conformity with minimum requirements, carried out at the premises of the *contractor* (3.6) or another agreed location

3.19
riser

section of pipeline carrying crude oil or gas between the ocean floor and the upper decks of the platform on offshore structures

Note 1 to entry: In ISO 14224:2016, "riser" is a specific equipment class as per ISO 14224:2016, Table A.4 (level 6) and "coating" is a "maintainable item" for risers, as per ISO 14224:2016, Table A.93.

3.20
self-healing

ability of a coating to restore its original film thickness (leaving no *holidays* (3.10) as a result), after a 6 mm diameter defect is made down to bare metal

3.21
shift

time period when a crew of workers is at work

iTeh STANDARD PREVIEW
(standards.iteh.ai)
ISO 18797-2:2021
<https://standards.iteh.ai/catalog/standards/sist/41d4a5c7-c13d-4df4-9f46-c076aa4f8a76/iso-18797-2-2021>

3.22
splash zone

external *surface* (3.26) of a *riser* (3.19) area above and below the mean water level that is periodically wet and dry due to the influence of the astronomical tides, winds and waves

Note 1 to entry: The limits are as defined by the contract specifications.

3.23
strain at break

strain at the last recorded data point before the stress is reduced to less than or equal to 10 % of the strength if the break occurs prior to yielding

[SOURCE: ISO 527-1:2019, 3.7.2, modified — Note 2 to entry has been deleted.]

3.24
stress at break

stress at which the specimen breaks

Note 1 to entry: Expressed in megapascals (MPa).

[SOURCE: ISO 527-1:2019, 3.6.4, modified — Note 2 to entry has been deleted.]

3.25
submerged zone

external *surface* (3.26) of a *riser* (3.19) below the water level

3.26
surface

interface between *substrate* (3.28) and environment where coating is applied

3.27**surface preparation**

method of preparing a *surface* (3.26) for coating application

Note 1 to entry: ISO 12944-4:2017, Clause 6, contains a comprehensive overview of suitable methods for surface preparation.

3.28**substrate**

material from which the *riser* (3.19) is made

3.29**technical assessment****TA**

application of coating and subsequent inspection and testing of its properties to confirm that the coatings are meeting the minimum requirements

Note 1 to entry: Technical assessment is usually carried out under controlled laboratory conditions.

3.30**weld cap**

outermost *surface* (3.26) of the weld

4 Symbols and abbreviated terms**4.1 Symbols**

T_{\max}	maximum service temperature of coating
ϵ_b	strain at break
ϵ_{tb}	nominal strain at break
σ_b	stress at break

4.2 Abbreviated terms

HDPE	high-density polyethylene
HSE	health, safety and environment
NACE	NACE International—The Corrosion Society (formerly: National Association of Corrosion Engineers). NACE has merged with SSPC to form the Association for Materials Protection and Performance AMPP
SDS	safety data sheet
SSPC	the Society for Protective Coatings (formerly: the Steel Structures Painting Council)

5 Coating types

The coating types covered by this document are listed in [Table 1](#). [Clauses 6](#) to [9](#) provide requirements that apply to all coating types. [Clauses 10](#) to [13](#) provide coating-specific requirements.