

FINAL  
DRAFT

INTERNATIONAL  
STANDARD

ISO/FDIS  
12736-1

ISO/TC 67/SC 2

Secretariat: UNI

Voting begins on:  
2023-07-06

Voting terminates on:  
2023-08-31

---

---

## Oil and gas industries including lower carbon energy — Wet thermal insulation systems for pipelines and subsea equipment —

### Part 1: Validation of materials and insulation systems

*Industries du pétrole et du gaz, y compris les énergies à faible teneur  
en carbone — Systèmes d'isolation thermique en milieu humide pour  
conduites et équipements sous-marins —*

*Partie 1: Validation des matériaux et des systèmes d'isolation*

ISO/CEN PARALLEL PROCESSING

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number  
ISO/FDIS 12736-1:2023(E)

© ISO 2023

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 12736-1

<https://standards.iteh.ai/catalog/standards/sist/13377be5-2c0f-42a4-864d-7517854222f3/iso-12736-1>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>2</b>
<b>4 Symbols and abbreviated terms.....</b>	<b>7</b>
4.1 Symbols.....	7
4.2 Abbreviated terms.....	8
<b>5 Conformance.....</b>	<b>9</b>
5.1 Rounding.....	9
5.2 Conformity to requirement.....	9
<b>6 Material classes.....</b>	<b>9</b>
<b>7 Materials and system validation testing.....</b>	<b>9</b>
7.1 General.....	9
7.2 Material validation testing.....	10
7.2.1 General.....	10
7.2.2 Small-scale exposure testing for materials.....	11
7.3 System validation testing.....	14
7.3.1 General.....	14
7.3.2 System test requirements.....	14
7.3.3 Full scale test program for systems.....	15
7.3.4 Small-scale full-system exposure test.....	17
7.4 System repairs.....	17
7.5 Validation of long-term performance.....	18
7.6 Technical validation dossier.....	18
7.6.1 General.....	18
7.6.2 Content of the validation dossier.....	19
7.7 Anti-corrosion coating documentation.....	20
<b>Annex A (informative) Guidelines for using this document.....</b>	<b>21</b>
<b>Annex B (normative) Thermal conductivity testing.....</b>	<b>26</b>
<b>Annex C (normative) Hydrostatic compressive behaviour/Tri-axial test procedures.....</b>	<b>38</b>
<b>Annex D (normative) Simulated bend test.....</b>	<b>45</b>
<b>Annex E (normative) System shear resistance test.....</b>	<b>48</b>
<b>Annex F (normative) Impact test.....</b>	<b>50</b>
<b>Annex G (normative) Simulated service test for pipelines.....</b>	<b>53</b>
<b>Annex H (normative) Simulated service test for subsea equipment.....</b>	<b>55</b>
<b>Annex I (normative) Small-scale full-system exposure test.....</b>	<b>58</b>
<b>Bibliography.....</b>	<b>60</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at [www.iso.org/patents](http://www.iso.org/patents). ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 67, *Oil and gas industries including lower carbon energy*, Subcommittee SC 2, *Pipeline transportation systems*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 12, *Oil and gas industries including lower carbon energy*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This first edition of ISO 12736-1, together with ISO 12736-2 and ISO 12736-3, cancels and replaces ISO 12736:2014.

The main changes are as follows:

- clearer delineation between validation and projects;
- introduction of material classes;
- modification of material property testing requirements, including detailed thermal conductivity testing requirements;
- introduction of additional long-term testing requirements;
- introduction of additional system testing requirements, including system interfaces;
- removal of project specific testing requirements;
- addition of requirement for risk-based analysis of the system long-term performance;
- modifications of the format and content requirements of the final validation dossier;
- addition of [Annex A](#) with guidance for using this document.

A list of all parts in the ISO 12736 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 12736-1

<https://standards.iteh.ai/catalog/standards/sist/13377be5-2c0f-42a4-864d-7517854222f3/iso-12736-1>



# Oil and gas industries including lower carbon energy — Wet thermal insulation systems for pipelines and subsea equipment —

## Part 1: Validation of materials and insulation systems

### 1 Scope

This document specifies requirements for the validation of wet thermal insulation systems applied to pipelines and subsea equipment in the oil and gas industry.

This document is applicable to wet thermal insulation systems submerged in seawater.

This document is not applicable to:

- maintenance works on existing installed wet thermal insulation systems;
- qualification for anti-corrosion coating;
- thermal insulation in the annulus of a steel pipe-in-pipe system.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 34-1, *Rubber, vulcanized or thermoplastic — Determination of tear strength — Part 1: Trouser, angle and crescent test pieces*

ISO 34-2, *Rubber, vulcanized or thermoplastic — Determination of tear strength — Part 2: Small (Delft) test pieces*

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 178, *Plastics — Determination of flexural properties*

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 527 (all parts), *Plastics — Determination of tensile properties*

ISO 604, *Plastics — Determination of compressive properties*

ISO 844, *Rigid cellular plastics — Determination of compression properties*

ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 1183 (all parts), *Plastics — Methods for determining the density of non-cellular plastics*

ISO 6721-1, *Plastics — Determination of dynamic mechanical properties — Part 1: General principles*

ISO 8301, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Heat flow meter apparatus*

ISO 8302, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Guarded hot plate apparatus*

ISO 11357-1, *Plastics — Differential scanning calorimetry (DSC) — Part 1: General principles*

ISO 11357-4, *Plastics — Differential scanning calorimetry (DSC) — Part 4: Determination of specific heat capacity*

ISO 11359-2, *Plastics — Thermomechanical analysis (TMA) — Part 2: Determination of coefficient of linear thermal expansion and glass transition temperature*

ISO 12736-2, *Oil and gas industries including lower carbon energy — Wet thermal insulation systems for pipelines and subsea equipment — Part 2: Qualification processes for production and application procedures*

ISO 12736-3, *Oil and gas industries including lower carbon energy — Wet thermal insulation systems for pipelines and subsea equipment — Part 3: Interfaces between systems, field joint systems, field repairs, and pre-fabricated insulation*

ISO 15711, *Paints and varnishes — Determination of resistance to cathodic disbonding of coatings exposed to sea water*

ISO 80000-1, *Quantities and units — Part 1: General*

ASTM D575, *Standard Test Methods for Rubber Properties in Compression*

ISO 80000-1, *Quantities and units — Part 1: General*

iteh STANDARD PREVIEW  
(standards.iteh.ai)

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

#### 3.1 agreed

specified in the purchase order

Note 1 to entry: To be discussed by the *system provider* (3.37) and *system purchaser* (3.38) with input from end user as required.

#### 3.2 application procedure specification APS

quality specification document, or group of specifications, describing procedures, method, equipment, tools, etc. used for *system* (3.35) application

#### 3.3 batch

quantity of *material* (3.18) produced in a continuous manufacturing operation using raw materials of the same source or grade

#### 3.4 blown foam

insulation *material* (3.18) formed by incorporating a gas phase into a polymer matrix



**3.5****certificate of analysis**

document provided by the manufacturer that indicates results of specific tests or analysis, including test methodology, performed on a specified lot of the manufacturer's product and corresponding conformity ranges

**3.6****construction joint**

*interface* (3.13) where both *systems* (3.35) are identical

**3.7****cutback**

length of item left uncoated at each end for joining purposes

Note 1 to entry: Welding is an example of joining purposes.

**3.8****field joint**

uncoated area that results when two pipe sections, or a pipe section and a *fitting* (3.9), with *cutbacks* (3.7) are assembled by welding or other methods

**3.9****fitting**

receptacle on a piece of *subsea equipment* (3.33), which interfaces to a *pipeline* (3.22)

**3.10****high molecular weight precursor thermoset**

*material* (3.18), which is a polymeric compound that remains malleable until application of sufficient heat to cause network formation and then does not flow upon reheating

EXAMPLE Butyl rubber.

**3.11****inorganic syntactic foam**

insulation *material* (3.18) formed by dispersing inorganic hollow particles within a polymer matrix

**3.12****inspection and test plan****ITP**

document providing an overview of the sequence of inspections and tests, including appropriate resources and procedures

**3.13****interface**

location where two *systems* (3.35) meet and affect each other

Note 1 to entry: A *field joint* (3.8) *system* (3.35) has two interfaces.

Note 2 to entry: In the case of multilayer *systems* (3.35), interfaces can be made up of multiple sub-interfaces.

**3.14****jumper**

short section of *pipeline* (3.22) that transfers fluid between two pieces of *subsea equipment* (3.33)

**3.15****liquid precursor elastomeric thermoset**

*material* (3.18), which is a polymeric compound with its glass transition below ambient temperature, that is produced via the combination of one or more components that can be pumped and flow as liquids and that react to create a crosslinked polymer that does not flow upon reheating

EXAMPLE Liquid precursor silicone rubber.

### 3.16

#### **liquid precursor non-elastomeric thermoset**

*material* (3.18), which is a polymeric compound with its glass transition above ambient temperature, that is produced via the combination of one or more components that can be pumped and flow as liquids and that react to create a crosslinked polymer that does not flow upon reheating

EXAMPLE Liquid epoxy.

### 3.17

#### **mainline**

portion of a *pipeline* (3.22) that is not a *field joint* (3.8)

### 3.18

#### **material**

polymeric compound applied to the *substrate* (3.34) protected or insulated in units of discrete thickness (layers) to build up a *system* (3.35)

### 3.19

#### **material manufacturer**

entity responsible for the manufacture of one or more *materials* (3.18) utilized in a *system* (3.35)

### 3.20

#### **material maximum and minimum rated temperature**

maximum and minimum temperature to which a particular *material* (3.18) can be continuously exposed, as per *system provider* (3.37) recommendation, during storage or in service as part of a *system* (3.35)

Note 1 to entry: For multi-layer systems, the material maximum rated temperature can be less than the *system maximum rated temperature* (3.36).

### 3.21

#### **maximum rated pressure**

maximum hydrostatic pressure to which the *system* (3.35) can be exposed, according to the *system provider* (3.37)

### 3.22

#### **pipeline flowline**

tubular piping used to convey fluids

Note 1 to entry: Pipeline includes *jumpers* (3.14), *risers* (3.28) and *field joints* (3.8).

### 3.23

#### **pre-fabricated insulation**

section of stand-alone insulation, which is factory manufactured into its final form and then installed in the field by mechanically fastening or bonding to a corrosion protected structure

### 3.24

#### **pre-production trial**

##### **PPT**

series of tests performed immediately before the start of production, designed to demonstrate that the requirements of the *validated* (3.43) *system* (3.35), the *procedure qualification trial* (3.25) or both are achieved

Note 1 to entry: Requirements for PPT shall be as outlined in ISO 12736-2 or ISO 12736-3 and as *agreed* (3.1).

**3.25****procedure qualification trial  
PQT**

series of tests designed to demonstrate that the *materials* (3.18), *system provider* (3.37), equipment and procedures can produce a *system* (3.35) in accordance with the *validation dossier* (3.44) and meet specific *project* (3.26) requirements

Note 1 to entry: Requirements for PQT shall be as outlined in ISO 12736-2 or ISO 12736-3 and as *agreed* (3.1).

**3.26****project**

scope of work *agreed* (3.1) upon contractually between *system purchaser* (3.38) and *system provider* (3.37)

**3.27****R-lay**

reel-lay

method of *pipeline* (3.22) installation in which long *stalks* (3.32) of pre-insulated pipes are pre-assembled by welding and application of *field joint* (3.8) *system* (3.35) onshore before being spooled onto large reels onboard the installation vessel, which then lays the pipes by unspooling the reel offshore

**3.28****riser**

vertical portion of a *pipeline* (3.22), including the bottom bend, arriving on or departing from an offshore surface installation

**3.29****safety data sheet****SDS**

DEPRACATED: material safety data sheet

document intended to provide workers and emergency personnel with procedures for handling and working with a *material* (3.18) utilized in the manufacture of the *system* (3.35) in a safe manner including physical data and first aid, etc.

Note 1 to entry: Physical data can include flash point and toxicity.

**3.30****service life**

specified period of use for a *system* (3.35) in service

**3.31****solid/solid filled**

insulation *material* (3.18) that systematically does not contain voids or hollow particles

**3.32****stalk**

continuous string of welded and *field joint* (3.8) coated pipe, which is prepared in readiness for pipe spooling onto a *R-lay* (3.27) barge

Note 1 to entry: A number of stalks will normally be required to make up a *pipeline* (3.22).

**3.33****subsea equipment**

components from a subsea production system, including subsea processing items and structures, meant to control hydrocarbons, not including *pipelines* (3.22)

EXAMPLE Valve, connector, manifold, christmas tree, flowline end termination.

**3.34****substrate**

surface to which a *material* (3.18) is applied or will be applied

**3.35  
system**

all of the various *materials* (3.18) and the combination thereof, which can include layers of anti-corrosion, insulation, adhesive, and protective materials, as defined by cross-section to the underlying *substrate* (3.34) at a single point, which function together to act as a *wet thermal insulation* (3.45)

**3.36  
system maximum and minimum rated temperature**

maximum and minimum temperature to which a particular *system* (3.35) can be continuously exposed, as per *system provider* (3.37) recommendation, during storage or in service

**3.37  
system provider**

legal entity which is selling the applied *system* (3.35)

**3.38  
system purchaser**

entity which is purchasing the applied *system* (3.35)

**3.39  
thermal conductivity  
k-value  
conductivity**

heat flow through a unit length of *material* (3.18) under the influence of a thermal gradient

Note 1 to entry: Thermal conductivity is expressed in  $W \cdot m^{-1} \cdot K^{-1}$ .

**3.40  
thermoplastic**

*material* (3.18), which is a polymeric compound that solidifies upon cooling and can flow and be reformed upon reheating

EXAMPLE Polypropylene. [standards.iteh.ai/catalog/standards/sist/13377be5-2c0f-42a4-864d-7517854222f3/iso-12736-1](https://standards.iteh.ai/catalog/standards/sist/13377be5-2c0f-42a4-864d-7517854222f3/iso-12736-1)

**3.41  
tie-in field joint**

connection of a *pipeline* (3.22) to a facility or *subsea equipment* (3.33), to other pipelines, or the connecting together of different sections of a single pipeline

**3.42  
U-value**

overall heat transfer coefficient  
rate of heat transfer from a reference surface under the influence of a thermal gradient

Note 1 to entry: U-value is expressed in  $W \cdot m^{-2} \cdot K^{-1}$ .

**3.43  
validation**

demonstration of *material* (3.18) and *system* (3.35) performance during storage, handling and operation, within a specified envelope of use, as determined by the *system provider* (3.39)

**3.44  
validation dossier**

collection of documentation and test reports, prepared in accordance with specific requirements, which provides detailed information on the proposed *system* (3.35), method of application, the *materials* (3.18) which form said *system* (3.35), and demonstration of *system* (3.35) performance

Note 1 to entry: Specific requirements are found in ISO 12736-1:202X, 7.6.

**3.45****wet thermal insulation**

system (3.35) that provides external corrosion protection and thermal insulation, and that is in direct contact with surrounding seawater

**4 Symbols and abbreviated terms****4.1 Symbols**

$E_{kin}$	impact energy (kinetic energy), expressed in joules
$g$	standard gravity, equivalent to 9,81 metres per seconds squared
$H$	pendulum height, expressed in metres
$m_h$	mass of hammer, expressed in kilograms
$Q_{ave,i}$	average value of heat flux transducers signals for sample $i$ , where $i = 1, 2$ , or $3$ , expressed in microvolts
$Q_{lower}$	lower plate heat flux transducer signal, expressed in microvolts
$Q_{Lower,Average}$	average lower plate heat flux transducer signal, expressed in microvolts
$Q_{Ref\ Mat\ ave}$	average value of heat flux transducers signals for reference material sample, expressed in watts per microvolts
$Q_{Ref\ Mat\ ave,i}$	average value of heat flux transducers signals for reference material sample $i$ , where $i = 1$ or $2$ , and $1$ is typically the thinner sample, expressed in watts per microvolts
$Q_{upper}$	upper plate heat flow, expressed in microvolts
$Q_{Upper,Average}$	average upper plate heat flow, expressed in microvolts
$S_{Cal}$	calibration factor, expressed in watts per microvolts
$S_{Cal1}$	single-thickness calibration factor, proportional factor between the electrical signal and heat flow, expressed in watts per microvolts
$S_{Cal2}$	two-thickness calibration factor, proportional factor between the electrical signal and heat flow, expressed in watts per microvolts
$S_{Cal,Lower}$	lower plate calibration factor, expressed in watts per microvolts
$S_{Cal,Upper}$	upper plate calibration factor, expressed in watts per microvolts
$\bar{R}_{ave}$	total average measured thermal resistance across all samples, expressed in metre square degrees kelvin per Watt
$R_{ave,i}$	average measured thermal resistance of sample $i$ , where $i = 1, 2$ , or $3$ , expressed in metre square degrees kelvin per Watt
$R_{cal}$	calibration contact resistance, expressed in metre square degrees kelvin per watt
$2R_{Cal,Lower}$	lower plate calibration contact resistance, expressed in metre square degrees kelvin per watt
$2R_{Cal,Upper}$	upper plate calibration contact resistance, expressed in metre square degrees kelvin per watt

$2R_{\text{sample}}$	contact resistance of the sample, expressed in metres square degrees kelvin per watt
$\Delta T$	average temperature difference across the sample(s), expressed in degrees Celsius
$T_{\text{lower}}$	lower plate temperature, expressed in degrees Celsius
$T_{\text{upper}}$	upper plate temperature, expressed in degrees Celsius
$x_{\text{ave},i}$	average measured thickness of sample $i$ , where $i = 1, 2$ , or $3$ , expressed in metres
$\bar{x}_{\text{ave}}$	total average measured thickness across all samples
$x_{\text{Ref Mat ave}}$	average thickness of the reference material sample, expressed in metres
$x_{\text{Ref Mat ave},i}$	average thickness of reference material sample $i$ , where $i = 1$ or $2$ , and $1$ is typically the thinner sample, expressed in metres
$\lambda_{\text{Ref Mat}}$	thermal conductivity of the calibration reference material, expressed in watts per metre kelvin
$\lambda_{\text{sampleA1}}$	single thickness sample thermal conductivity, Test Type A1 specimen, expressed in watts per metre kelvin
$\lambda_{\text{sampleA2}}$	single thickness sample thermal conductivity, Test Type A2 specimen, expressed in watts per metre kelvin

iteh STANDARD PREVIEW  
(standards.iteh.ai)

#### 4.2 Abbreviated terms

APS	application procedure specification
DMA	dynamic mechanical analysis <a href="https://standards.iteh.ai/catalog/standards/sist/13377be5-2c0f-42a4-864d-757854222f3/iso-12736-1">ISO 12736-1</a>
DSC	differential scanning calorimetry <a href="https://standards.iteh.ai/catalog/standards/sist/13377be5-2c0f-42a4-864d-757854222f3/iso-12736-1">https://standards.iteh.ai/catalog/standards/sist/13377be5-2c0f-42a4-864d-757854222f3/iso-12736-1</a>
ID	inner diameter
ITP	inspection and test plan
LVDT	linear variable differential transformer; linear variable displacement transformer; linear variable displacement transducer
OD	outer diameter
SI	International System of units
SST	simulated service test
QC	quality control
UV	ultraviolet

## 5 Conformance

### 5.1 Rounding

Unless otherwise stated in this document, observed or calculated values shall be rounded to the nearest unit in the last right-hand place of figures used in expressing the limiting value, in accordance with ISO 80000-1.

NOTE For the purpose of this provision, the rounding method of ASTM E29 is equivalent to ISO 80000-1:2022, Annex B, Rule A.

### 5.2 Conformity to requirement

Systems for quality and environmental management, and the competence of testing and calibration laboratories, should be used.

NOTE The following documents can be used:

- ISO 29001 gives sector-specific requirements with guidance for the use of quality management systems;
- ISO 14001 gives requirements with guidance for the use of environmental management systems;
- ISO/IEC 17025 gives general requirements for the competence of testing and calibration laboratories.

The system provider shall be responsible for conforming with all the applicable requirements for the application of this document. The system purchaser shall be allowed to make any investigation necessary to ensure conformity by the system provider and to reject any material and/or system that does not conform with this document.

## 6 Material classes

ISO 12736-1

The materials covered by this document are classified in [Table 1](#). Each material used to make up the system shall be classified into the appropriate class by the system provider.

If other materials, not fitting the classes within [Table 1](#), are used, the system provider shall identify the class that most closely represents the material and shall provide a gap analysis to the requirements for that class to be included in the validation dossier.

**Table 1 — Material classes**

	Solid/solid filled	Blown foam	Inorganic syntactic foam
Thermoplastics	1A	1B	1C
Liquid precursor non-elastomeric thermosets	2A	2B	2C
Liquid precursor elastomeric thermosets	3A	3B	3C
High molecular weight precursor thermosets	4A	4B	4C

## 7 Materials and system validation testing

### 7.1 General

This clause specifies the test requirements for validation of wet thermal insulation systems and for the materials used within such single or multi-layer systems.

The test data generated shall be considered when conducting a risk analysis in accordance with [7.5](#).