
**Copper and zinc sulfide
concentrates — Determination
of thallium — Acid digestion and
inductively coupled plasma-mass
spectrometry**

*Concentrés sulfurés de cuivre et de zinc — Dosage du thallium —
Digestion acide et plasma à couplage inductif-spectrométrie de masse*
(standards.iteh.ai)

[ISO 3483:2023](https://standards.iteh.ai/catalog/standards/sist/c6a4586d-d07e-49f6-b5d6-d1d76aa3eaa3/iso-3483-2023)

<https://standards.iteh.ai/catalog/standards/sist/c6a4586d-d07e-49f6-b5d6-d1d76aa3eaa3/iso-3483-2023>



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 3483:2023

<https://standards.iteh.ai/catalog/standards/sist/c6a4586d-d07e-49f6-b5d6-d1d76aa3eaa3/iso-3483-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Reagents.....	2
6 Apparatus.....	3
7 Sample.....	3
7.1 Laboratory sample.....	3
7.2 Test sample.....	3
7.3 Test portion.....	3
8 Procedure.....	4
8.1 Number of determinations.....	4
8.2 Blank test.....	4
8.3 Dissolution of the test portion.....	4
8.4 Preparation of test solutions.....	4
8.5 Preparation of calibration solutions.....	4
8.6 Preparation of thallium calibration curve.....	5
8.7 Determination of thallium content in test solutions.....	5
9 Expression of results.....	5
10 Precision.....	6
10.1 Expression of precision.....	6
10.2 Method for obtaining the final result.....	6
10.3 Between-laboratories precision.....	6
10.4 Check of trueness.....	7
10.4.1 General.....	7
10.4.2 Type of certified reference material (CRM) or reference material (RM).....	8
11 Test report.....	8
Annex A (informative) Procedure for the preparation and determination of the mass of a pre-dried test portion.....	10
Annex B (normative) Procedure for obtaining the final result.....	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 183, *Copper, lead, zinc and nickel ores and concentrates*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Copper and zinc sulfide concentrates — Determination of thallium — Acid digestion and inductively coupled plasma-mass spectrometry

WARNING — This Document may involve hazardous materials, operations and equipment. It is the responsibility of the user of this document to establish appropriate health and safety practices prior to use.

1 Scope

This Document specifies an acid digestion and inductively coupled plasma mass spectrometry (ICP-MS) procedure for determination of the mass fraction of thallium in copper and zinc sulfide concentrates as follows.

- a) For copper sulfide concentrates, the method is applicable to the determination of mass fractions of thallium from 0,000 1 % to 0,002 5 %.
- b) For zinc sulfide concentrates, the method is applicable to the determination of mass fractions of thallium from 0,000 1 % to 0,025 %.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385, *Laboratory glassware — Burettes*

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 4787, *Laboratory glass and plastic ware — Volumetric instruments — Methods for testing of capacity and for use*

ISO 9599, *Copper, lead, zinc and nickel sulfide concentrates — Determination of hygroscopic moisture content of the analysis sample — Gravimetric method*

ISO 12743, *Copper, lead, zinc and nickel concentrates — Sampling procedures for determination of metal and moisture content*

ISO/GUIDE 35, *Reference materials — General and statistical principles for certification*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

The test portion is decomposed in hydrochloric, nitric, hydrofluoric and perchloric acids. The thallium concentration is determined by ICP-MS using a constant amount of iridium as the internal standard.

5 Reagents

During the analysis, use only reagents of recognized guaranteed reagent quality and distilled water or water of equivalent purity.

5.1 Hydrochloric acid, concentrated (ρ_{20} 1,19 g/ml).

5.2 Nitric acid, concentrated (ρ_{20} 1,42 g/ml).

5.3 Nitric acid, dilute 1 + 1.

5.4 Hydrofluoric acid, concentrated (ρ_{20} 1,15 g/ml).

5.5 Perchloric acid, concentrated (ρ_{20} 1,70 g/ml).

5.6 Hydrogen peroxide, concentrated (ρ_{20} 1,13 g/ml).

5.7 Thallium oxide (Tl₂O₃), minimum purity 99,99 %.

5.8 Thallium standard solution, 1 ml contains 100 μ g of Tl.

Weigh, to the nearest 0,1 mg, 0,111 8 g of thallium oxide (5.7), transfer to a 250 ml beaker. Add 50 ml of nitric acid (5.3) and heat gently until the oxide is dissolved. Then cool to room temperature. Transfer to a 100 0 ml one-mark volumetric flask, dilute to the mark with water and mix thoroughly.

5.9 Thallium standard solution, 1 ml contains 10 μ g of Tl.

Pipette 10,00 ml of thallium standard solution (5.8) into a 100 ml one-mark volumetric flask. Add 3 ml of nitric acid (5.2), fill up nearly to the mark with water, mix, and cool to room temperature, then fill up exactly to the mark with water and mix again.

5.10 Thallium standard solution, 1 ml contains 100 ng of Tl.

Pipette 2,00 ml of thallium standard solution (5.9) into a 200 ml one-mark volumetric flask. Add 6 ml of nitric acid (5.2), fill up nearly to the mark with water, mix, and cool to room temperature, then fill up exactly to the mark with water and mix again.

5.11 Iridium standard stock solution, 1 ml contains 1 mg of Ir.

Weigh, to the nearest 0,1 mg, 0,1 g of iridium powder ($w_{Ir} \geq 99,99$ %), transfer to a 50 ml glass tube. Add 8 ml of hydrochloric acid (5.1), 2 ml hydrogen peroxide (5.6), sealing pipe. Under the temperature of 150 °C to dissolve 48 h until the powder is dissolved, then cool to room temperature, open the tube. Transfer to a 100 ml one-mark volumetric flask, add 10 ml of hydrochloric acid (5.1), fill up nearly to the mark with water, mix, and cool to room temperature, then fill up exactly to the mark with water and mix again.

5.12 Iridium internal standard solution, 1 ml contains 1 µg of Ir.

Pipette 1,00 ml of iridium standard stock solution (5.11) into a 1 000 ml one-mark volumetric flask. Add 20 ml of hydrochloric acid (5.1), fill up nearly to the mark with water, mix, and cool to room temperature, then fill up exactly to the mark with water and mix again.

NOTE Commercial and certified standard solutions can also be used.

6 Apparatus

6.1 Usual laboratory equipment, including fume hoods, hotplates and a drying oven.

6.2 Ordinary laboratory glassware.

6.3 Volumetric glassware, of class A complying with ISO 385, ISO 648 and ISO 1042, and used in accordance with ISO 4787.

6.4 Polytetrafluoroethylene beaker, of capacity 200 ml.

6.5 Analytical balance, sensitive to 0,1 mg.

6.6 Inductively Coupled Plasma Mass Spectrometer (ICP-MS). The ICP-MS should be set up according to the manufacturer's guidelines. The mass number of thallium should be set to ²⁰⁵Tl. The mass number of internal standard should be set to ¹⁹³Ir.

7 Sample

7.1 Laboratory sample

Laboratory sample shall be taken and prepared in accordance with the procedures described in ISO 12743.

7.2 Test sample

Prepare an air-equilibrated test sample in accordance with ISO 9599.

NOTE A test sample is not required if predried test portions are to be used (see [Annex A](#)).

7.3 Test portion

Taking multiple increments, extract approximately 0,20 g from the test sample and weigh to the nearest 0,1 mg. At the same time as test portions are being weighed for analysis, weigh test portions for the determination of hygroscopic moisture in accordance with ISO 9599.

Alternatively, the method specified in [Annex A](#) may be used to prepare predried test portions directly from the laboratory sample.

8 Procedure

8.1 Number of determinations

Carry out the determinations at least in duplicate, as far as possible under repeatability conditions, on each test sample.

NOTE Repeatability conditions exist where mutually independent test results are obtained with the same method on identical test material in the same laboratory by the same operator using the same equipment, within short intervals of time.

8.2 Blank test

Carry out a blank test in parallel with the analysis using the same quantities of all reagents but omitting the test portion. The purpose of the blank test in this method is to check the quality of the reagents, the environment of the laboratory room, the condition of the ICP-MS used, and the condition of the laboratory glass and plastic ware used. If a significant blank value is obtained as a result of the blank test, check all reagents and rectify the problem.

8.3 Dissolution of the test portion

Transfer the test portion (7.3) into a 200 ml polytetrafluoroethylene beaker (6.4) and moisten with 5 ml of water.

Add 10 ml of hydrochloric acid (5.1), and heat for 5 min at 60 °C to 70 °C and cool. Add 5 ml of nitric acid (5.2) and heat gently. Add 3 ml of hydrofluoric acid (5.4), then heat gradually until the solution is about 5 ml. Add 3 ml of perchloric acid (5.5), cover with a polytetrafluoroethylene lid, heat the solution at about 200 °C until the strong white fumes evolve completely, then remove the beaker from the hotplate and cool to room temperature.

Add 12 ml of nitric acid (5.3), rinse the sides of the beaker with a minimum volume of water and then heat until the onset of boiling, allow to cool.

8.4 Preparation of test solutions

Transfer the solution (8.3) and 2,00 ml iridium standard solution (5.12) into a 200 ml of one-mark volumetric flask, dilute to the mark with water and mix thoroughly. If a small amount of residue appears, dry filter.

8.5 Preparation of calibration solutions

Using thallium standard, prepare a series of calibration standards as Table 1. Transfer 0,00 ml, 0,50 ml, 1,00 ml, 10,00 ml volume of thallium standard (5.10) and 0,25 ml, 0,50 ml, 1,00 ml, 2,00 ml, 3,00 ml volume of thallium standard (5.9), then transfer 1,00 ml iridium standard solution (5.12) into a series of 100 ml volumetric flasks, add 6 ml nitric acid (5.3), fill up nearly to the mark with water, mix, and cool to room temperature, then fill up exactly to the mark with water and mix again.

Table 1 — Preparation of calibration solutions

Thallium standard solution	Volume of thallium standard, V1/ml	Volume of iridium standard (5.12), V2/ml	Volume after dilution, V/ml	Concentration of thallium, ng/ml
—	0,00	1,00	100	0,00
5.10	0,50	1,00	100	0,50
5.10	1,00	1,00	100	1,00

Calibration solutions should be prepared at the same ambient temperature as that at which the determinations will be conducted.

Table 1 (continued)

Thallium standard solution	Volume of thallium standard, V1/ml	Volume of iridium standard (5.12), V2/ml	Volume after dilution, V/ml	Concentration of thallium, ng/ml
5.10	10,00	1,00	100	10,00
5.9	0,25	1,00	100	25,00
5.9	0,50	1,00	100	50,00
5.9	1,00	1,00	100	100,00
5.9	2,00	1,00	100	200,00
5.9	3,00	1,00	100	300,00

Calibration solutions should be prepared at the same ambient temperature as that at which the determinations will be conducted.

NOTE Determination of thallium in copper sulfide concentrates, the concentration of calibration solutions to use are 0,00 ng/ml, 0,50 ng/ml, 1,00 ng/ml, 10,00 ng/ml, 25,00 ng/ml, 50,00 ng/ml.

8.6 Preparation of thallium calibration curve

Set up the ICP-MS according to the guidelines set out in [6.6](#). Aspirate each calibration solution, as prepared in step [8.5](#), through the ICP-MS and record the intensity ratio.

Manually or electronically plot a graph of the average intensity ratio versus concentration of thallium (in ng/ml) and repeat errant standards if necessary.

8.7 Determination of thallium content in test solutions

Immediately after calibrating the ICP-MS ([8.6](#)), determine the thallium content in the test solutions from step [8.4](#). Adjust the instrument read-out scale to zero. Aspirate the blank test solution ([8.2](#)) through the ICP-MS and record the concentration (ρ_0). Then aspirate the first duplicate of each sample through the ICP-MS and record the concentration (ρ).

Check the calibration of the instrument, then aspirate the second duplicate of each sample in the reverse order through the ICP-MS and record the concentration (ρ).

9 Expression of results

The mass fraction of thallium in the test portion, w_{Tl} , expressed as a percentage, is given in [Formula \(1\)](#).

$$w_{\text{Tl}} = \frac{(\rho - \rho_0) \cdot V}{m \times 10^9} \times \frac{100}{100 - H} \times 100 \quad (1)$$

where

- ρ is the concentration, in nanograms per millilitre, of thallium in the test solution obtained from the calibration curve;
- ρ_0 is the concentration, in nanograms per millilitre, of thallium in the blank solution;
- m is the mass, in grams, of the test portion;
- V is the total volume, in millilitre, of the test solution;
- H is the hygroscopic moisture content of the sample, expressed as a percentage, determined using ISO 9599.

NOTE If pre-dried test samples are used, $H = 0$.

10 Precision

10.1 Expression of precision

The precision of this analytical method is expressed by [Formulae \(2\)](#) to [\(7\)](#).

a) For copper sulfide concentrates:

$$s_r = 0,036 \bar{X} + 0,000\ 003 \quad (2)$$

$$s_L = 0,000\ 03 \ln(\bar{X}) + 0,000\ 3 \quad (3)$$

$$s_R = 0,07 \bar{X} + 0,000\ 02 \quad (4)$$

b) For zinc sulfide concentrates:

$$s_r = 0,018\ 8 \bar{X} + 0,000\ 03 \quad (5)$$

$$s_L = 0,031 \bar{X} + 0,000\ 07 \quad (6)$$

$$s_R = 0,034\ 91 \bar{X} + 0,000\ 09 \quad (7)$$

where

\bar{X} is the mean mass fraction of thallium in the sample, expressed as a percentage;

s_r is the within-laboratory standard deviation, expressed as a percentage by mass of thallium;

s_L is the between-laboratories standard deviation, expressed as a percentage by mass of thallium;

s_R is the reproducibility standard deviation, expressed as a percentage by mass of thallium.

10.2 Method for obtaining the final result

Calculate the following quantities from the duplicate results X_1 and X_2 (%) and process according to the flowchart in [Annex B](#).

a) Mean of duplicate results:

$$\bar{X} = \frac{X_1 + X_2}{2} \quad (8)$$

Within laboratory standard deviation (s_r), using [Formula \(2\)](#) for copper sulfide concentrates, [Formula \(5\)](#) for zinc sulfide concentrates.

b) Repeatability limit, r

$$r = 2,8s_r \quad (9)$$

10.3 Between-laboratories precision

The between-laboratories precision is used to determine the agreement between the results reported by two (or more) laboratories. The assumption is that all laboratories followed the same procedure.