INTERNATIONAL STANDARD

ISO 4437-5

Second edition

Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) —

Part 5:

Fitness for purpose of the system

Systèmes de canalisations en plastique pour la distribution de combustibles gazeux — Polyéthylène (PE) —

Partie 5: Aptitude à l'emploi du système

Document Preview

ISO/PRF 4437-5

https://standards.iteh.ai/catalog/standards/sist/eae85f43-d6ee-42c3-954b-06104bca4a23/iso-prf-4437-5

PROOF/ÉPREUVE



Reference number ISO 4437-5:2023(E)

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO/PRF 4437-5

https://standards.iteh.ai/catalog/standards/sist/eae85f43-d6ee-42c3-954b-06104bca4a23/iso-prf-4437-5



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Contents		Page
Fore	word	iv
Intro	oduction	v
1	Scope	1
2	Normative references	
3	Terms and definitions	
3	3.1 Terms related to geometry 3.2 Terms related to material 3.3 Terms related to material characteristics 3.4 Terms related to service conditions 3.5 Terms related to joints	
4	Symbols and abbreviated terms 4.1 Symbols 4.2 Abbreviated terms	5
5	Fitness for purpose of the system 5.1 Method of preparation of assemblies for testing 5.1.1 General 5.1.2 Butt fusion joints 5.1.3 Electrofusion joints 5.1.4 Mechanical joints 5.1.5 Socket fusion joints	
	5.2.1 General	
	5.3 Conditioning	10
	5.4 Requirements ISO/PRF 4437-5 Testing of pipe with coextruded layers 666-4263-954b-06104b-64423	
6	Design coefficient	
_	ex A (informative) Derating coefficients for operating temperatures	
	ex B (informative) Rapid crack propagation resistance of pipe at	
AIIII	temperature less than 0 °C	
Bibli	ography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 4, *Plastics pipes and fittings for the supply of gaseous fuels*.

This second edition cancels and replaces the first edition (ISO 4437-5:2014), which has been technically revised.

The main changes are as follows:

- PE 100-RC type materials with enhanced resistance to slow crack growth (SCG) have been added;
- test methods have been updated and new methods have been added for PE 100-RC materials.

A list of all parts in the ISO 4437 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The ISO 4437 series specifies the requirements for a piping system and its components made from polyethylene (PE) compounds, which is intended to be used for the supply of gaseous fuels.

This document covers the characteristics of fitness for purpose of the system.

Requirements and test methods for materials and components of the piping system are specified in ISO $4437-1^{1}$, ISO $4437-2^{2}$, ISO $4437-3^{3}$ and ISO 4437-4.

Recommended practice for design, handling and installation is given in ISO/TS 10839.

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO/PRF 4437-5

https://standards.iteh.ai/catalog/standards/sist/eae85f43-d6ee-42c3-954b-06104bca4a23/iso-prf-4437-5

¹⁾ Under preparation. Stage at the time of publication: ISO/PRF 4437-1:2023.

²⁾ Under preparation. Stage at the time of publication: ISO/PRF 4437-2:2023.

³⁾ Under preparation. Stage at the time of publication: ISO/PRF 4437-3:2023.

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO/PRF 4437-5

https://standards.iteh.ai/catalog/standards/sist/eae85f43-d6ee-42c3-954b-06104bca4a23/iso-prf-4437-5

Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) —

Part 5:

Fitness for purpose of the system

1 Scope

This document specifies the requirements of fitness for purpose of assembled polyethylene (PE) piping systems in the field of the supply of gaseous fuels.

It specifies the requirements for electrofusion, socket fusion, butt fusion and mechanical joints.

It specifies the method of preparation of test piece joints and the tests to be carried out on these joints for assessing the fitness for purpose of the system under normal and extreme conditions.

It specifies the test parameters for the test methods referred to in this document.

This document is intended to be used only by the product manufacturer and test laboratories to assess the performance of components in accordance with ISO 4437-2, ISO 4437-3 and ISO 4437-4 when joined together under normal and extreme conditions in accordance with this document. It is not intended for on-site testing of pipe systems.

In conjunction with ISO 4437-1, ISO 4437-2, ISO 4437-3 and ISO 4437-4, this document is applicable to PE pipes, fittings and valves, their joints, and joints with components of PE and other materials intended to be used under the following conditions:

- a) a maximum operating pressure (MOP), up to and including 10 bar⁴⁾, at a reference temperature of 20 °C for design purposes; hards/sist/eae85[43-d6ee-42c3-954b-06104bca4a23/iso-prf-4437-5
 - b) an operating temperature between -20 °C and 40 °C.

For operating temperatures between 20 °C and 40 °C, derating coefficients are defined in Annex A.

The ISO 4437 series covers a range of MOPs and gives requirements concerning colours.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1167-1:2006, Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method

ISO 1167-2, Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces

ISO 1167-4, Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 4: Preparation of assemblies

© ISO 2023 – All rights reserved **PROOF/ÉPREUVE** 1

⁴⁾ $1 \text{ bar} = 0.1 \text{ MPa} = 10^5 \text{ Pa}$; $1 \text{ MPa} = 1 \text{ N/mm}^2$.

ISO 4437-5:2023(E)

ISO 4437-2⁵), Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 2: Pipes

ISO 4437-36), Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 3: Fittings

ISO 4437-4, Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 4: Valves

ISO 11413:2019, Plastics pipes and fittings — Preparation of test piece assemblies between a polyethylene (PE) pipe and an electrofusion fitting

ISO 11414:2009, Plastics pipes and fittings — Preparation of polyethylene (PE) pipe/pipe or pipe/fitting test piece assemblies by butt fusion

ISO 13477, Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Small-scale steady-state test (S4 test)

ISO 13478, Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Full-scale test (FST)

ISO 13953, Polyethylene (PE) pipes and fittings — Determination of the tensile strength and failure mode of test pieces from a butt-fused joint

ISO 13954, Plastics pipes and fittings — Peel decohesion test for polyethylene (PE) electrofusion assemblies of nominal outside diameter greater than or equal to 90 mm

ISO 13955, Plastics pipes and fittings — Crushing decohesion test for polyethylene (PE) electrofusion assemblies

ISO 13956, Plastics pipes and fittings — Decohesion test of polyethylene (PE) saddle fusion joints — Evaluation of ductility of fusion joint interface by tear test

ISO 17885, Plastics piping systems — Mechanical fittings for pressure piping systems — Specifications

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at https://www.electropedia.org/

3.1 Terms related to geometry

3.1.1

nominal size

DN/OD

numerical designation of the size of a component related to the outside diameter

Note 1 to entry: It is a convenient round number approximately equal to the manufacturing dimension in millimetres (mm). It is not applicable to components designated by thread size.

3.1.2

nominal outside diameter

 d_n

specified outside diameter assigned to a *nominal size* (3.1.1)

Note 1 to entry: Nominal outside diameter is expressed in millimetres (mm).

⁵⁾ Under preparation. Stage at the time of publication: ISO/PRF 4437-2:2023.

⁶⁾ Under preparation. Stage at the time of publication: ISO/PRF 4437-3:2023

3.1.3

nominal wall thickness

 $e_{\rm n}$

numerical designation of the wall thickness of a component, which is a convenient round number, approximately equal to the manufacturing dimension in millimetres (mm)

Note 1 to entry: For thermoplastics components conforming to the ISO 4437 series, the value of the nominal wall thickness, e_n , is identical to the specified *minimum wall thickness at any point* (3.1.5).

3.1.4

wall thickness at any point

e

wall thickness at any point around the circumference of a component rounded to the next greater $0.1\,\mathrm{mm}$

Note 1 to entry: The symbol for the wall thickness of a fitting and valve body at any point is *E*.

3.1.5

minimum wall thickness at any point

 $e_{
m mir}$

minimum value for the *wall thickness at any point* (3.1.4) around the circumference of a component

3.1.6

standard dimension ratio

SDR

numerical designation of a *pipe series* (3.1.7), which is a convenient round number, approximately equal to the dimension ratio of the *nominal outside diameter* (3.1.2) and the *nominal wall thickness* (3.1.3)

3.1.7

pipe series

Ĉ

number for pipe designation

Note 1 to entry: The relationship between the pipe series, *S*, and the *standard dimension ratio (SDR)* (3.1.6) is given by the following formula, as specified in ISO 4065.

$$S = \frac{SDR - 1}{2}$$

3.2 Terms related to material

3.2.1

compound

homogenous extruded mixture of *base polymer* (3.2.2) (polyethylene) and additives (i.e. anti-oxidants, pigments, carbon black, UV-stabilizers and others) at a dosage level necessary for the processing and use of components

3.2.2

base polymer

polymer produced by the material supplier for the manufacture of the *compound* (3.2.1)

3.3 Terms related to material characteristics

3.3.1

lower confidence limit of the predicted hydrostatic strength

 $\sigma_{
m LPL}$

quantity, with the dimensions of stress, which represents the 97,5 % lower confidence limit of the predicted hydrostatic strength at temperature θ and time t

Note 1 to entry: It is expressed in megapascals (MPa).

3.3.2

minimum required strength

MRS

value of the *lower confidence limit of the predicted hydrostatic strength* (3.3.1) at 20 °C and 50 years, rounded down to the next lower value of the R10 series or R20 series

Note 1 to entry: Only compounds (3.2.1) with an MRS of 8 MPa or 10 MPa are specified in this document.

Note 2 to entry: The R10 series and the R20 series conform to ISO 3.

Note 3 to entry: It is expressed in megapascals (MPa).

[SOURCE: ISO 12162:2009, 3.3, modified — "the next smaller value" has been replaced by "the next lower value" in the definition. Note 1 to entry has been removed and replaced with new Notes 1 to 3 to entry.]

3.3.3

design coefficient

C

coefficient with a value greater than 1 which takes into consideration service conditions as well as properties of the components of a piping system other than those represented in the lower confidence limit

3.4 Terms related to service conditions

3.4.1

gaseous fuel

fuel which is in gaseous state at a temperature of 15 °C at atmospheric pressure

Note 1 to entry: There are proposals to inject gases from renewable sources in natural gas networks, e.g. hydrogen (H_2) . This is the subject of ongoing research.

3.4.2

maximum operating pressure

MOP

maximum effective pressure of the fluid in the piping system which is allowed in continuous use

Note 1 to entry: It is expressed in bar. It takes into account the physical and the mechanical characteristics of the components of a piping system. It is calculated using the following formula:

$$MOP = \frac{20 \times MRS}{C \times (SDR - 1)}$$

Note 2 to entry: Research on long-term performance prediction of polyethylene gas distribution systems shows a possible service life of at least 100 years; see References [7], [8] and [9].

3.4.3

reference temperature

temperature for which the piping system is designed

Note 1 to entry: It is used as the base for further calculation when designing a piping system or parts of a piping system for operating temperatures different from the reference temperature.

3.5 Terms related to joints

3.5.1

butt fusion joint

joint made by heating the planed ends of pipes or *spigot end fittings* (3.5.5), the surfaces of which are fused together by holding them against a flat heating plate until the polyethylene material reaches fusion temperature, removing the heating plate quickly and pushing the two softened ends against one another