
**Specification and qualification of
welding procedures for metallic
materials — Welding procedure test —**

**Part 13:
Upset (resistance butt) and flash
welding**

iTeh Standards

(<https://standards.iteh.ai/catalog/standards/iso/7027d4c2-8bb0-40a5-a12f-05864bf61cef/iso-15614-13-2021>)
Document Preview
*Descriptif et qualification d'un mode opératoire de soudage pour
les matériaux métalliques — Épreuve de qualification d'un mode
opératoire de soudage —
Partie 13: Soudage en bout par résistance pure et soudage par
étincelage*

[ISO 15614-13:2021](#)

<https://standards.iteh.ai/catalog/standards/iso/7027d4c2-8bb0-40a5-a12f-05864bf61cef/iso-15614-13-2021>



Reference number
ISO 15614-13:2021(E)

© ISO 2021

iTeh Standards

(<https://standards.iteh.ai>)

Document Preview

[ISO 15614-13:2021](#)

<https://standards.iteh.ai/catalog/standards/iso/7027d4c2-8bb0-40a5-a12f-05864bf61cef/iso-15614-13-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Preliminary welding procedure specification	2
4.1 General	2
4.2 Welding procedure test	2
5 Test pieces and test specimens	3
5.1 General	3
5.2 Shape and dimensions of test specimens	3
5.2.1 General	3
5.2.2 Tensile test specimen	4
5.2.3 Bend test specimen	4
5.2.4 Cupping test specimen	4
5.2.5 Hardness test specimen	4
5.2.6 Bend test specimen using thin sheets	5
5.3 Welding of components, test pieces or test specimens	5
6 Testing and examination	5
6.1 Extent of testing	5
6.2 Non-destructive testing (NDT)	5
6.2.1 General	5
6.2.2 Visual test	5
6.2.3 Penetrant test	5
6.2.4 Magnetic particle test	5
6.2.5 Eddy current test	5
6.2.6 Ultrasonic test	5
6.3 Destructive tests	6
6.3.1 Tensile test	6
6.3.2 Three-point bend test	6
6.3.3 Cupping test	6
6.3.4 Bend test	6
6.4 Macrosection	6
6.5 Hardness distribution	6
6.6 Re-testing	6
7 Range of qualification	6
7.1 General	6
7.2 Related to the manufacturer	7
7.3 Related to the parent metal	7
7.4 Welding procedures	7
7.4.1 Welding process	7
7.4.2 Welding equipment	7
7.4.3 Pre-/Postweld heat treatment	7
7.5 Test certificate	7
8 Welding procedure qualification record (WPQR)	7
Annex A (informative) Example of welding procedure qualification — Test certificate	8
Annex B (informative) Example of welding procedure qualifications record form (WPQR)	10
Bibliography	15

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 6, *Resistance welding and allied mechanical joining*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 15614-13:2012), which has been technically revised.

The main changes are as follows:

- petal test was changed to bend test and bend test was changed to three-point bend test;
- [Clauses 2](#) and [3](#) have been updated;
- [Clauses 7](#) and [8](#) have been updated;
- [Table 1](#) has been modified.

A list of all parts in the ISO 15614 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

Introduction

It is intended that all new welding procedure qualifications be carried out in accordance with this document from the date of its issue.

However, this document does not invalidate previous welding procedure qualifications made to other standards or specifications, provided the intent of its technical requirements is satisfied and the previous welding procedure qualifications are relevant to the application and production work on which they are to be employed.

Also, where additional tests need to be carried out to make the qualification technically equivalent, it is necessary only to perform the additional tests on a test piece made in accordance with this document.

Details on the ISO 15614 series on welding are given in ISO 15607:2019, Annex A.

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[ISO 15614-13:2021](#)

<https://standards.iteh.ai/catalog/standards/iso/7027d4c2-8bb0-40a5-a12f-05864bf61cef/iso-15614-13-2021>

Specification and qualification of welding procedures for metallic materials — Welding procedure test —

Part 13: Upset (resistance butt) and flash welding

1 Scope

This document specifies tests for the qualification of welding procedure specifications applicable to upset (resistance butt) welding and flash welding of metallic materials, e.g. with solid, tubular, flat or circular cross-section. Its basic principles can also be applied to other resistance welding processes when this is stated in the specification.

This document defines the conditions for carrying out tests and the limits of validity of a qualified welding procedure for all the practical welding operations that it covers.

It covers the following resistance welding processes, as defined in ISO 4063:

- 24 flash welding, using direct current or alternating current with various movement sequences, constant flashing and pulsed flashing;
- 25 resistance upset welding, using direct current or alternating current with various pressure sequences.

Document Preview

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. (For undated references, the latest edition of the referenced document (including any amendments) applies.)

ISO 669, *Resistance welding — Resistance welding equipment — Mechanical and electrical requirements*

ISO 4136, *Destructive tests on welds in metallic materials — Transverse tensile test*

ISO 5173, *Destructive tests on welds in metallic materials — Bend tests*

ISO 6520-2, *Welding and allied processes — Classification of geometric imperfections in metallic materials — Part 2: Welding with pressure*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 9015-1, *Destructive tests on welds in metallic materials — Hardness testing — Part 1: Hardness test on arc welded joints*

ISO 9015-2, *Destructive tests on welds in metallic materials — Hardness testing — Part 2: Microhardness testing of welded joints*

ISO 11666, *Non-destructive testing of welds — Ultrasonic testing — Acceptance levels*

ISO 14271, *Resistance welding — Vickers hardness testing (low-force and microhardness) of resistance spot, projection, and seam welds*

ISO 14732, *Welding personnel — Qualification testing of welding operators and weld setters for mechanized and automatic welding of metallic materials*

ISO 15607:2019, *Specification and qualification of welding procedures for metallic materials — General rules*

ISO/TR 15608:2017, *Welding — Guidelines for a metallic materials grouping system*

ISO 15609-5, *Specification and qualification of welding procedures for metallic materials — Welding procedure specification — Part 5: Resistance welding*

ISO 15620:2019, *Welding — Friction welding of metallic materials*

ISO 17637, *Non-destructive testing of welds — Visual testing of fusion-welded joints*

ISO 17638, *Non-destructive testing of welds — Magnetic particle testing*

ISO 17639, *Destructive tests on welds in metallic materials — Macroscopic and microscopic examination of welds*

ISO 17640, *Non-destructive testing of welds — Ultrasonic testing — Techniques, testing levels, and assessment*

ISO 17643, *Non-destructive testing of welds — Eddy current testing of welds by complex-plane analysis*

ISO 23277, *Non-destructive testing of welds — Penetrant testing — Acceptance levels*

ISO 23278, *Non-destructive testing of welds — Magnetic particle testing — Acceptance levels*

ISO 23279, *Non-destructive testing of welds — Ultrasonic testing — Characterization of discontinuities in welds*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 669, ISO 15607 and ISO 6520-2 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

<https://standards.iteh.ai/catalog/standards/iso/7027d4c2-8bb0-40a5-a12f-05864bf61cef/iso-15614-13-2021>

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Preliminary welding procedure specification

4.1 General

The preliminary welding procedure specification (pWPS) shall be prepared in accordance with ISO 15609-5. It shall specify all relevant parameters and requirements.

4.2 Welding procedure test

The manufacturing and testing of components and/or test pieces representing the type of welding used in production shall be in accordance with [Clauses 5](#) and [6](#).

The resistance weld setter who satisfactorily undertakes the welding procedure test in accordance with this part of ISO 15614 shall be qualified for the appropriate range of qualification given in ISO 14732.

5 Test pieces and test specimens

5.1 General

The welded assembly tested shall be the actual component used in production or a standardized test piece according to references included in [5.2](#).

Test specimens may be cut from the actual component if required. Test pieces are to be tested separately, in accordance with [5.2](#).

5.2 Shape and dimensions of test specimens

5.2.1 General

The testing includes non-destructive testing (NDT) and/or destructive testing.

The selection of test class A or B, test types and the number of test specimens depends on the performance, safety and quality requirements of the component or assembly and shall be established before any qualification is undertaken. Examples are given in [Table 1](#).

If not otherwise specified, test specimens of the shape and dimensions stipulated in [5.2.2](#) to [5.2.6](#) shall be used.

Table 1 — Examples for testing and examination of test specimens

Work piece	Test type	Extent of test ^h		Test class B
		Test class A	Test class B	
Bars/rods	Visual test	Every weld	Every weld	Every weld
	Penetrant test	Every weld	—	Every weld
	Tensile test	3 specimens ^a	—	—
	Three-point bend test	6 specimens ^a	2 specimens ^a	—
	Macrosection ^b	1 weld	—	—
	Hardness test ^b	1 measuring row ^g	—	—

Depending on the application, two optional test classes should be distinguished, according to the load:

A: For application under static stress up to the highest fatigue stress for the parent material.

B: For application under static stress of up to 50 % of the level allowed for the parent material.

^a When the used test pieces are large enough, more than one specimen can be taken from one weld joint.

^b Not required for steels in group 1 in accordance with ISO/TR 15608 under static loading except for low temperature applications.

^c With thin wall thicknesses, it is an advantage to carry out the cupping test instead of the bend test. A level surface of 70 mm in diameter is required for the cupping test (see [6.3.3](#)). Circular tubes with thin walls can be tested using the bend test (see [6.3.4](#)).

^d At least two welds shall be carried out.

^e One test specimen from each edge and one from the middle; if test class B is relevant, one specimen from the edge and one from the middle.

^f The cupping test is preferred for steels which have a tensile strength up to 450 N/mm² and wall thicknesses up to 5 mm. For higher tensile strength(s) and/or thicker materials, use the bend test. With aluminium materials, the deformation capacity of the unaffected parent material determines the wall thickness, up to which the cupping test can be used for the welded joints.

^g Measuring row in a macrosection transverse to the weld.

^h For statistical analysis, a higher number of samples, e.g. 11, shall be tested to compute average and standard deviation.

Table 1 (continued)

Work piece	Test type	Extent of test ^h	
		Test class A	Test class B
Hollow profile	Visual test	Every weld	Every weld
	Penetrant test	Every weld	Every weld
	Tensile test	3 specimens	2 specimens
	Bend test	6 specimens ^a	2 specimens ^a
	Macrosection ^{c f}	1 weld ^a	—
	Hardness test	1 measuring row ^g	—
Sheet metal and strips	Visual test	Every weld ^d	Every weld ^d
	Penetrant test	Every weld ^d	—
	Tensile test ^e	3 specimens per weld joint ^d	2 specimens per weld joint ^d
	Three-point bend test ^{e f}	3 specimens per weld joint ^d	2 specimens per weld joint ^d
	Cupping test ^{e f}	3 specimens per weld joint ^d	—
	Macrosection ^e	3 specimens per weld joint ^d	—
	Hardness test ^b	1 measuring row ^g	—

Depending on the application, two optional test classes should be distinguished, according to the load:

A: For application under static stress up to the highest fatigue stress for the parent material.

B: For application under static stress of up to 50 % of the level allowed for the parent material.

^a When the used test pieces are large enough, more than one specimen can be taken from one weld joint.

^b Not required for steels in group 1 in accordance with ISO/TR 15608 under static loading except for low temperature applications.

^c With thin wall thicknesses, it is an advantage to carry out the cupping test instead of the bend test. A level surface of 70 mm in diameter is required for the cupping test (see 6.3.3). Circular tubes with thin walls can be tested using the bend test (see 6.3.4).

^d At least two welds shall be carried out.

^e One test specimen from each edge and one from the middle; if test class B is relevant, one specimen from the edge and one from the middle.

^f The cupping test is preferred for steels which have a tensile strength up to 450 N/mm² and wall thicknesses up to 5 mm. For higher tensile strength(s) and/or thicker materials, use the bend test. With aluminium materials, the deformation capacity of the unaffected parent material determines the wall thickness, up to which the cupping test can be used for the welded joints.

^g Measuring row in a macrosection transverse to the weld.

^h For statistical analysis, a higher number of samples, e.g. 11, shall be tested to compute average and standard deviation.

5.2.2 Tensile test specimen

The test specimen shall be prepared taking into consideration ISO 4136 and ISO 6892-1 and any standard referenced by the applicable contract or specification.

5.2.3 Bend test specimen

The test specimen shall be prepared in accordance with ISO 5173.

5.2.4 Cupping test specimen

The specimen dimensions shall be such that they can be tested on Erichsen testing equipment.

5.2.5 Hardness test specimen

The test specimen shall be prepared in accordance with ISO 9015-1 and ISO 9015-2.