DRAFT INTERNATIONAL STANDARD ISO/DIS 13179-1

ISO/TC **150** Secretariat: **DIN**

Voting begins on: Voting terminates on:

2020-12-01 2021-02-23

Implants for surgery — Coatings on metallic surgical implants —

Part 1:

Plasma-sprayed coatings derived from unalloyed titanium and TiAl6V4 powders

ICS: 11.040.40

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/DIS 13179-1 https://standards.iteh.ai/catalog/standards/sist/bd115bdc-bf08-4d9d-983e-5b20d43707c6/iso-dis-13179-1

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.



Reference number ISO/DIS 13179-1:2020(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/DIS 13179-1 https://standards.iteh.ai/catalog/standards/sist/bd115bdc-bf08-4d9d-983e-5b20d43707c6/iso-dis-13179-1



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Co	Contents						
Fore	oreword						
Introduction							
1	Scop	e					
2	Norr	native references	1				
3	Terms and definitions						
4	Requirements						
	4.1	Powder for plasma spraying	2				
	4.2	Chemical analysis					
		4.2.1 Chemical composition					
		4.2.2 Sampling					
		4.2.3 Chemical analysis procedure					
	4.3	Morphology and microstructure	4				
	4.4	Coating mechanical properties	4				
		4.4.1 General					
		4.4.2 Static shear strength					
		4.4.3 Shear fatigue strength					
		4.4.4 Static tensile strength					
		4.4.5 Abrasion resistance	4				
	4.5	Applicable verifications Significance of numerical limits A.R.D. P.R.E.V. E.W.	5				
	4.6	Significance of numerical limits A.K.J. P.K.H., V.I.H. W	5				
5	Test	report (standards.iteh.ai)	5				
Rihl	iogrank		6				

<u>ISO/DIS 13179-1</u>

https://standards.iteh.ai/catalog/standards/sist/bd115bdc-bf08-4d9d-983e-5b20d43707c6/iso-dis-13179-1

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 150, *Implants for surgery*.

This second edition cancels and replaces the first edition (4SO/1317941:2014)) which has been technically revised. 5b20d43707c6/iso-dis-13179-1

The main changes compared to the previous edition are as follows:

- the title and scope of the document was changed to also cover coatings derived from TiAl6V4 powders;
- two new terms <u>3.2</u> and <u>3.3</u> were introduced to distinguish between vacuum plasma spraying and atmospheric plasma spraying;
- in 4.2.1 three separate tables were introduced to distinguish the chemical composition limits of different coating addressed by this document;
- in <u>4.4.3</u> the term shear fatigue maximum strain was corrected to shear fatigue maximum stress.

A list of all parts in the ISO 13179-1 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

While no known surgical implant material has ever been shown to be completely free of adverse reactions in the human body, long term clinical experience with the material referred to in this document has shown that an acceptable level of biological response can be expected, if the material is used in appropriate applications. However, this standard covers the raw material, coating structures and properties and not finished medical devices, where the design and fabrication of the device can also impact biological response.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/DIS 13179-1 https://standards.iteh.ai/catalog/standards/sist/bd115bdc-bf08-4d9d-983e-5b20d43707c6/iso-dis-13179-1

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/DIS 13179-1 https://standards.iteh.ai/catalog/standards/sist/bd115bdc-bf08-4d9d-983e-5b20d43707c6/iso-dis-13179-1

Implants for surgery — Coatings on metallic surgical implants —

Part 1:

Plasma-sprayed coatings derived from unalloyed titanium and TiAl6V4 powders

1 Scope

This document specifies general requirements for plasma-sprayed titanium coatings on metallic surgical implants.

This document applies to plasma spraying in atmosphere and in vacuum.

This document does not apply to coatings made of other materials than titanium or titanium alloy or to coatings realized by another technology than plasma spraying.

NOTE A quality management system can be useful, e.g. as described in ISO 13485. Requirements for the competence of testing laboratories can be found in ISO/IEC 17025.

2 Normative references (standards.iteh.ai)

The following documents are referred to On the text in such a way that some or all of their content constitutes requirements of this documenta For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4287, Geometrical Product Specifications (GPS) — Surface texture: Profile method — Terms, definitions and surface texture parameters

ISO 5832-2, Implants for surgery — Metallic materials — Part 2: Unalloyed titanium

ISO 10993-1, Biological evaluation of medical devices — Part 1: Evaluation and testing within a risk management process

ISO 14971, Medical devices — Application of risk management to medical devices

ASTM F1044, Standard Test Method for Shear Testing of Calcium Phosphate Coatings and Metallic Coatings

ASTM F1147, Standard Test Method for Tension Testing of Calcium Phosphate and Metallic Coatings

ASTM F1160, Standard Test Method for Shear and Bending Fatigue Testing of Calcium Phosphate and Metallic Medical and Composite Calcium Phosphate/Metallic Coatings

ASTM F1580, Standard Specification for Titanium and Titanium-6 Aluminium-4 Vanadium Alloy Powders for Coatings of Surgical implants

ASTM F1854, Standard Test Method for Stereological Evaluation of Porous Coatings on Medical Implants

ASTM F1978, Standard Test Method for measuring abrasion resistance of metallic thermal spray coatings by using the Taber Abraser

ASTM E2371, Test Method for analysis of Titanium and Titanium Alloy by Atomic Emission Plasma Spectrometry

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

plasma spraying

method of thermal spraying that produces coatings using a plasma jet

3.2

vacuum plasma spraying

plasma spraying process carried out at pressures below atmospheric pressure in a controlled inert environment

3.3

atmospheric plasma spraying

plasma spraying process carried out at atmospheric pressure

3.4

plasma-sprayed titanium coatings

titanium which has been deposited onto the surface of a substrate, by means of a plasma spraying process

4 Requirements

4.1 Powder for plasma spraying

The powder used for plasma spraying shall comply with ASTM F1580.

(Standards.iteh.ai)

4.2 Chemical analysis

ISO/DIS 13179-1

4.2.1 Chemical composition standards.iteh.ai/catalog/standards/sist/bd115bdc-bf08-4d9d-983e-5b20d43707c6/iso-dis-13179-1

A risk assessment shall be conducted to identify and assess impurities introduced during the plasma spraying process.

For vacuum plasma sprayed coatings and atmospheric plasma sprayed coatings, the compositional limits for the elements listed in <u>Table 1</u> to <u>Table 3</u> shall not exceed the mass fraction listed in those tables.

The chemical composition shall be determined using the sampling procedure in $\underline{4.4.3}$ and the chemical analysis procedure in $\underline{4.2.3}$. The results of the chemical analysis shall be included in the test report [see $\underline{5}$ h)].

Table 1 — Chemical composition for vacuum plasma sprayed unalloyed titanium coatings

Element	Composition limits
Element	(mass fraction)
Carbon (C)	≤ 0,10 %
Hydrogen (H)	≤ 0,30 %
Iron (Fe)	≤ 0,60 %
Nitrogen (N)	≤ 0,50 %
Oxygen (0)	≤ 1,00 %
Titanium (Ti)	Balance

Table 2 — Chemical composition for vacuum plasma sprayed Ti-6Al-4V coatings

Element	Composition limits
Element	(mass fraction)
Carbon (C)	≤ 0,10 %
Hydrogen (H)	≤ 0,30 %
Iron (Fe)	≤ 0,60 %
Nitrogen (N)	≤ 0,50 %
Oxygen (0)	≤ 1,00 %
Titanium (Ti) + Aluminium (Al) + Vanadium (V)	Balance

Table 3 — Chemical composition for atmospheric plasma sprayed unalloyed titanium coatings

	Element	Composition limits	
	Element	(mass fraction)	
	Carbon (C)	≤ 0,10 %	
	Hydrogen (H)	≤ 0,30 %	
	Iron (Fe)	≤ 0,60 %	
	Nitrogen (N)	≤ 5,00 %	
iT	Oxygen (O) Titanium (Ti)	A 10,00 % Balance E W	

NOTE 1 At the time of drafting of this document the committee was not aware of any atmospheric plasma sprayed Ti-6Al-4V coatings, therefore no table for their chemical composition is included.

NOTE 2 The above does not eliminate the necessity for biological evaluation of the final device in accordance with ISO 10993-1.

Sb20d43707c6/iso-dis-13179-1

4.2.2 Sampling

In order to perform the chemical analysis of the coating, a minimum of 5 g of coating, which has been deposited onto a substrate coupon shall be removed. The coupon shall be representative of and made from the same material as the implant the coating is intended to be deposited on. If the removal of 5 g of coating is not possible or not sensible, the sample weight may be decreased provided that the chemical analysis is not affected. The technique used to remove the coating shall not generate contamination of the coating. If a cleaning step is performed on the implants after coating, the same cleaning step shall be applied on the sample before analysis.

4.2.3 Chemical analysis procedure

Iron content shall be determined by Inductively Coupled Plasma Atomic Emission Spectrometry (ICP-AES) in accordance with ASTM E2371.

Nitrogen, oxygen, carbon and hydrogen content, shall be determined by combustion using a recognized validated method.

The analysis accuracy with a level of confidence of 95 % shall be taken into account when claiming the conformity of the chemical analysis to the limits specified in <u>Table 1</u> and <u>Table 2</u>.

EXAMPLE If the uncertainty for measuring the oxygen content is 1 % with a level of confidence of 95 %, the conformity shall be stated as \leq 9 % for the measured values.