INTERNATIONAL STANDARD

ISO 22391-2

> Second edition 2009-12-01 **AMENDMENT 1** ISO pub-date

Plastics piping systems for hot and cold water installations — Polyethylene of raised temperature resistance (PE-RT) —

Part 2: **Pipes**

AMENDMENT

Systèmes de canalisations en plastique pour les installations d'eau chaude et froide — Polyéthylène de meilleure résistance à la température (PE-RT) —

Partie 2: Tubes

AMENDEMENT 1

PROOF/ÉPREUVE



Reference number ISO 22391-2:2009/Amd.1:2020(E)

I ah SI A Bardards teal and standards to be a standard to



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for*

This document was prepared by Technical Committee ISO/TC 138, Plastics pipes, fittings and valves for the transport of fluids, Subcommittee SC 2, Plastics pipes and fittings for water supplies, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 155, Plastics piping systems and ducting systems, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2020 – All rights reserved **PROOF/ÉPREUVE**

iii

Interest Standards in the land of the land

Plastics piping systems for hot and cold water installations — Polyethylene of raised temperature resistance (PE-RT) —

Part 2: **Pipes**

AMENDMENT 1

6.2.2, Table 3

Replace Table 3 with the following table:

Table 3 — Pipe dimensions for dimension class A (sizes in accordance with ISO 4065 and applicable for all classes of service condition)

Dimensions in millimetres

		ABA Site 1: 18 sign of		3,200	Pipe series			
Nominal size	Nominal out- side diameter	Mean outsi	ide diameter	S 5	S 4	S 3,2	S 2,5	
DN/OD		elle and istanday 538		Wall thicknesses				
	$d_{ m n}$ $d_{ m em,min}$ $d_{ m em,max}$			$e_{ m min}$ and $e_{ m n}$				
12	12	12.0	ai 12,3	1,3a	1,4	1,7	2,0	
16	16	16,0	16,3	1,5	1,8	2,2	2,7	
20	20		20,3	1,9	2,3	2,8	3,4	
25	25	25,06	25,3	2,3	2,8	3,5	4,2	
32	32	32,0	32,3	2,9	3,6	4,4	5,4	
40	40 mili	40,0	40,4	3,7	4,5	5,5	6,7	
50	30	50,0	50,5	4,6	5,6	6,9	8,3	
63	63	63,0	63,6	5,8	7,1	8,6	10,5	
75	75	75,0	75,7	6,8	8,4	10,3	12,5	
90	90	90,0	90,9	8,2	10,1	12,3	15,0	
110	110	110,0	111,0	10,0	12,3	15,1	18,3	
125	125	125,0	126,2	11,4	14,0	17,1	20,8	
140	140	140,0	141,3	12,7	15,7	19,2	23,3	
160	160	160,0	161,5	14,6	17,9	21,9	26,6	
180	180	180,0	181,7	16,4	20,1	24,6	29,9	
200	200	200,0	201,8	18,2	22,4	27,4	33,2	
225	225	225,0	227,1	20,5	25,2	30,8	37,4	
250	250	250,0	252,3	22,7	27,9	34,2	41,5	
NOTE A non-preferred wall thickness of 1,1 mm is permitted for $d_n = 12$.								

6.2.2. Table 7

Replace Table 7 with the following table:

Table 7 — Tolerance on wall thicknesses

Dimensions in millimetres

Minimum wall thickness		Tolerancea	Minimum wall thickness		Tolerance ^a
$e_{ m min}$		X	$e_{ m m}$	in	X
>	≤		>	≤	
1,0 2,0 3,0 4,0	2,0 3,0 4,0 5,0	0,3 0,4 0,5 0,6	25,0 26,0 27,0 28,0	26,0 27,0 28,0 29,0	2,7 2,8 2,9 3,0
5,0 6,0 7,0 8,0	6,0 7,0 8,0 9,0	0,7 0,8 0,9 1,0	29,0 30,0 31,0 32,0	30,0 31,0 32,0 33,0	3,1 3,2 3,3 3,4
9,0 10,0 11,0 12,0	10,0 11,0 12,0 13,0	1,1 1,2 1,3 1,4	33,0 34,0 35,0 36,0	34,0 35,0 36,0 37,0	3,5 3,6 3,7 3,8
13,0 14,0 15,0 16,0	14,0 15,0 16,0 17,0	1,5 1,6 1,7 1,8	37,0 38,0 39,0 40,0	38,0 39,0 40,0 41,0	3,9 4,0 4,1 4,2
17,0 18,0 19,0 20,0	18,0 19,0 20,0 21,0	1,9 2,0 2,1 2,2	PR41.0	42,0,0.1. 2,0,0.1. 2,0,0.1. 2,0,0.1. 2,0,0.1. 2,0,0.1. 2,0,0.1. 2,0,0.1. 2,0,0.1. 2,0,0.1. 2,0,0.1. 2,0,0.1. 2	4,3
21,0 22,0 23,0 24,0	22,0 23,0 24,0 25,0	2,3 2,4 2,5 mida 2,6	40,0 40,0 Asitellardinards deitalage dange dange		

The tolerance is expressed in the form $^+$ 0 mm, where "x" is the value of the tolerance given. The level of the tolerances conforms to Grade V in ISO 11922-1.

ottps://standad

Interest Standards in the land of the land