# INTERNATIONAL STANDARD

ISO 22391-5

> Second edition 2009-12-01 **AMENDMENT 1** 2020-12

Plastics piping systems for hot and cold water installations — Polyethylene of raised temperature resistance (PE-RT) —

Part 5:

iTeh STANDARD PREVIEW the system (stAMENDMENT.1i)

Systèmes de canalisations en plastique pour les installations d'eau https://standards.iteh.avcatalogst

Partie 5: Aptitude à l'emploi du système AMENDEMENT 1



# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 22391-5:2009/Amd 1:2020 https://standards.iteh.ai/catalog/standards/sist/43e486a9-3029-4770-aa4d-7b78602f2179/iso-22391-5-2009-amd-1-2020



#### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

#### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>. (Standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 138, Plastics pipes, fittings and valves for the transport of fluids, Subcommittee SC 2, Plastics pipes and fittings for water supplies, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 155, Plastics piping systems and ducting systems, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

A list of all parts in the ISO 22391 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <a href="https://www.iso.org/members.html">www.iso.org/members.html</a>.

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 22391-5:2009/Amd 1:2020 https://standards.iteh.ai/catalog/standards/sist/43e486a9-3029-4770-aa4d-7b78602f2179/iso-22391-5-2009-amd-1-2020

# Plastics piping systems for hot and cold water installations — Polyethylene of raised temperature resistance (PE-RT) —

#### Part 5:

## Fitness for purpose of the system

## **AMENDMENT 1**

Normative references

Replace the reference to "EN 712" with the following:

ISO 3501, Plastics piping systems — Mechanical joints between fittings and pressure pipes — Test method for resistance to pull-out under constant longitudinal force

## Replace the reference to "EN 713" with the following: PREVIEW

ISO 3503, Plastics piping systems — Mechanical joints between fittings and pressure pipes — Test method for leaktightness under internal pressure of assemblies subjected to bending

Replace the reference to "EN 12293" with the following: 2020

ISO 19893, Plastics piping systems — Thermoplastics pipes and fittings for hot and cold water — Test method for the resistance of mounted assemblies to temperature cycling

Replace the reference to "EN 12294" with the following:

ISO 13056, Plastics piping systems — Pressure systems for hot and cold water — Test method for leaktightness under vacuum

Replace the reference to "EN 12295" with the following:

ISO 19892, Plastics piping systems — Thermoplastics pipes and fittings for hot and cold water — Test method for the resistance of joints to pressure cycling

#### 4.1, Table 1

Replace the reference to "EN 713" with "ISO 3503".

Replace the reference to "EN 712" with "ISO 3501".

Replace the reference to "EN 12293" with "ISO 19893".

Replace the reference to "EN 12295" with "ISO 19892".

Replace the reference to "EN 12294" with "ISO 13056".

#### ISO 22391-5:2009/Amd.1:2020(E)

#### 4.3, first paragraph

Replace the reference to "EN 713" with "ISO 3503".

#### 4.3, second paragraph

Replace "of nominal diameter greater than or equal to 32 mm" with "that are declared as being bendable by the system supplier."

#### 4.4, first paragraph

Replace the reference to "EN 712" with "ISO 3501".

#### 4.5, first paragraph

Replace the reference to "EN 12293" with "ISO 19893".

### 4.5, Table 7 iTeh STANDARD PREVIEW

Replace Table 7 with the following table: standards.iteh.ai)

Table 7 — Test parameters for thermal cycling test

https://standards.iteh.ai	n.ai/catalog/standards/sist/43c486a9-30/29-47/0-aa4d- 02/2179/iso-22391-5-2009-and-1-2020					
/0/80021	Class 1	Class 2	Class 4	Class 5		
Maximum design temperature, $T_{\rm max}$ , in °C	80	80	70	90		
Highest test temperature, in °C	90	90	80	95		
Lowest test temperature, in °C	20	20	20	20		
Test pressure, in bars	$p_{ m D}$	$p_{\mathrm{D}}$	$p_{ m D}$	$p_{ m D}$		
Number of cycles for $d_n \le 160 \text{ mm}^a$	5 000	5 000	5 000	5 000		
Number of cycles for $d_n > 160 \text{ mm}^b$	500	500	500	500		
Number of test pieces	One set of fittings in accordance with the configuration shown in ISO 19893 <sup>c</sup>					

<sup>&</sup>lt;sup>a</sup> Each cycle shall comprise  $150^{+1}_{0}$  min at the highest test temperature and  $150^{+1}_{0}$  min at the lowest (i.e. the duration of one cycle is  $30^{+2}_{0}$  min).

#### 4.5, third paragraph

Replace the reference to "EN 12293" with "ISO 19893".

Each cycle shall comprise  $150^{+5}_{0}$  min at the highest test temperature and  $150^{+5}_{0}$  min at the lowest (i.e. the duration of one cycle is  $300^{+10}_{0}$  min).

 $<sup>^{\</sup>rm c}$  The test arrangement consists of min. 4 pipe connectors or min. 6 pipe connections for  $d_{\rm n}$  > 160 mm. The free pipe length between the joints shall not be less than 150 mm. A representative set of fittings shall be used in the assembly.

#### 4.6, first paragraph

Replace the reference to "EN 12295" with "ISO 19892".

#### 4.6, Table 8

Replace Table 8 with the following table:

Table 8 — Test parameters for pressure cycling

Characteristics	Requirement	Test parameters			Test method
Pressure cycling	No leakage	Test temperature	23 °C 3		ISO 19892
		Number of test pieces			
			$d_{\rm n} \le 160$ mm	<i>d</i> <sub>n</sub> > 160 mm	
		Frequency (cycles/min)	$(30 \pm 5)$	(15 ± 3)	
		Number of cycles	10 000	5 000	
	Test pressure limits for a design pressure of:	Upper limit	Lower limit 0,5 bar		
	ındar@s.iteh.a	9,0 bar	0,5 bar		
		8 bar	12,0 bar	0,5 bar	
	ISO	<u>) 22391-5:<b>10</b>09aKmd 1:2020</u>	15,0 bar	0,5 bar	


https://standards.iteh.ai/catalog/standards/sist/43e486a9-3029-4770-aa4d-7b78602f2179/iso-22391-5-2009-amd-1-2020

#### 4.7, first paragraph

Replace the reference to "EN 12294" with "ISO 13056".

#### 4.7, Table 9

Replace the reference to "EN 12294" with "ISO 13056".



# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 22391-5:2009/Amd 1:2020 https://standards.iteh.ai/catalog/standards/sist/43e486a9-3029-4770-aa4d-7b78602f2179/iso-22391-5-2009-amd-1-2020