



**International
Standard**

ISO 4349

**Solid recovered fuels —
Determination of the recycling
index for co-processing**

*Combustibles solides de récupération — Détermination de
l'indice de recyclage pour le cotraitement*

**First edition
2024-05**

iteh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 4349:2024](https://standards.iteh.ai/catalog/standards/iso/febadedb-e784-4000-8294-76eff37fd782/iso-4349-2024)

<https://standards.iteh.ai/catalog/standards/iso/febadedb-e784-4000-8294-76eff37fd782/iso-4349-2024>

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 4349:2024

<https://standards.iteh.ai/catalog/standards/iso/febadedb-e784-4000-8294-76eff37fd782/iso-4349-2024>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and abbreviated terms	2
5 Reagents	2
6 Apparatus	2
7 Procedure	3
7.1 Preparation of the test sample.....	3
7.2 Determination of the ash content and preparation of ash sample.....	3
7.3 Determination of the elemental content.....	3
7.4 Methods.....	3
7.4.1 Method A – wet digestion followed by ICP-MS or ICP-OES analysis.....	3
7.4.2 Method B – preparation of fused beads followed by ICP-OES analysis.....	4
7.4.3 Method C – preparation of pellets followed by XRF analysis.....	4
7.4.4 Alternative procedures.....	4
7.5 Calculation.....	4
7.5.1 Calculation of element oxides.....	4
7.5.2 Calculation of R-index for co-processing.....	5
8 Performance characteristics	5
9 Test report	5
Annex A (informative) SRF ash composition from mixed municipal and commercial waste	6
Annex B (informative) Validation	15
Bibliography	23

<https://standards.iteh.ai/catalog/standards/iso/febadedb-e784-4000-8294-76eff37fd782/iso-4349-2024>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 300, *Solid recovered materials, including solid recovered fuels*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 343, *Solid recovered materials, including solid recovered fuels*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

<https://standards.iteh.ai/catalog/standards/iso/febadedb-e784-4000-8294-76eff37fd782/iso-4349-2024>

Introduction

When solid recovered fuels (SRFs) are co-processed mainly in the cement industry, simultaneous energy recovery and recycling of mineral components of waste material takes place because the ash is directly incorporated into the clinker. SRF co-processing therefore allows for the replacement of both mineral resources and fossil fuels.

SRF ashes contain various chemical components that are crucial raw materials for cement manufacturers, fulfil specific tasks in cement clinker production or represent clinker phases giving the clinker its specific properties. For example, a major part of SRF ashes from mixed municipal and commercial waste consists of the four main chemical components that are required for cement clinker production: Al_2O_3 , CaO , Fe_2O_3 and SiO_2 (see [Annex A](#)). Additionally, minor ash constituents include MgO and TiO_2 , both of which are present in or as clinker phases. K_2O and Na_2O are typical constituents of feldspars that are present in the clay used as a raw material for the process. SO_3 , which is also present in SRF ash, or another sulfate carrier is needed in order to convert these alkali oxides into alkali sulfates, a clinker phase that alters the clinker's chemical reactivity with water.

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ISO 4349:2024](#)

<https://standards.itih.ai/catalog/standards/iso/febadedb-e784-4000-8294-76eff37fd782/iso-4349-2024>

Solid recovered fuels — Determination of the recycling index for co-processing

1 Scope

This document specifies the determination of the share of material recovery in the case of energy recovery (i.e. co-processing) of solid recovered fuels (SRFs), for example, in a cement kiln. This share, called the recycling index (R-index), is calculated on the basis of the ash content and the ash composition.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3884:—¹⁾, *Solid recovered fuels — Methods for the determination of the content of elements (Al, Ca, Fe, K, Mg, Na, P, S, Si, Ti, As, Ba, Be, Cd, Co, Cr, Cu, Hg, Mo, Mn, Ni, Pb, Sb, Se, Sn, Tl, V, Zn)*

ISO 11885, *Water quality — Determination of selected elements by inductively coupled plasma optical emission spectrometry (ICP-OES)*

ISO 21645, *Solid recovered fuels — Methods for sampling*

ISO 21646, *Solid recovered fuels — Sample preparation*

ISO 21656:2021, *Solid recovered fuels — Determination of ash content*

ISO 22940, *Solid recovered fuels — Determination of elemental composition by X-ray fluorescence*

EN 15309, *Characterization of waste and soil. Determination of elemental composition by X-ray fluorescence*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 recycling index

R-index

share of SRF that can be considered as recycled on a material level, expressed as a mass fraction in per cent of the dry matter

3.2 co-processing

use of SRF in manufacturing processes for energy recovery and simultaneously for material recovery of mineral components

1) Under preparation. Stage at the time of publication: ISO/DIS 3884:2024.

4 Symbols and abbreviated terms

A_{db}	ash content at 815 °C on a dry basis
Al_2O_3	aluminium(III) oxide
CaO	calcium oxide
(d)	dry (dry basis)
Fe_2O_3	iron(III) oxide
K_2O	potassium oxide
MgO	magnesium oxide
Na_2O	sodium oxide
SiO_2	silicon dioxide
SO_3	sulfur trioxide
TiO_2	titanium dioxide

5 Reagents

Use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

5.1 Water, e.g. deionized (< 0,055 $\mu S/cm$).

5.2 Nitric acid (HNO_3), approximately 15 mol/l, mass fraction of 65 % to 70 %.

5.3 Hydrofluoric acid (HF), approximately 23 mol/l, mass fraction of 40 % to 45 %.

5.4 Hydrochloric acid (HCl), approximately 12 mol/l, mass fraction of 35 % to 37 %.

5.5 Lithium metaborate ($LiBO_2$), solid.

5.6 Binder, solid or liquid, for example wax. Specifications are given in EN 15309.

6 Apparatus

The usual laboratory apparatus and, in particular, the following shall be used.

6.1 Analytical balance, with an accuracy of 1 mg or better.

6.2 Muffle furnace, for temperatures of 1 050 °C.

6.3 Inductively coupled plasma, normal commercial instrumentation with optical or mass spectrometric detector (ICP-OES, ICP-MS).

6.4 X-ray fluorescence spectrometer, an energy or wavelength dispersion system suitable for qualitative and (semi-)quantitative analysis of the elements listed in this document.

6.5 Microwave unit, in accordance with ISO 3884:—.

6.6 **Press**, in accordance with ISO 22940 or EN 15309.

6.7 **Platinum crucible**, e.g. Pt/Au5 %.

6.8 **Inert bowl**, for example made from porcelain, silicon dioxide or platinum with a depth of 10 mm to 20 mm and with a size selected in a way that the occupancy of the bottom area does not exceed 0,1 g/cm².

6.9 **Magnetic stirrer**, with heating function and PTFE (polytetrafluoroethylene) stirring bone.

6.10 **Volumetric flasks**, e.g. 250 ml.

7 Procedure

7.1 Preparation of the test sample

The sampling of SRF shall be carried out in accordance with ISO 21645 and the sample preparation in accordance with ISO 21646, with the final sample having a nominal top size of 1,0 mm or less. Hard impurities, i.e. inert materials or metals, that cannot be reduced in size with the apparatuses defined in ISO 21646 are sorted out during sample preparation and are not considered in the subsequent analysis steps. Their amount shall be documented. The sample is dried at 105 °C according to ISO 21660-3. Further procedures and analyses are carried out with the dried sample <1,0 mm free of hard impurities.

7.2 Determination of the ash content and preparation of ash sample

The determination of the ash content shall be carried out in accordance with ISO 21656:2021, method B. If the determination provides a sufficient amount of material to proceed with the analyses, the ashed material shall be used for subsequent analyses. If the determination of the ash content provides insufficient amounts of ash for the subsequent analysis steps (examples of ash content of typical constituents of SRF from mixed municipal and commercial waste are given in [Annex A](#)), the sufficient amount of ash shall be reached by using one or both of the following two approaches:

- a) The ashing process is repeated and the ashes are collected and united in order to reach the minimum amounts required for subsequent ash analyses. This may be the preferable approach for method A (wet digestion/ICP-MS, requiring approximately 200 mg of ash sample) and method B (fused beads/ICP-OES, requiring approximately 100 mg of ash sample).
- b) A correspondingly larger inert bowl is used and the amount of sample is increased accordingly, which may be the preferable option for pellet preparation and XRF analyses (method C, approximately 4,5 g to 10 g is required). The bowl shall fulfil the requirements defined by ISO 21656 and its size shall be selected in such a way that the occupancy of the bottom area does not exceed 0,1 g/cm².

7.3 Determination of the elemental content

The determination of the elemental content shall be carried out according to ISO 3884:— or ISO 22940. The element content shall be determined in the ashed sample.

7.4 Methods

7.4.1 Method A – wet digestion followed by ICP-MS or ICP-OES analysis

The ash shall be digested using microwave-assisted acid digestion with hydrochloric acid, nitric acid and hydrofluoric acid and analysed by ICP-MS or ICP-OES as described in ISO 3884:—.

7.4.2 Method B – preparation of fused beads followed by ICP-OES analysis

100 mg (± 20 mg) of the ashed sample shall be thoroughly mixed with 1 000 mg (± 10 mg) of the fluxing agent lithium metaborate in a platinum crucible. The mixture shall be melted in a muffle furnace at $1\ 050\text{ °C} \pm 10\text{ °C}$ for 20 min. The resulting fused bead is allowed to cool down and dissolved incrementally by adding 80 ml of hydrochloric acid ($c = 2\text{ mol/l}$) into the crucible in small amounts. The dissolution shall be supported by heating (to approximately 60 °C) and stirring with a PTFE stirring bone. The digest solution shall be filled to a final volume of 250 ml with deionised water ($< 0,055\ \mu\text{S/cm}$). This solution shall contain 0,4 g/l of the sample and 4 g/l of the fluxing agent. Only clear solutions shall be subjected to subsequent analyses, turbid digest solutions are discarded. A blank shall be prepared using the same method, but no sample is added. The element content in the digestion solutions shall be determined by ICP-OES in accordance with ISO 11885.

7.4.3 Method C – preparation of pellets followed by XRF analysis

The pellet preparation and XRF analyses shall be performed in accordance with ISO 22940 or EN 15309. The fine ash sample shall be mixed and homogenized with binder at a defined ratio (different ratios can be applied and the dilution factor needs to be considered; a typical sample to wax mass ratio is 10:1) and shall be pressed with an automatic or manual press. For a pellet with a diameter of 40 mm, about 10,0 g of the ash sample is required. For a pellet with a diameter of 32 mm, approximately 4,5 g ash sample is required.

7.4.4 Alternative procedures

Alternative methods can be applied if their performance is proved to be comparable with those listed in the preceding subclauses.

7.5 Calculation

7.5.1 Calculation of element oxides

The results for the concentrations of chemical elements need to be converted into concentrations of element oxides. The conversion is performed by multiplying the concentration of the respective element, expressed as mg/kg (d), with the corresponding conversion factor as shown in [Formula \(1\)](#):

$$c_{i_2} = F_{ci} * c_{i_1} \quad \text{ISO 4349:2024} \quad (1)$$

<https://standards.iteh.ai/catalog/standards/iso/febadedb-e784-4000-8294-76eff37fd782/iso-4349-2024>

where

c_{i_1} is the concentration of a selected element expressed as mg/kg (d);

c_{i_2} is the concentration of the corresponding element oxide expressed as mg/kg (d), see [Table 1](#);

F_{ci} is the corresponding conversion factor as listed in [Table 1](#).

Table 1 — Conversion factors

Element	Element oxide	Conversion factor F_c
Al	Al ₂ O ₃	1,889 4
Ca	CaO	1,399 2
Fe	Fe ₂ O ₃	1,429 7
K	K ₂ O	1,204 6
Mg	MgO	1,658 3
Na	Na ₂ O	1,348 0
S	SO ₃	2,496 9
Si	SiO ₂	2,139 3
Ti	TiO ₂	1,668 5

7.5.2 Calculation of R-index for co-processing

The share of the SRF that is recycled on a material level (i.e. R-index), expressed as mass fraction in per cent of the dry matter [% (*d*)], can either be calculated considering the four main chemical compounds required for the production of cement clinker (R_{i4}) or considering additional elements that are introduced by natural raw materials and are part of clinker phases as well (R_{i9}). The R-indices shall be calculated as follows:

$$R_{i4} = \frac{A_{db} * \frac{c_{Al_2O_3} + c_{CaO} + c_{Fe_2O_3} + c_{SiO_2}}{10\,000}}{100} \quad (2)$$

$$R_{i9} = \frac{A_{db} * \frac{c_{Al_2O_3} + c_{CaO} + c_{Fe_2O_3} + c_{K_2O} + c_{MgO} + c_{Na_2O} + c_{SO_3} + c_{SiO_2} + c_{TiO_2}}{10\,000}}{100} \quad (3)$$

where

A_{db} is the ash content of the general analysis sample at 815 °C on a dry basis, expressed as mass fraction in per cent of the dry matter;

c_x is the concentration of element oxides expressed as mg/kg (*d*).

8 Performance characteristics

Data for repeatability and reproducibility for predefined solid recovered fuel samples (paper fibre sludge, high calorific waste fraction from non-hazardous municipal solid waste) are shown in [Annex B](#).

9 Test report

The test report shall contain at least the following information:

- a) name, address and location of any laboratory involved in the analysis;
- b) description and identification of the laboratory sample;
- c) date of receipt of laboratory sample and date(s) of performance of test;
- d) a reference to this document, i.e. ISO 4349:2024;
- e) reference to the analytical standard used for the determination of each element;
- f) the analytical results for R-index₄ and/or R-index₉, referring to % (*d*);
- g) amount of hard impurities, referring to % (*d*);
- h) any details not specified in this document or which are optional, and any other factors which can have affected the results;
- i) unique identification of report (such as serial number) and of each page and total number of pages of the report.

The laboratory should keep a trace of any analytical steps and intermediate results (raw data and calculation details) that should be kept available in case of specific requirements.