
**Physical and mechanical properties of
wood — Test methods for small clear
wood specimens —**

Part 18:
Vocabulary

*Propriétés physiques et mécaniques du bois — Méthodes d'essais sur
petites éprouvettes de bois sans défauts —
Partie 18: Vocabulaire*

[ISO 13061-18:2022](https://standards.iteh.ai/catalog/standards/sist/2f36e641-f0b2-4eed-a0e8-fd377c45c4d0/iso-13061-18-2022)

<https://standards.iteh.ai/catalog/standards/sist/2f36e641-f0b2-4eed-a0e8-fd377c45c4d0/iso-13061-18-2022>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 13061-18:2022

<https://standards.iteh.ai/catalog/standards/sist/2f36e641-f0b2-4eed-a0e8-fd377c45c4d0/iso-13061-18-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
3.1 Common terms relating to wood macrostructure.....	1
3.2 General terms relating to testing of wood.....	2
3.3 Common terms relating to physical tests.....	3
3.4 Common terms relating to mechanical tests.....	5
Bibliography	7
Alphabetical index	8

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 13061-18:2022](https://standards.iteh.ai/catalog/standards/sist/2f36e641-f0b2-4eed-a0e8-fd377c45c4d0/iso-13061-18-2022)

<https://standards.iteh.ai/catalog/standards/sist/2f36e641-f0b2-4eed-a0e8-fd377c45c4d0/iso-13061-18-2022>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

This document was prepared by Technical Committee ISO/TC 218, *Timber*.

This first edition of ISO 13061-18 cancels and replaces ISO 9086-1:1987, which has been technically revised. The main changes compared to the previous edition are as follows:

- title of the document has been changed to reflect the content:
- the content covers all common terminologies used in the sampling and test methods of small clear wood specimens;
- the terminologies were divided into four categories: general terms commonly used in test methods, terms related to wood macrostructure, physical and to mechanical tests properties.

A list of all parts in the ISO 13061 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document defines terms which are commonly used in sampling and testing of small clear wood specimen for physical and mechanical properties. The need to be able to comprehend and communicate clearly and precisely on the methods of sampling and testing of physical and mechanical characteristics of wood is of prime importance because of the great variety of species, variability of the material, advancement of equipment and testing facility, and many other factors that may affect the test results. Only with good similar understanding on the methods of sampling and testing that the test data from various sources can be scientifically compared and inferred.

This document has been revised into a single standard document for terminologies related to testing of small clear wood specimens for physical and mechanical characteristics of wood.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 13061-18:2022](https://standards.iteh.ai/catalog/standards/sist/2f36e641-f0b2-4eed-a0e8-fd377c45c4d0/iso-13061-18-2022)

<https://standards.iteh.ai/catalog/standards/sist/2f36e641-f0b2-4eed-a0e8-fd377c45c4d0/iso-13061-18-2022>

Physical and mechanical properties of wood — Test methods for small clear wood specimens —

Part 18: Vocabulary

1 Scope

This document lists the terms and definitions relating to general concepts, macrostructure, sampling, and methods of physical and mechanical testing of wood. Other terminologies that are not mentioned in this standard are defined in ISO 24294.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 Common terms relating to wood macrostructure

3.1.1

annual ring

growth ring (3.1.2) corresponding to an annual period of growth

[SOURCE: ISO 24294:2021, 9.9, modified — Note 1 to entry was deleted.]

3.1.1.1

annual ring width

distance, measured radially, between boundaries of adjacent *annual rings* (3.1.1) of wood

3.1.2

growth ring

layer of wood produced in one growing season

[SOURCE: ISO 24294:2021, 9.8, modified — Note 1 to entry was deleted.]

3.1.2.1

growth ring width

distance, measured radially, between boundaries of adjacent *growth rings* (3.1.2)

Note 1 to entry: The width of *growth rings* (3.1.2) depends on the tree species and on growing conditions. In temperate growth zones, growth rings correspond to *annual rings* (3.1.1).

3.1.3

juvenile wood

wood formed during the early years, found at the centre of the stem and branches, possessing physical and mechanical properties different from those of wood formed later

3.1.4

latewood content

portion of *growth ring* (3.1.2) or *annual ring width* (3.1.1.1) occupied by the late wood

3.1.5

wood macrostructure

wood structure which may be examined with the unaided eye or by means of a magnifier

3.2 General terms relating to testing of wood

3.2.1

clear wood

free of defects and imperfections

3.2.2

conditioning of wood

seasoning of wood at atmospheric pressure with constant set temperature and relative humidity until equilibrium moisture content is reached

3.2.3

longitudinal

parallel to the grain of wood

Note 1 to entry: Generally, *test pieces* (3.2.10) are cut with their long axis along the grain of wood.

3.2.4

mechanical properties of wood

quantitative characteristic relating a response of a *test piece* (3.2.10) to applied forces or deformations

EXAMPLE Strength, modulus of elasticity.

3.2.5

physical properties of wood

quantitative characteristic relating a condition of a *test piece* (3.2.10) and not involving in its manifestation a chemical change

EXAMPLE Density, moisture content.

3.2.6

radial

perpendicular to the *growth rings* (3.1.2) or parallel to the rays of wood

Note 1 to entry: In practice, it often means roughly perpendicular to the *growth rings* (3.1.2).

3.2.7

sampling

process of selecting wood sections from logs or sawn timber to represent the population for the purpose of testing

Note 1 to entry: Methods for the extensive and limited sampling of wood, conditioning and preparation of *test pieces* (3.2.10) are described in ISO 3129.

3.2.8

straight-grained wood

wood in which the fibres run essentially parallel to the long axis of a piece

3.2.9

tangential

parallel to the *growth rings* (3.1.2) or perpendicular to the rays of wood

Note 1 to entry: In practice, it often means roughly parallel to the *growth rings* (3.1.2).

3.2.10**test piece**
test specimen
specimen

unit or section of definite dimensions and shape intended for tests

Note 1 to entry: Usually cut from a wood piece with direction generally parallel to the grain of wood or the long axis of a work piece *sample* (3.2.13).

3.2.10.1**full-size test piece**

test piece (3.2.10) of identical size to the product or differing in length only

3.2.10.2**side plane of the test piece**

side surface of the *test piece* (3.2.10)

3.2.10.3**small clear test piece**
small clear test specimen
small clear wood specimen

test piece (3.2.10) of small cross-section of the *clear wood* (3.2.1), *straight-grained wood* (3.2.8)

3.2.11**transverse section**
cross-section

section perpendicular to the wood grain

Note 1 to entry: Usually perpendicular to the long axis of the *test piece* (3.2.10).

3.2.12**working section****working part of the test piece**

section of the *test piece* (3.2.10) where the effect of the characteristic being investigated is most important

3.2.13**workpiece sample**

unit or part of products intended for preparation of *test piece* (3.2.10)

3.3 Common terms relating to physical tests**3.3.1****dimensional stability**

ability to resist changes in dimension and volume with variation in *moisture content* (3.3.5)

3.3.2**density**

mass per volume of a *test piece* (3.2.10) at a specified *moisture content* (3.3.5)

Note 1 to entry: Influenced by rate of growth, percentage of late wood and in individual pieces, the proportion of heartwood.

Note 2 to entry: The *moisture content* (3.3.5) is specified for both mass and volume.

Note 3 to entry: Usually expressed in kg/m³ or g/cm³.

3.3.2.1

density in the absolutely dry condition **oven-dry density**

density (3.3.2) based on oven-dry mass and oven-dry volume of a *test piece* (3.2.10)

[SOURCE: ISO 13061-2:2014, 3.2]

3.3.2.2

density at specified moisture content

density (3.3.2) based on mass of a test piece including moisture and its volume at the same *moisture content* (3.3.5)

[SOURCE: ISO 13061-2:2014, 3.3]

3.3.2.3

basic (conventional) density

density (3.3.2) based on oven-dry mass of a test piece and its *green volume* (3.3.4)

[SOURCE: ISO 13061-2:2014, 3.4]

3.3.4

green volume

volume of a test piece at *moisture content* (3.3.5) greater than or equal to the fibre saturation point before any shrinkage occurs due to drying

[SOURCE: ISO 13061-2:2014, 3.5]

3.3.5

moisture content

amount of water contained in the *test piece* (3.2.10), expressed as a percentage of the mass of the wood in the oven-dry state

Note 1 to entry: Determined as mass of evaporable water divided by mass of wood in oven-dry state.

Note 2 to entry: When *moisture content* (3.3.5) is specified for production, it is expressed as either an average moisture content with a limit on the variation, or as a moisture content limit, which a large portion of the production should not exceed.

[SOURCE: ISO 24294:2021, 6.1, modified — In the definition, "in wood" was replaced by "in the test piece".]

3.3.6

specific gravity

relative density

ratio of the oven-dry weight of wood at a specified *moisture content* (3.3.5) to the weight of volume of water equal to the volume of wood

3.3.7

shrinkage

decrease in the dimensions or volume of *test piece* (3.2.10) due to reduction of *moisture content* (3.3.5) below fibre saturation point

3.3.7.1

radial shrinkage

shrinkage (3.3.7) in *radial* (3.2.6) direction

3.3.7.2

tangential shrinkage

shrinkage (3.3.7) in *tangential* (3.2.9) direction