



Designation: C1071 – 12

Standard Specification for Fibrous Glass Duct Lining Insulation (Thermal and Sound Absorbing Material)¹

This standard is issued under the fixed designation C1071; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers fibrous glass insulation used as a thermal and sound absorbing liner for interior surfaces of ducts, plenums, and other air handling equipment that handle air up to 250°F (121°C).

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- C167 Test Methods for Thickness and Density of Blanket or Batt Thermal Insulations
- C168 Terminology Relating to Thermal Insulation
- C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus
- C390 Practice for Sampling and Acceptance of Thermal Insulation Lots
- C411 Test Method for Hot-Surface Performance of High-Temperature Thermal Insulation
- C423 Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method
- C518 Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus

C665 Specification for Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured Housing

C1104/C1104M Test Method for Determining the Water Vapor Sorption of Unfaced Mineral Fiber Insulation

C1114 Test Method for Steady-State Thermal Transmission Properties by Means of the Thin-Heater Apparatus

C1304 Test Method for Assessing the Odor Emission of Thermal Insulation Materials

C1338 Test Method for Determining Fungi Resistance of Insulation Materials and Facings

E84 Test Method for Surface Burning Characteristics of Building Materials

E795 Practices for Mounting Test Specimens During Sound Absorption Tests

E2231 Practice for Specimen Preparation and Mounting of Pipe and Duct Insulation Materials to Assess Surface Burning Characteristics

G21 Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi

G22 Practice for Determining Resistance of Plastics to Bacteria (Withdrawn 2002)³

2.2 Other Standards:

CAN/ULC-S102 Method of Test for Surface Burning Characteristics of Building Materials and Assemblies⁴

NAIMA Fibrous Glass Duct Liner Standard⁵

NFPA 259 Test Method for Potential Heat of Building Materials⁶

SMACNA HVAC Duct Construction Standards⁷

UL 181 Factory-Made Air Ducts and Air Connectors⁴

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.23 on Blanket and Loose Fill Insulation.

Current edition approved March 1, 2012. Published March 2012. Originally approved in 1986. Last previous edition approved in 2005 as C1071 – 05 ^{ε1}. DOI: 10.1520/C1071-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from Underwriters Laboratories (UL), 2600 N.W. Lake Rd., Camas, WA 98607-8542, <http://www.ul.com>.

⁵ Available from North American Insulation Manufacturers Association (NAIMA), 44 Canal Center Plaza, Suite 310, Alexandria, VA 22314, <http://www.naima.org>.

⁶ Available from National Fire Protection Association (NFPA), 1 Batterymarch Park, Quincy, MA 02169-7471, <http://www.nfpa.org>.

⁷ Available from Sheet Metal and Air Conditioning Contractors' National Association 4201 Lafayette Center Drive Chantilly, Virginia 20151-1219, <http://www.smacna.org>

UL 723 Test for Surface Burning Characteristics of Building Materials⁴

3. Terminology

3.1 For definitions of terms used in this specification, see Terminology C168.

4. Classification

4.1 The insulation covered by this specification shall be of the following types:

4.1.1 *Type I*—Blanket in roll form up to 200 ft (61 m) in length, 36 to 72 in. (914 to 1829 mm) in width, and thicknesses of ½ to 3 in. (13 to 76 mm), in ½-in. (13-mm) increments.

4.1.2 *Type II*—Board in sheet form, up to 120 in. (3048 mm) in length, up to 48 in. (1219 mm) in width, and thicknesses of ½ to 3 in. (13 to 76 mm) in ½-in. (13-mm) increments.

5. Ordering Information

5.1 Purchasers shall select the preferred options permitted herein and include the following information in procurement documents:

5.1.1 Title, designation, and year of this specification.

5.1.2 Type of insulation (see 4.1).

5.1.3 Length, width, and thickness required (see 4.1).

5.1.4 Packaging required (see 16.1).

5.1.5 Marking required (see 16.2 and 16.3).

6. Materials and Manufacture

6.1 *Basic Material*—The basic material shall be made from glass processed from the molten state into fibrous form with a binder added to form dimensionally stable insulation. Asbestos shall not be used as an ingredient or component part of the product.

6.2 *Air Stream Surface*—Depending on the insulation surface characteristics and service air velocity, the air stream surface is plain or coated with a temperature resistant coating or faced with a plain or coated fibrous mat or fabric.

7. Physical Requirements

7.1 *Corrosiveness*—When tested in accordance with 12.3, the steel plates in contact with both sides of the insulation shall show no corrosion greater than the comparative plates in contact with sterile cotton which has been tested in the same manner.

7.2 *Water Vapor Sorption*—When tested in accordance with 12.4, the water vapor sorption of the insulation shall not be more than 3 % by weight.

7.3 *Fungi Resistance*—When tested in accordance with 12.5, the insulation shall be observed as having no fungal growth.

7.4 *Temperature Resistance*—When tested in accordance with 12.6, the air stream surface shall have no evidence of flaming, glowing, smoldering, visible smoke, or delamination, cracking, deformation or reduction in thickness.

7.5 *Erosion Resistance*—When tested in accordance with 12.7, the insulation shall not break away, crack, peel, flake off,

or show evidence of delamination or continued erosion when air is passed through typical duct sections at a velocity specified in 12.7.

7.6 *Odor Emission*—When tested in accordance with 12.8, a detectable odor of objectionable nature recorded by more than two of the five panel members shall constitute failure of the material.

7.7 *Surface Burning Characteristics*—When tested in accordance with 12.9, the air stream surface of the insulation shall have a maximum flame spread index of 25 and a maximum smoke developed index of 50.

7.8 *Apparent Thermal Conductivity*—When tested in accordance with 12.10, the apparent thermal conductivity (k) of the insulation, expressed as Btu-in/h-ft² ·°F (W/m·K) for the specified thickness shall not exceed the values shown in Table 1.

7.9 *Sound Absorption Coefficients*—When tested in accordance with 12.11, the insulation shall have sound absorption coefficients and noise reduction coefficients not less than shown in Table 2.

7.10 *Bacteria Resistance*—When tested in accordance with 12.12, the insulation shall be observed as having no growth.

7.11 *Combustion Characteristics*—When tested in accordance with 12.13, the material shall have a potential heat value not exceeding 3500 Btu/lb (8141 kJ/kg).

8. Dimensional Tolerances

8.1 After conditioning for a minimum of 24 h at 70 ± 3°F (21 ± 1.6°C) and 50 ± 5 % relative humidity, the insulation shall conform to the dimensional tolerances listed in Table 3.

9. Workmanship, Finish, and Appearance

9.1 The insulation units shall indicate good workmanship in fabrication and shall not have visible defects which adversely affect their service qualities.

10. Sampling

10.1 The insulation shall be sampled in accordance with Practice C390. Specific provisions for sampling shall be agreed upon between the purchaser and supplier as part of the purchase contract.

11. Qualification Requirements

11.1 The following requirements shall be employed for the purpose of initial material or product qualification:

11.1.1 Corrosiveness,

11.1.2 Water vapor sorption,

11.1.3 Fungi resistance,

11.1.4 Temperature resistance,

**TABLE 1 Apparent Thermal Conductivity (maximum),
Btu-in/h-ft² ·°F (W/m·K)**

Mean Temperature, °F (°C)	Type I	Type II
75 (24)	0.28 (0.040)	0.25 (0.036)