
**Textile fibres — Determination of
linear density — Gravimetric method
and vibroscope method**

*Fibres textiles — Détermination de la masse linéique — Méthode
gravimétrique et méthode au vibroscope*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/PRF 1973](https://standards.iteh.ai/catalog/standards/sist/f9ed700b-1ccc-4089-9d22-b4ad9a09e46a/iso-prf-1973)

[https://standards.iteh.ai/catalog/standards/sist/f9ed700b-1ccc-4089-9d22-
b4ad9a09e46a/iso-prf-1973](https://standards.iteh.ai/catalog/standards/sist/f9ed700b-1ccc-4089-9d22-b4ad9a09e46a/iso-prf-1973)

PROOF / ÉPREUVE



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/PRF 1973

<https://standards.iteh.ai/catalog/standards/sist/f9ed700b-1ccc-4089-9d22-b4ad9a09e46a/iso-prf-1973>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
4.1 General.....	2
4.2 Gravimetric method, for bundles of fibres.....	2
4.3 Vibroscope method, for individual fibres.....	2
5 Apparatus	2
5.1 Gravimetric method apparatus.....	2
5.2 Vibroscope method apparatus.....	2
6 Sampling	3
7 Conditioning and testing atmospheres	3
8 Procedure	3
8.1 Gravimetric method.....	3
8.2 Vibroscope method.....	3
9 Expression of results	4
9.1 General.....	4
9.2 Gravimetric method.....	4
9.3 Vibroscope method.....	5
10 Test report	5
Annex A (informative) Examples of calculation of mean linear density	7
Bibliography	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarns*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 248, *Textiles and textile products*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 1973:1995), which has been technically revised.

The main changes compared to the previous edition are as follows:

- ISO 6989 has been added as a normative reference in [Clauses 2](#) and [8.2.1](#);
- a note specifying the tension application has been added in [3.2](#);
- a correction factor (for measurements on stiff fibres) has been permitted in [4.3](#), [8.2.1](#) and [10.3](#);
- testing equipment without a scale but with a display, respectively connection to a computer system in [4.3](#) for linear density reading is permitted ;
- reference to [5.2.2](#) “Forceps” (instead of 5.1.6) has been corrected;
- automatic application of a loading force instead of the use of forceps in [5.2.2](#) and [8.2.3](#) is permitted;
- [Formulae \(A.1\) to \(A.8\)](#) have been corrected;
- grammar and linguistic consistency of definitions in [4.3](#), [8.1.3](#), [8.2.2](#), [9.2.1](#), [A.1](#) and [A.2](#) have been reviewed.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The linear density of individual fibres is one of the most important physical characteristics in terms of processability and predictability of the next-step intermediate product, such as spun-yarns and nonwovens. Other than testing methods, such as air-permeability on test specimen consisting of mass of fibres (Micronaire), this document describes two measurement methods to determine the mass per unit length (= linear density) using either a bundle of 50 fibres, or on individual fibres. While the first method determines an average value, only, in relatively short time, the second method measures the individual fibre fineness and therefore the statistical distribution of the laboratory sample, too.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/PRF 1973

<https://standards.iteh.ai/catalog/standards/sist/f9ed700b-1ccc-4089-9d22-b4ad9a09e46a/iso-prf-1973>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/PRF 1973

<https://standards.iteh.ai/catalog/standards/sist/f9ed700b-1ccc-4089-9d22-b4ad9a09e46a/iso-prf-1973>

Textile fibres — Determination of linear density — Gravimetric method and vibroscope method

1 Scope

This document specifies a gravimetric method and a vibroscope method for the determination of the linear density of textile fibres applicable respectively to:

- a) bundles of fibres;
- b) individual fibres.

Useful data can be obtained on man-made fibres and, with less precision, on natural fibres.

This document only applies to fibres which can be kept straight and, in the case of bundles, parallel, during test preparation. It is properly applicable when the fibres are readily freed of crimp. The methods in this document are not applicable to tapered fibres.

The vibroscope method is not always applicable to hollow and flat (ribbon-like) fibres.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the reference document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 1130, *Textile fibres — Some methods of sampling for testing*

ISO 6989, *Textile fibres — Determination of length and length distribution of staple fibres (by measurement of single fibres)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 tension

force tending to cause the extension of a body

3.2 tensioning force

force effective on a fibre specimen during the vibroscope test

Note 1 to entry: In textile testing, the tensioning force applied is based on the linear density or cross-sectional area.

4 Principle

4.1 General

Two methods for determining linear density are described.

4.2 Gravimetric method, for bundles of fibres

Specimens of a given length are weighed on a balance. This method is applicable to bundles of fibres.

4.3 Vibroscope method, for individual fibres

Individual fibres of a given length and under specified tensioning force are subjected to vibration at resonance frequency. The linear density is determined from the conditions of the resonance state, i.e. the resonance frequency, the vibrating length of the fibre and the tensioning force. The linear density is read directly on the scale or a display of the vibroscope apparatus respectively reported by a connected computer system. This method assumes that the linear density of the tested length of the fibre is constant.

Under certain circumstances (e.g. a short vibrating length, a low tensioning force, high-modulus fibres) the vibroscopic method results are falsified by the bending stiffness of the fibre. As a compensating countermeasure, a correction factor can be applied (refer to [8.2.1](#)), if agreed on by the interested parties.

iTeh STANDARD PREVIEW (standards.iteh.ai)

5 Apparatus

5.1 Gravimetric method apparatus

5.1.1 **Balance**, suitable for weighing the bundles of to an accuracy of at least ± 1 %.

5.1.2 **Device for cutting**, the bundles under tension to a length known within an accuracy of ± 1 % and allowing an adjustment of the tension of the bundles to be cut.

For example, two razor blades set parallel in a suitable holder may be used.

5.1.3 **Comb sorter**, for preliminary alignment of fibres.

5.1.4 **Textile support fabric**, of a colour contrasting with that of the fibres to be tested.

5.1.5 **Glass plate**, measuring approximately 100 mm \times 200 mm, with one polished edge.

5.2 Vibroscope method apparatus

5.2.1 **Vibroscope**¹⁾, having the following accuracy.

- a) The applied tensioning force shall be within the range of $\pm 0,5$ % of the specified value;
- b) The error in the vibroscope reading of resonance frequency measured or applied shall not exceed $\pm 0,5$ %;
- c) The error in the vibroscope reading of vibration length of the fibre shall not exceed ± 1 %.

1) For a list of suppliers of suitable vibroscope equipment, apply to the Secretariat of ISO Technical Committee 38.

5.2.2 Forceps, to apply the tensioning force to the individual fibre to be tested.

If the apparatus can apply the tensioning force automatically (e.g. by a moving lower clamp and a upper clamp connected to a force measuring device, as mentioned in [8.2.3](#)), forceps are not required.

6 Sampling

To ensure that the laboratory sample is representative of the material and that the test specimen is taken from the laboratory sample is representative of that sample, sampling shall be carried out in accordance with ISO 1130.

7 Conditioning and testing atmospheres

The atmospheres for preconditioning, conditioning and testing shall be in accordance with ISO 139.

8 Procedure

8.1 Gravimetric method

8.1.1 Condition the test specimens and carry out the tests in the standard atmosphere for testing as specified in [Clause 6](#).

8.1.2 From the laboratory sample, take ten tufts having a mass of several milligrams and bring the fibres of each tuft into parallel alignment by carefully combing them several times with the comb sorter ([5.1.3](#)).

8.1.3 Cut the middle part of each combed tuft to a given length (greatest possible), under the minimum tension necessary to remove crimp, by means of the cutting device ([5.1.2](#)). Take the necessary precautions so that there are no free fibre ends anywhere except at the two ends of the tuft bundle.

8.1.4 Place the ten bundles so obtained on the textile support fabric ([5.1.4](#)) and cover them with the glass plate ([5.1.5](#)) from the polished edge of which they shall protrude slightly.

8.1.5 From each of the ten bundles in turn, take out five fibres to form a bundle of 50 fibres, in each case drawing the fibres from one cut end. Make at least ten of these bundles. Recondition the specimen in the atmosphere specified in [Clause 6](#), if necessary. Weigh these bundles individually, using the balance ([5.1.1](#)), to an accuracy of ± 1 %.

If the bundle of 50 fibres cannot be weighed on the balance to the required 1 % accuracy, the number of fibres shall be increased accordingly (up to a maximum of 500).

8.2 Vibroscope method

8.2.1 Check the vibroscope, before examining the laboratory sample, as follows. Test 100 individual fibres using the vibroscope in question. Test these same fibres, for comparison, using the gravimetric method. Calculate the arithmetic mean and coefficient of variation of the vibroscope readings of linear density. If the coefficient of variation of the vibroscope readings is larger than 10 %, the sample is not suitable for determination of linear density using this vibroscope.

Weigh the bundle of 100 fibres that have been tested with the vibroscope using the balance ([5.1.1](#)). Measure the length of all fibres in accordance with ISO 6989 with an accuracy of ± 1 %. Or, where appropriate, cut the 100 fibres to a known length using the cutting device ([5.1.2](#)).