



Designation: ~~A582/A582M-05~~ Designation: A582/A582M – 12

Standard Specification for Free-Machining Stainless Steel Bars¹

This standard is issued under the fixed designation A582/A582M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers hot-finished or cold-finished bars, except bars for forging (Note 1), suitable for machining processes. It includes rounds, squares, and hexagons in the more commonly used types of stainless free-machining steels designed especially for optimum machinability and for general corrosion and high-temperature service. Stainless steel bars other than the free-machining types are covered in a separate specification (Note 2).

1.2 This specification is expressed in both inch-pound units and in SI units; however, unless the purchase order or contract specifies the applicable *M* specification designation (SI units), the inch-pound units shall apply. The values stated in either inch-pound units or SI (metric) units are to be regarded separately as standard: within the text and tables, the SI units are shown in [brackets]. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

NOTE 1—For bars for reforging, see Specification A314.

NOTE 2—For non-free machining stainless bars, see Specification A276.

2. Referenced Documents

2.1 ASTM Standards:²

A276 Specification for Stainless Steel Bars and Shapes

A314 Specification for Stainless Steel Billets and Bars for Forging

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A484/A484M Specification for General Requirements for Stainless Steel Bars, Billets, and Forgings

A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

A959 Guide for Specifying Harmonized Standard Grade Compositions for Wrought Stainless Steels

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.2 SAE Document:³

J1086 Recommended Practice for Numbering Metals and Alloys³ <https://www.astm.org/standards/J1086>

3. Ordering Information

3.1 It is the responsibility of the purchaser to specify all requirements that are necessary for product ordered under this specification. Such requirements to be considered include, but are not limited to, the following:

- 3.1.1 Quantity (weight or number of pieces),
- 3.1.2 Type (alloy) or UNS designation (Table 1),
- 3.1.3 Form (bars, angles, etc.),
- 3.1.4 Condition (Table 2),
- 3.1.5 Finish (5.1),
- 3.1.6 Applicable dimensions, including size, thickness, width, and length,
- 3.1.7 Cross section (round, square, etc.),
- 3.1.8 ASTM designation (Specification A582/A582M) and publication approval date,
- 3.1.9 Preparation for delivery, and

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.17 on Flat-Rolled and Wrought Stainless Steel.

Current edition approved March 1, 2005-2012. Published March 2005-2012. Originally approved in 1967. Last previous edition approved in 2000-2005 as A582/A582M-95b (2000)-^ε1-A582/A582M-05. DOI: 10.1520/A0582_A0582M-0512.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Chemical Requirements

| UNS Designation ^A | Type ^B | Chemical Composition, % | | | | | | | | | |
|------------------------------|--------------------|-------------------------|------------------------|-------------------------|---------------------|--------------|------------|-------------------|------------|----------|---|
| | | Carbon ^C | Manganese ^C | Phosphorus ^C | Sulfur ^C | Silicon, max | Chromium | Nickel | Molybdenum | Selenium | Other Elements |
| Austenitic | | | | | | | | | | | |
| S20300 | XM-1 | 0.08 | 5.0–6.5 | 0.04 | 0.18–0.35 | 1.00 | 16.0–18.0 | 5.0–6.5 | ... | ... | Cu 1.75–2.25 |
| S20300 | XM-1 ^D | 0.08 | 5.0–6.5 | 0.04 | 0.18–0.35 | 1.00 | 16.00–18.0 | 5.0–6.5 | ... | ... | Cu 1.75–2.25 |
| S30300 | 303 | 0.15 | 2.00 | 0.20 | 0.15 | 1.00 | 17.0–19.0 | 8.0–10.0 | ... | ... | ... |
| S30310 | XM-5 | 0.15 | 2.5–4.5 | 0.20 | 0.25 | 1.00 | 17.0–19.0 | 7.0–10.0 | ... | ... | ... |
| S30310 | XM-5 ^D | 0.15 | 2.5–4.5 | 0.20 | 0.25 | 1.00 | 17.0–19.0 | 7.0–10.0 | ... | ... | ... |
| S30323 | 303Se | 0.15 | 2.00 | 0.20 | 0.06 | 1.00 | 17.0–19.0 | 8.0–10.0 | ... | 0.15 min | ... |
| S30345 | XM-2 | 0.15 | 2.00 | 0.05 | 0.11–0.16 | 1.00 | 17.0–19.0 | 8.0–10.0 | 0.40–0.60 | ... | Al 0.60–1.00 |
| S30345 | XM-2 ^D | 0.15 | 2.00 | 0.05 | 0.11–0.16 | 1.00 | 17.0–19.0 | 8.0–10.0 | 0.40–0.60 | ... | Al 0.60–1.00 |
| Martensitic | | | | | | | | | | | |
| S41600 | 416 | 0.15 | 1.25 | 0.06 | 0.15 | 1.00 | 12.0–14.0 | ... | ... | ... | ... |
| S41610 | XM-6 | 0.15 | 1.50–2.50 | 0.06 | 0.15 | 1.00 | 12.0–14.0 | ... | ... | ... | ... |
| S41610 | XM-6 ^D | 0.15 | 1.50–2.50 | 0.06 | 0.15 | 1.00 | 12.0–14.0 | ... | ... | ... | ... |
| S41623 | 416Se | 0.15 | 1.25 | 0.06 | 0.06 | 1.00 | 12.0–14.0 | ... | ... | 0.15 min | ... |
| S42020 | 420F | 0.30–0.40 | 1.25 | 0.06 | 0.15 | 1.00 | 12.0–14.0 | 0.50 ^C | ... | ... | Cu 0.60 ^C |
| S42020 | 420F | 0.30–0.40 | 1.25 | 0.06 | 0.15 | 1.00 | 12.0–14.0 | 0.50 ^E | ... | ... | Cu 0.60 ^E |
| S42023 | 420FSe | 0.20–0.40 | 1.25 | 0.06 | 0.06 | 1.00 | 12.0–14.0 | 0.50 ^C | ... | 0.15 min | Cu 0.60 ^C |
| S42023 | 420FSe | 0.20–0.40 | 1.25 | 0.06 | 0.06 | 1.00 | 12.0–14.0 | 0.50 ^E | ... | 0.15 min | Cu 0.60 ^E |
| S44020 | 440F | 0.95–1.20 | 1.25 | 0.06 | 0.15 | 1.00 | 16.0–18.0 | 0.50 ^C | ... | ... | Cu 0.60 ^C |
| S44020 | 440F | 0.95–1.20 | 1.25 | 0.06 | 0.15 | 1.00 | 16.0–18.0 | 0.50 ^E | ... | ... | Cu 0.60 ^E |
| S44023 | 440FSe | 0.95–1.20 | 1.25 | 0.06 | 0.06 | 1.00 | 16.0–18.0 | 0.50 ^C | ... | 0.15 min | Cu 0.60 ^C |
| S44023 | 440FSe | 0.95–1.20 | 1.25 | 0.06 | 0.06 | 1.00 | 16.0–18.0 | 0.50 ^E | ... | 0.15 min | Cu 0.60 ^E |
| Ferritic | | | | | | | | | | | |
| S18200 | XM-34 | 0.08 | 2.50 | 0.04 | 0.15 | 1.00 | 17.5–19.5 | ... | 1.50–2.50 | ... | ... |
| S18200 | XM-34 ^D | 0.08 | 2.50 | 0.04 | 0.15 | 1.00 | 17.5–19.5 | ... | 1.50–2.50 | ... | ... |
| S18235 | ... | 0.025 | 0.50 | 0.030 | 0.15–0.35 | 1.00 | 17.5–18.5 | 1.00 | 2.00–2.50 | ... | Ti 0.30–1.00 N 0.025 C+N 0.035 |
| S41603 | ... | 0.08 | 1.25 | 0.06 | 0.15 | 1.00 | 12.0–14.0 | ... | ... | ... | ... |
| S43020 | 430F | 0.12 | 1.25 | 0.06 | 0.15 | 1.00 | 16.0–18.0 | ... | ... | ... | ... |
| S43023 | 430FSe | 0.12 | 1.25 | 0.06 | 0.06 | 1.00 | 16.0–18.0 | ... | ... | 0.15 min | ... |

^A Designation established in accordance with Practice E527 and SAE J 1086, Recommended Practice for Numbering Metals and Alloys (UNS).

^B Maximum unless otherwise indicated, a grade designation originally assigned by the American Iron and Steel Institute (AISI).

^C Maximum unless otherwise noted.

^D Naming system originated by ASTM.

^E At manufacturer's option, reported only when intentionally added.

3.1.10 Marking requirements.

NOTE 3—A typical ordering description is as follows: 5000 lb [2000 kg] Type 416 bars, annealed and centerless ground, 1½ in. [40 mm] round, 10 to 12 ft [3 to 4 m] in length, ASTM Specification A582/A582Mdated.