



Designation: ~~C401-91~~ (Reapproved 2005) Designation: C401 - 12

## Standard Classification of Alumina and Alumina-Silicate Castable Refractories<sup>1</sup>

This standard is issued under the fixed designation C401; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This classification covers alumina and alumina-silicate castable refractories that, when tempered with water, will develop structural strength by chemical action.

~~1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.~~

~~1.3~~

~~1.2~~ *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

C113 Test Method for Reheat Change of Refractory Brick

C133 Test Methods for Cold Crushing Strength and Modulus of Rupture of Refractories

C134 Test Methods for Size, Dimensional Measurements, and Bulk Density of Refractory Brick and Insulating Firebrick

C862 Practice for Preparing Refractory Concrete Specimens by Casting

C865 Practice for Firing Refractory Concrete Specimens

### 3. Significance and Use

3.1 Alumina and alumina-silicate castable refractories are produced to yield property characteristics commensurate with different end use properties. Volume stability, modulus of rupture, bulk density, and lime content have become useful measures to distinguish various alumina and alumina-silicate castable formulations for initial fitness for service. This classification is considered useful for purchase specifications and for quality control.

### 4. Basis of Classification

~~4.1 Regular Castable Refractories—This class includes alumina and alumino-silicate castable refractories which contain hydraulic-setting cement and which have a total lime (CaO) content greater than 2.5% on a calcined basis. Under this class, eastables having a modulus of rupture after drying of at least 300 psi (2.07 MPa) are normal-strength, and those having at least 600 psi (4.14 MPa) modulus of rupture are high-strength types. They are further classified on the basis of volume stability of cast test brick when fired at the temperatures prescribed in~~

~~4.1 Alumina and alumina silicate castable refractories that contain a hydraulic setting cement and have a density of greater than 105 lb/ft<sup>3</sup> (1.68 g/cm<sup>3</sup>) may be classified by the lime (CaO) content as contributed by the cement. The classifications are shown in Table 1:~~

~~4.2 Low-Cement Castable Refractories—This class includes alumina and alumino-silicate castable refractories which contain hydraulic-setting cement and which have a total lime (CaO) content of greater than 1.0 to 2.5% on a calcined basis.~~

~~4.3 Ultra-Low Cement Castable Refractories—This class includes alumina and alumino-silicate castable refractories which contain hydraulic-setting cement and which have a total lime (CaO) content of greater than 0.2 to 1.0% on a calcined basis.~~

~~4.4 No-Cement Castable Refractories—This class includes alumina and alumino-silicate castable refractories which do not contain hydraulic-setting cement and in which the bonding agent(s) contribute no significant amount of lime (CaO). The product~~

<sup>1</sup> This classification is under the jurisdiction of ASTM Committee C08 on Refractories and is the direct responsibility of Subcommittee C08.92; C08.92 The Joseph E. Kopanda Subcommittee for Editorial, Terminology and Classification.

Current edition approved Dec. March 1, 2005; 2012. Published January 2006; April 2012. Originally approved in 1957. Last previous edition approved in 2000; 2005 as C401 - 91 (2000); (2005). DOI: 10.1520/C0401-91R05; 10.1520/C0401-12.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.