



Designation: D3363 – 05 (Reapproved 2011)^{ε2}

Standard Test Method for Film Hardness by Pencil Test¹

This standard is issued under the fixed designation D3363; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

^{ε1} NOTE—Figure 1 was corrected editorially in August 2011.

^{ε2} NOTE—Figure 2 and Section 7 were corrected editorially in March 2012.

1. Scope*

1.1 This test method covers a procedure for rapid, inexpensive determination of the film hardness of an organic coating on a substrate in terms of drawing leads or pencil leads of known hardness.

1.2 This test method is similar in content (but not technically equivalent) to ISO 15184.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 Other Standards:

ISO 15184 Determination of film hardness by pencil test.²

3. Summary of Test Method

3.1 A coated panel is placed on a firm horizontal surface. The pencil is held firmly against the film at a 45° angle (point away from the operator) and pushed away from the operator in a 6.5-mm (1/4-in.) stroke. The process is started with the hardest pencil and continued down the scale of hardness to either of two end points: one, the pencil that will not cut into or gouge the film (pencil hardness), or two, the pencil that will not scratch the film (scratch hardness).

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.23 on Physical Properties of Applied Paint Films.

Current edition approved June 1, 2011. Published June 2011. Originally approved in 1974. Last previous edition approved in 2005 as D3363 – 05. DOI: 10.1520/D3363-05R11E02.

² Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

4. Significance and Use

4.1 Pencil hardness measurements have been used by the coatings industry for many years to determine the hardness of clear and pigmented organic coating films. This test method has also been used to determine the cure of these coatings, especially when forced dried using heat.

4.2 This test method is especially useful in developmental work and in production control testing in a single laboratory. It should be recognized that the results obtained may vary between different laboratories when different pencils as well as panels are used. Every effort should be made to standardize the hardness of the lead used and the technique followed.

4.3 If this test method is used as a basis for purchase agreement, maximum precision will be achieved if a given set of referee pencils be agreed upon between the purchaser and the seller.

5. Apparatus

5.1 A set of calibrated drawing leads (preferred) or equivalent calibrated wood pencils meeting the following scale of hardness:

$$\frac{6B-5B-4B-3B-2B-B-HB-F-H-2H-3H-4H-5H-6H}{\text{Softer} \qquad \qquad \qquad \qquad \qquad \qquad \qquad \qquad \qquad \text{Harder}} \quad (1)$$

The difference between two adjacent leads shall be considered one unit of hardness.

5.2 *Mechanical Lead Holder*, for drawing leads if used.

5.3 *Mechanical Sharpener*, draftsman-type, is helpful for trimming wood pencils if used.

5.4 *Abrasive Paper*, grit No. 400.

6. Test Specimens and Conditions

6.1 Apply the surface coating by appropriate means to a smooth rigid substrate and cure properly, or use representative panels cut from coated stock. The panels used, the curing conditions, and the age of the coating prior to the test shall be within the limits agreed upon between the purchaser and the seller.

*A Summary of Changes section appears at the end of this standard