



Designation: D4655 – 95 (Reapproved 2012)

## Standard Test Methods for Sulfates in Leather (Total, Neutral, and Combined Acid)<sup>1</sup>

This standard is issued under the fixed designation D4655; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 These test methods are intended for use in determining the total, neutral, and combined acid sulfate in mineral-tanned leather.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D2813 Practice for Sampling Leather for Physical and Chemical Tests

D4654 Test Method for Sulfate Basicity in Leather

### 3. Significance and Use

3.1 These test methods are used to determine the basicity of leather when used in accordance with Test Method D4654.

### 4. Apparatus

4.1 Volumetric Flask, 250 mL.

4.2 Filter paper, ashless, fine grained and porcelain crucible.

4.3 Crucible, Gooch, with porous porcelain filter (optional).

### 5. Reagents

5.1 *Ammonium Hydroxide Solution*, (0.1 N)—7 mL/L reagent grade concentrate  $\text{NH}_4\text{OH}$ . Optional: Potassium dihydro-

gen phosphate, 0.1 molar solution (13.6 g/L  $\text{KH}_2\text{PO}_4$ ) or sodium dihydrogen phosphate, 0.1 molar solution (13.8 g/L  $\text{NaH}_2\text{PO}_4\text{-H}_2\text{O}$ ).

5.2 *Hydrochloric Acid Solution*, (1.5 N)—125 mL/L reagent grade concentrate hydrochloric acid.

5.3 *Barium Chloride Solution*—( $\text{BaCl}_2\cdot 2\text{H}_2\text{O}$ ), 1 %.

5.4 *Sodium Hydroxide Solution*, 0.01 N, 0.4 g/L.

5.5 *Mixed Indicator*, consisting of 60 mL of a 0.1 % solution of methyl red and 40 mL of a 0.1 % solution of methylene blue, both in 95 % alcohol.

### 6. Sampling, Test Specimens, and Test Units

6.1 The specimen for each determination shall consist of 1 g leather from the composite sample (See Practice D2813).

6.2 Two specimens from the composite sample shall be tested for each determination.

### 7. Procedure

7.1 *Total Sulfates*—Weigh the specimen to the nearest milligram and record the value as  $W_1$ . Transfer the specimen to a 250-mL volumetric flask and add 200 mL of 0.1 N ammonium hydroxide or 0.1 molar potassium or sodium dihydrogen phosphate solution. Immerse the flask up to the neck in a bath of boiling water. Thoroughly wet all products by swirling occasionally. After 2 h cool the flask to room temperature, and make up to volume with distilled water, shake, and without delay filter through a folded filter paper. Discard the first 20 to 25 mL of the filtrate. Pipette 200 mL of the filtrate into a 600 mL beaker and add about 20 mL of 1.5 N hydrochloric acid. Heat the solution to boiling and while boiling and stirring the solution, add 20 mL of a 1 % solution of barium chloride dropwise. Keep the covered beaker in a warm place at least for 2 h and preferably overnight.

7.1.1 Filter the precipitate through a fine grained ashless filter paper and wash with hot water until free from chloride. A weighed Gooch crucible or a weighed porous crucible may be used as an alternative for the filtration. Transfer the paper with the precipitate to a weighed crucible and ignite gently, either over a gas burner or in a muffle oven at 900°C for 1 h. Cool the crucible in a desiccator, weigh, and record the value of the  $\text{BaSO}_4$  as  $W_2$ .

<sup>1</sup> These test methods are under the jurisdiction of ASTM Committee D31 on Leather and are the direct responsibility of Subcommittee D31.06 on Chemical Analysis. This test method was developed in cooperation with the American Leather Chemists Assn. (Method D20–1956).

Current edition approved April 1, 2012. Published April 2012. Originally approved in 1987. Last previous edition approved in 2006 as D4655–95 (2006). DOI: 10.1520/D4655-95R12.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.