



Designation: D5355 – 95 (Reapproved 2012)

## Standard Test Method for Specific Gravity of Oils and Liquid Fats<sup>1</sup>

This standard is issued under the fixed designation D5355; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers the determination of the specific gravity of oils and liquid fats by calculating the ratio of the weight of a unit volume of the sample to the weight of a unit volume of water at 25°C.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Terminology

#### 2.1 Definitions:

2.1.1 *density*—weight/unit volume expressed as grams per centimetre.

2.1.2 *liquid fats*—fats that melt below 58°C.

2.1.3 *oils*—substances that are fluid at 25°C, consisting of glycerides of fatty acids, aliphatic hydrocarbons, and aromatic hydrocarbons.

2.1.4 *specific gravity*—the ratio of the density of a substance to the density of the reference substance.

### 3. Significance and Use

3.1 This test method is used to measure the specific gravity of all oils and liquid fats that are used to soften leather, or that are used in products to soften leather. The specific gravity is one parameter that can be used to monitor the quality of these products.

### 4. Apparatus

4.1 *Specific Gravity Bottles*, with well-fitting ground glass joints and a capacity of approximately 50 mL.

4.2 *Water Bath*, maintained at  $25 \pm 0.2^\circ\text{C}$ .

4.3 *Water Bath*, maintained at  $60 \pm 0.2^\circ\text{C}$ .

4.4 *Thermometer*, laboratory thermometer having a range from  $-20$  to  $102^\circ\text{C}$  with 0.1 or 0.2 subdivisions.

### 5. Procedure

5.1 *Calibration of the Specific Gravity Bottles*—Clean and dry thoroughly and then fill with recently boiled and cooled distilled water at 20 to 23°C. Fill the bottle to overflowing by holding the bottle on its side in such a manner as to prevent the entrapment of air bubbles. Insert the stopper and immerse in a water bath at  $25 \pm 0.2^\circ\text{C}$ . Keep the entire bulb completely covered with water and hold at the specified temperature for 30 min. Carefully remove any water that has exuded from the side opening. Remove the bottle from the bath and wipe completely dry. Weigh the bottle and contents. Calculate the weight of water in the flask by subtracting the weight of the empty bottle from the weight of the bottle plus the water.

#### 5.2 Specific Gravity at 25/25°C:

5.2.1 Melt the sample and filter through filter paper to remove any impurities and the last traces of moisture. The sample must be completely dry.

5.2.2 Cool the sample from 20 to 23°C and fill the bottle to overflowing, holding the bottle on its side in such a manner as to prevent the entrapment of air bubbles.

5.2.3 Insert the stopper, immerse, and hold in the water bath at  $25 \pm 0.2^\circ\text{C}$  for 30 min.

5.2.4 Carefully wipe off any oil that has come through the capillary opening and remove from the bath. Clean and dry thoroughly.

5.2.5 Weigh the bottle and contents. Calculate the specific gravity as directed in 5.1.

#### 5.3 Specific Gravity at 60/25°C:

5.3.1 Melt the sample and filter through filter paper to remove any impurities and the last traces of moisture. The sample must be completely dry.

5.3.2 Pour the melted fat into the bottle at 56 to 58°C to overflowing, holding the bottle on its side in such a manner as to prevent the entrapment of air bubbles.

5.3.3 Insert the stopper, immerse, and hold in the water bath at  $60 \pm 0.2^\circ\text{C}$  for 30 min.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.08 on Fats and Oils. This test method was developed in cooperation with the American Leather Chemists Assn. (Method H 15-1957).

Current edition approved April 1, 2012. Published April 2012. Originally approved in 1993. Last previous edition approved in 2006 as D5355 – 95(2006). DOI: 10.1520/D5355-95R12.