



Designation: A434 – 06(Reapproved 2012)

Standard Specification for Steel Bars, Alloy, Hot-Wrought or Cold-Finished, Quenched and Tempered¹

This standard is issued under the fixed designation A434; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers hot-wrought and cold-finished quenched and tempered alloy steel bars.

1.2 Hot-wrought bars are available in three strength level classes designated BB, BC, and BD, and cold-finished bars in two strength level classes designated BB and BC. The bars are available in the conditions specified in 4.4 subject to the size limitations shown.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

A29/A29M Specification for Steel Bars, Carbon and Alloy, Hot-Wrought, General Requirements for

A108 Specification for Steel Bar, Carbon and Alloy, Cold-Finished

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

E112 Test Methods for Determining Average Grain Size

3. Ordering Information

3.1 Orders for material under this specification should include the following information:

3.1.1 Quantity (weight or number of pieces),

3.1.2 Name of material (heat-treated alloy steel bars),

3.1.3 Method of finish (condition) (4.4),

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.15 on Bars.

Current edition approved March 1, 2012. Published April 2012. Originally approved in 1959. Last previous edition approved in 2006 as A434 – 06. DOI: 10.1520/A0434-06R12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.4 Dimensions, including length (if hot-wrought bars are for cold finishing, the cold-finished size should also be specified),

3.1.5 ASTM designation and date of issue,

3.1.6 Chemical composition grade (Section 5),

3.1.7 Strength class (Table 1),

3.1.8 Test report, if required (Section 11),

3.1.9 Supplementary Requirements or Special Requirements, if required, and

3.1.10 End use.

NOTE 1—A typical ordering description is as follows: 10 000 lb, Heat-Treated Alloy Steel Bars, Hot Rolled, 1.000 in. diameter \times 10 ft, ASTM A434 dated ____, Grade 4140, Class BB, Test Report Required, Motor Shafts.

4. Materials and Manufacture

4.1 *Melting Practice*—The steel shall be made by one or more of the following primary processes: open-hearth, basic-oxygen, or electric-furnace. The primary melting may incorporate separate degassing or refining and may be followed by secondary melting using electroslag remelting or vacuum arc remelting. Where secondary melting is employed, the heat shall be defined as all of the ingots remelted from a single primary heat.

4.2 *Discard*—Sufficient discard shall be made to secure freedom from injurious piping and undue segregation.

4.3 *Slow Cooling*—Hot-wrought alloy bars shall, immediately after rolling, be allowed to cool to a temperature below the critical range under suitable conditions to prevent injury by too rapid cooling.

4.4 *Condition*—Bars shall be furnished in one of the following conditions, as specified by the purchaser. Generally, size limits for various methods of processing round bars are:

Hot-wrought or hot-wrought descaled	9½ in. (241.3 mm), max
Cold-drawn	⅛ to 4 in. (3.2 to 102 mm), incl
Cold-drawn, ground, and polished	⅛ to 4 in. (3.2 to 102 mm), incl
Turned and polished	¾ to 9 in. (19.1 to 229 mm), incl
Turned, ground, and polished	¾ to 9 in. (19.1 to 229 mm), incl

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ASTM A434-06\(2012\)](#)

<https://standards.itih.ai/catalog/standards/sist/c346f2a8-33a4-408f-81f3-a2ebcaa01713/astm-a434-062012>