



Designation: D2484 – 06 (Reapproved 2012)^{ε1}

Standard Specification for Polyester Film Pressure-Sensitive Electrical Insulating Tape¹

This standard is issued under the fixed designation D2484; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Table 2 was editorially revised in April 2012.

1. Scope*

1.1 This specification covers electrical insulating tape consisting of a polyester plastic film coated on one side with a pressure-sensitive adhesive.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parenthesis are provided for information only.

NOTE 1—This standard and IEC 60454–3–2 and –3 are similar but not equivalent in all details.

2. Referenced Documents

2.1 *ASTM Standards*:²

D876 Test Methods for Nonrigid Vinyl Chloride Polymer Tubing Used for Electrical Insulation

D1000 Test Methods for Pressure-Sensitive Adhesive-Coated Tapes Used for Electrical and Electronic Applications

D1711 Terminology Relating to Electrical Insulation

D2305 Test Methods for Polymeric Films Used for Electrical Insulation

2.2 *IEC Standard*:

Publication 60454–3 Specifications for Pressure-Sensitive Adhesive Tapes for Electrical Purposes. Sheet 2: Requirements for Polyester Film Tapes (PETP) with Thermosetting Adhesive. Sheet 3: Requirements for Polyester Film Tapes (PETP) with Non-Thermosetting Adhesive³

3. Terminology

3.1 *Definitions*— For definitions of terms used in this specification, refer to Terminology D1711.

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Flexible and Rigid Insulating Materials.

Current edition approved April 1, 2012. Published April 2012. Originally approved in 1966. Last previous edition approved in 2006 as D2484 – 06. DOI: 10.1520/D2484-06R12E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

4. Classification

4.1 This specification includes the requirements for four types as follows:

4.1.1 *Type 1*—General-purpose tape, nominal thickness 0.06 mm (0.0025 in.) and coated with a thermoplastic adhesive which is not chemically heat reactive.

4.1.2 *Type 2*—General-purpose tape, nominal thickness 0.06 mm (0.0025 in.) and coated with a heat-reactive thermosetting adhesive.

4.1.3 *Type 3*—General-purpose tape, nominal thickness 0.09 mm (0.0035 in.) and coated with a heat-reactive thermosetting adhesive.

4.1.4 *Type 4*—General-purpose tape, nominal thickness 0.025 mm (0.0010 in.) and coated with a heat-reactive thermosetting adhesive.

5. Materials and Manufacture

5.1 The polymer used as the backing shall be clear polyethylene terephthalate sheet.

5.2 The pressure-sensitive adhesive coating shall be free from lumps and bare spots. There shall be no adhesive transfer when tape is unwound from the roll.

5.3 Both transparent and colored tapes are available.

5.3.1 *Type 1*—Transparent.

5.3.2 *Types 2, 3, and 4*—Transparent and colors.

6. Standard Rolls

6.1 The standard widths and lengths shall be selected from the following:

6.1.1 *Widths*:

mm	in.	mm	in.
6	¼	22	⅞
9	⅜	25	1
12	½	30	1¼
15	⅝	38	1½
19	¾	50	2

Widths greater than 50 mm (2 in.) shall be agreed upon between the purchaser and the seller.

*A Summary of Changes section appears at the end of this standard