

# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 13000-1

ISO/TC 61/SC 9

Secretariat: **KATS**

Voting begins on:  
**2020-07-03**

Voting terminates on:  
**2020-09-25**

---

---

## Plastics — Polytetrafluoroethylene (PTFE) semi-finished products —

### Part 1: Requirements and designation

*Plastiques — Semi-produits en polytétrafluoroéthylène (PTFE) —  
Partie 1: Spécifications et désignation*

ICS: 83.140.01

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/DIS 13000-1](https://standards.iteh.ai/catalog/standards/sist/4b5ac28e-db18-4a20-9d37-5e6da6cbf602/iso-dis-13000-1)

<https://standards.iteh.ai/catalog/standards/sist/4b5ac28e-db18-4a20-9d37-5e6da6cbf602/iso-dis-13000-1>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

**ISO/CEN PARALLEL PROCESSING**



Reference number  
ISO/DIS 13000-1:2020(E)

© ISO 2020

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO/DIS 13000-1

<https://standards.iteh.ai/catalog/standards/sist/4b5ac28e-db18-4a20-9d37-5e6da6cbf602/iso-dis-13000-1>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
3.1 Abbreviated terms and symbols.....	2
<b>4 Requirements for PTFE semi-finished products</b> .....	<b>2</b>
4.1 General.....	2
4.2 Dimensions and dimensional tolerances.....	2
4.2.1 General.....	2
4.2.2 Skived tape, skived sheet, or film.....	2
4.2.3 Moulded sheet.....	2
4.2.4 Extruded or moulded rod.....	3
4.2.5 Tube extruded from coagulated dispersion powder.....	3
4.2.6 Extruded or moulded heavy-walled tube.....	3
4.3 Tensile strength and percentage elongation at break.....	4
4.4 Dimensional stability.....	4
4.5 Density.....	4
4.6 Hardness.....	4
4.7 Colour.....	4
4.8 Dielectric strength (DS).....	5
4.8.1 General.....	5
4.8.2 Skived tape, skived sheet, or film.....	5
4.8.3 Moulded sheet.....	5
4.8.4 Moulded basic shape.....	5
4.8.5 Extruded or moulded rod.....	6
4.8.6 Tube extruded from coagulated dispersion powder.....	6
4.8.7 Extruded or moulded heavy-walled tube.....	6
4.9 Requirements that may be specified depending on the specific application.....	7
<b>5 Format for presenting a designation</b> .....	<b>7</b>
5.1 General.....	7
5.2 Order of presenting codes.....	7
5.3 Examples of coding a designation.....	8
<b>Annex A (informative) Other standards relating to semi-finished products of polytetrafluoroethylene</b> .....	<b>9</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13000-1 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This third edition cancels and replaces the second edition (ISO 13000-1: 2005), which has been technically revised.

ISO 13000 consists of the following parts, under the general title *Plastics — Polytetrafluoroethylene (PTFE) semi-finished products*:

- *Part 1: Requirements and designation* [ISO/DIS 13000-1](https://standards.iteh.ai/catalog/standards/sist/4b5ae28e-db18-4a20-9d37-5e0da6cb1002/iso-dis-13000-1)
- *Part 2: Preparation of test specimens and determination of properties* <https://standards.iteh.ai/catalog/standards/sist/4b5ae28e-db18-4a20-9d37-5e0da6cb1002/iso-dis-13000-1>

# Plastics — Polytetrafluoroethylene (PTFE) semi-finished products —

## Part 1: Requirements and designation

### 1 Scope

This part of ISO 13000 specifies the requirements and establishes a system of designation for processed unfilled polytetrafluoroethylene (PTFE) products, which may occur in several forms. The PTFE used to make the semi-finished product is described in ISO 20568-1 and, as provided in ISO 20568-1, may contain up to 1 % of a comonomer. The PTFE used to make the semi-finished product may be virgin, reprocessed or recycled resin. The addition of up to 1,5 % by mass of pigment or colorant is permitted. This part of ISO 13000 allows for five grades based on tensile strength and elongation at break. The semi-finished products can be as-processed (type P) or dimensionally stabilized (type S) and may also have specified electrical properties or other properties when they are required for an application.

NOTE References to other standards for semi-finished products made from polytetrafluoroethylene are listed in [Annex A](#) for information.

### 2 Normative references (standards.iteh.ai)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

ISO 20568-1, *Plastics — Fluoropolymer dispersions and moulding and extrusion materials — Part 1: Designation system and basis for specifications*

ISO 13000-2, *Plastics — Polytetrafluoroethylene (PTFE) semi-finished products — Part 2: Preparation of test specimens and determination of properties*

### 3 Terms and definitions

For the purposes of this part of ISO 13000, the terms and definitions given in ISO 472 and ISO 20568-1 and the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

#### 3.1

##### **moulded basic shape**

(PTFE) semi-finished product made by preforming and sintering without additional processing

**3.2 semi-finished product**

material, in the form of skived tape, sheets, rods, tubes, tubing, moulded basic shapes or special shapes, that is produced for use either directly without further fabrication or in fabricating end use products, or both

**3.3 skived tape**

film or sheet prepared by cutting, slicing or shaving

Note 1 to entry: The term “veneered tape” is deprecated.

**3.1 Abbreviated terms and symbols**

The abbreviated terms given in ISO 1043-1 are applicable to this part of ISO 13000.

**4 Requirements for PTFE semi-finished products**

**4.1 General**

After considering the specific shape, dimensions and dimensional tolerances, the primary basis for designating a semi-finished product of PTFE is the tensile strength and percentage elongation at break of the product. Tests to determine the values for designation shall be run in accordance with the methods in ISO 13000-2. The semi-finished product is identified as “type P” for as-processed or “type S” for stabilized and also may be designated as “type E” with specified electrical properties when required for a particular application. The exclusion of the use of reprocessed or recycled material shall be specified if needed in order to meet special customer requirements. The values required for other properties are given in their respective subclauses.

<https://standards.iteh.ai/catalog/standards/sist/4b5ac28e-db18-4a20-9d37-5c0da0c01602/iso-dis-13000-1>

**4.2 Dimensions and dimensional tolerances**

**4.2.1 General**

Dimensional tolerances shall be measured at 23 °C ± 2 °C.

**4.2.2 Skived tape, skived sheet, or film**

Code-letter	Thickness	Tolerance
a	< 0,1 mm	$\begin{matrix} +0,01 \\ 0 \end{matrix}$ mm
b	≥ 0,1 mm	$\begin{matrix} +10 \\ 0 \end{matrix}$ %

The standard tolerance for width is  $\begin{matrix} +3 \\ 0 \end{matrix}$  %, with a maximum of 30 mm. For slit skived tape, the exact width shall be agreed upon between purchaser and supplier.

The standard tolerance for length is  $\begin{matrix} +2 \\ 0 \end{matrix}$  %.

**4.2.3 Moulded sheet**

Code-letter	Thickness	Tolerance
a	< 5 mm	$\begin{matrix} +0,75 \\ 0 \end{matrix}$ mm
b	≥ 5 mm	$\begin{matrix} +15 \\ 0 \end{matrix}$ %

The length and width tolerance shall be  $\begin{matrix} +3 \\ 0 \end{matrix}$  %.

#### 4.2.4 Extruded or moulded rod

As extruded or moulded:

Code-letter	Diameter	Tolerance
a	< 10 mm	$^{+0,6}_0$ mm
b	≥ 10 mm	$^{+6}_0$ %

The standard tolerance for length is:

Code-letter	Length	Tolerance
a	< 500 mm	$^{+10}_0$ mm
b	≥ 500 mm	$^{+2}_0$ %

Centreless ground:

Tolerance on diameter for all diameters:  $^{+0,04}_0$  mm.

Tolerance on length:

Code-letter	Length	Tolerance
a	< 500 mm	$^{+10}_0$ mm
b	≥ 500 mm	$^{+2}_0$ %

#### 4.2.5 Tube extruded from coagulated dispersion powder

NOTE The tube in 4.2.5 is extruded from coagulated PTFE powder. Other semi-finished PTFE products are made with suspension polymerized PTFE powder.

The standard tolerance on inner diameter and wall thickness is:

Code-letter	Dimension	Tolerance
a	Inner diameter < 5 mm	±0,25 mm
b	Inner diameter ≥ 5 mm	±5 %
c	Wall thickness < 1,0 mm	±0,1 mm
d	Wall thickness ≥ 1,0 mm	±10 %

The standard tolerance for length is  $^{+2}_0$  %.

#### 4.2.6 Extruded or moulded heavy-walled tube

Code-letter	Outer diameter	Tolerance on	
		inner diameter	outer diameter
a	< 10 mm	$^{0}_{-0,6}$ mm	$^{+0,6}_0$ mm
b	≥ 10 mm	$^{0}_{-6}$ %	$^{+6}_0$ %

The standard tolerance for length is:

Code-letter	Length	Tolerance
a	< 500 mm	$^{+10}_0$ mm
b	≥ 500 mm	$^{+2}_0$ %

The tube shall be capable of being machined concentrically to the required nominal dimensions and the eccentricity of the bore shall not exceed 4,0 % of the nominal inside diameter.

NOTE The machining of the tube to the nominal dimensions with the inner and outer surfaces concentric is feasible if the maximum inner diameter, calculated by difference between the outer diameter and two times the minimum wall thickness, is within the specified tolerance.

For a moulded tube, the tolerance on the outer diameter shall be a minimum value. A larger diameter than is provided for by the plus tolerance is acceptable for moulded tube, either type P or S, that is to be machined to the final dimension.

### 4.3 Tensile strength and percentage elongation at break

The grade for semi-finished products is determined by the values of tensile strength and percentage elongation at break shown in [Table 1](#), determined as specified in ISO 13000-2.

NOTE There are some configurations of PTFE that might not be able to be produced with a high grade classification.

**Table 1 — Tensile Strength and Percentage Elongation at Break**

Grade	1	2	3	4	5
Tensile strength MPa	≥ 25,0	20,0 - < 25,0	15,0 - < 20,0	10,0 - < 15,0	< 10,0
Elongation break %	≥ 280	200 - < 280	150 - < 200	75 - < 150	< 75

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

### 4.4 Dimensional stability

This requirement applies only to type S (stabilized) material.

The maximum change in any dimension shall not exceed 0,5 %, determined as specified in ISO 13000-2.

ISO/DIS 13000-1  
<https://standards.iteh.ai/catalog/standards/sist/4b5ae28e-db18-4a20-9d37-5e6da6cbf602/iso-dis-13000-1>

### 4.5 Density

All semi-finished products shall have a density in the range of 2,13 g/cm<sup>3</sup> to 2,19 g/cm<sup>3</sup> except that:

- a) products made from reprocessed material or blends with reprocessed material shall have a density in the range of 2,14 g/cm<sup>3</sup> to 2,23 g/cm<sup>3</sup>;
- b) tubing extruded from coagulated dispersion powders shall have a density in the range of 2,13 g/cm<sup>3</sup> to 2,23 g/cm<sup>3</sup>.

### 4.6 Hardness

All products that have a shape or dimensions such that measurements can be made precisely shall have a ball indentation hardness of more than 23 MPa or the hardness determined using the Shore D test shall have a value greater than 54. Both of the hardness tests are described in ISO 13000-2.

### 4.7 Colour

PTFE that does not contain a colorant shall be white to transparent after sintering. Visual perception of whiteness is usually adequate to appraise this characteristic of semi-finished products. If a quantitative value is required for whiteness, the test procedure in ISO 13000-2 shall be used. The value required shall be as agreed upon between producer and purchaser. If pigment or colorant has been added, its presence shall be reported in all documentation related to a particular product.

NOTE The presence of pigments or colorants may affect some properties of the material, e.g. chemical resistance and electrical properties, and it is advisable for the purchaser and supplier to agree upon the type and grade of pigment to be used.



## 4.8 Dielectric strength (DS)

### 4.8.1 General

This requirement applies only to materials coded E with specified electrical properties required for an application.

NOTE The IEC has responsibility for standards related to electrical properties. Since there are, however, no IEC standards that are pertinent to the scope and needs of this part of ISO 13000, provisions for electrical properties are included in this part of ISO 13000. Some references to general IEC standards and specific references to IEC standards for heat-shrinkable tubing of PTFE are included in [Annex A](#).

### 4.8.2 Skived tape, skived sheet, or film

**4.8.2.1** The values required for dielectric strength for each grade of skived tape, skived sheet, or film are shown in [Table 2](#). The requirements are based on a test specimen in same thickness prepared from the skived tape, skived sheet, and film. For thickness 1 mm and thicker of skived sheet, the requirements shall be based on a test specimen  $1,0 \pm 0,10$  mm in thickness prepared from the skived sheet.

**Table 2 — Dielectric Strength of Skived Tape, Skived Sheet, or Film**

Grade	DS (kV/mm)
E1	$\geq 100,0$
E2	$80,0 - < 100,0$
E3	$60,0 - < 80,0$
E4	$40,0 - < 60,0$
E5	$30,0 - < 40,0$
E6	$20,0 - < 30,0$
E7	$10,0 - < 20,0$
E8	$< 10,0$

### 4.8.3 Moulded sheet

The values required for dielectric strength for each grade of moulded sheet are shown in the table below. The requirements are based on a test specimen  $1,0 \pm 0,10$  mm in thickness prepared from the moulded sheet.

**Table 3 — Dielectric Strength of Moulded Sheet**

Grade	DS (kV/mm)
E1	$\geq 30,0$
E2	$20,0 - < 30,0$
E3	$10,0 - < 20,0$
E4	$< 10,0$

### 4.8.4 Moulded basic shape

The values required for dielectric strength for each grade of a moulded basic shape are shown in [Table 4](#). The requirements are based on a test specimen  $1,0 \pm 0,10$  mm in thickness prepared from the moulded basic shape.