



**Designation: B500/B500M-10** ~~Designation: B500/B500M - 12~~

## Standard Specification for Metallic Coated or Aluminum Clad Stranded Steel Core for Use in Overhead Electrical Conductors<sup>1</sup>

This standard is issued under the fixed designation B500/B500M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### 1. Scope\*

1.1 This specification covers 7-wire, 19-wire, 37-wire, and 61-wire zinc-coated (galvanized), zinc-5 % aluminum-mischmetal alloy-coated or aluminum clad stranded steel core intended for use in overhead electrical conductors.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

B498/B498M Specification for Zinc-Coated (Galvanized) Steel Core Wire for Use in Overhead Electrical Conductors

B957 Specification for Extra-High-Strength and Ultra-High-Strength Zinc-Coated (Galvanized) Steel Core Wire for Overhead Electrical Conductors

B958 Specification for Extra-High-Strength and Ultra-High-Strength Class A Zinc5% Aluminum-Mischmetal Alloy-Coated Steel Core Wire for Use in Overhead Electrical Conductors

B606 Specification for High-Strength Zinc-Coated (Galvanized) Steel Core Wire for Aluminum and Aluminum-Alloy Conductors, Steel Reinforced

B802/B802M Specification for Zinc5 % Aluminum-Mischmetal Alloy-Coated Steel Core Wire for Aluminum Conductors, Steel Reinforced (ACSR)

B803 Specification for High-Strength Zinc5 % Aluminum-Mischmetal Alloy-Coated Steel Core Wire for Use in Overhead Electrical Conductors

~~E83 Practice for Verification and Classification of Extensometer Systems~~ Practice for Verification and Classification of Extensometer Systems

B502 Specification for Aluminum-Clad Steel Core Wire for Use in Overhead Electrical Aluminum Conductors

### 3. Terminology

#### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *lot*—unless otherwise specified in the contract or order, a lot shall consist of all coils or reels of strand of the same diameter and unit lengths submitted for inspection at the same time.

3.1.2 *production lot*—all of the wire spools loaded into a stranding machine that are used to produce a completed strand cable.

### 4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

4.1.1 Length of each construction,

4.1.2 Constructional description of stranded core (for example,  $7 \times 0.0943$  in. or  $19 \times 0.0977$  in.) (8.1 and 8.2),

4.1.3 The multiple length of stranded core and the total number of multiple lengths per reel, if allowed (8.3 and Section 15),

~~4.1.4 Strength and coating type (Section~~

4.1.4 Strength and coating type or aluminum clad (Section 8),

4.1.5 Direction of lay of outer layer (Section 7),

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.05 on Conductors of Ferrous Metals.

Current edition approved Oct. April 1, 2010; 2012. Published November 2010; May 2012. Originally approved in 1969. Last previous edition approved in 2009; 2010 as B500/B500M - 109. DOI: 10.1520/B0500\_B0500M-102.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard.

- 4.1.6 Packaging (Section 15), and
- 4.1.7 Place of inspection (Section 13).

## 5. Material

5.1 The coated or aluminum clad steel wire used in the production of the stranded core shall, prior to stranding, meet all of the requirements of the appropriate specification that follows:

- 5.1.1 Specification B498/B498M,
- 5.1.2 Specification B606,
- 5.1.3 Specification B802/B802M, and
- 5.1.4 Specification B803.
- 5.1.5 Specification B957.
- 5.1.6 Specification B958.
- 5.1.7 Specification B502.

## 6. Joints

6.1 There shall be no joints of any kind made in the finished zinc-coated, zinc-5 % aluminum-mischmetal alloy-coated or aluminum clad steel wires.

## 7. Stranding

7.1 The lay length of the 6-wire layer of 7 and 19-wire stranded core shall be not less than 16 or more than 26 times the outside diameter of the 6-wire layer. (Outside diameter is three times nominal wire diameter.)

7.2 The lay length of the 12-wire layer of a 19-wire stranded core shall be not less than 14 or more than 22 times the outside diameter of the 12-wire layer. (Outside diameter is five times nominal wire diameter.)

7.3 The lay length of the 18-wire layer of a 37-wire stranded core shall be not less than 14 or more than 20 times the outside diameter of the 18-wire layer. (Outside diameter is seven times nominal wire diameter.)

7.4 The lay length of the 24-wire layer of a 61-wire stranded core shall be not less than 14 or more than 18 times the outside diameter of the 24-wire layer. (Outside diameter is nine times nominal wire diameter.)

7.5 The steel wires shall be so stranded that when the stranded core is cut the individual wires can be readily regrouped and then held in place by one hand.

7.6 For construction containing 19 or more wires, the direction of lay will alternate with each layer.

7.7 The direction of lay of the outer layer shall be as specified by the purchaser at the time of placing the order.

## 8. Construction and Recommended Standard Stranded-Core Lengths

8.1 Overhead Electrical Conductors may be constructed using steel core wire with any one of ~~six types of the~~ protective coatings or aluminum clad and associated strength grades. The acceptable core wires are produced to ASTM Specifications shown in Section 5 of this standard.

8.2 The number and diameters of the steel wires shall conform to the requirements in respective ASTM Conductor Standards.

8.3 Recommended standard unit-stranded-core multiple lengths are given in respective ASTM Conductor Standards.

## 9. Length Tolerance

9.1 All lengths of stranded core shall be furnished to a length tolerance of  $\pm 2$  %.

## 10. Tensile Properties

10.1 The rated ultimate strength or strength at 1 % extension of stranded core for overhead electrical conductors shall be taken as that percentage according to the number of wires, indicated below, of the sum of the strengths of the steel wires, calculated from their specified nominal wire diameter and the appropriate specified minimum stress at 1 % extension or ultimate strength given in Specifications B498/B498M, B606, B802/B802M, B803, B957, ~~or, B958~~ or B502:

7-wire strand—96 % of sum of components

B0500\_B0500M-12\_1

B0500\_B0500M-12\_2

B0500\_B0500M-12\_3

B0500\_B0500M-12\_4

10.2 Stranded steel core samples shall sustain loads equal to or greater than the values computed by the method of 10.1. Compliance can be shown either by testing the completed strand or by calculation using the strand's individual wire properties (e.g., ultimate strength or stress at 1% extension). When calculating the strand strengths using the strand's individual wire properties, it shall be computed as the percentage of the sum of the actual wire strengths as indicated below:

B0500\_B0500M-12\_5