INTERNATIONAL STANDARD

ISO 19337

Second edition 2023-05

Nanotechnologies — Characteristics of working suspensions of nano-objects for in vitro assays to evaluate inherent nano-object toxicity

Nanotechnologies — Caractéristiques des suspensions de nano-objets utilisées pour les tests in vitro évaluant la toxicité inhérente aux nano-objets objets

(standards.iteh.ai)

ISO 19337:2023

https://standards.iteh.ai/catalog/standards/sist/1b901fef-cce8-49df-a4ea-170195984757/iso 19337-2023



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 19337:2023 https://standards.iteh.ai/catalog/standards/sist/1b901fef-cce8-49df-a4ea-170195984757/iso



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org Published in Switzerland

Contents		Page
Forew	vord	iv
Introduction		v
1	Scope	1
2	Normative references	
3	Terms and definitions	
4	Abbreviated terms	
5	Characteristics and measurement methods	
	5.1 General	
	5.2 Stability of working suspensions 5.2.1 General	
	5.2.1 General 5.2.1 General 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change of secondary particles of nano-objects 5.2.2 Representative size change 5.2.2 Representative size change 6.2.2 Re	
	5.2.3 Concentration change of nano-objects	
	5.3 Concentration of metal ions	
	5.4 Concentration of culture medium components	
	5.4.2 Proteins	
	5.4.3 Calcium	
	5.5 Contamination	
6	Reporting A STANDARD PREVIEW	5
	6.1 General	5
	6.2 Name of nano-objects and manufacturing information	
	6.3 Composition and metallic elements included in the nano-object sample	5 5
	6.5 Measurement results 180.19337.2023	
	6.6 and Optional methods	6
Annex	x A (normative) Flow of measurements 7.2023	7
Annex	x B (informative) Measurement and evaluation of stability	8
Annex	x C (informative) Measurement of metal ions	9
Annex	x D (informative) Measurement of culture medium components	11
Annex	x E (informative) Contamination	12
Bibliography		13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 229, Nanotechnologies.

This second edition cancels and replaces the first edition (ISO/TS 19337:2016) which has been technically revised.

The main changes are as follows:

- "the flow of measurements" has been improved as shown in Figure A.1;
- the status of <u>Annex A</u> has been changed from informative to normative;
- "<u>5.2</u> Endotoxin" has been replaced by "<u>5.5</u> Contamination".

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Before nano-objects enter onto the market, their possible impact on human health and the environment should be carefully evaluated.

In vitro toxicity assays using cultured cells are frequently used as a tool in screening materials for possible hazardous properties. The testing provides essential information for understanding the mechanisms of biological effects induced by the materials. However, nano-objects require specific considerations with respect to the in vitro toxicity assays, because of their unique behaviour in cell culture medium. For example, immediately after the introduction of nano-object samples into the culture medium, the nano-objects can undergo changes in

- a) ionic dissolution,
- b) corona formation, or
- c) aggregation/agglomeration

leading to alteration in particles size and sedimentation. Therefore, it is critical to consider the above-mentioned phenomena in clarifying if the observed effects are related to the tested nano-object itself or from uncontrolled sources and to avoid false interpretation of assay results. For example, the corona formation, metal ion release from the nano-objects and impurities (residual from the nano-object synthesis process) can interfere with some in vitro assays^[1], producing inaccurate results. Additionally, the formation of agglomerates and aggregates can alter the toxicity of a suspension. It is important to carefully assess and describe the characteristics of the suspension of nano-objects being tested.

Therefore, the rigorous characterization of the working suspension prior and during in vitro toxicity assays on these characteristics is essential to exclude the in vitro experimental artefacts. In this document, the essential characteristics related to these three phenomena and applicable measurement methods were summarized. On the other hands, this document does not include a strategy to select the appropriate techniques from the applicable measurement methods because the working suspensions that contain nano-object samples for in vitro toxicity assays has the different materials components, concentration and sizes; thus, the appropriate selection is depending on the investigators. While the related informative annexes and the list of references in the Bibliography are included in this document to assist with appropriate method selection by investigators to make allowance for the characterization method selection, optional methods are also given in this document. In Clause 6, the details of the characterization methods/procedures are described; therefore, the appropriateness of the characterization can be judged.

The intention of this document is for reliable test results on nano-object toxicity to be shared and communicated among stakeholders of nano-objects, such as regulators, general public, manufacturers and end users.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 19337:2023

https://standards.iteh.ai/catalog/standards/sist/1b901fef-cce8-49df-a4ea-170195984757/iso-19337-2023

Nanotechnologies — Characteristics of working suspensions of nano-objects for in vitro assays to evaluate inherent nano-object toxicity

1 Scope

This document describes the characteristics of working suspensions of nano-objects to be considered when conducting in vitro assays to evaluate inherent nano-object toxicity. In addition, the document identifies applicable measurement methods for these characteristics.

This document is applicable to nano-objects, and their aggregates and agglomerates greater than 100 nm.

This document intends to help clarify whether observed toxic effects come from tested nano-objects themselves or from uncontrolled sources.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/TS 80004-2, Nanotechnologies — Vocabulary — Part 2: Nano-objects

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO/TS 80004-2 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at https://www.electropedia.org/

3.1

culture medium

aqueous solution of nutrients required for cell growth

3.2

secondary particle

agglomerate/aggregate of primary particle(s), proteins and other medium components

3.3

stability

properties to remain unchanged over a given time under stated or reasonably expected conditions of storage and use for an in vitro toxicity assay

3.4

working suspension

suspension prepared for an in vitro assay that includes *culture medium* (3.1) and nano-object sample

3.5

contamination

trace amounts of extrinsic substances present in the nano-object samples that affect cellular growth

4 Abbreviated terms

AAS atomic absorption spectrometry

BCA bicinchoninate acid

BSA Bovine serum albumin

C-U/F ultrafiltration assisted by centrifugation

DLS dynamic light scattering

AF4 asymmetrical-flow field-flow fractionation

ICP-AES inductively coupled plasma-atomic emission spectrometry

ICP-MS inductively coupled plasma mass spectrometry

LAL limulus amebocyte lysate

LD laser diffraction | CTA | D | P | R | V | R | V |

LPS liposaccharides

MAT monocyte activation test

PCR polymerase chain reaction ISO 19337:200

ttps://standards.iteh.ai/catalog/standards/sist/1b901fef-cce8-49df-a4ea-170195984757/iso

ppt parts per trillion 19337

SLS static light scattering

TFF tangential flow filtration

TOC total organic carbon

U/F ultrafiltration

UV-Vis ultraviolet-visible

5 Characteristics and measurement methods

5.1 General

To characterize the working suspension for in vitro toxicity assays, it is necessary to identify certain characteristics that can impact the biological system tested. Working suspensions for individual dose shall be divided into two samples, one for toxicity assay and another for characteristics measurements. Clause 5 specifies essential characteristics of the working suspension, listed below, and measurement methods that are applicable to them:

- stability of working suspensions;
- concentration of metal ions;
- concentration of culture medium components;

contamination.

Measurements of those characteristics shall be made for each dose of working suspensions. The flow of measurements shall be in accordance with <u>Annex A</u> and <u>Figure A.1</u>.

5.2 Stability of working suspensions

5.2.1 General

Stability of working suspension is a key characteristic as it directly impacts the in vitro assay conditions in terms of the dose of the nano-objects to the cells^{[2],[3],[4]}. Aggregation/agglomeration and gravitational settling of the nano-objects are major issues that can affect the stability of the suspended nano-objects. The suspension stability shall be evaluated for the two characteristics, i.e. the relative change of representative size of secondary particles of nano-objects and the relative change of the concentration of nano-objects in the working suspension. The change in size of secondary particles of nano-objects can result from agglomeration of smaller particles in culture media. The relative change of nano-object concentration can result from gravitational settling during an in vitro toxicity assay by considering experimental duration required for the in vitro toxicity assay. Evaluation results of the stability shall be expressed in the unit of per cent over the timescale for an in vitro toxicity assay.

ISO/TR 13097^[5] is recommended as comprehensive guidance for stability of working suspension.

5.2.2 Representative size change of secondary particles of nano-objects

An appropriate method shall be selected to directly measure the representative size change of secondary particles of nano-objects from among $DLS^{[3],[6]}$, $LD^{[7]}$ and $SLS^{[8]}$. Other methods not listed in this document can be used and reported according to the optional methods in <u>6.6</u>.

See Annex B for measurements.

5.2.3 Concentration change of nano-objects b901fef-cce8-49df-a4ea-170195984757/iso-

An appropriate method shall be selected to measure the concentration change of nano-objects suspended in the biological media from among the static light scattering^{[3],[6],[8]}, ICP-MS^{[9],[10],[11]}, UV-Vis absorption, X-ray transmission^[12] and the total organic carbon analysis^[13]. Other methods not listed in this document can be used and reported according to the optional methods in 6.6.

See Annex B for measurements.

5.3 Concentration of metal ions

Metal ions, produced as a result of nano-object test sample dissolution, can contribute to observed cell toxicity. The concentration of metal ions in the working suspension shall be measured after separation of particulate matter. Particulate matter can be separated from the ionic fraction by U/F, C-U/F TFF or centrifugation. The measurement shall be made for all metallic elements that are included in the nano-object sample. An appropriate method shall be selected to measure the metal ion concentrations from among ICP-AES, ICP-MS, AAS and the colorimetric method. It shall be noted that many constituents in culture media such as Na and Cl can interfere with metals analysis for some spectrometry techniques, especially ICP-MS^[14]-^[16]. Other methods not listed in this document can be used and reported according to the optional methods in 6.6. Measurement results of concentrations shall be expressed in the unit of molarity, mass/mass or mass/volume. The measurements can be omitted when a toxic effect is not observed to the cells in the working suspensions. See Annex A for an example of flow of measurements.

See Annex C for measurements.

5.4 Concentration of culture medium components

5.4.1 General

A nano-object sample added to a culture medium to generate a working suspension can adsorb components of the culture medium^[1]. This adsorption can result in starvation stress to the test cells. The concentration of protein components and calcium, as surrogates for the nutritional components in the solvent shall be measured after allowing enough time after the addition of nano-object sample to the culture medium. If culture medium components other than protein and calcium that can significantly affect the stability of the working suspension for in vitro toxicity assays are known, the concentration of those components shall be measured as well. The measurements can be omitted when a toxic effect is not observed to the cells in the working suspensions. See Annex A for an example of flow of measurements.

Nano-object sample in culture medium shall be incubated with the same conditions of in vitro test. Nano-objects can affect pH, osmolality and other essential characteristics in the culture medium.

5.4.2 Proteins

An appropriate method shall be chosen for the protein concentration measurement from among BCA, Bradford, Lowry, and ultraviolet, refractive index and SLS methods coupled with the AF4^{[17],[18]}. When BCA^[19], Bradford^[20] or Lowry^[21] method are chosen, the protein concentration in the solvent shall be measured after separation of particulate matter from the working suspension. Results of protein concentration measurement shall be expressed in the unit of mass/volume.

See Annex D for measurements.

5.4.3 Calcium

An appropriate measurement method shall be chosen for the calcium concentration measurement from among ICP-AES, ICP-MS, AAS and the colorimetric method. Results of calcium concentration measurement shall be expressed in the unit of molarity, mass/mass or mass/volume.

See <u>Annex D</u> for measurements.

5.5 Contamination

Contamination can be a source of additional toxic action. Endotoxin and mycoplasma shall be determined with appropriate methods.

Endotoxin measurement are available with LAL test (see ISO 29701), the chromogenic-based LAL assays^[22], the MAT^[23], recombinant Factor C test^[24] and high performance liquid chromatography coupled with mass spectrometry methods^[25].

Mycoplasma contamination is one of the major problems in vitro assay. Mycoplasma can be detected by PCR based methods^[26], culture methods^[27] and fluorescence microscopy method^[28].

Nano-object sample shall be treated aseptically. It shall be confirmed that there is no history of contamination except that which is described in this subclause.

See **Annex E** for measurements.

6 Reporting

6.1 General

Measurement and evaluation results obtained according to this document shall be reported describing the source and the constituents of the nano-objects, culture medium and serum, as described in $\underline{6.2}$ to $\underline{6.6}$.

6.2 Name of nano-objects and manufacturing information

Name, catalogue and lot/batch number of nano-objects and manufacturer information including name, address and contact information shall be reported.

6.3 Composition and metallic elements included in the nano-object sample

Define principal and accessory materials, coating materials, catalytic materials and impurities, including their known or estimated quantity.

6.4 Culture medium and serum

Name, manufacturer and lot/batch number of the medium, type and concentration of added serum (volume fraction %), pH values of original medium and pH values during assessment, and type and concentration of other additives, if any, shall be reported.

6.5 Measurement results

The following are required to report for individual doses of working suspensions and measurement time frame. However, the results of the test for contaminants can be reported for the stock of nano-objects instead of individual doses.

Reporting of metal ions, culture medium components and contaminants are not required when toxicity is not observed for the individual doses of working suspension.

- Stability of working suspension
 - a) representative size change and concentration change,
 - b) date of measurement,
 - c) employed measurement methods for representative size change and concentration change,
 - d) performing institution and data reliability information,
 - e) supporting information on preparation method of working suspension, and
 - f) other special supporting information if any;
- metal ions
 - a) names of metal ions and their concentrations.
 - b) date of measurement,
 - c) employed measurement method,
 - d) performing institution and data reliability information, and
 - e) other special supporting information if any;
- culture medium components