
**Rubber hoses and hose assemblies —
Wire- or textile-reinforced single-
pressure types for hydraulic
applications — Specification**

*Tuyaux et flexibles en caoutchouc — Types hydrauliques à pression
unique, avec armature de fils métalliques ou textiles tressés —
Spécifications*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18752:2022

<https://standards.iteh.ai/catalog/standards/sist/450bd51f-0764-473b-8611-5cf1620f2dd4/iso-18752-2022>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18752:2022

<https://standards.iteh.ai/catalog/standards/sist/450bd51f-0764-473b-8611-5cfl620f2dd4/iso-18752-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
4.1 Classes.....	2
4.2 Grades and types.....	2
5 Materials and construction	3
5.1 Hoses.....	3
5.2 Hose assemblies.....	3
6 Dimensions and tolerances	4
6.1 Diameters.....	4
6.2 Cover thickness.....	6
6.3 Concentricity.....	6
6.4 Length.....	6
7 Physical properties	7
7.1 Fluid resistance of rubber compounds.....	7
7.1.1 Test pieces.....	7
7.1.2 Oil resistance.....	7
7.1.3 Water-based fluid resistance.....	7
7.1.4 Water resistance.....	7
7.2 Performance requirements.....	7
7.2.1 Hydrostatic requirements.....	7
7.2.2 Change in length.....	8
7.2.3 Minimum bend radius.....	8
7.2.4 Resistance to impulse.....	10
7.2.5 Leakage of hose assemblies.....	10
7.2.6 Cold flexibility.....	10
7.2.7 Adhesion between components.....	10
7.2.8 Vacuum resistance.....	10
7.2.9 Ozone resistance.....	11
7.2.10 Abrasion resistance.....	11
8 Frequency of testing	11
9 Marking	11
9.1 Hoses.....	11
9.2 Hose assemblies.....	11
10 Recommendations for packaging and storage	11
11 Information by hose manufacturer	12
12 Test report	12
Annex A (normative) Type tests and routine tests	13
Annex B (informative) Production tests	14
Annex C (informative) Information to be provided by hose manufacturer	15
Bibliography	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 218, *Rubber and plastics hoses and hose assemblies*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 18752:2014), which has been technically revised.

The main changes are as follows:

- the scope has been extended to water-based fluid, in order to align the document with ISO 1436, ISO 3862 and ISO 4079;
- in [7.1.2](#):
 - “For all grades” was replaced with “For types AS, AC, BS and BC”;
 - a new temperature condition of 120 °C was added;
- a new subclause [7.1.3](#) was added;
- in [Annex B, Table B.1](#), change in length test per batch, was replaced “X” with “N/A”.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Rubber hoses and hose assemblies — Wire- or textile-reinforced single-pressure types for hydraulic applications — Specification

1 Scope

This document specifies requirements for ten classes, four grades and seven types of wire- or textile-reinforced hydraulic hoses and hose assemblies of nominal sizes ranging from 5 to 102. Each class has a single maximum working pressure for all sizes.

They are suitable for use with:

- oil-based hydraulic fluids HH, HL, HM, HR and HV as defined in ISO 6743-4 at temperatures ranging from -40 °C to $+100\text{ °C}$ for types AS, AC, BS and BC hoses and from -40 °C to $+120\text{ °C}$ for types CS, CC and DC hoses.
- water-based fluids HFC, HFAE, HFAS and HFB as defined in ISO 6743-4 at temperatures ranging from -40 °C to $+70\text{ °C}$.
- water at temperatures ranging from 0 °C to $+70\text{ °C}$.

This document does not include requirements for the connection ends. It is limited to the performance of hoses and hose assemblies. The hose assembly maximum working pressure is governed by the lowest maximum working pressure of the components.

NOTE It is the responsibility of the user, in consultation with the hose manufacturer, to establish the compatibility of the hose with the fluid to be used.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies*

ISO 6605, *Hydraulic fluid power — Test methods for hoses and hose assemblies*

ISO 6743-4, *Lubricants, industrial oils and related products (class L) — Classification — Part 4: Family H (Hydraulic systems)*

ISO 6803, *Rubber or plastics hoses and hose assemblies — Hydraulic-pressure impulse test without flexing*

ISO 7233, *Rubber and plastics hoses and hose assemblies — Determination of resistance to vacuum*

ISO 7326:2016, *Rubber and plastics hoses — Assessment of ozone resistance under static conditions*

ISO 8033, *Rubber and plastics hoses — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 10619-1:2017, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 1: Bending tests at ambient temperature*

ISO 10619-2:2021, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 2: Bending tests at sub-ambient temperatures*

ISO 17165-1, *Hydraulic fluid power — Hose assemblies — Part 1: Dimensions and requirements*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Classification

4.1 Classes

Ten classes of hose are specified, distinguished by their maximum working pressure, as shown in [Table 1](#). Each class may be manufactured in up to 14 nominal sizes.

Table 1 — Classes and nominal sizes

Class	35	70	140	210	250	280	350	420	490	560
MWP ^a (MPa)	3,5	7	14	21	25	28	35	42	49	56
MWP ^a (bar)	35	70	140	210	250	280	350	420	490	560
Nominal size										
5	X	X	X	X	X	X	X	X	N/A	N/A
6,3	X	X	X	X	X	X	X	X	N/A	N/A
8	X	X	X	X	X	X	X	X	N/A	N/A
10	X	X	X	X	X	X	X	X	N/A	N/A
12,5	X	X	X	X	X	X	X	X	N/A	N/A
16	X	X	X	X	X	X	X	X	X	X
19	X	X	X	X	X	X	X	X	X	X
25	X	X	X	X	X	X	X	X	X	X
31,5	X	X	X	X	X	X	X	X	X	X
38	X	X	X	X	X	X	X	X	N/A	N/A
51	X	X	X	X	X	X	X	X	N/A	N/A
63	X	X	X	X	X	X	X	N/A	N/A	N/A
76	X	X	X	N/A	N/A	N/A	N/A	N/A	N/A	N/A
102	X	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A

X = Applicable; N/A = Not applicable.

^a Maximum working pressure.

4.2 Grades and types

Hoses are classified into four grades according to their resistance to impulse: A, B, C and D. Each grade is classified by outside diameter into standard types (AS, BS and CS) and compact types (AC, BC, CC and DC), as shown in [Table 2](#).

Table 2 — Grades and types

Grade	Type ^a	Resistance to impulse		
		Temperature °C	Impulse pressure (% of MWP ^b)	Minimum number of cycles
A	AS	100	133 %	200 000
	AC			
B	BS	100	133 %	500 000
	BC			
C	CS	120	133 % and 120 % ^c	500 000
	CC			
D	DC	120	133 %	1 000 000

^a Standard or compact, e.g. CS is grade C and standard type. As shown in Table 4 and Table 8, standard types have larger outside diameters and larger bend radii and compact types have smaller outside diameters and smaller bend radii.

^b Maximum working pressure.

^c 120 % of the MWP shall be used for classes 350, 420, 490 and 560 instead of 133 %.

Each class includes one of each type or both as shown in Table 3.

Table 3 — Type and maximum working pressure

Class		35	70	140	210	250	280	350	420	490	560
MWP ^a (MPa)		3,5	7	14	21	25	28	35	42	49	56
MWP ^a (bar)		35	70	140	210	250	280	350	420	490	560
Grade	Type										
A	AS	X	X	X	X	X	X	X	X	N/A	N/A
	AC	X	X	X	X	X	X	X	X	N/A	N/A
B	BS	X	X	X	X	X	X	X	X	N/A	N/A
	BC	X	X	X	X	X	X	X	X	N/A	N/A
C	CS	N/A	N/A	N/A	X	X	X	X	X	N/A	N/A
	CC	N/A	N/A	N/A	X	X	X	X	X	X	X
D	DC	N/A	N/A	N/A	X	X	X	X	X	N/A	N/A

X = Applicable; N/A = Not applicable.

^a Maximum working pressure.

5 Materials and construction

5.1 Hoses

Hoses shall consist of a hydraulic-fluid-resistant rubber lining, one or multiple layers of steel wire or textile and an oil-, abrasion- and weather-resistant rubber cover. A layer of other materials on the rubber cover is allowed for improved resistance to abrasion or other.

5.2 Hose assemblies

Hose assemblies shall only be manufactured using hose fittings which conform to the requirements of 7.2.1, 7.2.4 and 7.2.5.

Follow the manufacturer's instructions for the proper preparation and fabrication of hose assemblies.

6 Dimensions and tolerances

6.1 Diameters

When measured in accordance with ISO 4671, the diameters of hoses shall conform to the values given in [Table 4](#).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 18752:2022](#)

<https://standards.iteh.ai/catalog/standards/sist/450bd51f-0764-473b-8611-5cf1620f2dd4/iso-18752-2022>

Table 4 — Diameters of hoses

Nominal size	Inside diameter (all classes) mm		Maximum outside diameter of hose mm																			
			Class 35		Class 70		Class 140		Class 210		Class 250		Class 280		Class 350		Class 420		Class 490		Class 560	
			Standard	Compact	Standard	Compact	Standard	Compact	Standard	Compact	Standard	Compact	Standard	Compact	Standard	Compact	Standard	Compact	Standard	Compact	Standard	Compact
5	4,6	5,4	14	11	14	11	14	11	14	11	17	15	17	15	17	15	17	15	—	—	—	—
6,3	6,1	7	17	14	17	14	17	14	19	15	19	15	19	15	19	15	19	15	—	—	—	—
8	7,7	8,5	19	15	19	15	19	16	20	16	20	16	20	16	20	16	20	18	—	—	—	—
10	9,3	10,1	21	17	21	17	23	19	23	19	23	19	23	19	23	21	24	22	—	—	—	—
12,5	12,3	13,5	24	21	24	22	26	22	26	22	26	22	26	23	27	24	27	25	—	—	—	—
16	15,5	16,7	27	25	27	25	29	26	29	27	29	27	29	27	29	28	34	34	—	—	—	30
19	18,6	19,8	31	28	31	29	33	31	34	32	34	32	34	32	38	36	50	46	—	—	—	36
25	25	26,4	40	36	40	38	41	39	41	39	41	39	41	39	50	45	54	50	—	—	—	45
31,5	31,4	33	53	45	53	45	54	49	54	49	54	49	54	49	54	52	60	56	—	—	—	52
38	37,7	39,3	59	56	59	56	59	56	59	56	59	56	59	56	60	59	75	72	—	—	—	—
51	50,4	52	72	69	72	69	73	70	73	70	73	70	73	70	75	73	80	77	—	—	—	—
63	63,1	65,1	84	—	84	—	85	—	90	—	90	—	90	—	—	—	—	—	—	—	—	—
76	74,6	77,8	100	—	100	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
102	100	103,2	130	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—

6.2 Cover thickness

When measured in accordance with ISO 4671, the outer cover thickness of hoses shall conform to the values given in Table 5. Standard types may be produced with either thick or thin covers, the tolerance limits for thin-cover standard types being the same as the tolerance limits for compact types.

Table 5 — Cover thickness

Nominal size	Cover thickness mm					
	Standard (thick cover)		Standard (thin cover)		Compact	
	min.	max.	min.	max.	min.	max.
5	1,5	3,2	0,8	1,5	0,8	1,5
6,3	1,5	3,2	0,8	1,5	0,8	1,5
8	1,5	3,2	0,8	1,5	0,8	1,5
10	1,5	3,2	0,8	1,5	0,8	1,5
12,5	1,5	3,2	0,8	1,5	0,8	1,5
16	1,5	3,2	0,8	1,5	0,8	1,5
19	1,5	3,2	0,8	1,5	0,8	1,5
25	1,5	4,6	1,0	2,0	1,0	2,0
31,5	1,8	4,6	1,0	2,0	1,0	2,0
38	1,8	4,6	1,3	2,5	1,3	2,5
51	1,8	4,6	1,3	2,5	1,3	2,5
63	1,8	5,0	—	—	—	—
76	1,8	5,0	—	—	—	—
102	1,8	5,0	—	—	—	—

6.3 Concentricity

When measured in accordance with ISO 4671, the concentricity of hoses shall conform to the values given in Table 6.

Table 6 — Concentricity of hoses

Nominal size	Maximum variation in wall thickness	
	between internal diameter and outside diameter	between internal diameter and reinforcement diameter
	mm	mm
5 and 6,3	0,8	0,5
Over 6,3 and up to and including 19	1,0	0,7
Over 19 and up to and including 63	1,3	0,9
Over 63	1,5	1,1

6.4 Length

The tolerances on the lengths of hose assemblies should conform to ISO 17165-1:2007, Table 6.

7 Physical properties

7.1 Fluid resistance of rubber compounds

7.1.1 Test pieces

Fluid resistance tests shall be carried out on moulded sheets of lining and cover compound having a minimum thickness 2 mm and a cure state equivalent to that of the hose.

7.1.2 Oil resistance

For types AS, AC, BS and BC, when tested in accordance with ISO 1817 by immersion in IRM 903 oil for 168 h at a temperature of 100 °C, the percentage change in volume ΔV of the lining shall be between 0 % and +25 % for braid-construction and textile-reinforced hoses and between 0 % and +60 % for spiral-wire-reinforced hoses (i.e. shrinkage is not permissible).

For types AS, AC, BS and BC, when tested in accordance with ISO 1817 by immersion in IRM 903 oil for 168 h at a temperature of 70 °C, the percentage change in volume ΔV of the cover shall be between 0 % and +100 % (i.e. shrinkage is not permissible).

For types CS, CC and DC, when tested in accordance with ISO 1817 by immersion in IRM 903 oil for 168 h at a temperature of 120 °C, the percentage change in volume ΔV of the lining shall be between 0 % and +100 % and of the cover shall be between 0 % and +125 % (i.e. shrinkage is not permissible).

7.1.3 Water-based fluid resistance

For all types of hose, when tested in accordance with ISO 1817 by immersion in a test fluid made up of equal volumes of 1, 2-ethanediol and distilled water for 168 h at a temperature of 70 °C, the percentage change in volume of the lining shall be between 0 % and +25 % and the percentage change in volume of the cover shall be between 0 % and +100 % (i.e. shrinkage is not permissible).

7.1.4 Water resistance

For all types of hose, when tested in accordance with ISO 1817 by immersion in distilled water for 168 h at a temperature of 70 °C, the percentage change in volume of the lining shall be between 0 % and +25 % and the percentage change in volume of the cover shall be between 0 % and +100 % (i.e. shrinkage is not permissible).

7.2 Performance requirements

7.2.1 Hydrostatic requirements

When determined in accordance with ISO 1402 or ISO 6605 at the relevant proof pressure and the relevant minimum burst pressure given in [Table 7](#), the hoses and hose assemblies shall not fail.

Table 7 — Maximum working pressure, proof pressure and minimum burst pressure

Class	Maximum working pressure		Proof pressure		Minimum burst pressure	
	MPa	bar	MPa	bar	MPa	bar
35	3,5	35	7	70	14	140
70	7	70	14	140	28	280
140	14	140	28	280	56	560
210	21	210	42	420	84	840
250	25	250	50	500	100	1 000
280	28	280	56	560	112	1 120