



Designation: A530/A530M-04a (Reapproved 2010) Designation: A530/A530M - 12

Standard Specification for General Requirements for Specialized Carbon and Alloy Steel Pipe¹

This standard is issued under the fixed designation A530/A530M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification² covers a group of requirements which, with the exceptions of Section ~~5.36.3~~, Section ~~13.14~~, Section ~~20~~, and Section ~~21~~, and Section ~~22~~, are mandatory requirements to the ASTM pipe product specifications noted below unless the product specification specifies different requirements, in which case the requirement of the product specification shall prevail.

1.2 Sections ~~5.3.6.3~~ or ~~20.21~~ are mandatory if the product specification has a requirement for product analysis or flattening tests.

1.3 Section ~~21.22~~ is mandatory if the product specification has a hydrostatic test requirement without defining the test parameters.

1.4 Section ~~13.14~~ is for information only.

1.5 In case of conflict between a requirement of the product specification and a requirement of this general requirement specification, only the requirement of the product specification need be satisfied.

Title of Specification	ASTM Designation ⁴
Seamless Carbon Steel Pipe for High-Temperature Service A106	A106/A106M
Seamless Carbon Steel Pipe for High-Temperature Service	A106/A106M
Metal-Arc-Welded Steel Pipe for Use With High-Pressure Transmission Systems	A381
Centrifugally Cast Ferritic Alloy Steel Pipe for High-Temperature Service	A426
Centrifugally Cast Austenitic Steel Pipe for High-Temperature Service	A451
Seamless Carbon Steel Pipe for Atmospheric and Lower Temperatures	A524
Centrifugally Cast Iron-Chromium-Nickel High-Alloy Tubing for Pressure Application at High-Temperatures	A608
Centrifugally Cast Carbon Steel Pipe for High-Temperature Service	A660
Electric-Fusion-Welded Steel Pipe for Atmospheric and Lower Temperatures A671	A671/A671M
Electric-Fusion-Welded Steel Pipe for Atmospheric and Lower Temperatures	A671/A671M
Electric-Fusion-Welded Steel Pipe for High-Pressure Service at Moderate Temperatures A672	A672/A672M
Electric-Fusion-Welded Steel Pipe for High-Pressure Service at Moderate Temperatures	A672/A672M
Carbon and Alloy Steel Pipe, Electric-Fusion-Welded for High-Pressure Service at High Temperatures A691	A691
Centrifugally Cast Ferritic/Austenitic Stainless Steel Pipe for Corrosive Environments	A872

⁴ These designations refer to the latest issue of the respective specifications.

1.6 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved April 1, 2010-2012. Published August 2010-June 2012. Originally approved in 1965. Last previous edition approved in 2004-2010 as A530/A530M-04a(2010). DOI: 10.1520/A0530_A0530M-04AR10.10.1520/A0530_A0530M-12.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-530 in Section II of that Code.

*A Summary of Changes section appears at the end of this standard.

independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the “M” designation (SI) of the product specification is specified in the order.

NOTE 1—The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as “nominal diameter,” “size,” and “nominal size.”

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:³

- [A106/A106M Specification for Seamless Carbon Steel Pipe for High-Temperature Service](#)
 - [A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)
 - [A381 Specification for Metal-Arc-Welded Steel Pipe for Use With High-Pressure Transmission Systems](#)
 - [A450/A450M Specification for General Requirements for Carbon and Low Alloy Steel Tubes](#)
 - [A524 Specification for Seamless Carbon Steel Pipe for Atmospheric and Lower Temperatures](#)
 - [A660 Specification for Centrifugally Cast Carbon Steel Pipe for High-Temperature Service](#)
 - [A671/A671M Specification for Electric-Fusion-Welded Steel Pipe for Atmospheric and Lower Temperatures](#)
 - [A672/A672M Specification for Electric-Fusion-Welded Steel Pipe for High-Pressure Service at Moderate Temperatures](#)
 - [A691/A691M Specification for Carbon and Alloy Steel Pipe, Electric-Fusion-Welded for High-Pressure Service at High Temperatures](#)
 - [A700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Shipment](#)
 - [A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products](#)
 - [A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys](#)
 - [A1058 Test Methods for Mechanical Testing of Steel Products Metric](#)
 - [D3951 Practice for Commercial Packaging](#)
 - [E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)
- ### 2.2 ANSI Standards:
- [B 36.10 Welded and Seamless Wrought Steel Pipe⁴](#)
 - [B 36.19 ⁴ Stainless Steel Pipe](#)
- ### 2.3 Military Standards:
- [MIL-STD-163 Steel Mill Products Preparation for Shipment and Storage⁵](#)
 - [MIL-STD-271 Nondestructive Testing Requirements for Metals⁵](#)
 - [MIL-STD-792 Identification Marking Requirements for Special Purpose Components⁵](#)
- ### 2.4 Federal Standards:
- [Fed. Std. No. 183 Continuous Identification Marking of Iron and Steel Products⁵](#)
- ### 2.5 Steel Structures Painting Council:
- [SSPC-SP 6 Surface Preparation Specification No. 6 Commercial Blast Cleaning⁶](#)

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

- 3.1.1 *remelted heat, n*—in secondary melting, all of the ingots remelted from a single primary heat.
- 3.1.2 *jointer, n*—a length of pipe created by welding two or more shorter lengths of pipe, end-to-end.
- 3.1.3 *thin-wall pipe, n*—a pipe having a wall thickness of 3 % or less of the outside diameter.

3.2 *Other defined terms*—The definitions in Test Methods and Definitions A370, Test Methods, Practices, and Terminology A751, and Terminology A941 are applicable to this specification and to those listed in 1.5.

4. Process

- 4.1 ~~The steel shall be made from any process.~~
- 4.2 ~~If a specific type of melting is required by the purchaser, it shall be stated on the purchase order.~~
- 4.3 ~~The primary melting may incorporate separate degassing or refining and may be followed by secondary melting, using electroslag remelting or vacuum remelting.~~

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁵ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

⁶ Available from Society for Protective Coatings (SSPC), 40 24th St., 6th Floor, Pittsburgh, PA 15222-4656, <http://www.sspc.org>.

~~4.4 Steel may be cast in ingots or may be strand cast. When steel of different grades is sequentially strand cast, identification of the resultant transition material is required. The producer shall remove the transition material by an established procedure that positively separates the grades.~~

4. Ordering Information

~~4.1 It shall be the responsibility of the purchaser to specify all requirements necessary for product under this specification. Such requirements to be considered include, but are not limited to, the following:~~

- ~~4.1.1 Quantity (feet, meters, or number of lengths),~~
- ~~4.1.2 Specification number with grade or class, or both, as applicable and year date,~~
- ~~4.1.3 Manufacture (hot-finished or cold drawn),~~
- ~~4.1.4 Size (NPS [DN] and weight class or schedule number, or both; outside diameter and nominal wall thickness; or inside diameter and nominal wall thickness),~~
- ~~4.1.5 Length (specific or random),~~
- ~~4.1.6 Test report required (see Section 23),~~
- ~~4.1.7 Choice of testing track from the options listed in Test Methods A1058 when material is ordered to an M suffix (SI units) product standard. If the choice of test track is not specified in the order, then the default ASTM test track shall be used as noted in Test Methods A1058~~
- ~~4.1.8 Supplementary Requirements, and~~
- ~~4.1.9 Additional requirements.~~

5. Process

- ~~5.1 The steel shall be made from any process.~~
- ~~5.2 If a specific type of melting is required by the purchaser, it shall be stated on the purchase order.~~
- ~~5.3 The primary melting may incorporate separate degassing or refining and may be followed by secondary melting, using electroslag remelting or vacuum remelting.~~
- ~~5.4 Steel may be cast in ingots or may be strand cast. When steel of different grades is sequentially strand cast, identification of the resultant transition material is required. The producer shall remove the transition material by an established procedure that positively separates the grades.~~

6. Chemical Composition

- ~~5.1~~
- ~~6.1 Chemical Analysis~~—Samples for chemical analysis and method of analysis shall be in accordance with Test Methods, Practices, and Terminology A751.
- ~~5.2~~
- ~~6.2 Heat Analysis~~—If the heat analysis reported by the steel producer is not sufficiently complete for conformance with the heat analysis requirements of the applicable product specification to be fully assessed, the manufacturer may complete the assessment of conformance with such heat analysis requirements by using a product analysis for the specified elements that were not reported by the steel producer, provided that product analysis tolerances are not applied and the heat analysis is not altered.
- ~~5.2.1~~~~For stainless~~~~6.2.1~~ For steels ordered under product specifications referencing this specification of general requirements, the steel shall not contain an unspecified element, other than nitrogen, element for the ordered grade to the extent that the steel conforms to the requirements of another grade for which that element is a specified element having a required minimum content. For this requirement, a grade is defined as an alloy described individually and identified by its own UNS designation in a table of chemical requirements within any specification listed within the scope as being covered by this specification.
- ~~5.3.6.3~~ ~~Product Analysis~~—Product analysis requirements and options, if any, are contained in the product specification.

~~6.~~

7. Mechanical Requirements

- ~~6.1~~
- ~~7.1 Method of Mechanical Tests~~—The specimens and the mechanical tests required shall be made in accordance with Annex A2 of Test Methods and Definitions A370, especially Annex A2 thereof.
- ~~6.2~~ ~~Specimens shall be tested at room temperature.~~
- ~~6.3~~ ~~Small or subsize specimens as described in Test Methods and Definitions if inch-pound units are specified, or to the requirements described in the applicable track of est Methods A1058, if SI units are specified.~~
- ~~7.2~~ Specimens shall be tested at room temperature.
- ~~7.3~~ Small or subsize specimens as described in Test Methods and Definitions A370 or Test Methods A1058 may be used only when there is insufficient material to prepare one of the standard specimens. When using small or subsize specimens, the largest one possible shall be used.

7.

8. Tensile Requirements

- 7.1The8.1 The material shall conform to the requirements as to tensile properties prescribed in the individual specifications.
- 7.2The8.2 The yield strength corresponding to a permanent offset of 0.2 % of the gage length or to a total extension of 0.5 % of the gage length under load shall be determined.
- 7.3The8.3 If the percentage of elongation of any test specimen is less than that specified and any part of the fracture is more than 3/4 in. [19.0 mm] from the center of the gage length, as indicated by scribe marks on the specimen before testing, a retest shall be allowed.

8.

9. Permissible Variation in Weight

8.1The9.1 The weight of any length of pipe NPS 12 [DN 300] and under shall not vary more than 10 % over or 3.5 % under that specified. For sizes over NPS 12 [DN 300], the weight of any length of pipe shall not vary more than 10 % over or 5 % under that specified. Unless otherwise specified, pipe of NPS 4 [DN 100] and smaller may be weighed in convenient lots; pipe in sizes larger than NPS 4 [DN 100] shall be weighed separately.

9.10. Permissible Variations in Wall Thickness

- 9.1
 - 10.1 *Seamless and Welded (no filler metal added)*—The minimum wall thickness at any point shall be within the tolerances specified in Table 1 , except that for welded pipe the weld area shall not be limited by the over tolerance. The minimum wall thickness on inspection for – 12.5 % is shown in Table X1.1.
 - 9.2
 - 10.2 *Forged and Bored*—The wall thickness shall not vary over that specified by more than 1/8 in. [3.2 mm]. There shall be no variation under the specified wall thickness.
 - 9.3
 - 10.3 *Cast*—The wall thickness shall not vary over that specified by more than 1/16 in. [1.6 mm]. There shall be no variation under the specified wall thickness.

10.

11. Permissible Variations in Inside Diameter

- 10.1
 - 11.1 *Forged and Bored, and Cast*—The inside diameter shall not vary under that specified by more than 1/16 in. [1.6 mm]. There shall be no variation over the specified inside diameter.

11.

12. Permissible Variations in Outside Diameter

- 11.2.1 Variations in outside diameter, unless otherwise specified, shall not exceed the limits prescribed in Table 2. The tolerances on outside diameter include ovality except as provided for in 11.2.2
- 11.2.2
 - 12.2 Thin-wall pipe usually develops significant ovality (out-of-roundness) during final annealing, straightening, or both. The diameter tolerances of Table 2 are not sufficient to provide for additional ovality expected in thin-wall pipe and are applicable only

TABLE 1 Permissible Variations in Wall Thickness

NPS Designator	Tolerance, % from Nominal	
	Over	Under
1/8 to 2 1/2 , incl., all $t/D^{A,B}$ ratios	20.0	12.5
3 to 18 incl., t/D up to 5 % incl.	22.5	12.5
3 to 18 incl., $t/D > 5 %$	15.0	12.5
20 and larger, welded, all t/D ratios	17.5	12.5
20 and larger, seamless, t/D up to 5 % incl.	22.5	12.5
20 and larger, seamless, $t/D > 5 %$	15.0	12.5

^A t = Nominal wall thickness.
^B D = Ordered outside diameter.

TABLE 2 Permissible Variations in Outside Diameter

NPS Designator	Permissible Variations In Outside Diameter			
	Over		Under	
	in.	mm	in.	mm
1/8 to 1 1/2, incl	1/64 (0.015)	0.4	1/32 (0.031)	0.8
Over 1 1/2 to 4, incl	1/32 (0.031)	0.8	1/32 (0.031)	0.8
Over 4 to 8, incl	1/16 (0.062)	1.6	1/32 (0.031)	0.8
Over 8 to 18, incl	3/32 (0.093)	2.4	1/32 (0.031)	0.8
Over 18 to 26, incl	1/8 (0.125)	3.2	1/32 (0.031)	0.8
Over 26 to 34, incl	5/32 (0.156)	4.0	1/32 (0.031)	0.8
Over 34	3/16 (0.187)	4.8	1/32 (0.031)	0.8

to the mean of the extreme (maximum and minimum) outside diameter readings in any one cross-section. However, for thin-wall pipe the difference in extreme outside diameter readings (ovality) in any one cross-section shall not exceed 1.5 % of the specified outside diameter.

12.

13. Permissible Variations in Length

13.1

13.1 Seamless and Welded (no filler metal added)—If definite cut lengths are ordered, no length of pipe shall be under the length specified and not more than 1/4 in. [6 mm] over that specified.

13.2

13.2 Forged and Bored, Cast, and Cast Cold-Wrought—If definite cut lengths are ordered, no length of pipe shall be under the length specified and not more than 1/8 in. [3 mm] over that specified.

13.3 For pipe ordered to random lengths, the lengths and variations shall be agreed upon between the manufacturer and purchaser.

13.4 No jointers are permitted unless otherwise agreed upon.

14. Standard Weight

14.1 A system of standard pipe sizes has been approved by the American National Standards Institute as ANSI B 36.10 and B 36.19. These standard sizes do not prohibit the production and use of other sizes of pipe produced to the various specifications referenced to this Specification.

14.2 For nonstandard sizes of pipe, the calculated weight per foot, shall be determined from the following equation:

$$W = C(D - t)r \quad (1)$$

A0530_A0530M-12_1

where:

C = 10.69 [0.0246615],

W = weight, lb/ft [kg/m],

D = specified or calculated (from specified inside diameter and wall thickness) outside diameter, in. [mm], and

t = specified wall thickness, in. (to 3 decimal places) [mm to 2 decimal places].

NOTE 2—The weights given in the American National Standards and the calculated weights given by Eq 1 are based on the weights for carbon steel pipe. The weight of pipe made of ferritic stainless steels may be about 5 % less, and that made of austenitic stainless steel about 2 % greater than the values given.

14. Ends

14.1 Unless otherwise specified, the pipe shall be furnished with plain ends. All burrs at the ends of the pipe shall be removed.

15. Ends

15.1 Unless otherwise specified, the pipe shall be furnished with plain ends. All burrs at the ends of the pipe shall be removed.

16. Straightness

16.1 The finished pipe shall be reasonably straight.

16.2 For metal-arc welded pipe, the maximum deviation from a 10-ft [3.0-m] straightedge placed so that both ends are in contact with the pipe shall be 1/8 in. [3.2 mm]. For metal-arc welded pipe with lengths shorter than 10 ft [3.0 m], this maximum deviation shall be pro-rated with respect to the ratio of the actual length to 10 ft [3.0 m].

16.

17. Repair by Welding

17.1

17.1 Repair by welding of defects in seamless pipe (including centrifugally cast and forged and bored) and of plate defects in welded pipe and, when specifically stated by the product specification weld seam defects in welded pipe, shall be permitted subject to the approval of the purchaser and with the further understanding that the composition of the deposited filler metal shall be suitable for the composition being welded. Defects shall be thoroughly chipped or ground out before welding and each repaired length shall be reheat treated or stress relieved as required by the applicable specification. Each length of repaired pipe shall be tested hydrostatically as required by the product specification.

~~16.2~~ Repair welding shall be performed using procedures and welders or welding operators that have been qualified in accordance with the ASME Boiler and Pressure Vessel Code, Section IX.

17. Retests

~~17.1~~ If the results of the mechanical tests of any group or lot do not conform to the requirements specified in the individual specification, retests may be made on additional lengths of pipe of double the original number from the same group or lot, each of which shall conform to the requirements specified. Only one retest of any group or lot will be permitted. Nonconformance will be cause for the rejection of the group or lot.

~~17.2~~ Any individual length of pipe that meets the test requirements is acceptable. Individual lengths that do not conform to the test requirements may be resubmitted for test provided the reason for nonconformance is established and the nonconforming portion removed.

17.2 Repair welding shall be performed using procedures and welders or welding operators that have been qualified in accordance with the ASME Boiler and Pressure Vessel Code, Section IX.

18. Retreatment

~~18.1~~ If individual lengths of pipe selected to represent any group or lot fail to conform to the test requirements, the group or lot represented may be reheat treated and resubmitted for test. The manufacturer may reheat treat the pipe, but not more than twice, except with the approval of the purchaser on the basis of satisfactory metallurgical evidence that the cause of failure of the test is curable and the quality of the material is satisfactory. ~~Retests~~

18.1 If the results of the mechanical tests of any group or lot do not conform to the requirements specified in the individual specification, retests may be made on additional lengths of pipe of double the original number from the same group or lot, each of which shall conform to the requirements specified. Only one retest of any group or lot will be permitted. Nonconformance will be cause for the rejection of the group or lot.

18.2 Any individual length of pipe that meets the test requirements is acceptable. Individual lengths that do not conform to the test requirements may be resubmitted for test provided the reason for nonconformance is established and the nonconforming portion removed.

19. Retreatment

19.1 If individual lengths of pipe selected to represent any group or lot fail to conform to the test requirements, the group or lot represented may be reheat treated and resubmitted for test. The manufacturer may reheat treat the pipe, but not more than twice, except with the approval of the purchaser on the basis of satisfactory metallurgical evidence that the cause of failure of the test is curable and the quality of the material is satisfactory.

20. Test Specimens

~~19.1~~ 20.1 Test specimens shall be taken from the ends of as-heat treated finished pipe prior to any forming operations, or being cut to length. They shall be smooth on the ends and free from burrs and flaws, except for specimens for the flattening test when made from crop ends.

~~19.2~~ 20.2 Specimens cut either longitudinally or transversely shall be acceptable for the tension test.

~~19.3~~ 20.3 If any test specimen shows flaws or defective machining, the specimen may be discarded and another substituted.

20.21. Flattening Test Requirements

~~20.1~~

21.1 *Seamless and Centrifugally Cast Pipe*—A section of pipe not less than 2½ in. [63 mm] in length shall be flattened cold between parallel plates in two steps. During the first step, which is a test for ductility, no cracks or breaks on the inside, outside, or end surfaces, except as provided for in ~~20.3.4~~ 21.3.4, shall occur until the distance between the plates is less than the value of *H* calculated as follows:

A0530_A0530M-12_2

where:

H = distance between flattening plates, in. [mm],

t = specified wall thickness, in. [mm],

D = specified or calculated (from the specified inside diameter and wall thickness) outside diameter, in. [mm], and