



Designation: A285/A285M – 12

Standard Specification for Pressure Vessel Plates, Carbon Steel, Low- and Intermediate-Tensile Strength¹

This standard is issued under the fixed designation A285/A285M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification² covers carbon steel plates of low- and intermediate-tensile strengths which may be made by killed, semi-killed, capped, or rimmed steel practices at the producer's option. These plates are intended for fusion-welded pressure vessels.

1.2 Plates under this specification are available in three grades having different strength levels as follows:

Grade	Tensile Strength, ksi [MPa]
A	45–65 [310–450]
B	50–70 [345–485]
C	55–75 [380–515]

1.3 The maximum thickness of plates under this specification, for reasons of internal soundness, is limited to a maximum thickness of 2 in. [50 mm] for all grades.

NOTE 1—For killed carbon steels only refer to the following ASTM specifications:³

- A 299/A 299M Pressure Vessel Plates, Carbon Steel, Manganese-Silicon.
- A 515/A 515M Pressure Vessel Plates, Carbon Steel, for Intermediate- and Higher-Temperature Service
- A 516/A 516M Pressure Vessel Plates, Carbon Steel, for Moderate- and Lower-Temperature Service.

1.4 For plates produced from coil and furnished without heat treatment or with stress relieving only, the additional

requirements, including additional testing requirements and the reporting of additional test results, of Specification A20/A20M apply.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

2.1 ASTM Standards:³

A20/A20M Specification for General Requirements for Steel Plates for Pressure Vessels

3. General Requirements and Ordering Information

3.1 Material supplied to this material specification shall conform to Specification A20/A20M. These requirements outline the testing and retesting methods and procedures, permitted variations in dimensions, and mass, quality and repair of defects, marking, loading, and ordering information.

3.2 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. The purchaser is referred to the listed Supplementary requirements in this specification and to the detailed requirements in Specification A20/A20M.

3.3 Coils are excluded from qualification to this specification until they are processed into finished plate. Plates produced from coil means plates that have been cut to individual lengths from coil. The processor directly controls, or is responsible for, the operations involved in the processing of coils into finished plates. Such operations include decoiling, leveling, cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved May 1, 2012. Published June 2012. Originally approved in 1946. Last previous edition approved in 2007 as A285/A285M – 03 (2007). DOI: 10.1520/A0285_A0285M-12.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-285/SA-285M in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard