
**Fine ceramics (advanced ceramics,
advanced technical ceramics) —
Test method for air-purification
performance of semiconducting
photocatalytic materials —**

**Part 4:
Removal of formaldehyde**

*Céramiques techniques — Méthodes d'essai relatives à la performance
des matériaux photocatalytiques semi-conducteurs pour la
purification de l'air —*

Partie 4: Élimination du formaldéhyde

ISO 22197-4:2021

<https://standards.iteh.ai/catalog/standards/iso/9f3c64ac-3a42-42d7-87d9-e1076c57496f/iso-22197-4-2021>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 22197-4:2021](https://standards.iteh.ai/catalog/standards/iso/9f3c64ac-3a42-42d7-87d9-e1076c57496f/iso-22197-4-2021)

<https://standards.iteh.ai/catalog/standards/iso/9f3c64ac-3a42-42d7-87d9-e1076c57496f/iso-22197-4-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols	2
5 Principle	2
6 Apparatus	3
6.1 Test equipment.....	3
6.2 Test gas supply.....	6
6.3 Photoreactor.....	6
6.4 Light source.....	6
6.5 Analytical system.....	6
7 Test piece	6
8 Procedure	7
8.1 General aspects.....	7
8.2 Pretreatment of test piece.....	7
8.3 Preparation for the test.....	8
8.4 Pretest.....	8
8.5 Removal test.....	8
9 Calculation	9
10 Test method for test pieces with lower performance	9
11 Test report	9
Bibliography	11

ISO 22197-4:2021

<https://standards.itech.ai/catalog/standards/iso/9f3c64ac-3a42-42d7-87d9-e1076c57496f/iso-22197-4-2021>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 206, *Fine ceramics*.

This second edition cancels and replaces the first edition (ISO 22197-4:2013), which has been technically revised.

The main changes to the previous edition are as follows:

- references to ISO 4892-3 and ISO 6145-7 deleted from [Clause 2](#);
- gas flow measurement changed from dry-gas basis to wet-gas basis in [6.2](#);
- tolerance on dimensions of test piece changed in [Clause 7](#);
- procedures for removing water-soluble contaminants added to [8.2](#);
- criterion for acceptable adsorption of formaldehyde added to [Clause 9](#).

A list of all parts in the ISO 22197 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for air-purification performance of semiconducting photocatalytic materials —

Part 4: Removal of formaldehyde

1 Scope

This document specifies a test method for the determination of the air-purification performance of materials that contain a photocatalyst or have photocatalytic films on the surface, usually made from semiconducting metal oxides, such as titanium dioxide or other ceramic materials, by continuous exposure of a test piece to the model air pollutant under irradiation with long-wave ultraviolet (UV) light. This document is intended for use with different kinds of materials, such as construction materials in flat sheet, board or plate shape, that are the basic forms of materials for various applications. This document also applies to structured filter materials including honeycomb-form, woven and non-woven fabrics, and to plastic or paper materials if they contain ceramic microcrystals and composites. This document does not apply to powder or granular photocatalytic materials.

This test method is usually applicable to photocatalytic materials produced for air purification. This method is not suitable for the determination of other performance attributes of photocatalytic materials, i.e. decomposition of water contaminants, self-cleaning, antifogging and antibacterial actions. It concerns the removal of formaldehyde.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10677, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Ultraviolet light source for testing semiconducting photocatalytic materials*

ISO 16000-3, *Indoor air — Part 3: Determination of formaldehyde and other carbonyl compounds in indoor air and test chamber air — Active sampling method*

ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 photocatalyst
substance that performs one or more functions based on oxidation and reduction reactions under photoirradiation, including decomposition and removal of air and water contaminants, deodorization, and antibacterial, self-cleaning and antifogging actions

3.2 photocatalytic material
material in which or on which the *photocatalyst* (3.1) is added by, for example, coating, impregnation or mixing

Note 1 to entry: Such photocatalytic materials are intended primarily for use as building and road construction materials to obtain the functions performed by photocatalysts.

3.3 zero-calibration gas
air that does not contain pollutants (i.e. in which common pollutants are below 0,01 µl/l)

Note 1 to entry: The zero-calibration gas is prepared from indoor air using a laboratory air purification system or supplied as a synthetic air in a gas cylinder.

3.4 formaldehyde gas
diluted gas of known formaldehyde concentration used for testing and calibration

3.5 test gas
mixture of air and pollutant(s) of known concentration prepared from a standard gas or a *zero-calibration gas* (3.3), to be used for the performance test of a *photocatalytic material* (3.2)

3.6 dark condition
test condition with no light irradiation by the light source for testing and room lighting

4 Symbols

For the purposes of this document, the following symbols apply.

f	flow rate of test gas converted into that at the standard state (0 °C and 101,3 kPa) (l/min)
ϕ_F	volume fraction of formaldehyde at the reactor exit (µl/l)
ϕ_{F0}	supply volume fraction of formaldehyde (µl/l)
ϕ_{FD}	volume fraction of formaldehyde at the reactor exit under dark conditions (µl/l)
n_F	removal quantity, by test piece, of formaldehyde (µmol)
R_F	removal percentage, by test piece, of formaldehyde (%)

5 Principle

This document concerns the development, comparison, quality assurance, characterization, reliability and design data generation of photocatalytic materials. The method described is intended to obtain the air-purification performance of photocatalytic materials by exposing a test piece to model polluted air under irradiation by UV light. Formaldehyde (HCHO) is chosen because it is a typical indoor air pollutant that causes the so-called sick-building syndrome. The test piece, placed in a flow-type photoreactor, is activated by UV irradiation, and adsorbs and oxidizes gas-phase formaldehyde to form carbon dioxide (CO₂) and other oxidation products. The air purification performance is determined from the net amount