

---

---

**Fine ceramics (advanced ceramics,  
advanced technical ceramics) —  
Test method for air-purification  
performance of semiconducting  
photocatalytic materials —**

**Part 5:  
Removal of methyl mercaptan**

**(standards.iteh.ai)**

*Céramiques techniques — Méthodes d'essai relatives à la performance  
des matériaux photocatalytiques semi-conducteurs pour la  
purification de l'air*

<https://standards.iteh.ai/catalog/standards/sui/6d935469-0708-4bc4-9ebe-97a2dad145f6/iso-prf-22197-5>

*Partie 5: Élimination du mercaptan méthylique*

**PROOF / ÉPREUVE**

---

---



## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO/PRF 22197-5](https://standards.iteh.ai/catalog/standards/sist/bd935469-0708-4bc4-9ebe-97a2dadd14d6/iso-prf-22197-5)

<https://standards.iteh.ai/catalog/standards/sist/bd935469-0708-4bc4-9ebe-97a2dadd14d6/iso-prf-22197-5>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Symbols</b> .....	<b>2</b>
<b>5 Principle</b> .....	<b>2</b>
<b>6 Apparatus</b> .....	<b>3</b>
6.1 Test equipment .....	3
6.2 Test gas supply .....	6
6.3 Photoreactor .....	6
6.4 Light source .....	6
6.5 Analytical system .....	6
<b>7 Test piece</b> .....	<b>7</b>
<b>8 Procedure</b> .....	<b>7</b>
8.1 General aspects .....	7
8.2 Pretreatment of test piece .....	8
8.3 Removal test .....	8
<b>9 Calculation</b> .....	<b>9</b>
<b>10 Test method for test pieces with lower performance</b> .....	<b>10</b>
<b>11 Test report</b> .....	<b>10</b>
<b>Bibliography</b> .....	<b>11</b>

iTech STANDARD PREVIEW  
(standards.iteh.ai)  
ISO/PRF 22197-5  
<https://standards.iteh.ai/catalog/standards/sist/bd935469-0708-4bc4-9ebe-97a2dadd14d6/iso-prf-22197-5>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 106, *Fine ceramics*.

This second edition cancels and replaces the first edition (ISO 22197-5:2013), which has been technically revised.

The main changes to the previous edition are as follows:

- references to ISO 2718 (withdrawn), ISO 4677-1 (withdrawn), ISO 4892-3 and ISO 6145-7 deleted from [Clause 2](#);
- precaution relating to the handling of methyl mercaptan added to [6.1](#);
- gas flow measurement changed from dry-gas basis to wet-gas basis in [6.2](#);
- tolerance on dimensions of test piece changed in [Clause 7](#);
- procedures for removing water-soluble contaminants added to [8.2](#);
- valid dark concentration level of methyl mercaptan changed in [8.3](#);
- criterion for acceptable adsorption of methyl mercaptan added to [Clause 9](#).

A list of all parts in the ISO 22197 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for air-purification performance of semiconducting photocatalytic materials —

## Part 5: Removal of methyl mercaptan

### 1 Scope

This document specifies a test method for the determination of the air-purification performance of materials that contain a photocatalyst or have photocatalytic films on the surface, usually made from semiconducting metal oxides, such as titanium dioxide or other ceramic materials, by continuous exposure of a test piece to the model air pollutant under irradiation with long-wave ultraviolet (UV) light. This document is intended for use with different kinds of materials, such as construction materials in flat sheet, board or plate shape, that are the basic forms of materials for various applications. This document also applies to structured filter materials including honeycomb-form, woven and non-woven fabrics, and to plastic or paper materials if they contain ceramic microcrystals and composites. This document does not apply to powder or granular photocatalytic materials.

This test method is usually applicable to photocatalytic materials produced for air purification. This method is not suitable for the determination of other performance attributes of photocatalytic materials, i.e. decomposition of water contaminants, self-cleaning, antifogging and antibacterial actions. It concerns the removal of methyl mercaptan.

<https://standards.iteh.ai/catalog/standards/sist/bd935469-0708-4bc4-9ebe-97a2dadd14d6/iso-prf-22197-5>

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10677, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Ultraviolet light source for testing semiconducting photocatalytic materials*

ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

#### 3.1

##### **photocatalyst**

substance that performs one or more functions based on oxidation and reduction reactions under photoirradiation, including decomposition and removal of air and water contaminants, deodorization, and antibacterial, self-cleaning and antifogging actions

### 3.2 photocatalytic material

material in which or on which the *photocatalyst* (3.1) is added by, for example, coating, impregnation or mixing

Note 1 to entry: Such photocatalytic materials are intended primarily for use as building and road construction materials to obtain the functions performed by photocatalysts.

### 3.3 zero-calibration gas

air that does not contain pollutants (i.e. in which common pollutants are below 0,01 µl/l)

Note 1 to entry: The zero-calibration gas is prepared from indoor air using a laboratory air purification system or supplied as a synthetic air in a gas cylinder.

### 3.4 standard gas

diluted gas of known concentration supplied in cylinders and certified by an accredited laboratory

### 3.5 test gas

mixture of air and pollutant(s) of known concentration prepared from a *standard gas* (3.4) or a *zero-calibration gas* (3.3), to be used for the performance test of a *photocatalytic material* (3.2)

### 3.6 dark condition

test condition with no light irradiation by the light source for testing and room lightings

## 4 Symbols

For the purposes of this document, the following symbols apply.

- $f$  air-flow rate of test gas converted into that at the standard state (0 °C and 101,3 kPa) (l/min)
- $\phi_M$  volume fraction of methyl mercaptan at the reactor exit (µl/l)
- $\phi_{M0}$  supply volume fraction of methyl mercaptan (µl/l)
- $\phi_{MD}$  average volume fraction of methyl mercaptan under dark condition (µl/l)
- $\phi_{MD1}$  volume fraction of methyl mercaptan under dark condition before the test (µl/l)
- $\phi_{MD2}$  volume fraction of methyl mercaptan under dark condition after the test (µl/l)
- $n_M$  removal quantity, by test piece, of methyl mercaptan (µmol)
- $R_M$  removal percentage, by test piece, of methyl mercaptan (%)

## 5 Principle

This document concerns the development, comparison, quality assurance, characterization, reliability and design data generation of photocatalytic materials. The method described is intended to obtain the air-purification performance of photocatalytic materials by exposing a test piece to model polluted air under irradiation by UV light. Methyl mercaptan (methanethiol, CH<sub>3</sub>SH) is chosen as a typical malodorous substance. The test piece, placed in a flow-type photoreactor, is activated by UV irradiation, and adsorbs and oxidizes gas-phase methyl mercaptan. The air purification performance is determined from the amount of the net removal of methyl mercaptan (µmol). The simple adsorption and desorption of CH<sub>3</sub>SH by the test piece (not due to photocatalysis) is evaluated by tests in the dark. It is noted that CH<sub>3</sub>SH undergoes not only adsorption but also catalytic oxidation to give other malodorous

products such as dimethyl disulphide by some test pieces under the dark condition. Therefore, this document adopts a different dark test condition from that in the other parts of the ISO 22197 series. However, this document cannot be applied to a test piece which does not give a stable concentration of methyl mercaptan in the designated time of test. The photocatalytic activity can depend on physical and chemical properties of pollutants mainly due to the adsorption process involved. For complete evaluation of air purification performance of photocatalytic materials, it is recommended that one or more suitable test methods as provided in other parts of the ISO 22197 series are combined.

## 6 Apparatus

### 6.1 Test equipment


The test equipment enables a photocatalytic material to be examined for its pollutant-removal capability by supplying the test gas continuously, while providing photoirradiation to activate the photocatalyst. It is the same as that used in the test method for the removal of nitric oxide (see ISO 22197-1) and consists of a test gas supply, a photoreactor, a light source and pollutant-measurement equipment. Since low concentrations of pollutants are to be tested, the system shall be constructed with materials of low absorption and resistant to UV radiation, e.g. acrylic resin, stainless steel, glass and fluorocarbon polymers. An example of a test system is shown in [Figure 1](#).

Tests should be carried out in a fume hood with a scrubber or similar ventilation system in order to protect the laboratory personnel from the strong, offensive odour of methyl mercaptan and its reaction products.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/PRF 22197-5](#)

<https://standards.iteh.ai/catalog/standards/sist/bd935469-0708-4bc4-9ebe-97a2dadd14d6/iso-prf-22197-5>




**Key**

- |   |                          |    |                          |
|---|--------------------------|----|--------------------------|
| 1 | test gas supply          | 9  | 4-way valve              |
| 2 | air compressor           | 10 | photoreactor             |
| 3 | air-purification system  | 11 | test piece               |
| 4 | standard gas (pollutant) | 12 | air-tight optical window |
| 5 | pressure regulator       | 13 | light source             |
| 6 | mass-flow controller     | 14 | analyser                 |
| 7 | humidifier               | 15 | vent                     |
| 8 | gas mixer                |    |                          |

**Figure 1 — Schematic diagram of the test equipment**





a) For flat test pieces

b) For filter-type test pieces

test piece length $l_1$	test piece width $l_2$	air layer thickness $l_g$
99,0 ± 1,0 mm	49,0 ± 1,0 mm	5,0 ± 0,5 mm

**Key**

- |                            |                             |
|----------------------------|-----------------------------|
| 1 test gas inlet           | 6 auxiliary plate           |
| 2 baffle                   | 7 test piece (flat-type)    |
| 3 air-tight optical window | 8 test gas outlet           |
| 4 flow channel             | 9 test piece holder         |
| 5 height-adjusting plate   | 10 test piece (filter-type) |

**Figure 2 — Cross-sectional views of photoreactor**

## 6.2 Test gas supply

The test gas supply provides air polluted with model contaminant at a predetermined concentration, temperature and humidity, and supplies it continuously to the photoreactor. It consists of flow regulators, a humidifier, gas mixers and so on. The flow rate of each gas should be within 5 % of the designated value, which is easily attained by using thermal mass-flow controllers with knowledge of temperature and gas type at calibration in accordance with ISO 6145-7. The expression of gas flow rate in this document is that converted to the standard state (0 °C and 101,3 kPa). Typical capacities of flow controller for pollutant gas, dry air and wet air are 50 ml/min, 1 000 ml/min and 1 000 ml/min, respectively. The standard methyl mercaptan gas in a cylinder, normally balanced with nitrogen, shall have a volume fraction of 100 µl/l to 1 000 µl/l.

## 6.3 Photoreactor

The photoreactor holds a planar test piece within a 50-mm-wide trough, with its surface parallel to an optical window for photoirradiation. The reactor shall be fabricated from materials that adsorb little test gas and withstand irradiation of near-UV light. The test piece shall be separated from the window by an air layer 5,0 mm ± 0,5 mm thick. The test gas shall pass only through the space between the test piece and the window. This gap shall be accurately set up according to the thickness of the test piece, for example, by using height-adjusting plates with different thicknesses, as shown in [Figure 2 a\)](#). When a filter-type material is tested, an alternative type of test-piece holder shall be used, which holds the test piece while allowing the test gas to pass through the cells of the filter under irradiation [[Figure 2 b\)](#)]. Quartz or borosilicate glass that absorbs minimal light at wavelengths longer than 300 nm shall be used for the window.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

## 6.4 Light source

The light source shall provide UV irradiation within a wavelength range of 300 nm to 400 nm. Suitable sources include the so-called black light (BL) and black light blue (BLB) fluorescent lamps, with a maximum at 351 nm, as specified in ISO 10677. The test piece shall be irradiated uniformly through the window by the light source. If testing filter-type photocatalysts, the light source shall irradiate one face of the test piece. A light source that requires warming up shall be equipped with a shutter. The distance between the light source and the reactor shall be adjusted so that the UV irradiance (300 nm to 400 nm) at the sample surface is 10 W/m<sup>2</sup> ± 0,5 W/m<sup>2</sup>. The irradiance along the length of the test piece shall also be constant within ± 5 %. The UV irradiance shall be measured with a radiometer which conforms to ISO 10677. The reactor shall be shielded from external light if necessary.

## 6.5 Analytical system

The concentration of methyl mercaptan shall be determined by gas chromatography. Either packed column or capillary column may be used as long as it can separate methyl mercaptan from related organic compounds. The detection shall be made by either a flame ionization detector (FID) or a flame photometric detector (FPD). The test gas shall be sampled with a gas-tight syringe. However, use of a six-way valve is recommended for reproducible and automatic sampling. The flow diagram when a six-way valve is used is shown in [Figure 3](#). A small sampling pump continuously ventilates the metering tube with the test gas. The pump is stopped when the test gas is sampled by switching the six-way valve. The volume of the metering tube is typically 0,5 ml, but it shall be determined by the sensitivity of the analytical system.