



SLOVENSKI STANDARD

SIST ENV 658-4:2000

01-december-2000

Advanced technical ceramics - Mechanical properties of ceramic composites at room temperature - Part 4: Determination of shear strength by compression loading of notched specimens

Advanced technical ceramics - Mechanical properties of ceramic composites at room temperature - Part 4: Determination of shear strength by compression loading of notched specimens

Hochleistungskeramik - Mechanische Eigenschaften von keramischen Verbundwerkstoffen bei Raumtemperatur - Teil 4: Bestimmung der Scherfestigkeit unter Druckbelastung von gekerbten Proben

[SIST ENV 658-4:2000](#)

<https://standards.iteh.ai/catalog/standards/sist/6c7f11bc-4e2e-4a5c-8002-1eab52110000/sist-env-658-4-2000>

Céramiques techniques avancées - Propriétés mécaniques des céramiques composites à température ambiante - Partie 4: Détermination de la résistance au cisaillement par compression d'éprouvette entaillée

Ta slovenski standard je istoveten z: ENV 658-4:1992

ICS:

81.060.30 Sodobna keramika Advanced ceramics

SIST ENV 658-4:2000 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ENV 658-4:2000](#)

<https://standards.iteh.ai/catalog/standards/sist/6c7f11bc-4e2e-4a5c-8002-4ffea5825349/sist-env-658-4-2000>

EUROPEAN PRESTANDARD

ENV 658-4:1992

PRÉNORME EUROPÉENNE

EUROPÄISCHE VORNORM

October 1992

UDC 666.7:620.176.25

Descriptors: Composite materials, reinforcing materials, ceramics, mechanical properties, determination, shear strength, notch strength, shear tests, environmental tests, test specimen

English version

Advanced technical ceramics - Mechanical properties of ceramic composites at room temperature - Part 4: Determination of shear strength by compression loading of notched specimens

iTeh STANDARD PREVIEW

Céramiques techniques avancées - Propriétés mécaniques des céramiques composites à température ambiante - Partie 4: Détermination de la résistance au cisaillement par compression d'éprouvette entaillée

Hochleistungskeramik - Mechanische Eigenschaften von keramischen Verbundwerkstoffen bei Raumtemperatur - Teil 4: Bestimmung der Scherfestigkeit unter Druckbelastung von gekerbten Proben

[SIST ENV.658-4:2000](https://standards.iteh.ai/catalog/standards/sist/6c7f11bc-4e2e-4a5c-8002-4ffea5825349/sist-env-658-4-2000)

<https://standards.iteh.ai/catalog/standards/sist/6c7f11bc-4e2e-4a5c-8002-4ffea5825349/sist-env-658-4-2000>

This European Prestandard (ENV) was approved by CEN on 1992-03-31 as a prospective standard for provisional application. The period of validity of this ENV is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the ENV can be converted into an European Standard (EN).

CEN members are required to announce the existence of this ENV in the same way as for an EN and to make the ENV available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the ENV) until the final decision about the possible conversion of the ENV into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
ENV 658-4:1992

Contents list	Page
Foreword	
1 Scope	4
2 Normative references	4
3 Principle	4
4 Definitions and symbols	4
5 Apparatus	5
6 Test specimens	5
7 Test specimen preparation	5
8 Procedure	6
9 Calculation of result	6
10 Test report	7

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ENV 658-4:2000

<https://standards.iteh.ai/catalog/standards/sist/6c7f11bc-4e2e-4a5c-8002-4ffea5825349/sist-env-658-4-2000>

Foreword

This European Prestandard has been prepared by CEN/TC 184 "Advanced technical ceramics", of which the secretariat is held by BSI.

ENV 658 has six parts:

- Part 1: Determination of tensile strength
- Part 2: Determination of compressive strength
- Part 3: Determination of flexural strength
- Part 4: Determination of shear strength by compression loading of notched specimens
- Part 5: Determination of shear strength by short span bend test (three-point)
- Part 6: Determination of shear strength by double-punch shearing

CEN/TC 184 approved this European Prestandard by resolution 4/1992 during its fifth meeting, held in Brussels on 1992-03-31.

In accordance with the CEN/CENELEC Internal Regulations, the following countries are bound to announce this European Prestandard:

Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This Part of ENV 658 specifies the conditions for the determination of the interlaminar shear strength matrix composite materials with continuous fibre reinforcement at ambient temperature, by loading a notched specimen in compression. The method applies to unidirectionally and bidirectionally reinforced ceramic matrix composites, as well as to tridirectional composites with weak reinforcement in the third direction.

NOTE : Two other methods for the determination of shear strength are given in further Parts of ENV 658. The interlaminar shear characteristics can vary significantly depending on specimen preparation and dimensions, rate of application of the test force, surface condition, etc. Comparison of test results is only valid for tests performed under identical conditions.

2 Normative references

This European Pre-Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at appropriate places in the text and in the publications listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

<https://standards.iteh.ai/catalog/standards/sist/6c7f11bc-4e2e-4a5c-8002-4ffea5825349/sist-env-658-4-2000>

- EN 10002-2 Metallic materials - Tensile testing - Part 2: Verification of the force measuring system of tensile testing machines
- ISO 3611 Micrometer callipers for external measurements

3 Principle

The test consists of measuring the force required to fracture a transversely notched test specimen of defined shape and dimensions, subjected to compressive loading in direction 1 or 2, such that failure occurs in the form of interlaminar shear in plane 12. The test is performed at constant crosshead displacement rate.

4 Definitions and symbols

4.1 Shear failure force (F)

The maximum force required to fracture a shear loaded test specimen in a test up to failure.

4.2 Interlaminar shear strength (ILSS)

Ratio calculated on the basis of the shear failure force and the shear loaded area.

NOTE : The notation ILSS is supplemented by a small letter referring to the test method described; in this case ILSS(c) for the interlaminar shear strength obtained from a compression loading test.

5 Apparatus

5.1 Test machine

The test machine shall be equipped with a system for recording the force applied to the specimen. The machine shall conform to grade 1 in EN 10002 : Part 2.

5.2 Micrometer

Micrometers used for the measurement of the specimen dimensions (distance between notches), shall be accurate to ± 0.1 mm and in accordance with ISO 3611.

NOTE : In order to prevent bending of the specimen, an appropriate tool may be used (e.g. as shown in figure 1).

6 Test specimens

The test specimen is shown in figure 2. A notch is machined on both sides. The recommended specimen dimensions are given in table 1. The notch spacing measured between the inner flanks of the notches (see figure 2) shall be determined, taking into account the requirements to obtain shear failure.

Table 1 : Recommended test specimen dimensions

<https://standards.iteh.ai/catalog/standards/sist/6c7f11bc-4e2e-4a5c-8002-25349/sist-env-658-4-2000>
(Dimensions in millimetres)

Measurement	Dimension	Tolerance
total length, L(T)	25 to 30	± 1
thickness, h	2 to 10	± 1
width, b	10 to 13	± 0.1
distance between notches, L	8 to 13	± 0.1
notch depth	$h/2 + 0.1$	± 0.05
notch width, d	0.5	± 0.1
plan parallelism of machined parts		0.05 to 0.1

7 Test specimen preparation

7.1 Machining

During cutting out, care shall be taken that the specimen axes coincide with the fibre directions. Machining parameters which avoid damage to the material shall be established and documented. These parameters shall be adhered to during test piece preparation.

7.2 Number of specimens

At least five valid test results, (see 8.4) are required.

8 Procedure

8.1 Test rate

Use a constant cross head speed which allows completion of the test within 15 s, and record the speed used.

8.2 Measurement of test specimens

Measure the width and thickness to the nearest 0,1 mm in the centre and at each end of the specimen. Report the arithmetic means of the measurement and measure the distance between the notches to the nearest 0,1 mm.

8.3 Testing technique

Install the test specimen in the test machine and set the crosshead speed. Make a record of force versus time during the test. Verify the failure location and failure mode.

8.4 Test validity

The following circumstances will invalidate a test:

- a. failure to specify and record test conditions
- b. failure to note the mode and location of fracture
- c. specimen failure not occurring in a shear plane close to the median plane delineated by the notches
- d. visible bending of the specimen or specimen slippage occurring during the test.

9 Calculation of result

The following expression shall be used to calculate the interlaminar shear strength:

$$ILSS(c) = \frac{F}{B.L}$$

where ILSS(c) is the interlaminar shear strength, in plane 12 (MPa)

F is the shear failure force (N)

b is the mean specimen width (mm)

L is the distance between the notches (mm).

NOTE : Care should be exercised in interpreting the results of the proposed testing methods to obtain absolute values of the interlaminar shear strength of ceramic matrix composites for design purposes.

10 Test report

The test report shall contain the following information:

- a) Name and address of the testing establishment
- b) Date of the test, unique identification of report and of each page, customer name and address and signatory
- c) A reference to this standard, i.e. determined in accordance with ENV 658 : Part 4
- d) Test specimen drawing showing the orthotropic directions of the material
- e) Description of the test material (material type, manufacturing code, batch number)
- f) The area and orientation of test specimens taken from a sample of material
- g) Number of test carried out and the number of valid results obtained
- h) Force and time record
- i) Individual results and arithmetic means
- j) Mode and failure location of all the test specimens used for obtaining the above results
- k) Any comments about the test or test results.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

SIST ENV 658-4:2000

<https://standards.iteh.ai/catalog/standards/sist/6c7f11bc-4e2e-4a5c-8002-4ffea5825349/sist-env-658-4-2000>