

---

---

**Textiles — Quality labelling  
specification for dehaired cashmere**

*Textiles — Spécification d'étiquetage qualité du cachemire épilé*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 5162:2023

<https://standards.iteh.ai/catalog/standards/sist/ff5256b0-45c7-4b95-bee5-b97e1f41b499/iso-5162-2023>



# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 5162:2023

<https://standards.iteh.ai/catalog/standards/sist/ff5256b0-45c7-4b95-bee5-b97e1f41b499/iso-5162-2023>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword.....	iv
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Quality labelling requirements.....</b>	<b>3</b>
4.1 Product classification.....	3
4.2 Product type.....	3
4.3 Other quality parameters.....	4
4.4 Quality labelling.....	4
<b>5 Test methods.....</b>	<b>4</b>
5.1 Standard atmospheres.....	4
5.2 Mean fibre diameter test.....	4
5.3 Mean fibre length and short fibre content test.....	4
5.4 Guard fibre content test.....	5
5.5 Foreign matter content test.....	5
5.6 Dark fibre test.....	5
5.7 Damaged fibre content test.....	5
5.8 Animal fibre, other animal fibre, non-animal matter and polymer matter content test.....	6
5.9 Moisture regain test.....	6
5.10 Grease content test.....	6
5.11 pH value test.....	6
5.12 APEO test.....	6
5.13 Calculation of conditioned weight.....	6
<b>6 Inspection rules.....</b>	<b>6</b>
6.1 Sampling.....	6
6.1.1 Lot sample proportion and number.....	6
6.1.2 Drawing of samples.....	7
6.1.3 Test specimen preparation.....	7
6.2 Inspection.....	7
<b>7 Packaging and labelling.....</b>	<b>7</b>
<b>8 Test report.....</b>	<b>8</b>
<b>Annex A (informative) Identification of skin cashmere.....</b>	<b>9</b>
<b>Bibliography.....</b>	<b>13</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarns*.

ISO 5162:2023

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Textiles — Quality labelling specification for dehaired cashmere

## 1 Scope

This document specifies the terms and definitions, labelling requirements, test methods, inspection rules, packaging, labelling and test report of pure virgin dehaired cashmere.

This document is not applicable to dehaired cashmere tops, skin cashmere, recycled cashmere and products after spinning, including yarns, fabrics, garments, apparel and accessories, household textiles, etc.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 137, *Wool — Determination of fibre diameter — Projection microscope method*

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 1833 (all parts), *Textiles — Quantitative chemical test*

ISO 3071, *Textiles — Determination of pH of aqueous extract*

ISO 3074, *Wool — Determination of dichloromethane-soluble matter in combed sliver*

ISO 17751-1, *Textiles — Quantitative analysis of cashmere, wool, other specialty animal fibers and their blends — Part 1: Light microscopy method*

ISO 17751-2, *Textiles — Quantitative analysis of cashmere, wool, other specialty animal fibers and their blends — Part 2: Scanning electron microscopy method*

ISO 18254-1, *Textiles — Method for the detection and determination of alkylphenol ethoxylates (APEO) — Part 1: Method using HPLC-MS*

ISO 18596, *Test method for staple length of dehaired cashmere — Hand-arranging method*

ISO 20705, *Textiles — Quantitative microscopical analysis — General principles of testing*

IWTO-12 *Measurement of the Mean and Distribution of Fibre Diameter Using the Sirolan-Laserscan Fibre Diameter Analyser*

IWTO 19 *Determination of Wool Base and Vegetable Matter Base of Core Samples of Raw Wool*

IWTO-33 *Method for the Determination of Oven-Dry Mass and Calculated Invoice Mass of Scoured or Carbonised Wool*

IWTO-47 *Measurement of the Mean and Distribution of Fibre Diameter of Wool using an Optical Fibre Diameter Analyser (OFDA)*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

### 3.1

#### **raw cashmere**

unprocessed down fibre from the fine, soft undercoat or underlayer of live cashmere goat producing two layers of hair, predominated by fine undercoat down with minor amount of natural *foreign matters* (3.8)

### 3.2

#### **dehaired cashmere**

processed cashmere after industrialized scouring and dehairing of *raw cashmere* (3.1)

### 3.3

#### **pure virgin cashmere**

100 % unused *dehaired cashmere* (3.2) without any other animal and non-animal fibre, which never goes through process(es) of dyeing, spinning, knitting or weaving, finishing or chemically treated (such as bleaching, decolouration, depigmentation etc.)

### 3.4

#### **skin cashmere**

cashmere recovered from the pelts of dead cashmere goat by chemical method or reagents

### 3.5

#### **recycled cashmere**

loose cashmere fibre recollected after going through processing stage(s), such as spinning, knitting, weaving, finishing, felting or used by consumers

### 3.6

#### **guard hair**

coarser hair in cashmere fibre with diameter  $\geq 30 \mu\text{m}$

### 3.7

#### **guard hair content**

percentage of mass of coarse fibre with diameter  $\geq 30 \mu\text{m}$  in the total fibre mass

### 3.8

#### **foreign matter**

non-fibrous matter such as soil, dandruff and burrs etc. included in cashmere

### 3.9

#### **foreign matter content**

number of pieces of *foreign matters* (3.8) in one gram of *dehaired cashmere* (3.2)

### 3.10

#### **dark fibre**

fibre longer than 5 mm with colour showing obvious difference from the original base colour of cashmere, including dark fibre and non-white fibre

### 3.11

#### **short fibre content**

percentage of number of cashmere fibres  $\leq 15 \text{ mm}$  in the total number of a specific mass

### 3.12

#### **damaged fibre content**

percentage of number of fibres showing fibrillation, axial splitting, ruptures, split ends, scale lifting, kinked bends or other damage in the total number of a specific number of fibres observed

**3.13****non-animal matter**

vegetable fibres, chemical fibres and/or other *polymer matter* (3.15) contained in *dehaired cashmere* (3.2)

**3.14****other animal fibre**

animal fibres other than cashmere in *dehaired cashmere* (3.2)

**3.15****polymer matter**

synthetic matter in particles or fragments of polymer matter (such as polypropylene), but not confined to those derived from packing materials

**4 Quality labelling requirements****4.1 Product classification**

Based on its natural colour, cashmere is classified into white, grey and brown cashmere, which is expressed with letter W, G and B, respectively. The characteristics of each type is described as follows:

- white cashmere(W): both cashmere and coarse hair show natural white colour;
- grey cashmere(G): cashmere shows grey, white and light brown colours, coarse hair shows light brown and white or brown colour;
- brown cashmere(B): cashmere shows brown colour, coarse hair shows dark brown colour.

In the case that different colour types are blended, colour class is assigned according to the darker one.

**4.2 Product type**

Pure virgin cashmere is classified into five types of A, B, C, D and E based on its corresponding mean fibre diameter range. It is further sub-classified by combining mean fibre length, short fibre content, guard hair content and foreign matter content, as shown in [Table 1](#).

**Table 1 — Dehaired cashmere types**

Type and grade	Mean fibre diameter ( $\mu\text{m}$ )	Mean fibre length (mm)	Short fibre content (%)	Guard hair content (%)	Foreign matter content (pcs/g)	Non-animal matter (%)
A	1	$\leq 14,9$	$\geq 36,0$	$\leq 19$	$\leq 0,15$	$\leq 40$
	2		32,0 - 36,0	19 - 21	0,15 - 0,20	40 - 70
	3		28,0 - 32,0	21 - 25	0,20 - 0,28	70 - 100
	4		$\leq 28,0$	$\geq 25$	$\leq 0,35$	$\geq 100$
B	1	14,9 - 15,9	$\geq 36,0$	$\leq 19$	$\leq 0,15$	$\leq 40$
	2		32,0 - 36,0	19 - 22	0,15 - 0,25	40 - 70
	3		28,0 - 32,0	22 - 25	0,25 - 0,30	70 - 100
	4		$\leq 28,0$	$\geq 25$	$\leq 0,60$	$\geq 100$
C	1	15,9 - 16,9	$\geq 36,0$	$\leq 19$	$\leq 0,25$	$\leq 40$
	2		32,0 - 36,0	19 - 23	0,25 - 0,30	40 - 70
	3		28,0 - 32,0	23 - 26	0,30 - 0,35	70 - 100
	4		$\leq 28,0$	$\geq 26$	$\leq 0,65$	$\geq 100$

NOTE The value range in each column is an open interval, the same value in each column is classified into its upper interval in its corresponding type and grade.

**Table 1 (continued)**

Type and grade	Mean fibre diameter ( $\mu\text{m}$ )	Mean fibre length (mm)	Short fibre content (%)	Guard hair content (%)	Foreign matter content (pcs/g)	Non-animal matter (%)
D	1	16,9 - 17,9	32,0 - 36,0	$\leq 23$	$\leq 0,30$	$\leq 40$
	2		28,0 - 32,0	23 - 27	0,30 - 0,35	40 - 70
	3		$\leq 28,0$	$\geq 27$	$\leq 0,70$	$>70$
E	1	17,9 - 19,0	28,0 - 32,0	$\leq 30$	$\leq 0,35$	$\leq 70$
	2		$\leq 28,0$	$>30$	$\leq 0,80$	$>70$

NOTE The value range in each column is an open interval, the same value in each column is classified into its upper interval in its corresponding type and grade.

### 4.3 Other quality parameters

All types of pure virgin cashmere shall meet the following requirements:

- Coefficient of variation (CV %) of mean fibre diameter  $\leq 24$  %;
- No other animal fibre shall be present;
- Dark fibre number for white cashmere: Whiter in white type(L) $\leq 15$  dark fibres/5 g; Normal white type(N):16 to 30 dark fibres/5 g;
- pH value 6,0 to 7,5;
- Residual surfactant APEO (OP, OPEO, NP, NPEO) shall be less than 50 mg/kg.

### 4.4 Quality labelling

Quality labelling codes of dehaired cashmere are composed of the English name of dehaired cashmere, cashmere-d, colour code (see 4.1 and 4.3 c) for white cashmere only) and type code (see 4.2).

EXAMPLE Dehaired white in white cashmere with mean fibre diameter 14,9  $\mu\text{m}$  to 15,9  $\mu\text{m}$ , mean fibre length 36,0 mm – 32,0 mm, short fibre content 19 % – 22 %, guard hair content  $\leq 0,25$  % - 0,30 %, foreign matter content 50 pcs/g, and other parameters meet all requirements described in 4.3, its quality labelling code is “cashmere-d-W-(L)-B2232”, which represents dehaired white cashmere with less than 15 dark fibres in 5/g of mean fibre diameter type B with mean fibre length grade 2, short fibre content grade 2, guard hair content grade 3 and foreign matter content grade 2.

## 5 Test methods

### 5.1 Standard atmospheres

The standard atmosphere for conditioning and testing textiles in ISO 139 shall be used.

### 5.2 Mean fibre diameter test

The mean fibre diameter test shall be in accordance with the methods given in either: ISO 137, IWTO-12 or IWTO-47.

In case issues arise concerning the test results, ISO 137 shall be used to distinguish the results.

### 5.3 Mean fibre length and short fibre content test

The mean fibre length and short fibre content test shall be as described in ISO 18596.



#### 5.4 Guard fibre content test

Condition the test specimen as described in ISO 139 and then take 2 test specimens, mass of each 2 g, accurate to 0,000 1 g. Place each test specimen respectively onto a board or a flat surface exhibiting distinctive colour difference from the fibre to be tested. Pick out all the guard fibres in accordance with ISO 20705. Weigh and record the mass, with an accuracy of 0,000 1 g. Calculate guard fibre percentage using [Formula \(1\)](#):

$$B_c = \frac{m_c}{m} \times 100 \quad (1)$$

where

- $B_c$  is the guard hair content, in %;
- $m_c$  is the mass of guard hair, in gram (g);
- $m$  is the mass of test specimen, in gram (g).

Take the mean value of the two test specimens as the test result. In case the absolute difference between the two test results exceeds 0,05 %, a third test specimen shall be tested. Take the mean value of the 3 test results from the 3 test specimens as the final result, rounding off to 2 decimals.

#### 5.5 Foreign matter content test

Weigh two test specimens, mass of each 1 g, accurate to 0,01 g. Put each test specimen on a working table with its surface exhibiting a distinctive colour difference from the fibre to be tested (or a bench magnifier), pick out each dandruff and burr or other non-fibrous matter from every fibre and those dropped from the test specimen, count and record the number. Foreign matter content of each test specimen is expressed as how many pieces per gram “xx pcs/g”.

Take the mean value of the 2 foreign matter test results as the final result. If the absolute difference between the two test specimens exceeds 10 pcs/g, a third test specimen shall be tested. In this case, take the mean value of the 3 test results from the 3 test specimens as the final result, rounding off the calculated result to an integer.

#### 5.6 Dark fibre test

Weigh two test specimens each of 5 g, accurate to 0,01 g. Loosen the test specimen on an appropriate plate. Place the test specimen in an illuminated desktop magnifier (6x to 8x) and on white lining paper. Carry out the test under a white light source (5 500 °K to 6 500 °K and not less than 400 lx). Pick out with tweezers dark fibre equal to or longer than 5 mm in white cashmere and record the number. The number of dark fibres in each lot of sample is expressed as how many pieces per 5 gram “xx pcs/5 g”.

Take the mean value of the 2 test specimens as the test result, rounding off to an integer.

#### 5.7 Damaged fibre content test

Prepare a test specimen as described in ISO 17751-1, observe at least 1 000 fibres by light microscopy at the magnification of 500x. Determine whether a fibre is a damaged fibre by comparing with damaged cashmere fibre images shown in [Annex A](#). Record the number of damaged fibres and calculate the damaged fibre percentage of the number in the total number of observed fibres.

## 5.8 Animal fibre, other animal fibre, non-animal matter and polymer matter content test

The animal fibre and other animal fibre test shall be in accordance with ISO 17751-1 or ISO 17751-2; The test on non-animal matter including polymeric matter shall be in accordance with the ISO 1833 series or IWTO 19.

## 5.9 Moisture regain test

The moisture regain test shall be in accordance with IWTO-33.

## 5.10 Grease content test

The grease content test shall be in accordance with ISO 3074.

## 5.11 pH value test

The pH value test shall be in accordance with ISO 3071.

## 5.12 APEO test

The APEO test shall be in accordance with ISO 18254-1.

## 5.13 Calculation of conditioned weight

Conditioned weight can be calculated in accordance with [Formula \(2\)](#). The moisture regain of dehaired cashmere is as per commercial conventional moisture regain.

$$m = m_1 \times \frac{(100 + W_0) \times (100 - Y_1)}{(100 + W_1) \times (100 - Y_0)} \quad (2)$$

where

$m$  is the conditioned mass, in kilogram (kg);

$m_1$  is the tested mass, in kilogram (kg);

$W_0$  is the conditioned moisture regain, in % (conventional moisture regain of dehaired cashmere is 17 %);

$W_1$  is the tested moisture regain, in %;

$Y_0$  is the conditioned grease content, in % (conventional grease content of dehaired cashmere is 1,5 %);

$Y_1$  is the tested grease content, in %.

## 6 Inspection rules

### 6.1 Sampling

#### 6.1.1 Lot sample proportion and number

Draw samples at 30 % if a lot size is  $\leq 10$  bales; for a lot size larger than 10, draw at 20 % of the increased bale number exceeding 10; draw at 30 % of the increased bale number exceeding 20 bales in a lot; an incomplete bale is counted as one bale when calculating the number of bales to be drawn. The total