



Designation: C1227 – 12

Standard Specification for Precast Concrete Septic Tanks¹

This standard is issued under the fixed designation C1227; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This specification covers design requirements, manufacturing practices, and performance requirements for monolithic or sectional precast concrete septic tanks.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- A82/A82M Specification for Steel Wire, Plain, for Concrete Reinforcement
- A185/A185M Specification for Steel Welded Wire Reinforcement, Plain, for Concrete
- A496/A496M Specification for Steel Wire, Deformed, for Concrete Reinforcement
- A497/A497M Specification for Steel Welded Wire Reinforcement, Deformed, for Concrete
- A615/A615M Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement
- A706/A706M Specification for Low-Alloy Steel Deformed and Plain Bars for Concrete Reinforcement
- A996/A996M Specification for Rail-Steel and Axle-Steel Deformed Bars for Concrete Reinforcement
- C33 Specification for Concrete Aggregates
- C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens

- C94/C94M Specification for Ready-Mixed Concrete
- C125 Terminology Relating to Concrete and Concrete Aggregates
- C150 Specification for Portland Cement
- C231 Test Method for Air Content of Freshly Mixed Concrete by the Pressure Method
- C260 Specification for Air-Entraining Admixtures for Concrete
- C330 Specification for Lightweight Aggregates for Structural Concrete
- C494/C494M Specification for Chemical Admixtures for Concrete
- C595 Specification for Blended Hydraulic Cements
- C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C685/C685M Specification for Concrete Made by Volumetric Batching and Continuous Mixing
- C890 Practice for Minimum Structural Design Loading for Monolithic or Sectional Precast Concrete Water and Wastewater Structures
- C990 Specification for Joints for Concrete Pipe, Manholes, and Precast Box Sections Using Preformed Flexible Joint Sealants
- C1116/C1116M Specification for Fiber-Reinforced Concrete
- C1644 Specification for Resilient Connectors Between Reinforced Concrete On-Site Wastewater Tanks and Pipes

2.2 ACI Standard:³

- ACI 318 Building Code Requirements for Reinforced Concrete

2.3 NSF/ANSI Standard:⁴

- NSF/ANSI 46–2005 Evaluation of Components and Devices used in Wastewater Treatment Systems

3. Terminology

3.1 For definitions of terms relating to concrete, see Terminology C125.

3.2 *Definitions of Terms Specific to This Standard:*

¹ This specification is under the jurisdiction of ASTM Committee C27 on Precast Concrete Products and is the direct responsibility of Subcommittee C27.30 on Water and Wastewater Containers.

Current edition approved June 1, 2012. Published July 2012. Originally approved in 1993. Last previous edition approved in 2010 as C1227 – 10a. DOI: 10.1520/C1227-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.aci-int.org>.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

3.2.1 *access opening*, *n*—hole in the top slab used to gain access to the inside of the tank for the purpose of cleaning and removing sludge without a person actually having to enter the tank.

3.2.2 *air scum volume*, *n*—number of cubic inches (centimetres) in the space between the liquid surface and the underside of the top slab.

3.2.3 *baffle*, *n*—device placed in a tank to dissipate energy, direct flow, retain solids, and/or draw liquid off at a specific depth.

3.2.4 *baffle, inlet*, *n*—tee or wall segment at or near the inlet pipe of a tank designed to direct flow below the liquid surface.

3.2.5 *baffle, outlet*, *n*—tee or wall segment at or near the outlet pipe of a tank designed to collect flow from the liquid effluent layer.

3.2.6 *cement*, *n*—powdered substance of lime and clay mixed with water to make concrete.

3.2.7 *connector*, *n*—device that provides a flexible seal between a pipe and the precast concrete tank.

3.2.8 *corrosion-resistant*, *adj*—materials that are resistant to deterioration when in contact with the corrosive materials found in a septic tank.

3.2.9 *dead load*, *n*—mass of a structure and all permanent loads imposed on the structure (that is, soil).

3.2.10 *detention time*, *n*—average length of time a unit volume of liquid or a suspended particle remains in a tank; mathematically, it is the volume of liquid in the tank divided by the flow rate through the tank.

3.2.11 *effective volume*, *n*—maximum amount of liquid and solids that can be contained in a tank under normal operating conditions.

3.2.12 *effluent filter device*, *n*—device, made from corrosion-resistant materials, that separates solid material from tank liquid before the liquid exits the tank.

3.2.13 *grinder*, *n*—device for grinding and flushing cooking wastes; also known as a garbage disposal.

3.2.14 *inspection opening*, *n*—hole in the top slab used for the purpose of observing conditions inside the tank.

3.2.15 *joint*, *n*—physical separation where two pieces of precast concrete are in contact.

3.2.16 *liquid effluent layer*, *n*—area in a tank made up of liquids and semibuoyant waste particles after the sludge and scum waste have separated and settled.

3.2.17 *live load*, *n*—loads exerted on or above a structure when the source of the load is dynamic and transient.

3.2.18 *non-sealed joint*, *n*—joint in which sealant is not used but in which a machined fit will minimize the movement of liquid from one side of a precast concrete wall to the opposite side.

3.2.19 *owner*, *n*—is by definition, end user, customer, or purchaser.

3.2.20 *rated volume*, *n*—depth from the bottom of a septic tank to the invert of the outlet pipe.

3.2.21 *scum layer*, *n*—buoyant waste floating near the surface of liquid, consisting of lighter-than-water materials, such as greases and soaps.

3.2.22 *sealed joint*, *n*—joint that is sealed to prevent liquid passing from one side of a precast concrete wall to the opposite side.

3.2.23 *septic tank system*, *n*—anaerobic digestion chamber in which domestic sewage is received and retained, and from which the liquid effluent, which is comparatively free from settleable and floating solids, is then discharged.

3.2.24 *sludge layer*, *n*—heavier waste solids that separate and settle at the bottom of a tank.

3.2.25 *tee*, *n*—“T”-shaped pipe fitting made of corrosion-resistant materials used to connect horizontal piping with vertical piping and used to provide access for cleaning piping.

4. Ordering Information

4.1 The purchaser shall include the following information in bidding documents and on the purchase order, as applicable to the units being ordered:

4.1.1 Reference to this specification and date of issue.

4.1.2 Quantity, that is, number of units ordered.

4.1.3 Capacity of tank in gallons or litres.

4.1.4 Special cement requirements including moderate sulfate-resisting cement, Specification **C150** Type II, or highly sulfate-resisting cement, Specification **C150**, Type V. If the purchaser does not stipulate, the manufacturer shall use any cement meeting the requirements of Specification **C150** or **C595**.

4.1.5 Acceptance will be based on a review of the calculations or on proof tests.

4.1.6 Design requirements such as depth of earth cover, live load applied at the surface, and ground water level.

4.1.7 Testing for water leakage shall not be required at the job site unless specifically required by the purchaser.

4.1.8 Manufacturer is permitted to require testing on site prior to backfill.

5. Materials and Manufacture

5.1 *Cement*—Portland cement shall conform to the requirements of Specification **C150** or shall be portland blast-furnace slag cement or portland-pozzolan cement conforming to the requirements of Specification **C595**.

5.2 *Aggregates*—Aggregates shall conform to Specification **C33** and lightweight aggregates shall conform to Specification **C330**, except that the requirements for grading shall not apply.

5.3 *Water*—Water used in mixing concrete shall be clean and free of injurious amounts of oils, acids, alkalies, salts, organic materials, or other substances that will be incompatible with concrete or steel.

5.4 *Admixtures*—Admixtures, when used, shall conform to Specification **C494/C494M** or Specification **C618** and shall not be injurious to other products used in the concrete.

5.4.1 *Air-Entraining Admixtures*—Air-entraining admixtures conforming to Specification **C260** shall be used when there is a risk that the concrete will be exposed to freezing and

thawing. Then the concrete mixture shall contain 5.5 ± 1.5 % air by volume as determined by Test Method **C231**.

5.5 Steel Reinforcement—Steel reinforcement shall conform to Specification **A82/A82M** or **A496/A496M** for wire, Specification **A185/A185M** or **A497/A497M** for wire fabric, or Specifications **A615/A615M**, **A706/A706M**, or **A996/A996M** for steel reinforcement bars.

5.5.1 Locating Reinforcement—Reinforcement shall be placed in the forms as required by the design.

5.5.2 Holding Reinforcement in Position During Pouring Placement—Reinforcement shall be securely held in place by tying, clipping, or welding to maintain position during concrete placing operations. Welding procedures shall conform to the appropriate material specification. Chairs, bolsters, braces, and spacers in contact with forms shall have a corrosion-resistant surface.

5.6 Concrete Mixtures—The aggregates, cement, and water shall be proportioned and mixed to produce a homogeneous concrete meeting the requirements of this specification, and in accordance with Specification **C94/C94M** or Specification **C685/C685M**. The concrete shall have a maximum water cementitious materials ratio of 0.45.

5.7 Forms—The forms used in manufacture shall be sufficiently rigid and accurate to maintain the dimensions of the structure within the stated tolerances. All casting surfaces shall be of smooth nonporous material. Form releasing agents used shall not be injurious to the concrete.

5.8 Concrete Placement—Concrete shall be placed in the forms at a rate to allow the concrete to consolidate in all parts of the form, and around all reinforcement steel and embedded fixtures without segregation of materials.

5.9 Curing—The precast concrete sections shall be cured by any method or combination of methods that will develop the specified compressive strength at 28 days or less.

5.10 Concrete Quality—The quality of the concrete shall be in accordance with the chapter on concrete quality in ACI 318, except for frequency of tests, which shall be specified by the purchaser. Concrete compressive strength tests shall be conducted in accordance with Test Method **C39/C39M**.

5.11 Fibers—Polypropylene or polyolefin fibers are only permitted as a secondary reinforcing material, at the manufacturer's option, in precast concrete septic tanks. For the purposes of this specification, secondary reinforcing material is only used to resist temperature and shrinkage effects. Only Type III conforming to the requirements of Specification **C1116/C1116M** shall be accepted.

5.12 Sealants—Flexible sealants used in the manufacture and installation of tanks shall conform to Specification **C990**. Rigid (mortar) sealing of tank sections is not permitted.

5.13 Pipe Connections—Pipe-to-tank connections shall use flexible connectors conforming to the requirements of Specification **C1644**.

6. Structural Design Requirements

6.1 Structural design of septic tanks shall be by calculation or by performance.

6.1.1 Design by calculation shall be completed using the Strength Design Method (ultimate strength theory) or the Alternate Design Method (working stress theory) outlined in ACI 318. The Strength Design Method is outlined in Chapter 9 and the Alternate Design Method is in Appendix A.

6.1.2 Design by performance requires the manufacturer to demonstrate that failure will not occur by physically applying loads to the product. The load applied shall be 1.5 times the anticipated actual loads.

6.1.3 Tanks shall be designed so that they will not collapse or rupture when subjected to anticipated earth and hydrostatic pressures when the tanks are either full or empty.

6.1.4 All dead and live loads shall be considered in the design. For tanks located in residential lawn areas and not subject to loads greater than the minimum stated herein, the minimum live load shall be 100 lbf/ft² (5 kPa) or a concentrated load of 2250 lbs (10 kN) applied to a 10 by 10 in. (250 by 250 mm) area, which ever produces the greatest stress on the structure. Concentrated loads shall be distributed in accordance with provisions of Practice **C890**. Loading conditions other than described herein shall conform with provision of Practice **C890**.

6.1.5 After conditions are established, loads from Practice **C890** shall be used for design. Unless heavier live loads are expected, the minimum live load at the surface for design shall be 300 lbf/ft² (14 kPa).

6.1.6 The live loads imposed at lifting points shall be considered in the design of the structure.

6.1.7 Inserts embedded in the concrete shall be designed for an ultimate load that is four times the working load (Factor of Safety = 4).

6.2 Concrete Strength—The minimum compressive strength (f'c) for designs shall be 4000 psi (28 MPa) at 28 days of age.

6.3 Reinforcing Steel Placement—The concrete cover for reinforcing bars, mats, or fabric shall not be less than 1 in. (25 mm).

6.4 Openings—The structural design shall take into consideration the number, placement, and size of all openings.

6.5 Lift equipment shall be designed for an ultimate load that is five times the working load (Factor of Safety = 5).

7. Physical Design Requirements

7.1 Capacity—Sizes are generally specified by local regulations and they shall supersede the following guidelines. When local regulations are not available, the following minimum sizes will be required:

1-bedroom residence	750 gal (2800 L)
2 and 3-bedroom residence	1000 gal (3800 L)
4-bedroom residence	1200 gal (4500 L)
5-bedroom residence	1400 gal (5300 L)
Motels	100 gpd/unit (380 Lpd/unit)
Restaurant	70 gpd/seat (265 Lpd/seat)
Office building	20 gpd/seat (75 Lpd/seat)
Additional capacity is required when grinders are available	

7.2 Shape:

7.2.1 There shall be a total of no less than 25 ft² (2.3 m²) of surface liquid area and a total inside length of at least 6 ft (2 m) between inlet and outlet of the tank.