



Designation: D4797 – 12

# Standard Test Methods for Gravimetric Analysis of White and Yellow Thermoplastic Traffic Marking<sup>1</sup>

This standard is issued under the fixed designation D4797; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 These test methods cover procedures for the gravimetric analysis of the binder and hydrochloric Acid (HCL) insoluble particles in white and yellow thermoplastic traffic markings. The HCL insoluble particles can be retroreflective optics, such as glass beads or some other type of retroreflective optic, or non-retroreflective particles such as silica sand, or a combination of any two or more of these materials.

1.2 This standard does not address the physical separation and the individual quantification of each component when a mixture of two or more HCL insoluble materials is present. Rather it requires the user to visually evaluate the HCL insoluble material (obtained from following this test method) and report the types of materials present.

1.3 This standard does not purport to address the titanium dioxide or lead chromate pigment measurement (after ashing) which is detailed in Test Methods D1394 and D126.

1.4 This standard will attempt to address the interference of organic pigments with the binder results.

1.5 The analytical procedures appear in the following order:

	Sections
Percent Binder	10
Percent Retroreflective Optics or Non-Retroreflective Particles	11

1.6 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

<sup>1</sup> These test methods are under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of Subcommittee D01.44 on Traffic Coatings.

Current edition approved June 1, 2012. Published August 2012. Originally approved in 1988. Last previous edition approved in 2007 as D4797 – 88 (2007). DOI: 10.1520/D4797-12.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

D126 Test Methods for Analysis of Yellow, Orange, and Green Pigments Containing Lead Chromate and Chromium Oxide Green

D1394 Test Methods for Chemical Analysis of White Titanium Pigments

D7307 Practice for Sampling of Thermoplastic Traffic Marking Materials

D7308 Practice for Sample Preparation of Thermoplastic Traffic Marking Materials

## 3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *ash, n*—the inorganic components of thermoplastic traffic marking including the pigment, glass spheres, and filler.

3.1.2 *binder, n*—the organic components (resinous components) of thermoplastic traffic marking that bind the pigments, glass spheres, and filler together as a unit.

3.1.3 *filler, n*—the inorganic components of thermoplastic traffic marking not including the pigments, retroreflective optics, or non-retroreflective particles that are considered functional.

3.1.4 *retroreflective optic, n*—functional particle that reflects and returns a relatively high proportion of light in a direction close to the light source. This characteristic is maintained over a wide variation of the angle made by the incident light ray and normal to the retroreflective surface. This includes a single component structure such as a spherical glass bead or a multi component structure with a core and a surface covered with a small retroreflector.

3.1.5 *non-retroreflective particles, n*—functional particle that is insoluble in HCL, such as aluminum oxide, ground glass, quartz, etc., that are added for skid resistance or other non-retroreflective functional purpose.

3.1.6 *pigment, n*—titanium dioxide, lead chromate colorants, and/or organic pigments.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.