### INTERNATIONAL STANDARD

ISO 17639

Second edition

# Destructive tests on welds in metallic materials — Macroscopic and microscopic examination of welds

Essais destructifs des soudures sur matériaux métalliques — Examens macroscopique et microscopique des assemblages soudés

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/PRF 17639 https://standards.iteh.ai/catalog/standards/sist/6ad32649-920e-48d8-a933-465f9233dafc/iso-prf-17639

# PROOF/ÉPREUVE



Reference number ISO 17639:2021(E)

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO/PRF 17639</u> https://standards.iteh.ai/catalog/standards/sist/6ad32649-920e-48d8-a933-465f9233dafc/iso-prf-17639



#### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

| Contents |                                   |   |    |  |  |  |
|----------|-----------------------------------|---|----|--|--|--|
| Forev    | vord                              |   | iv |  |  |  |
| 1        | Scop                              | oe  | 1  |  |  |  |
| 2        | Norr                              | mative references                               | 1  |  |  |  |
| 3        | Tern                              | ns and definitions                              | 1  |  |  |  |
| 4        | Symbols and abbreviated terms     |   |    |  |  |  |
| 5        | Prin                              | ciple   | 2  |  |  |  |
| 6        | Purpose of the test               |   |    |  |  |  |
| 7        |                                   | oval of test specimens                          |    |  |  |  |
| 8        | Test procedure                    |   |    |  |  |  |
|          | 8.1                               | General   | 3  |  |  |  |
|          | 8.2                               | Test specimen preparation                       | 3  |  |  |  |
|          | 8.3                               | Surface finish                                  |    |  |  |  |
|          | 8.4                               | Etching methods                                 | 4  |  |  |  |
|          | 8.5                               | Etchants  | 4  |  |  |  |
|          | 8.6                               | Safety measures                                 | 4  |  |  |  |
| 9        | Examination                       |   |    |  |  |  |
| 10       | Designation iTeh STANDARD PREVIEW |   |    |  |  |  |
| 11       | Test                              | report Tell STANDARD PREVIEW                    | 7  |  |  |  |
| Anne     | <b>x A</b> (in                    | nformative) Example of a test reports. iteh.ai) | 8  |  |  |  |
|          | -                                 | hy second residence                             |    |  |  |  |

<u>ISO/PRF 17639</u> https://standards.iteh.ai/catalog/standards/sist/6ad32649-920e-48d8-a933-465f9233dafc/iso-prf-17639

#### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*, in collaboration with the European Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 17639:2003), which has been technically revised.

The main changes are as follows:

- <u>Clause 2</u> has been updated;
- the designations according to ISO/TR 15608 have been updated in Clause 10.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <a href="https://www.iso.org/members.html">www.iso.org/members.html</a>.

1

## Destructive tests on welds in metallic materials — Macroscopic and microscopic examination of welds

#### 1 Scope

This document gives recommendations for specimen preparation, test procedures and their main objectives for macroscopic and microscopic examination.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6520-1, Welding and allied processes — Classification of geometric imperfections in metallic materials — Part 1: Fusion welding

#### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- https://standards.iteh.ai/catalog/standards/sist/6ad32649-920e-48d8-a933-— IEC Electropedia: available at https://www.electropedia.org/

#### 3.1

#### macroscopic examination

examination of a test specimen by the naked eye, or under low magnification (generally less than ×50), with or without etching

#### 3.2

#### microscopic examination

examination of a test specimen by microscope with a magnification of generally ×50 to ×500, with or without etching

#### 3.3

#### examiner

person who performs the macroscopic examination (3.1) and/or microscopic examination (3.2)

#### 4 Symbols and abbreviated terms

For the purposes of this document, the following abbreviations apply.

- A macroscopic examination
- I microscopic examination
- E etched
- U unetched

Symbols for parent metals are given as material grouping system in ISO/TR 15608.

© ISO 2021 – All rights reserved **PROOF/ÉPREUVE** 

#### ISO 17639:2021(E)

The same grouping systems shall also be used for weld metal. For consumables not classified under ISO/TR 15608, the consumables used shall be identified in the report.

The abbreviations for etchants should be taken from ISO/TR 16060 whenever applicable.

NOTE A trademark can be used if ISO/TR 16060 is not applicable.

#### 5 Principle

Macroscopic and microscopic examination is used to reveal the macroscopic or microscopic features of a welded joint, usually by the examination of transverse sections.

This is done by visual and/or optical examination of the prepared surface, before or after etching.

#### 6 Purpose of the test

The purpose of macroscopic and microscopic examinations is to assess the structure (including grain structure, morphology and orientation, precipitates and inclusions) independently and/or in relation to various cracks and cavities. Sections can also provide a record of sample shape in the planes of the section. Table 1 gives guidance on the assessment of features which can be detected by macroscopic and microscopic examination.

### 7 Removal of test specimens TANDARD PREVIEW

Test specimens are generally oriented perpendicular to the weld axis (transverse section), including the weld deposit and heat affected zones on both sides of the weld However, test specimens may also apply to other orientations.

The location, orientation and number of test pieces should be specified prior to testing, for example by reference to an application standard.

465(9233dafc/iso-prf-17639)

Table 1 — Guidelines for assessment of features by microscopic and macroscopic examination

| Features                        | Defect in ac-<br>cordance with<br>ISO 6520-1 | Macro exam-<br>ination with-<br>out etching | Macro exam-<br>ination with<br>etching | Micro exam-<br>ination with-<br>out etching | Micro exam-<br>ination with<br>etching |
|---------------------------------|--|---|--|---|--|
| Hot cracks                      | 100  | X   | X                                      | X   | X                                      |
| Cold cracks                     | 100  | X   | X                                      | X   | X                                      |
| Lamellar tearing                | 100  | X   | X                                      | X   | X                                      |
| Cavities                        | 200  | X   | X                                      | X   | X                                      |
| Inclusions                      | 300  | X   | X                                      | X   | X                                      |
| Lack of fusion/penetra-<br>tion | 400  | X   | X                                      | X   | X                                      |
| Geometrical shape               | 500  | X   | X                                      | _   | _                                      |
| Heat affected zone              | _  | _   | X                                      | _   | X                                      |
| Runs and layers                 | _  | _   | X                                      | _   | (X)                                    |
| Grain boundary                  | _  | _   | _                                      | (X)   | X                                      |
| Grain structure                 | _  | _   | _                                      | _   | X                                      |
| Solidification structure        | _  | _   | X                                      | _   | X                                      |

X features revealed

NOTE A number of the features listed can be beyond the resolution of an optical microscope, e.g. precipitates and inclusions.

<sup>(</sup>X) features can be revealed or not

**Table 1** (continued)

| Features                              | Defect in accordance with ISO 6520-1 | Macro exam-<br>ination with-<br>out etching | Macro exam-<br>ination with<br>etching | Micro exam-<br>ination with-<br>out etching | Micro exam-<br>ination with<br>etching |
|---------------------------------------|--------------------------------------|---|--|---|--|
| Joint preparation                     | _                                    | (X)   | X                                      | X   | X                                      |
| Direction of rolling/<br>extrusion    |                                      | _   | X                                      | _   | X                                      |
| Direction of fibre structure (grains) |                                      | _   | X                                      | _   | X                                      |
| Segregation                           | _                                    | _   | X                                      | _   | X                                      |
| Precipitation                         | _                                    | _   | _                                      | _   | X                                      |
| Repair and non-con-<br>formance       |                                      | (X)   | X                                      | (X)   | X                                      |
| Mechanical/thermal effects            | _                                    | _   | X                                      | _   | X                                      |

X features revealed

NOTE A number of the features listed can be beyond the resolution of an optical microscope, e.g. precipitates and inclusions.

## 8 Test procedure Teh STANDARD PREVIEW

#### 8.1 General

(standards.iteh.ai)

The following information shall be considered:

ISO/PRF 17639

- parent metals and welding consumables; ndards/sist/6ad32649-920e-48d8-a933-465f9233dafc/iso-prf-17639
- object of the test;
- composition/name of the etchant;
- surface finish (see <u>8.3</u>);
- etching methods (see <u>8.4</u>);
- additional measures (see <u>8.6</u>);
- any additional requirements (e.g, etching time).

#### 8.2 Test specimen preparation

The test specimen shall be prepared for examination by cutting, mounting, grinding and/or polishing and/or etching as appropriate (see ISO/TR 16060). The surface to be examined shall not be adversely influenced by these processes.

#### 8.3 Surface finish

The requirement for surface finish depends on aspects such as:

- type of examination (macroscopic or microscopic);
- type of material;
- documentation (such as photographs).

<sup>(</sup>X) features can be revealed or not

#### ISO 17639:2021(E)

NOTE Details of the grinding and polishing media and methods of grinding and polishing are given in  $ISO/TR\ 16060$ .

#### 8.4 Etching methods

The method of etching shall be specified prior to etching. The most common methods are:

- etching by immersing the test specimen in the etchant;
- etching by swabbing the surface of the test specimen;
- electrolytic etching.

Other methods may be used but should be specified, e.g. by reference to an application standard.

When etching is completed, the test specimen should be washed and dried.

NOTE To avoid deterioration of the etched specimen, precautions can be taken, such as storage of the specimens in a protected atmosphere, or for macroscopic specimen the application of a lacquer or varnish protection of the etched surface.

#### 8.5 Etchants

Typical etchants for various parent metals, weld deposits, purposes and types of examination are given in ISO/TR 16060.

Depending on the information required, the type and concentration of the etchant as well as the etching temperature and time may vary according to the material and type of examination.

For similar joints, different etchants may be used.

ISO/PRF 17639

**8.6 Safety measures** https://standards.iteh.ai/catalog/standards/sist/6ad32649-920e-48d8-a933-465f9233dafc/iso-prf-17639

The following safety measures shall be observed:

- wear eye or face protection, as appropriate;
- handle etchants with suitable gloves or tongs;
- mixtures shall be made in a fume cupboard or under a fume hood;
- always pour acid into water and not vice versa;
- always pour solute into solvent; i.e. the smaller quantity (solute) into the larger quantity (solvent).

#### 9 Examination

The prepared surface may be examined before and/or after etching, as appropriate, or in accordance with the relevant standards and/or specifications.

#### 10 Designation

The examination shall be designated as follows:

- reference to this document (i.e. ISO 17639:—);
- type of examination (macroscopic or microscopic examination);
- unetched or etched;
- object of the test (weld metal and/or parent metal);

- welded joints (parent metal left, parent metal right and weld metal);
- etchant (number of the table in ISO/TR 16060).

Some welding consumables cannot be classified under ISO/TR 15608, the consumables used shall be identified in the report.

The designation may be given in a full or a shortened version (see EXAMPLES 1 and 2).

NOTE The object of the test is expressed between hyphens.

EXAMPLE 1 Full version

A microscopic examination with the following conditions:

- Etched:
- Object of the test: 43;
- Parent metal left: 5.4

right: <u>8.2</u>

- Consumable: 43
- Etchant:



a) Object of the test: Weld metal only 465f9233dafc/iso-prf-17639

Examination - ISO 17639 - I - E - 43 - 5.4 / 8.2 / 43 / xy

where

ISO 17639 is the reference to this document;

- I is the microscopic examination;
- E is the = etched;
- is the object of the test;
- 5.4 is the steel with 7,0 % <  $Cr \le 10,0$  % and 0,7 % <  $Mo \le 1,2$  %;
- is the austenitic stainless steel with Cr > 19%:
- is the weld metal: Ni/Fe/Cr/Mo with Ni max. 40 %;
- xy is the etchant.

b) Object of the test: Weld metal and parent metal left

Examination - ISO 17639 - I - E - 43, 5.4 - 5.4 / 8.2 / 43 / xy

#### ISO 17639:2021(E)

#### where

ISO 17639 is the reference to this document;

I is the microscopic examination;

E is the etched:

43, 5.4 is the object of the test;

5.4 is the steel with 7.0 % <  $Cr \le 10.0$  % and 0.7 % <  $Mo \le 1.2$  %;

8.2 is the austenitic stainless steel with Cr > 19 %;

is the weld metal: Ni/Fe/Cr/Mo with Ni max. 40 %;

xy is the etchant.

c) Object of the test: Weld metal and parent metals left and right

Examination - ISO 17639 - I - E - 43, 5.4, 8.2 - 5.4 / 8.2 / 43 / xy

where

ISO 17639 is the reference to this document;

I is the microscopic examination, DARD PREVIEW

E is the etched; (standards.iteh.ai)

43, 5.4, <u>8.2</u> is the object of the test; <u>ISO/PRF 17639</u>

5.4 is the steel with 7,0 % <  $Cr_{45-10.0}$  % and 0,7 %  $Mo \le 1,2$  %;

8.2 is the austenitic stainless steel with Cr > 19%;

is the weld metal: Ni/Fe/Cr/Mo with Ni max. 40 %;

xy is the etchant.

EXAMPLE 2 Shortened version

A macroscopic examination with the following conditions:

— Etched;

Object of the test: 22.4;

— Parent metal left: 22.4

right: 22.4

— Weld metal: 22.4

— Etchant: xy

NOTE Object of the test (22.4) means weld metal and parent metal left and right.