



Designation: C722 – 04 (Reapproved 2012)

Standard Specification for Chemical-Resistant Monolithic Floor Surfacing¹

This standard is issued under the fixed designation C722; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the requirements for aggregate-filled, resin-based, monolithic surfacings for use over concrete floors in areas where chemical resistance and the protection of concrete are required.

1.2 The application methods for these floor surfacings include troweled, broadcast, slurry broadcast, self-leveling, sprayed, and reinforced. The resin chemistries include epoxy, urethane, polyester, and vinyl ester.

1.3 Floor surfacings used as vessel linings are excluded from this specification.

1.4 The values stated in SI units are to be regarded as the standard. The values in parenthesis are provided for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- C267 Test Methods for Chemical Resistance of Mortars, Grouts, and Monolithic Surfacing and Polymer Concretes
- C307 Test Method for Tensile Strength of Chemical-Resistant Mortar, Grouts, and Monolithic Surfacing
- C413 Test Method for Absorption of Chemical-Resistant Mortars, Grouts, Monolithic Surfacing, and Polymer Concretes
- C531 Test Method for Linear Shrinkage and Coefficient of Thermal Expansion of Chemical-Resistant Mortars, Grouts, Monolithic Surfacing, and Polymer Concretes

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.46 on Industrial Protective Coatings.

Current edition approved July 1, 2012. Published August 2012. Originally approved in 1972. Last previous edition approved in 2004 as C722 – 44. DOI: 10.1520/C0722-04R12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- C579 Test Methods for Compressive Strength of Chemical-Resistant Mortars, Grouts, Monolithic Surfacing, and Polymer Concretes
- C580 Test Method for Flexural Strength and Modulus of Elasticity of Chemical-Resistant Mortars, Grouts, Monolithic Surfacing, and Polymer Concretes
- C811 Practice for Surface Preparation of Concrete for Application of Chemical-Resistant Resin Monolithic Surfacing (Withdrawn 2012)³
- C904 Terminology Relating to Chemical-Resistant Nonmetallic Materials
- C1028 Test Method for Determining the Static Coefficient of Friction of Ceramic Tile and Other Like Surfaces by the Horizontal Dynamometer Pull-Meter Method
- C1486 Practice for Testing Chemical-Resistant Broadcast and Slurry-Broadcast Resin Monolithic Floor Surfacing
- D638 Test Method for Tensile Properties of Plastics
- D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials
- D1308 Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes
- D2047 Test Method for Static Coefficient of Friction of Polish-Coated Flooring Surfaces as Measured by the James Machine
- D6132 Test Method for Nondestructive Measurement of Dry Film Thickness of Applied Organic Coatings Using an Ultrasonic Gage
- 2.2 *ESD Association Standard:*
 - ESD-S7.1 ESD Association Standard for Protection of Electrostatic Discharge Susceptible Items—Floor Materials—Resistive Characterization of Materials

3. Terminology

3.1 *Definitions:* For definitions of terms used in this standard, see Terminology C904.

4. Significance and Use

4.1 This standard specification covers the requirements for floor surfacing products. When specifying surfacing over concrete according to this standard, the floor surfacing shall be

³ The last approved version of this historical standard is referenced on www.astm.org.

classified by the application method, resin chemistry, aggregate type, and applied thickness.

4.2 The specifier must consider service conditions such as chemical exposure, traffic, and temperature conditions in selecting the flooring system.

4.3 Other items that are not specified in this standard but are important to the performance of the floor surfacing include condition of the concrete, concrete surface preparation, surfacing installation, and finished floor slope and surface texture.

4.4 Additional items that may be required for specific applications but are not specified in this standard include floor surfacing electrical conductivity, spark generation properties, and flatness and levelness.

5. Classification

5.1 Classification by application method includes: troweled (TR), broadcast (BC), slurry broadcast (SBC), self-leveling (SL), spray (SP), and reinforced (RF).

5.2 Classification by resin chemistry includes epoxy (EP), urethane (UR), polyester (PE), and vinyl ester (VE).

6. Materials

6.1 Most of these systems include three components: a resinous liquid, a liquid setting agent, and an aggregate component.

6.2 The resinous liquid shall be epoxy, urethane (polyol), polyester or vinyl ester.

6.3 The setting agents for these materials are usually amines (for epoxies), isocyanates (for urethanes), and peroxides (for polyesters and vinyl esters).

6.4 The aggregates or fillers are usually siliceous or carbonaceous materials. These materials are selected to have adequate resistance to the chemicals that are in the area where they are installed and are properly sized to provide ease of application.

6.4.1 Other aggregates and/or filler components are frequently used to obtain specific properties. Aluminum oxide and silicon carbide are used to provide increased abrasion and/or slip resistance properties in the flooring system.

6.5 Reinforcing materials used with these flooring systems must themselves be chemical resistant. Such materials include synthetic, carbon or fiberglass materials in mats, strands or rovings.

6.6 The surfacing materials for TR, SL and SP systems are usually installed by mixing the resin with the setting agent, blending in the aggregate component until uniform and homogenous, and then placing and finishing the mixture onto a properly prepared concrete substrate as per Practice C811.

6.7 The surfacing materials for BC systems are usually installed by mixing the resin with the setting agent (called liquids here), and then spreading onto a properly prepared concrete substrate. This is followed by broadcasting the aggregate to excess into the wet film. The application is allowed to harden. The excess aggregate is removed. The surface is then

topcoated with the same liquids or the application process is repeated until the desired thickness is reached, and then the surface is topcoated.

6.8 In a SBC system, the resin, setting agent and aggregate are blended and applied on a properly prepared concrete substrate. More aggregate is then broadcast into this slurry and allowed to harden. The excess aggregate is removed and the system is then topcoated.

6.9 RF systems are usually applied as the TR, SL or SP systems. The reinforcement is usually embedded in this layer and then the reinforcement is saturated with liquids. A second TR, SL, or SP layer is then applied.

6.10 The components of the floor surfacing systems are usually formulated to perform optimally at specified mixing ratios. They are usually either packaged by the manufacturer in the required proportions (weight or volume) or mixing instructions include guidelines for mixing proportions.

6.11 Any of these systems may be topcoated. At the recommendation of the manufacturer of the system, this topcoat may be mandatory for optimal appearance and performance.

6.12 Many floor surfacings include some type of finish texture or profile incorporated into the design of the surface that can range from relatively smooth to extremely aggressive. TR systems without a sealing topcoat, BC and SBC systems inherently produce surfaces with a texture. SL systems usually produce a smooth surface. Other common methods for incorporating texture include: broadcasting an aggregate into a topcoat (and optionally, resealing); or mixing an aggregate directly into the topcoat before application.

6.13 Occasionally, floor surfacings are required to have specific conductive or static dissipative electrical properties for personnel or product protection. Specific requirements for electrical resistance are not covered in this standard. Refer to ESD-S7.1 for test methods to determine this property.

6.14 In areas where flammable materials are present, it may be required that floor surfacings be non-sparking when impacted with metallic or other hard materials. Specific requirements for non-sparking properties are not covered in this standard.

7. Physical Properties, Chemical Resistance and Performance Requirements

7.1 Requirements for Troweled (TR) systems are listed in Table 1.

7.2 Requirements for Broadcast (BC) and Slurry Broadcast (SBC) systems are listed in Table 2.

7.3 Requirements for Self-Leveling (SL) systems are listed in Table 3.

7.4 Requirements for Sprayed (SP) systems are listed in Table 4.

7.5 Requirements for Reinforced (RF) systems are listed in Table 5.