
**Space systems — Safety and
compatibility of materials —**

**Part 3:
Determination of off-gassed
compounds from materials and
assembled articles**

*Systèmes spatiaux — Sécurité et compatibilité des matériaux —
Partie 3: Détermination des composés issus du dégazage sous
atmosphère des matériaux et des articles assemblés*

[ISO 14624-3:2023](https://standards.iteh.ai/catalog/standards/sist/859cbbef-23a3-4d08-888d-8183dc07b8e2/iso-14624-3-2023)

<https://standards.iteh.ai/catalog/standards/sist/859cbbef-23a3-4d08-888d-8183dc07b8e2/iso-14624-3-2023>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 14624-3:2023](https://standards.iteh.ai/catalog/standards/sist/859cbbef-23a3-4d08-888d-8183dc07b8e2/iso-14624-3-2023)

<https://standards.iteh.ai/catalog/standards/sist/859cbbef-23a3-4d08-888d-8183dc07b8e2/iso-14624-3-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	3
5 Health and safety of test operators.....	3
6 Test conditions.....	3
7 Apparatus and materials.....	4
8 Test samples.....	5
8.1 Handling/receipt.....	5
8.2 Preparation.....	5
8.3 Cleaning.....	6
8.4 Inspection.....	6
9 Pretest procedure.....	6
10 Test procedure.....	6
11 Precision.....	7
12 Test report.....	7
13 Good laboratory practices (GLP).....	8
Annex A (informative) Materials and assembled articles toxic hazard index and maximum limit mass/article example calculations.....	10
Annex B (normative) Determination of off-gassed compounds from high temperature sensitive materials and assembled articles at 40 °C.....	13
Bibliography.....	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 20, *Aircraft and space vehicles*, Subcommittee SC 14, *Space systems and operations*.

This second edition cancels and replaces the first edition (ISO 14624-3:2005), which has been technically revised.

The main changes are as follows:

- updated the definitions;
- updated [Clauses 10](#) and [12](#) as well as [Table 2](#).

A list of all parts in the ISO 14624 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

In this document, the following verbal forms are used:

- “shall” indicates a requirement;
- “should” indicates a recommendation;
- “may” indicates a permission;
- “can” indicates a possibility or a capability.

Recommended criteria are, while not mandatory, considered to be of primary importance in providing serviceable economical and practical designs. Deviations from the recommended criteria may be made only after careful consideration, extensive testing and thorough service evaluation have shown an alternative method to be satisfactory.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 14624-3:2023](https://standards.iteh.ai/catalog/standards/sist/859cbbef-23a3-4d08-888d-8183dc07b8e2/iso-14624-3-2023)

<https://standards.iteh.ai/catalog/standards/sist/859cbbef-23a3-4d08-888d-8183dc07b8e2/iso-14624-3-2023>

Space systems — Safety and compatibility of materials —

Part 3:

Determination of off-gassed compounds from materials and assembled articles

1 Scope

This document specifies a method for determining the identity and quantity of volatile off-gassed compounds from materials and assembled articles utilized in manned, pressurized spacecraft.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

assembled article

combination of materials and/or subcomponents resulting in a complete assembly

3.2

average percent relative standard deviation

quotient of the standard deviations for each off-gassed constituent of y replicate samples of a standard material and the total number of off-gassed constituents

Note 1 to entry: For actual samples, the expected test results and average relative standard deviations for the quantities of *off-gassed compounds* (3.6) can be near 50 %. The calculations for standard deviation and average percent relative standard deviation are as follows:

The standard deviation, s , is given by:

$$s = \sqrt{\frac{\sum_{i=1}^n (x_i - \bar{x})^2}{n-1}}$$

where \bar{x} is the mean for an individual off-gassed constituent.

Therefore, the calculation for the average percent relative standard deviation A_s , is given by:

$$A_s = \frac{\sum s}{y} \times 100 \%$$

where

\sum_s is the summation of the standard deviations for each off-gassed constituent;

y is the total number of off-gassed constituents, for a standard material.

3.3

equilibrium plateau

point at which the quantified total hydrocarbon content (normalized to a certified laboratory gas standard such as propane or methane) shows <10 % change

3.4

good laboratory practice

GLP

practice which involves the testing of standard reference materials to verify data accuracy and repeatability

[SOURCE: ISO 14624-1:2023, 3.5, modified — Note 1 to entry has been removed.]

3.5

maximum limit

value indicative of the maximum mass of material or the maximum number of *assembled articles* (3.1) that can be safely utilized inside the habitable volume of the spacecraft without exceeding a total *toxic hazard index (T)* (3.14) of 0,5

Note 1 to entry: Maximum limit can be maximum limit mass (MLM) or maximum limit article (MLA).

Note 2 to entry: See [Annex A](#) for detailed calculations.

3.6

off-gassed compound

organic or inorganic compound evolved as a gas from a material or *assembled article* (3.1)

3.7

off-gassing

evolution of gaseous products from a liquid or solid material into an atmosphere

<https://standards.iteh.ai/catalog/standards/sist/859cbbef-23a3-4d08-888d-8183dc07b8e2/iso-14624-3-2023>

3.8

primary gas standard

gas mixtures that have gravimetric or analytical traceability and to which all measurements are ultimately compared

3.9

reportable quantities

quantities determined by each analytical laboratory and based on analysed concentrations of the specific compound

Note 1 to entry: Compounds that have been identified, but for which the specific compound is unavailable as a standard, may have reportable quantities based on analysed concentrations of a representative compound.

3.10

ambient temperature

temperature equal to $(23 \pm 5) ^\circ\text{C}$

3.11

sample container

vessel which contains the test sample

3.12 spacecraft maximum allowable concentration SMAC

maximum concentration of an *off-gassed compound* (3.6) allowed in the habitable area of the spacecraft for a specified flight duration

Note 1 to entry: SMAC values for manned spacecraft are determined by the cognizant procuring authority/user toxicologist. SMAC values vary with exposure duration; SMAC values for a seven-day flight duration are normally used to evaluate toxicity of off-gassed compounds. A current listing of NASA SMAC values is maintained on the Internet at <https://maptis.ndc.nasa.gov/matsel/GasPage.aspx> with registration via <https://maptis.nasa.gov/>.

3.13 thermal chamber

apparatus into which the *sample container* (3.11) is placed during thermal conditioning

3.14 toxic hazard index

T

dimensionless ratio of the projected concentration of each *off-gassed compound* (3.6) in the habitable volume of the spacecraft under consideration to its *spacecraft maximum allowable concentration (SMAC)* (3.12) value and summing the ratios for all off-gassed compounds without separation into toxicological categories

Note 1 to entry: See [Annex A](#) for detailed calculations of the *T* value for materials or *assembled articles* (3.1).

Note 2 to entry: *T* value calculations for materials assume the use of 45 kg of material in habitable volume of the spacecraft for concentration calculations. *T* value calculations for assembled articles assumes a single assembled article used in the in habitable volume of the spacecraft for concentration calculations.

3.15 trace

off-gassed compound (3.6) present in less than the threshold limit defined by an individual laboratory

Note 1 to entry: This category includes compounds that are labelled as unidentified components, because the concentration is too low for the spectral information to allow for identification. It does not include compounds that have adequate spectral information but are labelled as unidentified components because suitable standard spectra for identification are not available.

4 Principle

When this method is utilized for a toxicological assessment for a component or a material (assuming 45 kg of material use) and/or assembled article, the total toxic hazard index (*T*) values for all volatile off-gassed compounds shall be less than 0,5 (see [Annex B](#)). In addition, the toxic hazard index can be used to calculate the maximum limit mass (MLM) for use in the habitable volume of the spacecraft. See [Annex B](#).

5 Health and safety of test operators

Testing outlined in this document may generate toxic substances in either the gas or condensed phase. Care shall be taken to protect test operators, other personnel and, if necessary, the environment from such substances.

6 Test conditions

6.1 The test atmosphere should be at least a volume fraction of $(20,9 \pm 2)$ % for oxygen with the balance nitrogen or argon, and the test pressure should be ± 15 kPa of the ambient pressure of the test

facility. The maximum volume fraction limits (expressed as a volume fraction in $\mu\text{l}/\text{l}^{(1)}$) for impurities in the compressed gases are:

- a) carbon monoxide 1;
- b) carbon dioxide 3,0;
- c) total hydrocarbons, as methane 0,1;
- d) halogenated compounds 0,5;
- e) water 7,0.

6.2 Batteries or assembled articles containing batteries should be tested in an inert atmosphere to reduce the risk of generating an explosive gas mixture. Batteries or assembled articles containing batteries tested in an inert atmosphere do not need to be tested again in an oxygen atmosphere.

6.3 The sample shall be subject to a thermal exposure for (72 ± 1) h at (50 ± 3) °C. Samples do not have to be tested in spacecraft anticipated oxygen concentration. Off-gassed compounds from materials and assembled articles which are sensitive to high temperatures shall be determined in accordance with [Annex B](#).

7 Apparatus and materials

The test system shall comprise the following major components: sample container, thermal chamber with controlled temperature, and analytical instrumentation.

7.1 Sample container, being easy to clean and construct so that gas samples can be collected easily. The sample container, including any soft goods, shall not affect the concentration of products off-gassed from the samples.

7.2 Thermal chamber, having the capability to maintain the test temperature to within ± 3 °C for the duration of the test. The thermal chamber instrumentation shall have the capability to continuously record the temperature.

7.3 Analytical instrumentation, capable of the separation, identification, and quantification of selected off-gassed compounds (indicated in [Table 1](#) and [Table 2](#)), with reportable quantities at, or below, their SMAC concentrations.

If the instrumentation cannot achieve this sensitivity, the minimum reportable concentration for those off-gassed compounds (except formaldehyde) should be reported.

For formaldehyde, the analytical technique shall be capable of detecting a concentration of 0,1 $\mu\text{l}/\text{l}$ or current SMAC.

The recommended analytical instruments include a gas chromatograph using primarily a flame ionization detector, gas chromatograph/mass spectrometer, and infrared spectrophotometer. Some analytical compounds can be more difficult to determine, therefore, special methods may be required to identify and quantify these compounds.

In some cases, where there is a specific target compound of concern that has a reporting limit greater than the SMAC, it is necessary to test more than the standard test material. The quantity of test material should be increased proportionally from the standard sample-mass-to-container-volume ratio $(5,0 \pm 0,25)$ g/l to a quantity that allows the analysis to meet the SMAC requirement.

EXAMPLE

-
- 1) 1 $\mu\text{l}/\text{l}$ = 1 part per million (ppm). The use of "ppm" is deprecated.