



Designation: C308 – 00 (Reapproved 2012)^{ε1}

Standard Test Methods for Working, Initial Setting, and Service Strength Setting Times of Chemical-Resistant Resin Mortars¹

This standard is issued under the fixed designation C308; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Units information was corrected editorially in September 2012.

1. Scope

1.1 These test methods cover the determination of the working, initial setting, and service strength setting times of chemical-resistant resin mortars.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C279 Specification for Chemical-Resistant Masonry Units

C307 Test Method for Tensile Strength of Chemical-Resistant Mortar, Grouts, and Monolithic Surfacing

C904 Terminology Relating to Chemical-Resistant Nonmetallic Materials

3. Terminology

3.1 *Definitions*—For definitions of terms used in these test methods, see Terminology C904.

4. Significance and Use

4.1 These test methods offer a means of determining the working time, initial setting time and service strength setting time of chemical-resistant resin mortars. The results obtained

should serve as a guide in, but not as the sole basis for, selection of a chemical-resistant mortar for a particular application.

5. Apparatus

5.1 *Weighing Equipment*—Shall be capable of weighing materials or specimens to $\pm 0.3\%$ accuracy.

5.2 *Mixing Equipment:*

5.2.1 *Porcelain Enameled Pan*—Measuring approximately 10 in. long by 16 in. wide by 2 in. deep (250 mm by 400 mm by 50 mm).

5.2.2 *Bricklayer's Triangular Trowel*—Approximately 4 in. (100 mm) in length.

5.3 *Bricks*—As per Specification C279, Type III.

5.4 *Vicat Apparatus*—The Vicat apparatus shall consist of a frame, A (see Fig. 1), bearing a movable rod, B, weighing 300 g, one end, C, the plunger end, being 10 mm in diameter for a distance of at least 50 mm and the other end having a removable steel needle, D, for initial setting time determination, 1 mm in diameter and 50 mm in length. The rod, B, is reversible, and can be held in any desired position by a set screw, E, and has an adjustable indicator, F, which moves over a scale (graduated in millimetres) attached to the frame, A. In addition to the above, the Vicat apparatus shall conform to the following requirements:

5.4.1 *Weight of Plunger*— 300 ± 0.5 g.

5.4.2 *Diameter of Larger End of Plunger*— 10 ± 0.05 mm.

5.4.3 *Diameter of Needle*— 1 ± 0.05 mm.

5.4.4 *Graduated Scale*—The graduated scale, when compared with a standard scale accurate to within 0.1 mm at all points, shall not show a deviation at any point greater than 0.25 mm.

6. Temperature

6.1 All materials used in this method shall be stored for at least 16 h prior to use at the standard test temperature of $73 \pm 4^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$). The standard temperature for the working and initial setting time tests shall be $73 \pm 4^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$). Other

¹ These test methods are under the jurisdiction of Committee D01 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of D01.46 on Industrial Protective Coatings.

Current edition approved Aug. 1, 2012. Published September 2012. Originally approved in 1953. Last previous edition approved in 2005 as C308 – 05. DOI: 10.1520/C0308-00R12E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.