



Designation: ~~B439-08~~ Designation: B439 - 12

## Standard Specification for Iron-Base Powder Metallurgy (PM) Bearings (Oil- Impregnated)<sup>1</sup>

This standard is issued under the fixed designation B439; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification covers the requirements for porous iron-base metallic sleeve, flange, thrust, and spherical iron-base bearings that are produced from mixed-metal powders utilizing powder metallurgy (PM) technology and then impregnated with oil to supply operating lubrication.

~~1.2 Included~~ 1.2 Listed are the specifications for the chemical, physical, and mechanical requirements of specifications for those standardized ferrous PM materials that have been developed and standardized specifically for use in the manufacture of these self-lubricating bearings.

1.3 ~~This specification accompanies standard is a companion to Specification B438/B438M~~ B438 that covers the requirements for Bronze-Base Powder Metallurgy (PM) Bearings (Oil-Impregnated)-porous oil-impregnated bronze-base bearings.

1.4 Typical applications for self-lubricating iron-base PM bearings are discussed in Appendix X1.

1.5 Commercial bearing dimensional tolerance data are shown in Appendix Appendix X2, while engineering information regarding installation and operating parameters of PM bearings is included in Appendix Appendix X3. Additional useful information on self-lubricating bearings can be found in MPIF Standard 35 (Bearings), ISO 5755 (Bearings) and the technical literature.<sup>2</sup>

~~1.6 With the exception of density values for which the g/cm~~

1.6 Units—With the exception of density values for which the use of the g/cm<sup>3</sup> unit is the industry standard, the values stated in inch-pound units are to be regarded as standard. The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard. unit is the long-standing practice of the PM industry, the values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not to be regarded as standard

1.7 The following safety hazards caveat pertains only to the test methods described in this specification. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.<sup>12</sup>

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>3</sup>

B243 Terminology of Powder Metallurgy ~~B328 Test Method for Density, Oil Content, and Interconnected Porosity of Sintered Metal Structural Parts and Oil-Impregnated Bearings~~

~~B438/B438M~~ B438 Specification for Bronze-Base Powder Metallurgy (P/M)(PM) Bearings (Oil-Impregnated)

B939 Test Method for Radial Crushing Strength, K, of Powder Metallurgy (PM) Bearings and Structural Materials

B962 Test Methods for Density of Compacted or Sintered Powder Metallurgy (PM) Products Using Archimedes' Principle

B963 Test Methods for Oil Content, Oil-Impregnation Efficiency, and Interconnected Porosity of Sintered Powder Metallurgy (PM) Products Using Archimedes' Principle

B966 Test Method for Permeability of Powder Metallurgy (PM) Bearings Using Nitrogen Gas

B970 Test Method for Cleanliness of Powder Metallurgy (PM) Bearings and Structural Parts

E9 Test Methods of Compression Testing of Metallic Materials at Room Temperature

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee B09.04 on Bearings.

Current edition approved April 1, 2008; 2012. Published May 2008; September 2012. Replaces portions of B612 and B782. Originally approved in 1966 to replace portions of B202. Last previous edition approved in 2007; 2008 as B439 - 078. DOI: 10.1520/B0439-08.10.1520/B0439-12.

<sup>2</sup> *Machine Design Magazine*, Vol 54, No. 14, June 17, 1982, pp. 130-142.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard.

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E1019 Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Fusion Techniques

2.2 *MPIF Standard*:<sup>4</sup>

MPIF Standard 35 Materials Standards for PM Self-Lubricating Bearings

2.3 *IEEE/ASTM Standard*:<sup>3</sup>

SI-10 American National Standard for Use of the International System of Units (SI): The Modernized Metric System

## iTeh Standards (<https://standards.itih.ai>) Document Preview

[ASTM B439-12](#)

<https://standards.itih.ai/catalog/standards/sist/031ed524-0a84-4902-b9eb-a5a540626af2/astm-b439-12>

---

<sup>4</sup> Available from Metal Powder Industries Federations, 105 College Road East, Princeton, NJ 08540, <http://www.info@mpif.org>.

~~2.4 ISO Standard: ISO Standards:<sup>5</sup>~~

~~ISO 2795 Plain bearings from sintered metal—Dimensions and tolerances— Plain bearings from sintered metal—Dimensions and tolerances~~

~~ISO 5755 Sintered Metal Materials – Specifications,~~

### 3. Terminology

3.1 *Definitions*—The definitions of the terms used in this specification are found in Terminology B243. Additional descriptive information is available in the Related Materials section of Volume 02.05 of the *Annual Book of ASTM Standards*.

### 4. Classification

~~4.1 This specification uses the established three-part alphanumeric *PM Material Designation Code* to identify the ferrous materials used for self-lubricating bearings. The complete explanation of this classification system is presented in~~

~~4.1 The following list of standardized iron-base oil-impregnated PM bearing material compositions classified by composition are included in this specification. Their complete chemical, physical and mechanical requirements can be found in the specification tables. Typical applications are discussed in Annex A1.~~

~~4.2 The following standard oil-impregnated iron-base bearing material compositions are contained in this specification:~~

~~4.2 The three-part alphanumeric PM Material Designation Code, developed by the PM industry, is used to identify these materials. A complete explanation of this classification system is presented in Annex A1.~~

~~4.2.1 Prefix *F*—Iron Bearing Material:~~

~~Iron and Iron-Carbon Bearing Materials, (Prefix F)~~

~~4.2.1.1 *F-0000-K15*—Iron with 21 % oil. Iron Materials~~

~~F-0000-K15~~

~~F-0000-K23~~

~~4.2.1.2 Iron-Carbon Materials~~

~~F-0005-K20~~

~~F-0005-K28~~

~~F-0008-K20~~

~~F-0008-K32~~

~~4.2.2 Prefix *F*—Iron-Carbon (Steel) Bearing Material: Iron-Copper Bearing Materials (Prefix FC)~~

~~4.2.2.1 *F-0005-K20*—Low carbon steel with 21 % oil. Low-Copper Materials~~

~~FC-0200-K20~~

~~FC-0200-K34~~

~~4.2.2.2 Medium-Copper Materials~~

~~FC-1000-K20~~

~~FC-1000-K30~~

~~FC-1000-K40~~

~~4.2.2.3 High-Copper Materials~~

~~FC-2000-K25~~

~~FC-2000-K30~~

~~FC-2000-K40~~

~~4.2.3 Prefix *FC*—Iron-Copper Bearing Materials:~~

~~Iron-Copper-Carbon Bearing Materials (Prefix FC)~~

~~4.2.3.1 *FC-1000-K20*—Iron, 10% copper with 22 % copper oil. Low-Copper- Carbon Materials.~~

~~FC-0205-K20~~

~~FC-0205-K35~~

~~FC-0208-K25~~

~~FC-0208-K40~~

~~4.2.3.2 *FC-2000-K25*—Iron, 20% copper with 22 % oil. Medium-Copper-Carbon Materials.~~

~~FC-0508-K35~~

~~FC-0508-K46~~

~~4.2.3.3 High-Copper-Carbon Materials.~~

~~FC-2008-K44~~

~~FC-2008-K46~~

~~4.2.4 Prefix *FCTG*—Iron-Bronze-Graphite (Diluted Bronze) Bearing Material:~~

~~4.2.4.1 *FCTG-3604-K22*— Iron, 40 % bronze, ¾ % graphite with 17 % oil. Iron-Graphite Bearing Materials (Prefix FG)~~

~~FG-0303-K10~~

<sup>5</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

FG-0303-K12

FG-0308-K16

FG-0308-K22

4.2.5 ~~Prefix FG—Iron-Graphite Bearing Materials:~~

~~4.2.5.1 FG-0303-K10—Iron, 2 1/2% graphite with 18 % oil.~~

~~4.2.5.2 FG-0308-K16—Steel, 2% graphite with 18 % oil.~~ Iron-Bronze-Graphite (Diluted Bronze) Bearing Materials (Prefix FCTG)

FCTG-3604-K16

FCTG-3604-K22

4.2.6 Diffusion Alloyed Iron-Bronze Bearing Materials (Prefix FDCT)

FDCT-1802- K22

FDCT-1802- K31

FDCT-1802- K39

## 5. Ordering Information

5.1 Purchase orders or contracts for iron-base oil-impregnated PM bearings covered by this purchasing specification shall include the following information:

- 5.1.1 A copy of the bearing print showing dimensions and tolerances (Section 10),
- 5.1.2 Reference to this ASTM specification, including date of issue,
- 5.1.3 Identification of bearing material by the *PM Material Designation Code* (Section 4),
- 5.1.4 Request for certification and test report documents, if required (Section 16),
- 5.1.5 Type and grade of special lubricating oil, if required (6.2.3), and
- 5.1.6 Instructions for special packaging, if required (Section 17).

## 6. Materials and Manufacture

6.1 *Porous Metallic Bearing:*

~~6.1.1 Porous~~ 6.1.1 Porous iron-base bearings shall be ~~produced by first preparing~~ processed from a mixture of elemental-~~i~~, prealloyed or diffusion-alloyed metal powders with or without the additions of copper, tin, ~~pre-alloyed-bronze or graphite powders to powder that together meet~~ the specified chemical composition and then compacting the of the material.

6.1.2 The powder mixture ~~into~~ shall be compacted to produce a green bearing configuration having of the required green density. ~~dimensions, shape and density~~

~~6.1.2 The~~ 6.1.3 The green bearings shall then be sintered in a furnace having a protective atmosphere for a time and temperature cycle that will produce the required sintered ferrous-base PM material.

6.1.3 After sintering, the iron-base bearings are normally sized to achieve the density, dimensional characteristics, concentricity, and surface finish required of the finished metallic bearing.

6.2 *Oil for Operating Lubrication :*

6.2.1 The interconnected or open porosity in the bearings shall be filled to the required volume with lubricating oil, either by an extended soaking in the hot oil or preferably by a vacuum impregnation operation.

6.2.2 A medium viscosity petroleum oil is the lubricant used for most bearing applications, but extreme operating conditions such as elevated temperatures, intermittent rotation, extremely low speeds, or heavy loads may require a synthetic lubricant or an oil with a different viscosity.

6.2.3 Unless otherwise specified by the purchaser, a high-grade turbine oil with antifoaming additives and containing corrosion and oxidation inhibitors, having a kinematic viscosity of 280 to 500 SSU [(60 × 10<sup>-6</sup> to 110 × 10<sup>-6</sup> m<sup>2</sup>/s), (60 to 110 cSt)] at 100 °F (38 °C) is normally used as the general purpose lubricating oil.

## 7. Chemical Composition

7.1 *Chemical Composition Specifications*—Each iron-base PM bearing material shall conform to the chemical composition requirements prescribed in Table 1 when determined on a clean test sample obtained from oil-free bearings.

7.2 *Limits on Nonspecified Elements*—By agreement between the purchaser and the supplier, limits may be established and chemical analyses required for elements or compounds not specified in Table 1.

## 8. Physical Properties

8.1 *Oil Content*—For each bearing material, the oil content of the as-received bearing shall not be less than the minimum percentage listed in Table 1 ±2.

8.2 *Impregnation Efficiency*—A minimum of 90 % of the interconnected porosity in the as-received bearings shall be impregnated with lubricating oil.

8.3 *Impregnated Density*—The density of the sample bearings, when fully impregnated with lubricating oil, shall meet the requirements specified in Table 1 ±2 for each bearing material.

**TABLE 1 Compositional Specifications for Iron-Base Materials Used in PM Bearing Materials**

Material Designation Designation Code	Chemical Composition Requirements										
Iron mass %	Physical Requirements		Mechanical Requirements				All Others % Impregnated- Density g/cm <sup>3</sup>	Oil-Content vol-%	Radical-Crushing-Strength, (K)		
	Total Carbon mass %	Combined Carbon A mass %	Graphitic Carbon mass %	Copper mass %	Tin mass %	Graphitic Carbon B mass %			Copper mass %	Tin mass %	All Others mass % Impregnated- Density g/cm <sup>3</sup>
	Iron mass %	Total Carbon mass %	Combined Carbon A mass %	Graphitic Carbon B mass %	Copper mass %	Tin mass %	Copper mass %	Tin mass %	All Others mass % Impregnated- Density g/cm <sup>3</sup>	Oil-Content vol-%	Radical-Crushing (K)
<b>Iron</b>											
<b>Iron and Iron-Carbon</b>											
F-0000-K15	bal.	0.3 max	---	1.5 max	---	---	---	---	---	0 to 2.0	---
F-0000-K15	bal.	0 to 0.3	---	---	0 to 1.5	---	---	---	---	0 to 2.0	---
F-0000-K23	bal.	0 to 0.3	---	---	0 to 1.5	---	---	---	---	0 to 2.0	---
-2.0 max F-0005-K20	5.6 to 6.0 bal.	21 min	15 min	{	1.5	---	---	---	---	00 min)	---
F-0005-K20	bal.	---	0.3 to 0.6	---	0 to 1.5	---	---	---	---	0 to 2.0	---
F-0005-K28	bal.	---	0.3 to 0.6	---	0 to 1.5	---	---	---	---	0 to 2.0	---
F-0008-K20	bal.	---	---	---	---	---	---	---	---	0 to 2.0	---
F-0008-K20	bal.	---	---	---	---	---	---	---	---	0 to 2.0	---
Iron-Carb 0.9 0.6 to 0.9											
F-0005-K20	bal.	0.3 to 0.6	---	1.5 max	0 to 1.5	---	---	---	---	0 to 2.0	---
F-0008-K32	bal.	---	0.6 to 0.9	---	0 to 1.5	---	---	---	---	0 to 2.0	---
<b>Iron-Copper</b>											
-2.0 max FC-0200-K20	5.6 to 6.0 bal.	21 min	20 min	(14.5 to 3.9	---	---	---	---	---	0 min)	---
FC-0200-K20	bal.	0 to 0.3	---	1.5 to 3.9	---	---	---	---	---	0 to 2.0	---
FC--0200-K34	bal.	0 to 0.3	---	1.5 to 3.9	---	---	---	---	---	0 to 2.0	---
FC-1000-K20	bal.	0 to 0.3	fr	en-C 11.0	---	---	---	---	---	0 to 2.0	---
FC-1000-K20	bal.	0 to 0.3	---	9.0 to 11.0	---	---	---	---	---	0 to 2.0	---
FC-1000-K20	bal.	0.3 max	---	9.0 to 11.0	---	2.0 max	---	---	---	5.6 to 6.0	---
FC-1000-K30	bal.	0 to 0.3	---	9.0 to 11.0	---	---	---	---	---	0 to 2.0	---
FC-1000-K40	22 min	20 min	{	140 min)	---	---	---	---	---	---	---
FC-1000-K40	bal.	0 to 0.3	---	9.0 to 11.0	---	---	---	---	---	0 to 2.0	---
FC-2000-K25	bal.	0.3 max	---	18.0 to 22.0	---	2.0 max	---	---	---	5.6 to 6.0	---
FC-2000-K25	bal.	0 to 0.3	---	18.0 to 22.0	---	---	---	---	---	0 to 2.0	---
FC-2000-K30	22 min	25 min	{	170 min) to 22.0	---	---	---	---	---	0 to 2.0	---
FC-2000-K30	bal.	0 to 0.3	---	18.0 to 22.0	---	---	---	---	---	0 to 2.0	---
FC-2000-K40	bal.	0 to 0.3	---	18.0 to 22.0	---	---	---	---	---	0 to 2.0	---
FC-2000-K40	bal.	0 to 0.3	---	18.0 to 22.0	---	---	---	---	---	0 to 2.0	---
<b>Iron-Copper-Carbon</b>											
<b>Iron-Bronze-Graphite (Diluted-Bronze)</b>											
FCTG-3604-K22	bal.	0.5 max	---	34.0 to 38.0	3.5 to 4.5	---	---	---	---	0 to 2.0	---
FC-0205-K20	bal.	---	0.3 to 0.6	---	1.5 to 3.9	---	---	---	---	0 to 2.0	---
-2.0 max FC-0205-K35	6.0 to 6.4 bal.	17 min	22 to 50	{	150 to 34.9	---	---	---	---	0)	---
FC-0205-K35	bal.	---	0.3 to 0.6	---	1.5 to 3.9	---	---	---	---	0 to 2.0	---
FC-0208-K25	bal.	---	0.6 to 0.9	---	1.5 to 3.9	---	---	---	---	0 to 2.0	---
FC-0208-K40	bal.	---	0.6 to 0.9	---	1.5 to 3.9	---	---	---	---	0 to 2.0	---
FC-0208-K40	bal.	---	0.6 to 0.9	---	1.5 to 3.9	---	---	---	---	0 to 2.0	---
FC-0508-K35	bal.	---	0.6 to 0.9	---	4.0 to 6.0	---	---	---	---	0 to 2.0	---
FC-0508-K46	bal.	---	0.6 to 0.9	---	4.0 to 6.0	---	---	---	---	0 to 2.0	---
FC-2008-K44	bal.	---	0.6 to 0.9	---	18.0 to 22.0	---	---	---	---	0 to 2.0	---
FC-2008-K46	bal.	---	0.6 to 0.9	---	18.0 to 22.0	---	---	---	---	0 to 2.0	---
<b>Iron-Graphite</b>											
FG-0303-K10	bal.	0.5 max	0 to 0.5	2.0 to 3.0	---	---	---	---	---	2.0 max	---
FG-0303-K10	bal.	---	0 to 0.5	2.0 to 3.0	---	---	---	---	---	0 to 2.0	---
-	5.6 to 6.0	18 min	10 to 25	(70 to 170)	---	---	---	---	---	---	---
FG-0303-K12	bal.	---	0 to 0.5	2.0 to 3.0	---	---	---	---	---	0 to 2.0	---
FG-0308-K16	bal.	---	0.5 to 1.0	1.5 to 2.5	---	---	---	---	---	2.0 max	---
FG-0308-K16	bal.	---	0.5 to 1.0	1.5 to 2.5	---	---	---	---	---	0 to 2.0	---
-	5.6 to 6.0	18 min	16 to 45	1.5 to 2.5	---	---	---	---	---	0 to 2.0	---
FG-0308-K22	bal.	---	0.5 to 1.0	1.5 to 2.5	---	---	---	---	---	0 to 2.0	---
<b>Iron-Bronze (Diluted Bronze)</b>											
FCTG-3604-K16	bal.	0.5 to 1.3	0.5 max	<sup>C</sup>	34.0 to 38.0	3.5 to 4.5	---	---	---	0 to 2.0	---
FCTG-3604-K22	bal.	0.5 to 1.3	0.5 max	<sup>C</sup>	34.0 to 38.0	3.5 to 4.5	---	---	---	0 to 2.0	---
FCTG-3604-K22	bal.	0.5 to 1.3	0.5 max	<sup>C</sup>	34.0 to 38.0	3.5 to 4.5	---	---	---	0 to 2.0	---
<b>Diffusion Alloyed Iron-Bronze</b>											
FDCT-1802-K22	bal.	0 to 0.1	---	<sup>D</sup>	5	17.0 to 19.0	1.5 to 2.5	---	---	0 to 1.0	---
FDCT-1802-K31	bal.	0 to 0.1	---	<sup>D</sup>	---	17.0 to 19.0	1.5 to 2.5	---	---	0 to 1.0	---
FDCT-1802-K39	bal.	0 to 0.1	---	<sup>D</sup>	---	17.0 to 19.0	1.5 to 2.5	---	---	0 to 1.0	---

<sup>A</sup>The metallurgically combined carbon value listed is based on the mass percentage of the iron in the alloy, not the mass percentage of the alloy.

TABLE 2 Physical and Mechanical Property Specifications for Iron-Base PM Bearing Materials

Material Designation Code	Physical Requirements		Mechanical Requirements <sup>A</sup>			
	Oil Content vol %	Impregnated Density g/cm <sup>3</sup>	Radical Crushing Strength, (K)		MPa	
			10 <sup>3</sup> psi			
			min	max	min	max
<b>Iron and Iron-Carbon</b>						
F-0000-K15	21	5.6 to 6.0	12		100	
F-0000-K23	17	6.0 to 6.4	23		160	
F-0005-K20	21	5.6 to 6.0	20		140	
F-0005-K28	17	6.0 to 6.4	28		190	
F-0008-K20	21	5.6 to 6.0	20		140	
F-0008-K32	17	6.0 to 6.4	32		220	
<b>Iron-Copper</b>						
FC-0200-K20	22	5.6 to 6.0	20		140	
FC--0200-K34	17	6.0 to 6.4	34		230	
FC-1000-K20	22	5.6 to 6.0	20		140	
FC-1000-K30	19	5.8 to 6.2	30		210	
FC-1000-K40	17	6.0 to 6.4	40		280	
FC-2000-K25	22	5.6 to 6.0	25		170	
FC-2000-K30	19	5.8 to 6.2	30		210	
FC-2000-K40	17	6.0 to 6.4	40		280	
<b>Iron-Copper-Carbon</b>						
FC-0205-K20	22	5.6 to 6.0	20		140	
FC-0205-K35	17	6.0 to 6.4	35		240	
FC-0208-K25	22	5.6 to 6.0	25		170	
FC-0208-K40	17	6.0 to 6.4	40		280	
FC-0508-K35	22	5.6 to 6.0	35		240	
FC-0508-K46	17	6.0 to 6.4	46		320	
FC-2008-K44	22	5.6 to 6.0	44		300	
FC-2008-K46	17	6.0 to 6.4	46		320	
<b>Iron-Graphite</b>						
FG-0303-K10	18	5.6 to 6.0	10	25	70	170
FG-0303-K12	12	6.0 to 6.4	12	35	80	240
FG-0308-K16	18	5.6 to 6.0	16	45	110	310
FG-0308-K22	12	6.0 to 6.4	22	55	150	380
<b>Iron-Bronze (Diluted Bronze)</b>						
FCTG-3604-K16	22	5.6 to 6.0	16	36	110	250
FCTG-3604-K22	17	6.0 to 6.4	22	50	150	340
<b>Diffusion Alloyed Iron-Bronze</b>						
FDCT-1802-K22	24	5.6 to 6.0	22		150	
FDCT-1802-K31	19	6.0 to 6.4	31		215	
FDCT-1802-K39	13	6.4 to 6.8	39		270	

<sup>A</sup>These requirements are based on bearings in the finished, oil-impregnated condition.




FIG. 1 Standard Sleeve Bearing

## 9. Mechanical Properties

9.1 *Radial Crushing Strength*—The radial crushing strength of the oil-impregnated bearing material determined on a plain sleeve bearing or a test specimen prepared from a flange or spherical bearing shall meet the minimum and maximum (if required) strength values listed in Table 2.

## 10. Dimensions, Mass, and Permissible Variations

10.1 This specification is applicable to iron-base PM sleeve and flange bearings having a 3 to 1 maximum length to inside diameter ratio and a 20 to 1 maximum length to wall thickness ratio.