



Designation: ~~D2616-96~~ (Reapproved 2003) Designation: D2616 - 12

## Standard Test Method for Evaluation of Visual Color Difference With a Gray Scale<sup>1</sup>

This standard is issued under the fixed designation D2616; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### INTRODUCTION

This test method was developed to provide a precise procedure for visually evaluating color difference of non-self luminous specimens. It was patterned after a method standardized by the American Association of Textile Chemists and Colorists (AATCC)<sup>2</sup> designed to evaluate “change in color” and this antecedent was reflected in the original title.

This test method provides for evaluation of small to moderate color differences (less than 15 CIELAB (International Commission on Illumination) color difference units) by comparing test specimens to a series of paired gray color chips having progressively larger lightness differences. Color difference is rated according to which of nine gray pairs of differences is visually closest to the test pair, or by interpolation between gray-pair differences.

~~The gray-scale pairs are specified in terms of decimal differences in CIELAB color space. This change together with two continuous, decimal numerical scale equations modeling the original scale comprise the major differences between the previous edition and this revision. The changes were made to provide an ASTM test method that parallels closely the AATCC method.~~

### 1. Scope

1.1 This test method describes a painted gray scale and the procedure to be used in the visual evaluation of color differences of non-self luminous materials by comparison to this scale.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>3</sup>

E284 Terminology of Appearance

~~E1729 Practice for Visual Appraisal of Colors and Color Differences of Diffusely-Illuminated Opaque Materials~~ Practice for Field Collection of Dried Paint Samples for Subsequent Lead Determination

E1499 Guide for Selection, Evaluation, and Training of Observers

#### 2.2 AATCC Procedures:

AATCC Evaluation Procedure ~~1, Gray 1~~ Gray Scale for Color Change<sup>2</sup>

### 3. Terminology

#### 3.1 Definitions:

3.1.1 Definitions of appearance terms in Terminology E284 are applicable to this test method.

### 4. Summary of Test Method

4.1 The gray scale consists of nine pairs of neutral gray color standards of which Reference Pair 5 is two examples of the same

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee E12 on Color and Appearance and is the direct responsibility of Subcommittee E12.11 on Visual Methods. Current edition approved Dec. 1, 2003. Published December 2003. Originally approved in 1967. Last previous edition approved in 1996 as D2616-96. DOI: 10.1520/D2616-96R03.

Current edition approved July 1, 2012. Published September 2012. Originally approved in 1967. Last previous edition approved in 2003 as D2616 - 96 (2003) which was withdrawn April 2012 and reinstated in July 2012. DOI: 10.1520/D2616-12.

<sup>2</sup> *Technical Manual of the American Association of Textile Chemists and Colorists*, P.O. Box 12215, Research Triangle Park, NC 27709, Vol 68, 1993; 86, 2011, pp. 348-349; 365-366.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

gray. One element common to each pair is the gray of Reference Pair 5; the other element, being progressively lighter, provides a succession of lightness differences. Total color differences between non-self luminous specimens are expressed as either fractional, linear scale value between 1 and 5 or as equivalent CIELAB color differences ( $\Delta E^*_{ab}$ ) by comparison with the paired differences of the gray scale, which are predominantly lightness differences.

NOTE 1—The gray specimen common to each pair is specified to have CIE 1976 metric lightness,  $L^* = 41.2(+0.6, -0.6)$ .

## 5. Significance and Use

5.1 The total perceived color difference between two non-self luminous specimens is compared as an equivalent lightness difference between two neutral gray specimens on a gray scale. A fundamental assumption is made that the total color difference can be so evaluated in terms of an equivalent lightness difference. Only the total color differences, that is, a summation of the differences in hue, lightness, and chroma between two specimens is evaluated; this test method is not applicable to the separate precise evaluation of the hue, lightness, and chroma components of color difference.

**TABLE 1 Gray Scale Characteristics**

AATCC Step Designations	CIELAB ( $\Delta E^*$ )	
	Color Difference	Tolerance( $\pm$ )
5.0	0.0	0.2
4.5	0.8	0.2
4.0	1.7	0.3
3.5	2.5	0.3
3.0	3.4	0.4
2.5	4.8	0.5
2.0	6.8	0.6
1.5	9.6	0.7
1.0	13.6	1.0

5.2 The total color difference determined by this test method depends on the degree of uniformity of the specimens and on the sharpness of the dividing line between them. The color difference between specimens having rough or mottled surfaces appears smaller than it would if the specimens had smooth and uniform surfaces. Thus the equivalent CIELAB lightness difference determined for non-uniform specimens will be smaller than for uniform specimens. Likewise, specimens whose dividing line is not sharp will appear to have smaller color differences than those with sharp dividing lines, and for this reason, the equivalent visually observed CIELAB lightness differences will be smaller than the color differences obtained from instrumental measurements.

5.2.1 A physically sharp border between colors differing slightly in the yellow-blue direction in color space appears diffuse. The perceived color difference is noticeably increased by a hairline black separation. This technique imposes a more rigorous test of such small differences.

5.3 In the CIELAB system, a unit of color difference is intended to represent the same visual difference in each of the three attributes; lightness, hue and chroma or alternatively lightness, redness-greenness, yellowness-blueness. It is valid to express color differences that are not simply lightness differences by comparison to a lightness-difference scale.

5.4 Personnel to be employed in the evaluation of color differences with the paired gray scale should be tested for color vision using the procedures in Guide E1499.

## 6. Apparatus

6.1 *Gray Scale Chart*,<sup>4</sup> having the characteristics as shown in Table 1. The  $\Delta E^*$  values in this table are only for the purpose of determining if the Gray Scale Chart itself meets performance specifications. It is not to be used to convert either visual ratings to  $\Delta E^*$  values or  $\Delta E^*$  values to Gray Scale ratings.

NOTE 2—It should be recognized that the practical requirements of gray scale production mitigate against members of a reference pair either being absolutely neutral, or being of identical near-neutral chromaticity. However, chromaticity differences, if present, are of negligible magnitude.

6.2 *Gray Masks*—Light gray masks with rectangular openings shall be used to ensure comparison of equal areas of specimen and reference pairs. Masks are included with each AATCC gray-scale chart.

6.3 *Color Matching Light Booth*—See Practice ~~D1729~~ E1729 for a description of an appropriate color-matching light booth for use in visual evaluation of color differences.

## 7. Preparation of Specimens

7.1 Specimens shall be uniform in color and gloss and shall be free of scratches and other imperfections of surface texture. The specimen being compared to the standard should have the same gloss and surface texture as the standard for maximum precision of color differences determination.

<sup>4</sup> Available from American Association of Textile Chemists and Colorists (as Gray Scale for Color Change).