



Designation: D5867 – 12

Standard Test Methods for Measurement of Physical Properties of Raw Cotton by Cotton Classification Instruments¹

This standard is issued under the fixed designation D5867; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the measurement of color, trash content, micronaire, upper half mean length (length), uniformity index and breaking tenacity (strength) of raw cotton for cotton marketing using a cotton classification instrument.

1.2 This test method is applicable to Upland and Extra Long Staple (ELS) raw cotton.

1.3 This test method is applicable to roller and saw ginned raw cottons.

1.4 This test method contains the following sections.

	Section
Color	8-11
Trash Content	12-15
Micronaire Reading	16-19
Upper Half Mean Length (Length) and Uniformity Index	20-23
Breaking Tenacity (Strength)	24-27

1.5 The values stated in both inch-pound and SI units are to be regarded separately as the standard. The values given in parentheses are for information only.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D123 Terminology Relating to Textiles

D1441 Practice for Sampling Cotton Fibers for Testing

D1445 Test Method for Breaking Strength and Elongation of Cotton Fibers (Flat Bundle Method)

D1447 Test Method for Length and Length Uniformity of Cotton Fibers by Photoelectric Measurement

D1448 Test Method for Micronaire Reading of Cotton Fibers

D1776 Practice for Conditioning and Testing Textiles

D2253 Test Method for Color of Raw Cotton Using the Nickerson-Hunter Cotton Colorimeter (Withdrawn 1995)³

D2495 Test Method for Moisture in Cotton by Oven-Drying

D2812 Test Method for Non-Lint Content of Cotton

D3025 Practice for Standardizing Cotton Fiber Test Results by Use of Calibration Cotton Standards

D4848 Terminology Related to Force, Deformation and Related Properties of Textiles

D7139 Terminology for Cotton Fibers

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

3. Terminology

3.1 For all terminology related to D13.11, refer to D7139.

3.1.1 The following terms are relevant to this standard: micronaire reading, particle count (trash), percent area (trash), Rd (color reflectance) and +b (color yellowness), breaking tenacity (strength), uniformity index, upper-half-mean length.

3.2 For all other terminology related to textiles, refer to Terminology D123 and Terminology D4848.

4. Significance and Use—General

4.1 This test method is accepted for testing of bales of raw cotton in commercial shipments.

4.2 This test method describes acceptable practices for testing of raw cotton using cotton classification instruments that are capable of testing the fiber properties of micronaire reading, length, uniformity index, strength, Rd (color), +b (color), percent area (trash) and particle count (trash).

5. Sampling

5.1 *Bale Sample*—For a bale sample, take a 4 oz (100 g) subsample of cotton from each of two opposite sides of the bale

¹ These test methods are under the jurisdiction of ASTM Committee D13 on Textiles and are the direct responsibility of Subcommittee D13.11 on Cotton Fibers.

Current edition approved July 1, 2012. Published September 2012. Originally approved in 1995. Last previous edition approved in 2005 as D5867 – 05. DOI: 10.1520/D5867-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

and combine the two subsamples into a single bale sample weighing 8 oz (200 g).

6. Conditioning

6.1 Condition the cotton samples to the temperature and relative humidity levels of $21 \pm 1^\circ\text{C}$ ($70 \pm 2^\circ\text{F}$) and $65 \pm 2\%$ until moisture equilibrium is reached.

6.2 Accelerated conditioning is an acceptable practice for this test method.

6.3 Moisture content (dry basis) measured by resistance technique referenced to oven method Test Method **D2495** shall be within 6.75 to 8.25 %.

NOTE 1—This range covers the equilibrium moisture content range for all cottons.

NOTE 2—Cotton is normally received in the laboratory in a relative dry condition, making special preconditioning procedures unnecessary. Samples that are obviously damp should be preconditioned before being brought into the laboratory for conditioning.

7. Calibration

7.1 Follow instrument manufacturers' procedures for sample placement.

7.2 *Calibration of Rd (color reflectance) and +b (color yellowness):*

7.2.1 For color calibration of Rd and +b, calibrate using USDA color materials in accordance with instrument manufacturers' recommendations to establish a testing level consistent with the industry accepted Universal HVI Rd/+b Cotton Color Standards.

7.3 *Calibration of Percent Area (trash) and Particle Count (trash):*

7.3.1 For trash calibration of percent area and particle count calibrate using USDA trash materials in accordance with instrument manufacturers' recommendations.

7.4 *Calibration of Micronaire:*

7.4.1 For calibration of micronaire, cotton calibration or orifice calibration methods are accepted practices within the industry.

7.4.2 For cotton calibration of micronaire, calibrate using Universal HVI Micronaire Calibration Cotton Standards in accordance with instrument manufacturers' recommendations.

7.4.3 For orifice calibration of micronaire, calibrate using USDA micronaire materials in accordance with instrument manufacturers' recommendations to establish a testing level consistent with the industry accepted Universal HVI Micronaire Calibration Cotton Standards.

7.5 *Calibration of Upper Half Mean Length, Uniformity Index and Breaking Tenacity (Strength):*

7.5.1 For Upland saw ginned and roller ginned raw cotton testing, calibrate the instrument with Universal HVI Calibration Cotton Standards (Short/Weak and Long/Strong).

7.5.2 For ELS saw ginned and roller ginned raw cotton testing, calibrate the instrument with Universal HVI Short/Weak Calibration Cotton Standard and Extra Long Staple HVI Long/Strong Calibration Cotton Standard.

7.6 The calibration materials can be obtained from the USDA, AMS, Cotton Division's Standardization and Engineering Branch. The contact information is provided below:

USDA, AMS, Cotton Division
Standardization and Engineering Branch
3275 Appling Road, Room #5
Memphis, TN 38133 USA
<http://www.ams.usda.gov/cotton/>
phone: 901-384-3030 / fax: 901-384-3032

COLOR

8. Scope

8.1 This section describes the measurements of Rd (color reflectance) and +b (color yellowness) for raw cotton. The Rd and +b measurements are based upon standards established by USDA.

9. Summary of Test Method

9.1 A smooth representative surface of a cotton sample is placed in the color measurement area and pressed flat with a minimum force of 4 lb/in.² (0.3 kg/cm²).

10. Significance and Use

10.1 Color is an element of cotton quality, and raw cotton color measurements are useful in controlling the color of manufactured greige, bleached, or dyed yarns and fabrics.

11. Procedure

11.1 One or more test replications shall be made on each subsample of the bale sample.

11.2 The surface of each subsample shall be large enough to completely cover the instrument's measurement area and thick enough to be opaque (no light transmitted through the sample). An uncompressed minimum thickness of 2 in. (50 cm) and a minimum surface area of 9 in.² (58 cm²) of each subsample are required.

11.3 For the bale sample, report the average Rd (color reflectance) of the test replications to the nearest one tenth of a unit.

11.4 For the bale sample, report the average +b (color yellowness) of the test replications to the nearest one tenth of a unit.

TRASH CONTENT

12. Scope

12.1 This section describes the measurements of percent area (trash) and particle count (trash) for raw cotton. The percent area and the particle count measurements are based upon standards established by USDA.

13. Summary of Test Method

13.1 A smooth representative surface of a cotton sample is placed in the trash measurement area and pressed flat with a minimum force of 4 lb/in.² (0.3 kg/cm²).

14. Significance and Use

14.1 Trash content is useful for: estimating the net amount of manufactured textile product obtainable from raw cotton,