



Designation: D3633/D3633M – 12

Standard Test Method for Electrical Resistivity of Membrane-Pavement Systems¹

This standard is issued under the fixed designation D3633/D3633M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the measurement of the electrical resistivity of water-barrier membrane-pavement systems when applied to concrete bridge decks.

1.2 Measurements shall be performed on the bituminous pavement surface covering the water-barrier membrane.

1.3 This test method utilizes a measure of electrical resistance between the saturated top surface of the water-barrier membrane and the reinforcing steel embedded in the concrete bridge deck.

1.4 The values measured represent the electrical resistance obtained with the equipment and procedures stated herein and do not necessarily agree or correlate with those using other equipment or procedures.

1.5 *Units*—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials](#)

[D3743 Terminology Relating to Bridge Deck and Substruc-](#)

[ture Protection \(Withdrawn 2004\)](#)³

[D4071 Practice for Use of Portland Cement Concrete Bridge Deck Water Barrier Membrane Systems](#)

[E105 Practice for Probability Sampling of Materials](#)

3. Terminology

3.1 For definitions of terms used in this specification, refer to Terminology [D3743](#).

4. Significance and Use

4.1 This test method for measuring the electrical resistivity of water-barrier membrane-pavement systems may be interpreted to indicate the effectiveness of such systems.

4.2 This test method is predicated on the fact that an electrical connection between the surface of the pavement and the reinforcing steel in the concrete pavement cannot be made through an impermeable water-barrier membrane.

4.3 This test method may be used for acceptance when the accepting agency specifies the minimum resistance value desired.

5. Apparatus

5.1 *Ohmmeter*, dc, 20 000 Ω/V rating connected to a double-pole, double-throw switch box or ac ohmmeter (switch box not required).

NOTE 1—When this test method is used for acceptance, the accepting agency should specify the type of ohmmeter to be used.

5.2 *Insulated Wire*, No. 18, Belden test probewire or equivalent. Two spools, minimum 38 m [125 ft].

5.3 *Copper Plate*, 305 by 305 by 3.0 mm [12 by 12 by $\frac{1}{8}$ in.], with the means for connecting the ohmmeter lead and a wooden handle approximately 1 m [39 in.] in length.

5.4 *Polyurethane Sponge*, 305 by 305 by 13 mm [12 by 12 by $\frac{1}{2}$ in.], to be attached to the copper plate with rubber bands or other suitable means. When assembled this apparatus is called the probe.

5.5 *Pressure Spray Can*, 12-L [3-gal] capacity, with a hose and spray nozzle.

³The last approved version of this historical standard is referenced on www.astm.org.

¹ This test method is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.32 on Bridges and Structures.

Current edition approved June 1, 2012. Published July 2012. Originally approved in 1977. Last previous edition approved in 2006 as D3633 – 98 (2006). DOI: 10.1520/D3633-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.