



Designation: ~~F31–05 (Reapproved 2010)~~ F31 – 12

Standard Specification for ~~42 % Nickel-6 % Chromium-Iron Sealing Alloy~~ 42 % Nickel-6 % Chromium-Iron Sealing Alloys¹

This standard is issued under the fixed designation F31; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers ~~an~~two iron-nickel-chromium alloy (~~UNS K94760~~) alloys (UNS K94760 and UNS K95150) used primarily for glass-sealing applications in electronic devices.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following safety hazards caveat applies only to Section 13. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[E18 Test Methods for Rockwell Hardness of Metallic Materials](#)

[E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

[E38 Methods for Chemical Analysis of Nickel-Chromium and Nickel-Chromium-Iron Alloys \(Withdrawn 1989\)](#)³

[E112 Test Methods for Determining Average Grain Size](#)

[E228 Test Method for Linear Thermal Expansion of Solid Materials With a Push-Rod Dilatometer](#)

[F14 Practice for Making and Testing Reference Glass-Metal Bead-Seal](#)

[F140 Practice for Making Reference Glass-Metal Butt Seals and Testing for Expansion Characteristics by Polarimetric Methods](#)

[F144 Practice for Making Reference Glass-Metal Sandwich Seal and Testing for Expansion Characteristics by Polarimetric Methods](#)

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Size,

3.1.2 Temper (Section 6),

3.1.3 Surface finish (Section 8),

3.1.4 Marking and packaging (Section 13), and

3.1.5 Certification if required.

4. Chemical Composition

4.1 The material shall conform to the requirements of [Table 1](#) as to chemical composition.

NOTE 1—The major constituents of this alloy may be adjusted by the manufacturer so that the alloy meets the requirement for thermal expansion.

5. Chemical Analysis

5.1 Chemical analysis shall be made, when desired, in accordance with Methods [E38](#).

¹ This specification is under the jurisdiction of ASTM Committee [F01](#) on Electronics and is the direct responsibility of Subcommittee [F01.03](#) on Metallic Materials. Current edition approved ~~Oct. 1, 2010~~ July 1, 2012. Published ~~November 2010~~ August 2012. Originally approved in 1963 as F31 – 63 T. Last previous edition approved in 2005/2010 as ~~F31–05~~ [F31 – 05](#) (2010). DOI: ~~10.1520/F0031-05R10~~ 10.1520/F0031-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

TABLE 1 Chemical Composition

Element	42Ni-6Cr(UNS K94760)	47Ni-6Cr(UNS K95150)
	Composition, %	Composition, %
Nickel, nominal	42.0	47.0
Chromium, nominal	5.6	6.0
Carbon, max	0.07	0.02
Manganese, max	0.25	0.30
Phosphorus, max	0.025	0.025
Sulfur, max	0.025	0.025
Silicon, max	0.30	0.30
Aluminum, max	0.20	-
Iron	remainder	remainder

6. Surface Lubricants

6.1 All lubricants used during cold-working operations such as drawing, rolling, or spinning, shall be capable of being removed readily by any of the common organic degreasing solvents.

7. Temper

7.1 The desired temper of the material shall be specified on the purchase order. Unless otherwise specified, wire, rod, and tubing shall be given a final bright anneal by the manufacturer. Strip and sheet shall be annealed properly to develop drawing properties. For deep drawing, the hardness shall not exceed Rockwell B90 when determined in accordance with Test Methods E18.

8. Grain Size

8.1 Strip and sheet for deep drawing applications shall have an average grain size not larger than ASTM No. 5 (Note 2), with no more than 10 % of the grains larger than No. 5 when measured in accordance with Test Methods E112. For materials less than 0.005 in. (0.13 mm) in thickness, the grain size shall be such that there are no less than 4 grains across the thickness.

NOTE 2—This corresponds to a grain size finer than 0.065 mm or 16 grains/in. ² of image at 100×.

9. Dimensional Tolerances

9.1 *Cold-Rolled Strip*—Cold-rolled strip shall conform to the permissible variations in dimensions prescribed in Table 2, Table 3, and Table 4.

9.2 *Round Wire and Rod*—Wire and rod shall conform to the permissible variations in dimension prescribed in Table 5.

9.3 *Cold-Drawn Tubing*—Cold-drawn tubing, available either as seamless or welded, shall conform to the permissible variations prescribed in Table 6.

10. Surface Finish

10.1 The standard surface finishes available shall be those resulting from the following operations:

10.1.1 Hot rolling,

10.1.2 Forging,

10.1.3 Centerless grinding (rod),

10.1.4 Belt polishing,

TABLE 2 Permissible Variations in Thickness of Cold-Rolled Strip

NOTE 1— Measurement shall be made at least 3/8 in. (9.5 mm) from the edge of strip over 1-in. (25.4 mm) wide.

Specified Thickness		Permissible Variations in Thickness for Width Given, ±							
in.	(mm)	Under 3 in.	(Under 76 mm)	Over 3 to 6 in.	(76 to 150 mm)	Over 6 to 12 in.	(150 to 300 mm)	Over 12 to 16 in.	(300 to 400 mm)
0.160 to 0.100, incl	(4.06 to 2.54)	0.002	(0.05)	0.003	(0.076)	0.004	(0.10)	0.004	(0.10)
0.099 to 0.069, incl	(2.51 to 1.75)	0.002	(0.05)	0.003	(0.076)	0.003	(0.076)	0.004	(0.10)
0.068 to 0.050, incl	(1.73 to 1.27)	0.002	(0.05)	0.003	(0.076)	0.003	(0.076)	0.003	(0.076)
0.049 to 0.035, incl	(1.24 to 0.89)	0.002	(0.05)	0.0025	(0.064)	0.003	(0.076)	0.003	(0.076)
0.034 to 0.029, incl	(0.86 to 0.74)	0.0015	(0.038)	0.002	(0.05)	0.0025	(0.064)	0.0025	(0.064)
0.028 to 0.026, incl	(0.71 to 0.66)	0.0015	(0.038)	0.0015	(0.038)	0.002	(0.05)	0.002	(0.05)
0.025 to 0.020, incl	(0.64 to 0.51)	0.001	(0.025)	0.0015	(0.038)	0.002	(0.05)	0.002	(0.05)
0.019 to 0.017, incl	(0.48 to 0.43)	0.001	(0.025)	0.001	(0.025)	0.0015	(0.038)	0.002	(0.05)
0.016 to 0.012, incl	(0.41 to 0.30)	0.001	(0.025)	0.001	(0.025)	0.0015	(0.038)	0.0015	(0.038)
0.011 to 0.0101, incl	(0.28 to 0.256)	0.001	(0.025)	0.001	(0.025)	0.001	(0.025)	0.0015	(0.038)
0.010 to 0.0091, incl	(0.254 to 0.231)	0.001	(0.025)	0.001	(0.025)	0.001	(0.025)	0.001	(0.025)
0.009 to 0.006, incl	(0.228 to 0.152)	0.00075	(0.019)	0.00075	(0.019)
Under 0.006	(0.152)	0.0005	(0.013)	0.0005	(0.013)