



Designation: ~~D1921—06~~<sup>ε1</sup> D1921—12

## Standard Test Methods for Particle Size (Sieve Analysis) of Plastic Materials<sup>1</sup>

This standard is issued under the fixed designation D1921; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

*This standard has been approved for use by agencies of the Department of Defense.*

---

<sup>ε1</sup> NOTE—Added research report information to Section 17 editorially in September 2010.

---

### 1. Scope\*

1.1 These test methods cover the measurement of the particle size of plastic materials in the powdered, granular, or pelleted forms in which they are commonly supplied. As these test methods utilize dry sieving, the lower limit of measurement is considered to be about 38  $\mu\text{m}$  (No. 400 sieve). For smaller particle sizes, sedimentation test methods are recommended.

1.2 Two test methods are described:

1.2.1 *Test Method A*—This test method uses multiple sieves selected to span the particle size of the material. This method is used to determine the mean particle diameter and particle size distribution.

1.2.2 *Test Method B*—This test method is an abbreviated version of Test Method A conducted with a few specific sieves. This test method determines “percent passing” or “percent retained” on a given sieve. Test Method B is applicable to materials which do not have a normal particle size distribution such as pellets and cubes.

1.3 The values stated in SI units shall be considered standard for dimensions of the wire cloth openings and the diameter of the wires used in the wire cloth. The values stated in inch-pound units shall be considered standard with regard to the sieve frames.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no technically equivalent ISO standard known ISO equivalent for this test method.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

### 3. Summary of Test Methods

3.1 A dry mass of plastic material is placed on a series of sieves arranged in order of increasing fineness and the mass is divided into fractions corresponding to the sieve opening.

### 4. Significance and Use

4.1 These test methods can be used to determine particle size distribution and therefore are useful for determining lot-to-lot uniformity.

4.2 The particle sizes of plastic materials affect the handling characteristics and sometimes will affect the processing characteristics of some polymers.

---

<sup>1</sup> These test methods are under the jurisdiction of ASTM Committee D20 on Plastics and are the direct responsibility of Subcommittee D20.70 on Analytical Methods (Section D20.70.01).

Current edition approved April 1, 2006 Aug. 1, 2012. Published June 2006 September 2012. Originally approved in 1961. Last previous edition approved in 2004 2006 as ~~D1921—01~~ D1921—06<sup>ε1</sup>. DOI: 10.1520/D1921-06E01; 10.1520/D1921-12.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

## 5. Interferences

5.1 Some materials develop a static charge during sieving. This charge interferes with the sieving process and results in a coarse bias. Use of an antistat is necessary to obtain meaningful results.

5.2 The choice of antistat (or slip agent) has been known to affect the coarse bias. Some materials are more effective in aiding the fines to separate from the mass.

5.3 Too much material on a sieve causes mass blinding and results in a coarse bias. The sieve selection and charge weight must be chosen to avoid overloading any sieve.

5.4 Wavy, improperly stretched wire-cloth ~~may allow~~ potentially allows wires to separate without being visually damaged. Sieves with wavy or torn wires shall not be used, as they no longer conform to Specification E11.

## 6. Apparatus

6.1 *Balance*, 500-g minimum capacity with the capability of reading to the nearest 0.1 g.

6.2 *Mechanical Sieving Device and Time Switch*—A mechanical sieve-shaking device equipped with an automatic time switch. This device shall be capable of imparting uniform rotary motion and a tapping action at a rate of  $150 \pm 10$  taps/min.

6.3 *Wire Cloth Sieves*, woven wire cloth conforming to Specification E11, as shown in Table 1, mounted in 8-in. [203-mm] frames. The number of sieves and the choice of sizes shall be selected for the material being tested. A cover and a bottom pan are also required.

6.4 *Accessories for Cleaning the Screens:*

6.4.1 *Brush*<sup>3</sup>,

6.4.2 *Vacuum Cleaner*, and

6.4.3 *Air Hose*.

## 7. Reagents and Materials

7.1 Antistat (or slip) agent suitable to the material being tested.

## 8. Hazards

8.1 The sieving operation and cleaning of the sieves sometimes introduce fine plastic particles and antistat agent into the atmosphere. Take precautions to avoid breathing these particles.

## 9. Sampling

9.1 Homogenize the lot where possible before removing the test sample to avoid segregation of particles during handling.

## 10. Preparation of Apparatus

10.1 Thorough cleaning and inspection of the sieve are required prior to initiating a test. Carefully clean the sieves with a brush and vacuum cleaner or compressed air, or both. Periodic washing with soap and water or suitable solvent is recommended with some materials.

10.2 Tare each sieve and the pan. Record tare weights to the nearest 0.1 g.

10.3 Assemble sieves so that the sieve openings decrease in size in sequence from the top of the stack. Place the pan at the bottom.

10.4 Use full- or half-size screens to accommodate the holder in the shaker.

## 11. Conditioning

11.1 The plastic material must be in a free-flowing condition.

11.2 If possible, condition the material to the laboratory temperature and humidity.

## TEST METHOD A

## 12. Procedure

12.1 Select sieves in sufficient number to cover the expected range of particle sizes, and nest them together in order of diminishing opening with the coarsest sieve on top and the pan on the bottom.

<sup>3</sup> The sole source of supply of the Type 8577 (W. S. Tyler) Brush known to the committee at this time is W. S. Tyler, Inc., 8750 Tyler Blvd., Mentor, OH 44060. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

**TABLE 1 Nominal Dimensions, Permissible Variations for Wire Cloth of Standard Test Sieves (U.S.A.) Standard Series**

Sieve Designation		Nominal Sieve Opening, in. <sup>A</sup>	Permissible Variation of Average Opening from the Standard Sieve Designation	Opening Dimension Exceeded By Not More Than 5 % of the Openings	Maximum Individual Opening	Nominal Wire Diameter, mm <sup>B</sup>
Standard <sup>C</sup>	Alternative					
(1)	(2)	(3)	(4)	(5)	(6)	(7)
125 mm	5 in.	5	±3.70 mm	130.0 mm	130.9 mm	8.00
106 mm	4.24 in.	4.24	±3.20 mm	110.2 mm	111.1 mm	6.30
100 mm <sup>D</sup>	4 in. <sup>D</sup>	4	±3.00 mm	104.0 mm	104.8 mm	6.30
90 mm	3½ in.	3.5	±2.70 mm	93.6 mm	94.4 mm	6.30
75 mm	3 in.	3	±2.20 mm	78.1 mm	78.7 mm	6.30
63 mm	2½ in.	2.5	±1.90 mm	65.6 mm	66.2 mm	5.80
53 mm	2.12 in.	2.12	±1.60 mm	55.2 mm	55.7 mm	5.00
50 mm <sup>D</sup>	2 in. <sup>D</sup>	2	±1.50 mm	52.1 mm	52.6 mm	5.00
45 mm	1¾ in.	1.75	±1.40 mm	46.9 mm	47.4 mm	4.50
37.5 mm	1½ in.	1.5	±1.10 mm	39.1 mm	39.5 mm	4.50
31.5 mm	1¼ in.	1.25	±1.00 mm	32.9 mm	33.2 mm	4.00
26.5 mm	1.06 in.	1.06	±800 µm	27.7 mm	28.0 mm	3.55
25.0 mm <sup>D</sup>	1.00 in. <sup>D</sup>	1	±800 µm	26.1 mm	26.4 mm	3.55
22.4 mm	⅞ in.	0.875	±700 µm	23.4 mm	23.7 mm	3.56
19.0 mm	¾ in.	0.750	±600 µm	19.9 mm	20.1 mm	3.15
16.0 mm	⅝ in.	0.625	±500 µm	16.7 mm	17.0 mm	3.15
13.2 mm	0.530 in.	0.530	±410 µm	13.83 mm	14.05 mm	2.80
12.5 mm <sup>D</sup>	½ in. <sup>D</sup>	0.500	±390 µm	13.10 mm	13.31 mm	2.50
11.2 mm	⅞ in.	0.438	±350 µm	11.75 mm	11.94 mm	2.50
9.5 mm	⅜ in.	0.375	±300 µm	9.97 mm	10.16 mm	2.24
8.0 mm	⅝ in.	0.312	±250 µm	8.41 mm	8.58 mm	2.00
6.7 mm	0.265 in.	0.265	±210 µm	7.05 mm	7.20 mm	1.80
6.3 mm <sup>D</sup>	¼ in. <sup>D</sup>	0.250	±200 µm	6.64 mm	6.78 mm	1.80
5.6 mm	No. 3½ <sup>E</sup>	0.223	±180 µm	5.90 mm	6.04 mm	1.60
4.75 mm	No. 4	0.187	±150 µm	5.02 mm	5.14 mm	1.60
4.00 mm	No. 5	0.157	±130 µm	4.23 mm	4.35 mm	1.40
3.35 mm	No. 6	0.132	±110 µm	3.55 mm	3.66 mm	1.25
2.80 mm	No. 7	0.110	±95 µm	2.975 mm	3.070 mm	1.12
2.36 mm	No. 8	0.0937	±80 µm	2.515 mm	2.800 mm	1.00
2.00 mm	No. 10	0.0787	±70 µm	2.135 mm	2.215 mm	0.900
1.7 mm	No. 12	0.0661	±60 µm	1.820 mm	1.890 mm	0.800
1.4 mm	No. 14	0.0556	±50 µm	1.505 mm	1.565 mm	0.710
1.18 mm	No. 16	0.0469	±45 µm	1.270 mm	1.330 mm	0.830
1.00 mm	No. 18	0.0394	±40 µm	1.080 mm	1.135 mm	0.560
850 µm <sup>F</sup>	No. 20	0.0331	±35 µm	925 µm	970 µm	0.500
710 µm	No. 25	0.0278	±30 µm	775 µm	815 µm	0.450
600 µm	No. 30	0.0234	±25 µm	660 µm	695 µm	0.400
500 µm	No. 35	0.0197	±20 µm	550 µm	585 µm	0.315
425 µm	No. 40	0.0165	±19 µm	471 µm	502 µm	0.280
355 µm	No. 45	0.0139	±16 µm	396 µm	426 µm	0.224
300 µm	No. 50	0.0117	±14 µm	337 µm	363 µm	0.200
250 µm	No. 60	0.0098	±12 µm	283 µm	306 µm	0.160
212 µm	No. 70	0.0083	±10 µm	242 µm	263 µm	0.140
180 µm	No. 80	0.0070	±9 µm	207 µm	227 µm	0.125
150 µm	No. 100	0.0059	±8 µm	174 µm	192 µm	0.100
125 µm	No. 120	0.0049	±7 µm	147 µm	163 µm	0.090
106 µm	No. 140	0.0041	±6 µm	126 µm	141 µm	0.071
90 µm	No. 170	0.0035	±5 µm	108 µm	122 µm	0.063
75 µm	No. 200	0.0029	±5 µm	91 µm	103 µm	0.050
63 µm	No. 230	0.0025	±4 µm	77 µm	89 µm	0.045
53 µm	No. 270	0.0021	±4 µm	66 µm	76 µm	0.036
45 µm	No. 325	0.0017	±3 µm	57 µm	66 µm	0.032
38 µm	No. 400	0.0015	±3 µm	48 µm	57 µm	0.030
32 µm	No. 450	0.0012	±3 µm	42 µm	50 µm	0.028
25 µm <sup>D</sup>	No. 500	0.0010	±3 µm	34 µm	41 µm	0.025
20 µm <sup>D</sup>	No. 635	0.0008	±3 µm	29 µm	35 µm	0.020

<sup>A</sup> Only approximately equivalent to the metric values in Column 1.

<sup>B</sup> The average diameter of the wires in the x and y direction, measured separately, of any wire cloth shall not deviate from the nominal values by more than ±15 %.

<sup>C</sup> These standard designations correspond to the values for test sieve openings recommended by the International Standards Organization, Geneva, Switzerland, except where noted.

<sup>D</sup> These sieves are not in the standard series, but they have been included because they are in common usage.

<sup>E</sup> These numbers (3½ to 635) are the approximate number of openings per linear inch, but it is preferred that the sieve be identified by the standard designation in millimetres or micrometres.

<sup>F</sup> 1000 µm—1 mm.

12.2 Select sieves in sufficient number to have significant measurable quantities on four or more sieves. Weigh the sieves on a balance reading to the nearest 0.1 g. Record these sieve masses as their tare masses, respectively.