



Designation: D3308 – 12

## Standard Specification for PTFE Resin Skived Tape<sup>1</sup>

This standard is issued under the fixed designation D3308; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification covers skived tape in thicknesses from 0.013 to 6.35 mm (0.0005 to 0.250 in.) manufactured by skiving (Note 1) from PTFE resin molding and extrusion materials.

NOTE 1—Skiving is the process of continuously shaving a film on a lathe from the outer surface to the core of a molded cylindrical tube of material.

NOTE 2—Abbreviations have been approved from Terminology D1600.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are for information only.

1.3 The following hazard caveat pertains only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 3—This specification and ISO 13000-1 and ISO 13000-2 differ in approach or detail, and data obtained using either may not be technically equivalent.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

- D149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies
- D374 Test Methods for Thickness of Solid Electrical Insulation
- D618 Practice for Conditioning Plastics for Testing
- D638 Test Method for Tensile Properties of Plastics

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials (Section D20.15.12).

Current edition approved Aug. 1, 2012. Published September 2012. Originally approved in 1974. Last previous edition approved in 2006 as D3308 - 06. DOI: 10.1520/D3308-12.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement
- D882 Test Method for Tensile Properties of Thin Plastic Sheet
- D883 Terminology Relating to Plastics
- D1389 Test Method for Proof-Voltage Testing of Thin Solid Electrical Insulating Materials
- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D3892 Practice for Packaging/Packing of Plastics
- D4894 Specification for Polytetrafluoroethylene (PTFE) Granular Molding and Ram Extrusion Materials

#### 2.2 ISO Standards:

- ISO 13000-1 Plastics—Polytetrafluoroethylene (PTFE) Semi-Finished Products Part 1: Requirements and Designation<sup>3</sup>
- ISO 13000-2 Plastics—Polytetrafluoroethylene (PTFE) Semi-Finished Products Part 2: Preparation of Specimens and Determination of Properties<sup>3</sup>

### 3. Terminology

#### 3.1 Definitions:

Definitions are in accordance with Terminology D883 unless otherwise specified.

#### 3.2 Definitions of Terms Specific to this Standard:

- 3.2.1 *lot, n*—One production run, or a uniform blend of two or more production runs.
- 3.2.2 *film, n*—full-width material received as finished film.
- 3.2.3 *Mil, n*— $1/1000$  (0.001) of an inch.

### 4. Classification

4.1 This specification covers four types of PTFE resin skived tape:

- 4.1.1 *Type I*—Premium; normally used for exacting electrical, mechanical, or chemical applications.
- 4.1.2 *Type II*—General purpose; for electrical, mechanical, and chemical applications not requiring premium material.
- 4.1.3 *Type III*—Commercial; for non-critical chemical, electrical, and mechanical applications.

<sup>3</sup> Available from American National Standards Institute, 25 W. 43rd St., 4th Floor, New York, NY 10036.

\*A Summary of Changes section appears at the end of this standard

TABLE 1 Width Tolerances for Skived Tape

Width		Tolerance	
mm	in.	mm	in.
Up to 12.700	Up to 0.500	-0/+0.510	-0/+0.020
12.701 to 25.400	0.501 to 1.000	-0/+0.640	-0/+0.025
25.401 to 50.800	1.001 to 2.000	-0/+0.890	-0/+0.035
50.801 to 76.200	2.001 to 3.000	-0/+1.905	-0/+0.075
76.201 to 152.400	3.001 to 6.000	-0/+3.175	-0/+0.125
152.401 or greater	6.001 or greater	-0/+6.350	-0/+0.250

TABLE 2 Thickness Tolerances for Skived Tape

Thickness		Tolerance	
mm	in.	mm	in.
0.013 to 0.025	0.0005 to 0.0010	±0.003	±0.0001
0.028 to 0.076	0.0011 to 0.0030	±0.008	±0.0003
0.091 to 0.254	0.0036 to 0.0100	±0.013	±0.0005
0.257 to 0.381	0.0101 to 0.0150	±0.025	±0.0010
0.384 to 1.016	0.0151 to 0.0400	±0.038	±0.0015
1.019 to 3.175	0.0401 to 0.1250	±0.127	±0.0050
>3.175	>0.1250	±0.254	±0.0100

4.1.4 *Type IV*—Utility; having no electrical requirements, and with mechanical properties at lower level.

4.2 Types I, II, III, and IV may be subdivided into two grades in accordance with the base resin used as follows:

4.2.1 *Grade 1*—Made only from virgin resin.

4.2.2 *Grade 2*—May be made using reprocessed resin, or a mixture of virgin and reprocessed resin.

4.3 A one-line system may be used to specify materials covered by this specification. The system uses predefined cells to refer to specific aspects of this specification, as illustrated below:

Standard Number Block	Specification			
	Type	Grade	Class	Special Notes
:	:	:	:	:
:	:	:	:	:

Example: Specification D3308 – 06

1 2 ...

For this example, the line callout would be: Specification D3308 – 06, I2, Oil and would specify a skived tape that has all of the properties listed for that Type and Grade, in the appropriate specified properties, tables, or both, in the specification identified. A comma is used as the separator between the Standard number and the Type. Separators are not needed between the Type and Grade, because they are, in turn, Roman numerals and Arabic digits.<sup>4</sup> Provision for “Special Notes” is included so that other information can be provided when required. This example would be premium PTFE tape without special requirements. When Special Notes are used, they should be preceded by a comma.

5. Physical Requirements

5.1 The tape shall be made from unpigmented PTFE resin.

5.2 The length and width of the roll shall be as agreed upon between the purchaser and the seller. Width tolerances shall be in accordance with Table 1.

5.3 The melting point for all types of tape shall be 327 ± 10°C (621 ± 18°F).

5.4 The thickness tolerances for skived tape shall be as shown in Table 2.

5.5 Tensile strength and elongation shall meet the requirements shown in Table 3.

5.6 The requirements for specific gravity shall be as shown in Table 3.

5.7 The minimum required values for dielectric strength *S* (V/mil), shall be computed for applicable thicknesses of materials in accordance with the following formulas, where *t* is the thickness of the tape in mils.

Type I:  $S = 1000$  times square root of  $(20/t)$

Type II (thickness ≥0.003 in.):  $S = 840$  times square root of  $(20/t)$

Type II (thickness <0.003 in.):  $S = 630$  times square root of  $(20/t)$

Type III:  $S = 500$  times square root of  $(20/t)$

Type IV: No requirement for dielectric strength

5.8 The number of non-dielectric strength failure mode electrical flaws shall be determined in accordance with Test Method D1389.

6. Sampling

6.1 Sampling shall be statistically adequate to satisfy the requirements of 9.4.

7. Number of Tests and Retests

7.1 One set of test specimens as prescribed in Section 8 shall be considered sufficient for testing each batch. The average result of the specimens shall conform to the requirements of this specification.

8. Test Methods

8.1 The properties enumerated in this specification shall be determined in accordance with the following test methods:

8.1.1 *Conditioning*—For those tests where conditioning is required, condition the test specimens in accordance with Procedure A of Practice D618 for a period of at least 4 h prior to test. If the test material has been exposed to temperatures below 20°C within 24 h prior to test, the conditioning shall be for at least 24 h.

8.1.2 *Test Conditions*—Conduct tests at the standard laboratory temperature of 23 ± 2°C (70 to 77°F). The maintenance of constant humidity is not necessary. In reference cases, the standard atmosphere, 50 ± 5 % relative humidity, shall apply.

8.1.3 *Thickness*—Measure thickness in accordance with Method A of Test Methods D374, for all thicknesses.

8.1.4 *Melting Point*—Determine the melting point on one specimen in accordance with the test method stated in Specification D4894.

<sup>4</sup> See the ASTM Form and Style Manual. Available from ASTM Headquarters.