



Designation: **D3170–03 (Reapproved 2007) D3170–12**

Standard Test Method for Chipping Resistance of Coatings¹

This standard is issued under the fixed designation D3170; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers the determination of the resistance of coatings to chipping damage by stones or other flying objects.

NOTE 1—This test method is similar to SAE J-400.

1.2 The values stated in metric units are to be regarded as the standard. The English units given in parentheses are for information only. All dimensions are nominal unless otherwise specified.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D609 Practice for Preparation of Cold-Rolled Steel Panels for Testing Paint, Varnish, Conversion Coatings, and Related Coating Products](#)

[D823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels](#)

[D1005 Test Method for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers](#)

[D1186 Test Methods for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to a Ferrous Base \(Withdrawn 2006\)](#)³

[D1400 Test Method for Nondestructive Measurement of Dry Film Thickness of Nonconductive Coatings Applied to a Nonferrous Metal Base \(Withdrawn 2006\)](#)³

[D1733 Method for Preparation of Aluminum Alloy Panels for Testing Paint, Varnish, Lacquer, and Related Products \(Withdrawn 1979\)](#)³

[D2201 Practice for Preparation of Zinc-Coated and Zinc-Alloy-Coated Steel Panels for Testing Paint and Related Coating Products](#)

2.2 *Other Documents:*

[Test for Chip Resistance of Surface Coatings \(J-400\)](#)⁴

3. Summary of Test Method

3.1 Standardized road gravel is projected by means of a controlled air blast at the coated specimens. All testing is conducted under controlled temperature conditions, generally either at ambient (room) temperature or at $-29 \pm 3^\circ\text{C}$ ($-20 \pm 5^\circ\text{F}$). After the gravel impact, tape is applied to remove any loose coating chips and the degree of chipping is determined.

4. Significance and Use

4.1 Owners consider chipping of coatings, particularly on the leading faces and edges of automobile surfaces, unacceptable. In formulating a coating or coating system to meet service requirements, the resistance to chipping damage by flying objects such

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.55 on Factory Applied Coatings on Preformed Products.

Current edition approved ~~June 1, 2007~~ July 15, 2012. Published ~~July 2007~~ October 2012. Originally approved in 1973. Last previous edition approved in ~~2003~~ 2007 as ~~D3170–03~~ D3170 DOI: ~~10.1520/D3170-03R07-~~ 03 (2007). DOI: 10.1520/D3170-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, http://www.sae.org.




FIG. 1 Gravel Projecting Machine

as gravel is one of the properties of importance since it can vary considerably as other properties are adjusted. Since resistance to chipping decreases at lower temperatures partly as the result of decreased flexibility, the test may be more directly related to service conditions by performing it at a low temperature. This test method is designed to produce a controlled amount of impact by the media on the coated panel in order to enhance reproducibility.

5. Apparatus

5.1 *Gravel-Projecting Machine (Gravelometer)*, constructed according to the design specifications shown in Fig. 1.^{5,6} There are two types of Gravelometers: the old cabinet style and the newer, modular style with an electronic feed mechanism.

NOTE 2—It is recommended that the operation/maintenance checklist shown in Appendix X1 should be completed at least once per month for gravelometers that are operated on a weekly basis, and once every 6 months for gravelometers that are operated less frequently. Note that values in the checklist are specific to the standard gravel testing protocol. Different specifications may be necessary for other media types.

5.2 *Gravel*—Water-eroded alluvial road gravel^{7,6} passing through a 16-mm (5/8-in.) space screen but retained on a 9.5-mm (3/8-in.) space screen. Note that mesh screen is not a substitute for a space screen. It is important to remove the small pieces of gravel before reusing the gravel. Other media may be used as agreed by contractual parties.

⁵ The sole source of a suitable apparatus meeting these specifications known to the committee at this time is Q-Panel Co., 26200 First St., Westlake, OH 44135.


⁶ If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁷ The sole source of supply of gravel meeting these specifications known to the committee at this time is Q-Panel Co., 26200 First St., Westlake, OH 44135.

5.3 *Tape*, 100 mm (4 in.) wide.^{8,6} Other tape may be used as agreed upon by the contractual parties.

5.4 *Temperature-Conditioning Equipment (alternatives):*

⁸ The sole source of supply of No. 898 filament strapping tape known to the committee at this time is the 3M Co., St. Paul MN 55101.



NOTE 1—Reprinted with permission from SAE EA-400 (c) 1985, Society of Automotive Engineers, Inc.

FIG. 2 Representation of Chipping Ratings

5.4.1 A cold room or freezer of sufficient size in which the gravel-projecting machine and test specimens can be maintained at the specified temperature of testing.

5.4.2 A freezer or cooler in which the test panels can be cooled 5°C (10°F) below the specified test temperature.

5.4.3 *Ambient*—Room maintained at a temperature between 20°C (68°F) and 30°C (86°F).

5.5 *Transparent Grid*—A chip counting aid constructed of transparent plastic approximately 3.176 mm thick by 12.7 cm square (½ by 5 by 5 in.), on which a 10.16 cm by 10.16 cm (4 by 4 in.) grid of 2.54 cm (1 in.) squares has been etched or scribed.

5.6 *Chipping Rating Standards*—A photographic transparency^{9,6} depicting size and number of chips in each category. See Fig. 2 for an example of the transparencies. These standards depict various degrees of chipping severity and are arranged sequentially from best to worst according to chipping frequency.

6. Test Specimens

6.1 The composition, surface preparation, and size of specimens shall be agreed upon between the purchaser and the seller. Test panels of 102 by 305 mm (4 by 12 in.) are commonly used.

NOTE 3—It is recommended that three replicates of each test specimen be exposed in the gravelometer. More replicates will improve the accuracy.

6.2 The number, type, method of application, and aging of coatings shall be agreed upon between the purchaser and the seller.

NOTE 4—Application, metal preparation, and film thickness measurement methods are given in the following ASTM Practices: D609, D823 and D2201, and Test Methods D1005, D1186, D1400, and D1733.

7. Procedure

7.1 Condition the specimens for a minimum of 1 h at the specified test temperature in the equipment specified in 5.4. Make certain the test specimens are separated and have free access to the conditioning environment so that optimum heat transfer occurs.

7.2 Adjust the air pressure on the gravel apparatus to 480 ± 20 kPa (70 ± 3 psi) with the air valve open.

NOTE 5—For cabinet type gravelometers, keep the lid to the gravel chamber closed during this operation as a safety precaution. Other air pressures can be used as agreed upon by the contractual parties.

7.3 Cabinet Style Gravelometer:

7.3.1 After adjusting the air pressure, shut off the air valve, open the lid to the gravel chamber and collect ~~550 mL (1 pt)~~ 473 mL (1.00 US Liquid Pint) of graded gravel (approx 250 to ~~3000~~300 stones) in a suitable container. Collect the gravel by scraping across the screen to allow fines to fall through.

7.3.2 Place one test specimen at the desired test temperature in the panel holder with the coated side facing the front of the apparatus and close the lid to the panel chamber.

7.3.3 Open the gravel feed door and pour gravel from the one pint container obtained from 7.3.1 into the top of the gravel hopper. Do not allow gravel to fall into the nozzle entrance.

7.3.4 Open the air valve to allow the air to project the gravel at the specimen.

NOTE 6—The gravel hopper must empty in 7 to 10 s. If gravel remains in the hopper after 10 s, stop the test and investigate the cause. The operator should not touch the gravel during the test or otherwise physically help the gravel into the funnel.

NOTE 7—It is important to know that the vibrator may become frozen when the chamber is installed in a cold room or freezer. If the vibrator is frozen, discontinue the test until the vibrator has thawed and is operating correctly.

7.3.5 Shut the air valve, open the lid to the specimen chamber and remove the specimen.

7.4 Modular Style Gravelometer:

7.4.1 After adjusting the air pressure, shut off the air valve, open the lid to the gravel hopper and pour ~~550 mL (1 pt)~~ 473 mL (1.00 US Liquid Pint) of graded gravel (approx. 250 to ~~3000~~300 stones) into the top of the gravel hopper.

7.4.2 Pull back on the specimen mounting clamp to open the specimen holder on the holder assembly. Place one test specimen at the desired test temperature in the panel holder with the coated side facing the front of the apparatus. Clamp to close the specimen holder.

7.4.3 Set the test timer.

NOTE 8—There are two ways to operate a test on the Modular style gravelometer. A timed test is a test that shuts off the machine after a preset amount of time has passed. A manual test requires the operator to shut off the machine after the desired amount of time has passed.

7.4.3.1 Timed Test:

- (a) Make sure that the control switch is set to stop.
- (b) Set the test timer to the desired test time. A typical test time is 10 s.
- (c) Turn the main power switch on.
- (d) Turn the control switch to Timed Start.

7.4.3.2 Manual Test:

- (a) Make sure that the control switch is set to stop.
- (b) Turn the main power switch on.
- (c) Turn the control switch to Manual.
- (d) After the desired amount of time has passed turn the control switch to Off.

NOTE 9—Manual mode requires the operator to manually stop the test. Once started, the test will not stop by itself.

⁹ The sole source of supply of *Chipping Rating Standards*, Part #AE-400, known to the committee at this time is the Society of Automotive Engineers, 400 Commonwealth Dr., Warrendale, PA 15096.