



**International
Standard**

ISO 4080

**Rubber and plastics hoses and
tubing, and their assemblies —
Determination of permeability to gas**

*Tuyaux et tubes en caoutchouc et en plastique, et leurs
assemblages — Détermination de la perméabilité au gaz*

**Fifth edition
2024-06**

iteh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 4080:2024](https://standards.iteh.ai/catalog/standards/iso/dc24b48d-4be9-4c88-a98d-9b685fd1e78c/iso-4080-2024)

<https://standards.iteh.ai/catalog/standards/iso/dc24b48d-4be9-4c88-a98d-9b685fd1e78c/iso-4080-2024>

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 4080:2024](https://standards.iteh.ai/catalog/standards/iso/dc24b48d-4be9-4c88-a98d-9b685fd1e78c/iso-4080-2024)

<https://standards.iteh.ai/catalog/standards/iso/dc24b48d-4be9-4c88-a98d-9b685fd1e78c/iso-4080-2024>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Test pieces	2
4.1 Method 1.....	2
4.2 Method 2.....	2
4.3 Method 3.....	2
5 Apparatus	2
6 Test conditions	3
6.1 Test pieces.....	3
6.2 Test temperature.....	3
6.3 Test gas.....	3
6.4 Test pressure.....	3
7 Procedure	3
7.1 General.....	3
7.2 Method 1.....	4
7.3 Method 2.....	4
7.4 Method 3.....	5
8 Expression of results	6
9 Test report	7
Annex A (informative) Guidance on permeability	8
Annex B (informative) Guidance on test methods and their application	10
Annex C (informative) Saturated vapour pressure	11
Bibliography	12

<https://standards.iteh.ai/catalog/standards/iso/dc24b48d-4be9-4c88-a98d-9b685fd1e78c/iso-4080-2024>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 218, *Rubber and plastics hoses and hose assemblies*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fifth edition cancels and replaces the fourth edition (ISO 4080:2009), which has been technically revised.

<https://standards.iteh.ai/catalog/standards/iso/dc24b48d-4be9-4c88-a98d-9b685fd1e78c/iso-4080-2024>

The main changes are as follows:

- revised gas permeability test as a whole;
- title changed;
- terms [3.1](#) and [3.2](#) added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Rubber and plastics hoses and tubing, and their assemblies — Determination of permeability to gas

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices.

1 Scope

This document specifies three methods to determine the permeability to gas by measuring the volume of gas diffusing through a rubber or plastics hose or length of tubing used for gas applications in a specified time.

- Method 1 is for determining the permeability of the complete hose wall or length of tubing wall, excluding end fittings, to the test gas.
- Method 2 is for determining the permeability at the hose and fitting interface to the test gas.
- Method 3 is for precisely determining the permeability of the complete hose or length of tubing, including end fittings.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purpose of this document, the terms and definitions given in ISO 8330 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 end fitting

device attached to the end of a hose or tubing to facilitate connection to equipment constituting hose assembly

Note 1 to entry: End fitting can include an attached matching part to facilitate the test, if necessary.

3.2 permeability

property of a material of transmitting gases and liquids by passage through one surface and out at another surface by diffusion and sorption processes

Note 1 to entry: Not to confuse with “porosity”.

Note 2 to entry: The property of a permeability involves the diffusion of molecules, called the permeant, through a membrane or interface. The permeability property works through diffusion< the permeant will move from high concentration to low concentration across the interface.

Note 3 to entry: In a pressurized hose the permeant can pass from the inside of the hose to the outside through the hose lining and cover.

[SOURCE: ISO 8330:2022, 3.8.5]

4 Test pieces

4.1 Method 1

The test piece shall be a length of hose or tubing fitted with end fittings long enough to ensure that the length of the exposed hose or tubing under the gas-collecting trough is $1 \text{ m} \pm 0,01 \text{ m}$. The test piece shall have a pricked cover or a textile braid cover.

4.2 Method 2

The test piece shall be a length of hose fitted with end fittings. It shall have a length of $1 \text{ m} \pm 0,01 \text{ m}$ between the end fittings. The test piece shall be a textile reinforced hose with an unpricked cover.

NOTE The type of coupling used and the method by which the fittings are fixed to the test piece can affect the permeability results obtained using this method.

4.3 Method 3

The test piece shall be a length of hose or tubing fitted with end fittings. It shall have a minimum test length of 0,5 m with $\pm 1 \%$ tolerance between the end fittings. A test length of $1 \text{ m} \pm 0,01 \text{ m}$ between the end fittings may be used when comparison of test result among the three methods are necessary.

NOTE The type of end fittings used and the method by which the end fittings are fixed to the test piece can affect the permeability results obtained using this method.

5 Apparatus

Schematic layouts of the test arrangements for the three test methods are shown in [Figure 1](#) to [Figure 3](#).

5.1 Gas supply, provided with a suitable pressure regulator gauge and emergency excess flow shutoff valves in case of test piece failure.

5.2 Calibrated pressure gauge or pressure transducer with digital readout, chosen for each test so that the test pressure is between 15 % and 85 % of the full-scale reading.

5.3 Water bath, capable of being maintained at a specified temperature and of sufficient length to accommodate the test piece.

5.4 Gas-collecting apparatus, comprising measuring cylinders and in some instances additional apparatus appropriate to each of the three methods, as illustrated in [Figure 1](#) (collecting trough), [Figure 2](#) (collecting funnels) and [Figure 3](#) (collecting funnel and transparent glass tube), respectively. The capacity and accuracy of the measuring cylinders shall be selected in accordance with the volume of gas that is expected to be collected.

A transparent glass tube may be replaced with a tube made from acrylic, polycarbonate and similar materials, or with a transparent collecting trough large enough to cover the whole test piece to collect escaped gas.

5.5 Barometer, to record the barometric pressure during the test.