
**Paper, board and pulps —
Determination of conductivity of
aqueous extracts**

*Papier, carton et pâtes — Détermination de la conductivité des
extraits aqueux*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 6587:2021](https://standards.iteh.ai/catalog/standards/iso/eb0d9ba4-672c-4592-b557-3b4c6bf845e7/iso-6587-2021)

<https://standards.iteh.ai/catalog/standards/iso/eb0d9ba4-672c-4592-b557-3b4c6bf845e7/iso-6587-2021>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 6587:2021

<https://standards.iteh.ai/catalog/standards/iso/eb0d9ba4-672c-4592-b557-3b4c6bf845e7/iso-6587-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	2
5.1 Distilled or deionized water.....	2
5.2 Potassium chloride, standard solutions.....	2
5.2.1 0,01 mol/l solution.....	2
5.2.2 0,001 mol/l solution.....	2
6 Apparatus	2
7 Sampling and sample preparation	3
7.1 Sampling.....	3
7.2 Sample preparation.....	3
7.3 Determination of dry matter content.....	3
8 Procedure	3
8.1 Determination of cell constant.....	3
8.2 Preparation of the aqueous extract.....	4
8.2.1 Weighing of sample.....	4
8.2.2 Hot extraction method.....	4
8.2.3 Cold extraction method.....	4
8.3 Determination of conductivity.....	4
8.4 Blank test.....	4
9 Calculation and expression of results	4
9.1 If the meter gives conductance.....	4
9.2 If the meter gives resistance.....	5
9.3 Expression of results.....	5
10 Test report	5
Bibliography	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This third edition cancels and replaces the second edition (ISO 6587:1992), which has been technically revised.

The main changes are as follows:

- editorial updates;
- requirement added to [7.1](#);
- bibliography update.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Conductivity measurement provides an indication of the level of residual ionic impurities in pulp. It can thus be used, for example, to assess the effectiveness of washing in the pulp and paper manufacturing process.

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ISO 6587:2021](https://standards.itih.ai/catalog/standards/iso/eb0d9ba4-672c-4592-b557-3b4c6bf845e7/iso-6587-2021)

<https://standards.itih.ai/catalog/standards/iso/eb0d9ba4-672c-4592-b557-3b4c6bf845e7/iso-6587-2021>

